
**Elastomeric seals — Material
requirements for seals used in pipes
and fittings carrying gaseous fuels and
hydrocarbon fluids**

*Garnitures d'étanchéité en élastomères — Exigences matérielles pour
les joints utilisés dans les canalisations et les raccords véhiculant des
combustibles gazeux et des hydrocarbures liquides*

[iteh standards
\(https://standards.iteh.ai\)](https://standards.iteh.ai)
Document Preview

[ISO 16010:2019](https://standards.iteh.ai/catalog/standards/iso/a850af35-bbd4-4091-a391-9e84825f84fe/iso-16010-2019)

<https://standards.iteh.ai/catalog/standards/iso/a850af35-bbd4-4091-a391-9e84825f84fe/iso-16010-2019>



iTeh Standards
(<https://standards.iteh.ai>)
Document Preview

[ISO 16010:2019](https://standards.iteh.ai/catalog/standards/iso/a850af35-bbd4-4091-a391-9e84825f84fe/iso-16010-2019)

<https://standards.iteh.ai/catalog/standards/iso/a850af35-bbd4-4091-a391-9e84825f84fe/iso-16010-2019>



COPYRIGHT PROTECTED DOCUMENT

© ISO 2019

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Fax: +41 22 749 09 47
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Contents

Page

Foreword	iv
1 Scope	1
2 Normative references	1
3 Terms and definitions	2
4 Classification	2
5 Requirements	2
5.1 Materials.....	2
5.2 Finished-seal requirements.....	3
5.2.1 Dimensional tolerances.....	3
5.2.2 Imperfections and defects.....	3
5.2.3 Hardness.....	3
5.2.4 Tensile strength and elongation at break.....	3
5.2.5 Compression set in air.....	3
5.2.6 Accelerated ageing in air.....	4
5.2.7 Stress relaxation in compression.....	4
5.2.8 Volume change in liquid B.....	4
5.2.9 Volume change in oil.....	4
5.2.10 Ozone resistance.....	4
5.2.11 Compression set at -15 °C.....	5
6 Test pieces and temperature	5
6.1 Preparation of test pieces.....	5
6.2 Test temperature.....	5
7 Quality assurance	7
8 Storage	7
9 Designation	8
10 Marking and labelling	8
Annex A (informative) Quality assurance	9
Annex B (informative) Guidance on storage of seals	10
Bibliography	11

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 45, *Rubber and rubber products*, Subcommittee SC 4, *Products other than hoses*.

This second edition cancels and replaces the first edition (ISO 16010:2005), which has been technically revised.

The main changes compared to the previous edition are as follows:

- normative references has been updated to the latest version

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

Elastomeric seals — Material requirements for seals used in pipes and fittings carrying gaseous fuels and hydrocarbon fluids

1 Scope

This document specifies requirements for elastomeric materials used in seals for supply pipes and fittings, ancillaries and valves at operating temperatures in general from -5 °C up to 50 °C and in special cases from -15 °C up to 50 °C , for the following:

- a) general applications (see [Table 4](#), type G series):
 - gaseous fuel [manufactured, natural and liquefied petroleum gas (LPG) in the gaseous phase],
 - hydrocarbon fluids with an aromatic content up to 30 % (by volume), including LPG in the liquid phase;
- b) special applications (see [Table 4](#), type H):
 - materials suitable for carrying gaseous fuels containing gas condensates and hydrocarbon fluids of unrestricted aromatic content.

General requirements for finished joint seals are also given; any additional requirements called for by the particular application are specified in the relevant product standards, taking into account that the performance of pipe joints is a function of the seal material properties, seal geometry and pipe joint design. This document is used where appropriate with product standards which specify performance requirements for joints.

This document is applicable to joint seals for all pipeline materials, including iron, steel, copper and plastics.

In the case of composite sealing rings, the requirements in [5.2.8](#) and [5.2.9](#) apply only when the materials used for any elastomeric parts come into contact with gaseous fuel or hydrocarbon fluid.

Elongation at break, tensile strength, compression set and stress relaxation requirements for materials of hardness classes 80 and 90 apply only when they constitute that part of the seal which participates directly in the sealing function or contributes directly to long-term stability.

This document is not applicable to the following:

- seals made from cellular materials;
- seals with enclosed voids as part of their design;
- seals required to be resistant to flame or to thermal stress;
- seals which contain splices joining pre-vulcanized profile ends.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 16010:2019(E)

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 37, *Rubber, vulcanized or thermoplastic — Determination of tensile stress-strain properties*

ISO 48-2, *Rubber, vulcanized or thermoplastic — Determination of hardness — Part 2: Hardness between 10 IRHD and 100 IRHD*

ISO 188:2011, *Rubber, vulcanized or thermoplastic — Accelerated ageing and heat resistance tests*

ISO 815-1, *Rubber, vulcanized or thermoplastic — Determination of compression set — Part 1: At ambient or elevated temperatures*

ISO 815-2, *Rubber, vulcanized or thermoplastic — Determination of compression set — Part 2: At low temperatures*

ISO 1431-1, *Rubber, vulcanized or thermoplastic — Resistance to ozone cracking — Part 1: Static and dynamic strain testing*

ISO 1817, *Rubber, vulcanized or thermoplastic — Determination of the effect of liquids*

ISO 3302-1, *Rubber — Tolerances for products — Part 1: Dimensional tolerances*

ISO 3384-1:2011, *Rubber, vulcanized or thermoplastic — Determination of stress relaxation in compression at ambient and at elevated temperatures*

ISO 9691:1992, *Rubber — Recommendations for the workmanship of pipe joint rings — Description and classification of imperfections*

ISO 23529, *Rubber — General procedures for preparing and conditioning test pieces for physical test methods*

3 Terms and definitions

No terms and definitions are listed in this document.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <http://www.electropedia.org/>

4 Classification

Five classes of material for pipe seals are specified in [Tables 2](#) and [3](#).

A nominal hardness shall be specified within the ranges in [Table 1](#).

Table 1 — Hardness classification

Hardness class	50	60	70	80	90
Range of hardness, IRHD	46 to 55	56 to 65	66 to 75	76 to 85	86 to 95

5 Requirements

5.1 Materials

The materials shall be free of any substances which may have a deleterious effect on the life of the seals, or on the pipe or fittings.