
**Rubber — Determination of metal
content by atomic absorption
spectrometry —**

**Part 2:
Determination of lead content**

iTeh STANDARD PREVIEW
*Caoutchouc — Détermination de la teneur en métal par
spectrométrie d'absorption atomique —
Partie 2: Dosage du plomb*
(standards.iteh.ai)

ISO 6101-2:2019

<https://standards.iteh.ai/catalog/standards/sist/063575dc-8499-4fec-9875-1f021aa93492/iso-6101-2-2019>



iTeh STANDARD PREVIEW
(standards.iteh.ai)

ISO 6101-2:2019

<https://standards.iteh.ai/catalog/standards/sist/063575dc-8499-4fec-9875-1f021aa93492/iso-6101-2-2019>



COPYRIGHT PROTECTED DOCUMENT

© ISO 2019

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Fax: +41 22 749 09 47
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Contents

	Page
Foreword.....	iv
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Principle	2
5 Reagents	2
6 Apparatus	3
7 Sampling	3
8 Procedure	4
8.1 Test portion.....	4
8.2 Preparation of test solution.....	4
8.2.1 Destruction of organic matter.....	4
8.2.2 Dissolution of inorganic residue.....	4
8.3 Preparation of the calibration graph.....	5
8.3.1 Preparation of calibration solutions.....	5
8.3.2 Spectrometric measurements.....	5
8.3.3 Plotting the calibration graph.....	5
8.4 Determination.....	5
8.4.1 Spectrometric measurements.....	5
8.4.2 Dilution.....	6
8.5 Blank determination.....	6
8.6 Number of determinations.....	6
9 Expression of results	6
10 Test report	7
Annex A (informative) Method of standard additions	9

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 45, *Rubber and rubber products*, Subcommittee SC 2, *Testing and analysis*.

This third edition cancels and replaces the second edition (ISO 6101-2:1997), of which it constitutes a minor revision to update normative references in [Clause 2](#).

A list of all parts in the ISO 6101 series can be found on the ISO website.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

Rubber — Determination of metal content by atomic absorption spectrometry —

Part 2: Determination of lead content

WARNING 1 — Persons using this document should be familiar with normal laboratory practice. This document does not purport to address all of the safety problems, if any, associated with its use. It is the responsibility of the user to establish appropriate safety and health practices and to determine the applicability of any other restrictions.

WARNING 2 — Certain procedures specified in this document might involve the use or generation of substances, or the generation of waste, that could constitute a local environmental hazard. Reference should be made to appropriate documentation on safe handling and disposal after use.

1 Scope

This document specifies an atomic absorption spectrometric method for the determination of the lead content of rubbers.

The method is applicable to raw rubber and rubber products. There is no limit to the concentration of lead that can be determined. High or low concentrations can be determined, provided that suitable adjustments are made to the mass of the test portion and/or the concentration of the solutions used. The use of the standard-additions method might lower the bottom limit of detection.

<https://standards.iteh.ai/catalog/standards/sist/063575dc-8499-4fec-9875-1f021aa93492/iso-6101-2-2019>

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 123, *Rubber latex — Sampling*

ISO 247-1:2018, *Rubber — Determination of ash — Part 1: Combustion method*

ISO 648, *Laboratory glassware — Single-volume pipettes*

ISO 1042, *Laboratory glassware — One-mark volumetric flasks*

ISO 1772, *Laboratory crucibles in porcelain and silica*

ISO 1795, *Rubber, raw natural and raw synthetic — Sampling and further preparative procedures*

3 Terms and definitions

No terms and definitions are listed in this document.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <http://www.electropedia.org/>

4 Principle

If the rubber does not contain halogenated compounds, a test portion is directly ashed at $550\text{ °C} \pm 25\text{ °C}$ as specified in ISO 247-1:2018, method A. If the rubber contains halogenated compounds, a test portion is first mineralized with sulfuric and nitric acids, the acids are removed by evaporation, and the portion is ashed at $550\text{ °C} \pm 25\text{ °C}$.

NOTE The presence of even small amounts of halogens can lead to the loss of volatile lead salts during dry ashing.

The ash obtained is boiled with ammonium acetate solution to dissolve the lead. Insoluble lead silicates, if present, are converted to chloride by boiling with a mixture of hydrochloric acid, nitric acid and hydrogen peroxide.

The solution is aspirated into an atomic absorption spectrometer and the absorbance is measured at a wavelength of 283,3 nm, using a lead hollow-cathode lamp as the lead emission source.

5 Reagents

During the analysis, unless otherwise stated, use only reagents of recognized analytical grade, and only distilled water or water of equivalent purity.

5.1 Sulfuric acid, $\rho_{20} = 1,84\text{ Mg/m}^3$.

5.2 Nitric acid, $\rho_{20} = 1,40\text{ Mg/m}^3$.

5.3 Hydrochloric acid, $\rho_{20} = 1,18\text{ Mg/m}^3$.

5.4 Hydrochloric acid, diluted 1 + 2.

Dilute 1 volume of concentrated hydrochloric acid (5.3) with 2 volumes of water.

5.5 Hydrogen peroxide, 30 % (mass fraction) solution.

5.6 Ammonium acetate, 180 g/dm^3 solution.

5.7 Standard lead stock solution, containing 1 g of Pb per cubic decimetre.

Either use a commercially available standard lead solution, or prepare as follows:

Weigh, to the nearest 0,1 mg, 1 g of metallic lead (purity $\geq 99,95\%$) and transfer to a 100 cm^3 beaker (6.12). Add 30 cm^3 of water and 20 cm^3 of nitric acid (5.2) and boil on a sand bath (6.10). If the lead is dissolved, continue boiling until the solution is reduced to about 20 cm^3 or less. No nitrogen oxides should be observed. Otherwise, add water and continue boiling. Transfer to a $1\ 000\text{ cm}^3$ one-mark volumetric flask (see 6.7) with 1 + 2 hydrochloric acid (5.4) and fill to the mark with 1 + 2 hydrochloric acid (5.4).

1 cm^3 of this standard stock solution contains 1 mg of Pb.

5.8 Standard lead solution, containing 10 mg of Pb per cubic decimetre.

Using a pipette (6.9), carefully introduce 10 cm^3 of the standard lead stock solution (5.7) into a $1\ 000\text{ cm}^3$ one-mark volumetric flask (see 6.7). Dilute to the mark with 1 + 2 hydrochloric acid (5.4), and mix thoroughly.

Prepare this solution on the day of use.

1 cm^3 of this standard solution contains $10\text{ }\mu\text{g}$ of Pb.

6 Apparatus

Ordinary laboratory apparatus, plus the following.

6.1 Atomic absorption spectrometer, fitted with a burner fed with acetylene and air, compressed to at least 60 kPa and 300 kPa, respectively, and also fitted with a lead hollow-cathode lamp as the lead emission source. The instrument shall be operated in accordance with the manufacturer's instructions for optimum performance.

Alternatively, an **electrothermal atomization device (graphite furnace)** may be used. It shall be operated by a competent person in accordance with the manufacturer's instructions for optimum performance, during drying, ashing and volatilization of the test portion.

6.2 Balance, accurate to 0,1 mg.

6.3 Muffle furnace, capable of being maintained at $550\text{ °C} \pm 25\text{ °C}$.

6.4 Evaporating dish, of capacity about 100 cm^3 , made of quartz glass, with a clock-glass cover.

6.5 Conical flask, of capacity 250 cm^3 , made of silica or borosilicate glass.

6.6 Measuring cylinder, of capacity 25 cm^3 , graduated in $0,5\text{ cm}^3$ divisions.

6.7 One-mark volumetric flasks, glass-stoppered, of capacities 50 cm^3 , 100 cm^3 , 200 cm^3 , 500 cm^3 and $1\ 000\text{ cm}^3$, in accordance with the requirements of ISO 1042, class A.

6.8 Filter funnel, 65 mm diameter, 60° angle.

6.9 Volumetric pipettes, of capacities 5 cm^3 , 10 cm^3 , 20 cm^3 and 50 cm^3 , in accordance with the requirements of ISO 648, class A.

6.10 Electric hotplate or sand bath heated by a gas burner.

6.11 Steam bath.

6.12 Beaker, of capacity 100 cm^3 .

6.13 Crucible, of platinum, and of capacity 50 cm^3 to 150 cm^3 depending on the test portion size.

6.14 Crucible, of silica or borosilicate glass, of capacity 50 cm^3 to 150 cm^3 depending on the test portion size, in accordance with the requirements of ISO 1772.

7 Sampling

Carry out sampling as follows:

- raw rubber: in accordance with ISO 1795;
- latex: in accordance with ISO 123;
- products: to be representative of the whole batch.

8 Procedure

8.1 Test portion

8.1.1 If the rubber does not contain halogenated compounds, weigh, to the nearest 0,1 mg, 0,5 g to 2,0 g (depending on the expected lead content) of milled or finely cut rubber into a crucible (6.13 or 6.14).

It is advisable to run the Beilstein test on a preliminary test portion for halogen content, as volatile lead compounds are possibly formed in the presence of halogen-containing admixtures.

8.1.2 If the rubber contains halogenated compounds (for example, in the case of chloroprene rubber), weigh to the nearest 0,1 mg, 0,5 g to 2,0 g (depending on the expected lead content) of milled or finely cut rubber into the conical flask (6.5).

8.2 Preparation of test solution

8.2.1 Destruction of organic matter

8.2.1.1 If the rubber does not contain halogenated compounds, ash the test portion in accordance with method A of ISO 247-1:2018.

8.2.1.2 If the rubber contains halogenated compounds (8.1.2), use the following alternative procedure.

To the flask containing the test portion, add 10 cm³ to 15 cm³ of sulfuric acid (5.1) and heat moderately on the electric hotplate or on the sand bath heated by a gas burner (6.10) until the rubber has disintegrated. Carefully add 5 cm³ of nitric acid (5.2). Continue heating until the rubber has completely decomposed and white fumes are evolved.

Some rubber formulations cause considerable splashing; in this case, use a larger conical flask.

Transfer the reaction mixture quantitatively into the evaporating dish (6.4), evaporate to dryness and ash in the muffle furnace (6.3), maintained at 550 °C ± 25 °C, until all the carbon has burnt off.

8.2.2 Dissolution of inorganic residue

After cooling, boil the residue obtained in 8.2.1.1 or 8.2.1.2 with 15 cm³ of ammonium acetate solution (5.6) and filter through a paper filter. Retain this filtrate (A) and ash the filter with the residue in the muffle furnace (6.3), maintained at 550 °C ± 25 °C, until all the carbon has burnt off.

Cool to room temperature, add a mixture of 10 cm³ of hydrochloric acid (5.3), 5 cm³ of nitric acid (5.2) and 10 drops of hydrogen peroxide (5.5), then boil for about 10 min.

Cool and filter the reaction mixture. Evaporate the filtrate on the steam bath (6.11) to dryness and take up the residue with water. Add this to filtrate A. Transfer the combined solutions, quantitatively, to a 50 cm³ one-mark volumetric flask (see 6.7) with hydrochloric acid (5.4). Dilute to the mark with hydrochloric acid (5.4) and proceed in accordance with 8.4.

Test solutions in hydrochloric acid shall be of the same concentration as in 5.4. If evaporation, etc., has reduced or increased this concentration, adjust it accordingly with concentrated hydrochloric acid (5.3) or with water.

8.3 Preparation of the calibration graph

8.3.1 Preparation of calibration solutions

8.3.1.1 Into a series of five 100 cm³ one-mark volumetric flasks (see 6.7) introduce, using pipettes (see 6.9), the volumes of standard lead solution (5.8) indicated in Table 1. Dilute to the mark with 1 + 2 hydrochloric acid (5.4) and mix thoroughly.

Table 1 — Standard calibration solutions

Volume of standard lead solution cm ³	Mass of lead contained in 1 cm ³ µg
50	5
20	2
10	1
5	0,5
0	0

8.3.1.2 Prepare the set of calibration solutions immediately prior to the determination.

8.3.1.3 If the test portion was prepared with sulfuric acid and ammonium acetate, use the same quantities in the calibration solutions and for the corresponding calibration blank.

8.3.2 Spectrometric measurements

Switch on the spectrometer (6.1) sufficiently in advance to ensure stabilization. With the lead hollow-cathode lamp suitably positioned, adjust the wavelength to 283,3 nm and the sensitivity and slit aperture according to the characteristics of the instrument.

Adjust the pressures and flow rates of the air and of the acetylene in accordance with the manufacturer's instructions so as to obtain a clear blue, non-luminous, oxidizing flame, suited to the characteristics of the particular spectrometer being used.

Aspirate the set of calibration solutions in succession into the flame and measure the absorbance of each solution twice, averaging the readings. Take care that the aspiration rate is constant throughout this process. Ensure also that at least one calibration solution is at or below the analyte level found in the rubber being tested.

Aspirate water through the burner after each measurement.

If sulfuric acid has been used in the preparation of the test portion, it is advisable to use a background correction.

8.3.3 Plotting the calibration graph

Plot graph, having, for example, the masses, in micrograms of lead contained in 1 cm³ of the calibration solutions, as abscissae and the corresponding values of absorbance, corrected for the absorbance of the calibration blank, as ordinates. Represent the points on the graph by the best straight line as judged visually or as calculated by the least-squares fit method.

8.4 Determination

8.4.1 Spectrometric measurements

Carry out duplicate spectrometric measurements at a wavelength of 283,3 nm on the test solution prepared in 8.2.2, following the procedure specified in 8.3.2.