



SLOVENSKI STANDARD
SIST EN 14058:2018+A1:2023

01-julij-2023

Varovalna obleka - Oblečila za zaščito v hladnih okoljih (vključuje dopolnilo A1)

Protective clothing - Garments for protection against cool environments

Schutzkleidung - Kleidungsstücke zum Schutz gegen kühle Umgebungen

Habillement de protection - Vêtements de protection contre les environnements frais

Ta slovenski standard je istoveten z: EN 14058:2017+A1:2023

<https://standards.iteh.ai/catalog/standards/sist/9186b936-ebe3-4e82-98a8-974e878ac53e/sist-en-14058-2018a1-2023>

ICS:

13.340.10 Varovalna obleka Protective clothing

SIST EN 14058:2018+A1:2023 **en,fr,de**

EUROPEAN STANDARD

EN 14058:2017+A1

NORME EUROPÉENNE

EUROPÄISCHE NORM

April 2023

ICS 13.340.10

Supersedes EN 14058:2017

English Version

Protective clothing - Garments for protection against cool environments

Habillement de protection - Vêtements de protection
contre les environnements fraisSchutzkleidung - Kleidungsstücke zum Schutz gegen
kühle Umgebungen

This European Standard was approved by CEN on 4 September 2017 and includes Amendment 1 approved by CEN on 20 June 2022.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Türkiye and United Kingdom.

<https://standards.iteh.ai/catalog/standards/sist/9186b936-ebe3-4e82-98a8-974e878ac53e/sist-en-14058-2018a1-2023>



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels

Contents	Page
European foreword.....	4
Introduction	5
1 Scope.....	6
2 Normative references.....	6
3 Terms and definitions	7
4 Performance assessment and requirements	8
4.1 General requirements and innocuousness.....	8
4.1.1 General requirements	8
4.1.2 Innocuousness.....	9
4.2 Thermal Resistance, R_{ct}	9
4.3 Air permeability, AP.....	9
4.4 Resistance to water penetration, WP.....	10
4.5 Water vapour resistance, R_{et}	10
4.6 Resultant effective thermal insulation, I_{cler}	10
4.7 Mechanical and physical properties	10
4.7.1 Tear resistance of outer shell material.....	10
4.7.2 Burst strength of knitted outer shell material	10
4.8 Dimensional change due to cleaning.....	10
5 Pre-treatment.....	10
6 Test methods	11
6.1 Sampling.....	11
6.2 General requirements and innocuousness.....	11
6.2.1 General requirements	11
6.2.2 Innocuousness.....	11
6.3 Thermal resistance, R_{ct}	11
6.4 Air permeability, AP.....	11
6.5 Resistance to water penetration, WP.....	11
6.6 Water vapour resistance, R_{et}	11
6.7 Resultant effective thermal insulation, I_{cler}	11
6.8 Mechanical and physical properties	12
6.8.1 Tear resistance of outer shell material.....	12
6.8.2 Burst strength of knitted outer shell material	12
6.9 Dimensional change due to cleaning.....	12
7 Size designation	12
8 Marking and care labelling.....	12
9 Information supplied by the manufacturer.....	13
Annex A (informative) Significant changes between this document and the previous edition.....	14
Annex B (normative) Standard ensemble R for the testing of protective garments against cool environments	15
Annex C (informative) Temperature ranges of utility	17

Annex ZA (informative) A1 Relationship between this European Standard and the essential requirements of Regulation (EU) 2016/425 of the European Parliament and of the Council of 9 March 2016 on personal protective equipment aimed to be covered 20

Bibliography 22

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN 14058:2018+A1:2023

<https://standards.iteh.ai/catalog/standards/sist/9186b936-ebe3-4e82-98a8-974e878ac53e/sist-en-14058-2018a1-2023>

EN 14058:2017+A1:2023 (E)**European foreword**

This document (EN 14058:2017+A1:2023) has been prepared by Technical Committee CEN/TC 162 “Protective clothing including hand and arm protection and lifejackets”, the secretariat of which is held by DIN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by October 2023, and conflicting national standards shall be withdrawn at the latest by October 2023.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

This document supersedes A1 EN 14058:2017 A1.

Regarding the most significant changes that have been made in this new edition, see Annex A.

This document includes Amendment 1 approved by CEN on 20 June 2022.

The start and finish of text introduced or altered by amendment is indicated in the text by tags A1 A1.

This document has been prepared under a Standardization Request given to CEN by the European Commission and the European Free Trade Association, and supports essential requirements of EU Directive(s) / Regulation(s).

For relationship with EU Directive(s) / Regulation(s), see informative Annex ZA, which is an integral part of this document.

Any feedback and questions on this document should be directed to the users' national standards body. A complete listing of these bodies can be found on the CEN website.

According to the CEN-CENELEC Internal Regulations, the national standards organisations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Türkiye and the United Kingdom.

Introduction

In many cases single garments are placed on the market to protect against local body cooling (for ensembles see EN 342). These garments can be e.g. waistcoats, jackets, coats or trousers and/or separable thermal linings. They can provide a certain degree of protection to cool environment for a certain length of time, depending e.g. on the personal constitution and activity, the accompanying clothing and the environmental features (wind speed, temperature, humidity). In critical situations (e.g. combination of cold, moisture and wind, long exposure duration, no help nearby) it is important to assess the cold protection properties of the garment (see Annex C), especially if the user cannot safely identify the risk at moderate low temperatures above -5 °C in an appropriate time.

At moderate low temperatures above -5 °C garments against local body cooling are not only used for outdoor activities e.g. in construction industry but can be used for indoor activities e.g. in food processing industry. In these cases garments often do not need to be made of watertight or air impermeable materials. Therefore, in this European Standard, these requirements are applicable if the manufacturer claims in his instructions for use protection for hazards covered by these properties.

The resultant effective thermal insulation value I_{cler} can be used to assess temperature ranges according to Tables C.1 and C.2.

If exposure to wet conditions is expected, EN 343 applies.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN 14058:2018+A1:2023

<https://standards.iteh.ai/catalog/standards/sist/9186b936-ebe3-4e82-98a8-974e878ac53e/sist-en-14058-2018a1-2023>

EN 14058:2017+A1:2023 (E)**1 Scope**

This European Standard specifies requirements and test methods for the performance of garments for protection against the effects of cool environments above -5 °C (see Annex C). These effects comprise not only low air temperatures, but also humidity and air velocity.

Cold protective ensembles are excluded from this standard.

The protective effects and requirements of footwear, gloves and separate head wear are excluded from the scope of this standard.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 342:2017, *Protective clothing — Ensembles and garments for protection against cold*

A1 EN ISO 811:2018, *Textiles — Determination of resistance to water penetration — Hydrostatic pressure test (ISO 811:2018)* **A1**

EN ISO 4674-1:2016, *Rubber- or plastics-coated fabrics — Determination of tear resistance — Part 1: Constant rate of tear methods (ISO 4674-1:2016)*

EN ISO 9237:1995, *Textiles — Determination of permeability of fabrics to air (ISO 9237:1995)*

EN ISO 11092:2014, *Textiles — Physiological effects — Measurement of thermal and water-vapour resistance under steady-state conditions (sweating guarded-hotplate test) (ISO 11092:2014)*

EN ISO 13688:2013, *Protective clothing — General requirements (ISO 13688:2013)*

A1 EN ISO 13688:2013/A1:2021, *Protective clothing — General requirements — Amendment 1 (ISO 13688:2013/Amd 1:2021)* **A1**

A1 EN ISO 13938-1:2019, *Textiles — Bursting properties of fabrics — Part 1: Hydraulic method for determination of bursting strength and bursting distension (ISO 13938-1:2019)* **A1**

A1 EN ISO 13938-2:2019, *Textiles — Bursting properties of fabrics — Part 2: Pneumatic method for determination of bursting strength and bursting distension (ISO 13938-2:2019)* **A1**

EN ISO 15831:2004, *Clothing — Physiological effects — Measurement of thermal insulation by means of a thermal manikin (ISO 15831:2004)*

A1 ISO 7000:2019, *Graphical symbols for use on equipment — Registered symbols* **A1**

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

3.1

cool environment

environment characterized by the combination of humidity and wind (wind cooling effect) at air temperatures above $-5\text{ }^{\circ}\text{C}$

3.2

garment

individual component of a clothing ensemble covering a part of the body, except separate garments for head, hands and feet and providing protection against hypothermia and / or local cooling

3.3

ensemble

clothing consisting of a two-piece suit or one-piece suit (coverall) or a number of garments covering the body, except separate garments for head, hands and feet and providing protection against hypothermia

3.4

thermal lining

non-watertight layer providing thermal insulation

3.5

thermal resistance insulation

R_{ct}

temperature difference between the two faces of a material divided by the resultant heat flux per unit area in the direction of the gradient

Note 1 to entry: It is a quantity specific to textile materials or composites which determine the dry heat flux across a given area in response to a steady applied temperature gradient. The dry heat flux can consist of one or more conductive, convective and radiant components.

Note 2 to entry: The thermal resistance is expressed in square metres kelvin per watt.

[SOURCE: EN ISO 11092:2014, 2.1]

3.6

water vapour resistance

R_{et}

water vapour pressure difference between the two faces of a material divided by the resultant evaporative heat flux per unit area in the direction of the gradient

Note 1 to entry: It is a quantity specific to textile materials or composites, which determines the “latent” evaporative heat flux across a given area in response to a steady applied water-vapour pressure gradient. The evaporative heat flux can consist of both diffusive and convective components.

Note 2 to entry: The water-vapour resistance is expressed in square metres pascal per watt.

[SOURCE: EN ISO 11092:2014, 2.2]

EN 14058:2017+A1:2023 (E)**3.7
resultant effective thermal insulation** I_{cler}

thermal insulation from skin to outer clothing surface under defined conditions measured with a moving manikin determined in relation to the naked body surface area

Note 1 to entry: I_{cler} is expressed in square metres kelvin per watt.

**3.8
resistance to water penetration
WP**

hydrostatic pressure supported by a material as a measure of the opposition to the passage of water through material

Note 1 to entry: WP is expressed in pascal.

**3.9
air permeability
AP**

velocity of an air flow passing perpendicularly through a test specimen under specified conditions of test area, pressure drop and time

Note 1 to entry: AP is expressed in millimetre per second.

[SOURCE: EN ISO 9237:1995, 3.1]

**3.10
outer shell material**

outermost material of which the protective clothing is made

4 Performance assessment and requirements**4.1 General requirements and innocuousness****4.1.1 General requirements**

When tested in accordance with 6.2.1 the following requirements shall be met:

- the garment shall not have rough, sharp or hard surfaces that may irritate or injure the user;
- the jacket/coat or coverall shall be closable up to the collar or neckband;
- the jacket/coat shall be long enough to cover the tops of the trousers;
- external pockets intended to be used in wet conditions (see 4.4) shall be closable;
- closures, such as slide fasteners, fasteners, buttons etc. shall not open inadvertently;
- slide fasteners shall lock when completely closed.

NOTE Waistcoats can be lengthened at the back to protect the kidney region against the effects of cool environment.

4.1.2 Innocuousness

A1 When tested in accordance with 6.2.2 the requirements of EN ISO 13688:2013, EN ISO 13688:2013/A1:2021, 4.2, shall be met with regard to innocuousness. **A1**

4.2 Thermal Resistance, R_{ct}

When tested in accordance with 6.3 the thermal resistance, R_{ct} of all layers of the garment shall be classified in accordance with Table 1.

Table 1 — Classification of thermal resistance R_{ct}

R_{ct} m ² · K/W	Class
$0,06 \leq R_{ct} < 0,12$	1
$0,12 \leq R_{ct} < 0,18$	2
$0,18 \leq R_{ct} < 0,25$	3
$0,25 \leq R_{ct}$	4

NOTE The maximum level of protection is given when the thermal insulation is adapted to the ambient temperature and the activity level (examples are given in Annex C). In this case the wearer is in a thermally neutral state. A too high thermal insulation leads to excessive sweating and wetting the garments. As a consequence the effective thermal insulation of the garment is lowered.

Garments containing materials with a thermal resistance above 0,25 m² K/W shall comply with 4.6.

4.3 Air permeability, AP

If the information supplied by the manufacturer indicates that the garment may be used outdoors, the air permeability shall be classified in accordance with Table 2, when the material of the garment is tested in accordance with 6.4.

Table 2 — Classification of air permeability AP

AP mm/s	Class
$100 < AP$	1
$5 < AP \leq 100$	2
$AP \leq 5$	3

Class 1 material layers of a garment should be considered as appropriate for low air velocities of less than 1 m/s as e.g. in cool indoor environments.

Class 2 material layers should be appropriate for air velocities of less than 5 m/s.

NOTE Class 3 materials are appropriate for high air velocities ≥ 5 m/s e.g. common in outdoor activities.