
**Steel wire and wire products — Hose
reinforcement wire**

Fils et produits tréfilés en acier — Fil d'armature pour flexibles

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[ISO 23717:2022](https://standards.iteh.ai/catalog/standards/sist/6b78873e-dcff-4755-bd35-2ced2c2f656e/iso-23717-2022)

<https://standards.iteh.ai/catalog/standards/sist/6b78873e-dcff-4755-bd35-2ced2c2f656e/iso-23717-2022>



iTeh STANDARD PREVIEW
(standards.iteh.ai)

ISO 23717:2022

<https://standards.iteh.ai/catalog/standards/sist/6b78873e-dcff-4755-bd35-2ced2c2f656e/iso-23717-2022>



COPYRIGHT PROTECTED DOCUMENT

© ISO 2022

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Contents

	Page
Foreword.....	iv
1 Scope.....	1
2 Normative references.....	1
3 Terms and definitions.....	1
4 Classification.....	2
5 Designation and ordering.....	2
5.1 Designation.....	2
5.2 Information supplied by the purchaser and items to be agreed upon.....	2
6 Requirements.....	3
6.1 Material.....	3
6.1.1 Steel.....	3
6.1.2 Chemical composition.....	3
6.1.3 Wire.....	3
6.1.4 Coating material.....	3
6.2 Mechanical properties.....	3
6.2.1 Tensile strength, breaking load and elongation.....	3
6.2.2 Reverse bend test.....	3
6.2.3 Torsion test.....	3
6.3 Surface quality.....	6
6.3.1 General.....	6
6.3.2 Coating mass.....	6
6.3.3 Cast and tip rise/dead cast.....	6
6.4 Dimensions and tolerances.....	6
6.4.1 Tolerance on diameter.....	6
6.4.2 Out of roundness.....	6
6.5 Delivery conditions.....	7
6.5.1 Unit package.....	7
6.5.2 Welds.....	7
7 Testing and inspection.....	7
7.1 Testing and inspection documents.....	7
7.2 Scope of test programme for acceptance inspection.....	7
7.3 Test procedures.....	7
7.3.1 Tensile test.....	7
7.3.2 Reverse bend test and torsion test.....	7
7.3.3 Diameter and out of roundness.....	7
7.3.4 Cast and tip rise/dead cast.....	8
7.3.5 Coating test.....	8
7.4 Retests.....	8
8 Marking, labelling and packaging.....	8
Annex A (informative) Packaging of hose reinforcement wire.....	9
Bibliography.....	12

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 17, *Steel*, Subcommittee SC 17, *Steel wire rod and wire products*.

This second edition cancels and replaces the first edition (ISO 23717:2006), which has been technically revised.

The main changes are as follows:

- [Annex A](#) on packaging added;
- [Clause 2](#) updated;
- [Clause 3](#) updated;
- classification from LT to UT updated (see [Clause 4](#));
- Cu content of coating updated (see [6.1.4](#));
- breaking load for mechanical properties added (see [6.2.1](#) and [Table 1](#));
- product list and mechanical properties updated (see [Table 1](#));
- cast and tip rise/dead cast requirement added (see [6.3.3](#) and [Table 3](#));
- tolerance on diameter updated (see [Table 4](#));
- welds requirement updated (see [6.5.2](#));
- test procedures for Cast and tip rise/dead cast and coating test added (see [7.3.4](#) and [7.3.5](#));
- labelling information for packing updated (see [Table 5](#)).

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

ISO 23717:2022

<https://standards.iteh.ai/catalog/standards/sist/6b78873e-dcff-4755-bd35-2ced2c2f656e/iso-23717-2022>

Steel wire and wire products — Hose reinforcement wire

1 Scope

This document specifies the composition, dimensions and mechanical properties of steel wire with a high mass fraction of carbon, generally brass coated, for reinforcing high-pressure hoses.

It is applicable to multiple parallel wires, braided or spirally wrapped for reinforcement in a rubber or synthetic hose that is made to withstand a relatively high bursting pressure.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 404, *Steel and steel products — General technical delivery requirements*

ISO 6892-1, *Metallic materials — Tensile testing — Part 1: Method of test at room temperature*

ISO 7800, *Metallic materials — Wire — Simple torsion test*

ISO 7801, *Metallic materials — Wire — Reverse bend test*

ISO 10474, *Steel and steel products — Inspection documents*

ISO 16120-1, *Non-alloy steel wire rod for conversion to wire — Part 1: General requirements*

ISO 16120-2, *Non-alloy steel wire rod for conversion to wire — Part 2: Specific requirements for general purpose wire rod*

ISO 16120-4, *Non-alloy steel wire rod for conversion to wire — Part 4: Specific requirements for wire rod for special applications*

ISO 23475-1, *Testing method for steel tyre cord — Part 1: General requirements*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminology databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <https://www.electropedia.org/>

3.1

nominal diameter

d

value of the diameter by which the wire is designated and specified by the purchaser

Note 1 to entry: The nominal diameter is expressed in millimetres.

Note 2 to entry: This is the basis on which the values of all relevant characteristics are determined for the acceptance of the wire.

3.2

out of roundness

arithmetic difference between the maximum and minimum diameter measured in a transverse cross-section perpendicular to the wire axis

3.3

cast

smallest external diameter of a wire loops naturally formed when placed on a smooth surface without external tension

3.4

tip rise/dead cast

vertical height of the cut wire end that protrudes above the flat and smooth surface, on which the wire is placed without external tension

4 Classification

Hose wire is classified according to five classes of tensile strength.

- LT: Low tensile strength, 2 150 MPa to 2 450 MPa;
- NT: Normal tensile strength, 2 450 MPa to 2 750 MPa;
- HT: High tensile strength, 2 750 MPa to 3 050 MPa;
- ST: Super tensile strength, 3 050 MPa to 3 350 MPa;
- UT: Ultra tensile strength, 3 350 MPa to 3 650 MPa.

5 Designation and ordering

[ISO 23717:2022](https://standards.iteh.ai/catalog/standards/sist/6b78873e-dcff-4755-bd35-2ced2c2f656e/iso-23717-2022)

5.1 Designation

<https://standards.iteh.ai/catalog/standards/sist/6b78873e-dcff-4755-bd35-2ced2c2f656e/iso-23717-2022>

For hose wire supplies, the designation shall state, in the following order:

- the term: hose wire;
- the coating: see [6.1.4](#);
- a reference to this document, i.e. ISO 23717:2022;
- the tensile strength class (see [Clause 4](#)) and the nominal tensile strength;
- the nominal diameter.

Example Brass coated hose wire, 0,30 mm, high tensile strength HT in accordance with ISO 23717 shall be designated.

Hose wire brass coated ISO 23717-HT-0,30.

5.2 Information supplied by the purchaser and items to be agreed upon

The purchaser shall clearly state the following information concerning the product in the enquiry or order:

- the required nominal diameter;
- the desired quantity;
- the coating material;

— the type of inspection document.

EXAMPLE 20 t hose wire brass coated ISO 23717-HT-0,30 on spools of 30 kg doc ISO 10474-“3.1”.

6 Requirements

6.1 Material

6.1.1 Steel

The wire shall be manufactured from steel rod in accordance with ISO 16120-1 and ISO 16120-2 for tensile strengths LT and NT, and in accordance with ISO 16120-4 for tensile strengths HT, ST and UT.

6.1.2 Chemical composition

The chemical composition according to the heat analysis and the permissible deviation of the product analysis from the heat analysis shall be in accordance with ISO 16120-2 and ISO 16120-4.

In cases of dispute, the analysis shall be carried out by a laboratory approved by the two parties. The method of analysis to be applied shall be agreed upon, see for example ISO/TR 9769.

6.1.3 Wire

The wire shall be patented or hard rolled and cold drawn in order to provide the required mechanical properties.

6.1.4 Coating material

If not otherwise stipulated by the purchaser at the time of enquiry or order (see 5.2), the coating material shall be brass with a chemical composition of Cu: $(67,5 \pm 4)$ %. A tighter range may be agreed upon.

In the case of other coatings, the specification shall be agreed between the purchaser and supplier at the time of enquiry or order.

6.2 Mechanical properties

6.2.1 Tensile strength, breaking load and elongation

Purchaser and supplier can agree to specify the tensile strength class and diameter, or breaking load range and diameter.

When tested in accordance with 7.3.1 before and after the braiding operation, the wire shall conform to the tensile strength or breaking load values and have an elongation at rupture as specified in Table 1.

6.2.2 Reverse bend test

When tested in accordance with 7.3.2, the wire shall withstand the minimum number of reverse bends (N_b), as specified in Table 1 without rupture.

6.2.3 Torsion test

When tested in accordance with 7.3.2, the wire shall withstand the minimum number of torsions (N_t), as specified in Table 1 without fracture.

Table 1 — Mechanical properties

Diameter, d mm	Tensile strength class ^a MPa	Breaking load range ^b N	Elongation at rupture A_r , %, min.	Reverse bends (N_b) on r2,5 mm min.	Torsion (N_t) ($l=200d$) min.
Low tensile strength (LT)					
0,28	2 150 to 2 450	129 to 154	1,6	125	80
0,295	2 150 to 2 450	143 to 171	1,6	105	78
0,30	2 150 to 2 450	148 to 177	1,6	105	78
0,35	2 150 to 2 450	203 to 239	1,6	85	72
0,38	2 150 to 2 450	241 to 281	1,6	75	70
0,40	2 150 to 2 450	267 to 311	1,6	65	68
0,45	2 150 to 2 450	339 to 392	1,8	55	63
0,50	2 150 to 2 450	420 to 483	1,9	46	60
0,56	2 150 to 2 450	529 to 604	2,0	45	55
0,60	2 150 to 2 450	608 to 693	2,0	40	52
0,65	2 150 to 2 450	715 to 812	2,2	35	48
0,71	2 150 to 2 450	854 to 967	2,2	30	45
0,75	2 150 to 2 450	954 to 1 078	2,2	24	40
0,78	2 150 to 2 450	1 033 to 1 165	2,2	23	37
0,80	2 150 to 2 450	1 087 to 1 225	2,2	22	35
1,00	2 150 to 2 450	1 705 to 1 908	2,5	10	15
Normal tensile strength (NT)					
0,20	2 450 to 2 750	73 to 90	1,6	170	85
0,22	2 450 to 2 750	89 to 109	1,6	150	82
0,25	2 450 to 2 750	116 to 139	1,6	125	78
0,28	2 450 to 2 750	146 to 174	1,6	110	76
0,295	2 450 to 2 750	163 to 192	1,6	95	74
0,30	2 450 to 2 750	169 to 199	1,6	95	74
0,33	2 450 to 2 750	205 to 240	1,6	85	69
0,35	2 450 to 2 750	231 to 269	1,6	80	67
0,38	2 450 to 2 750	273 to 316	1,6	65	66
0,40	2 450 to 2 750	303 to 350	1,6	60	65
0,45	2 450 to 2 750	386 to 441	1,8	50	58
0,50	2 450 to 2 750	478 to 544	1,9	35	55
0,56	2 450 to 2 750	601 to 680	2,0	30	49
0,60	2 450 to 2 750	691 to 779	2,0	28	47
Normal tensile strength (NT)					
0,65	2 450 to 2 750	812 to 913	2,2	27	43
0,71	2 450 to 2 750	971 to 1 088	2,2	25	40
0,75	2 450 to 2 750	1 085 to 1 213	2,2	23	36
0,78	2 450 to 2 750	1 174 to 1 311	2,2	21	33
NOTE Special requirement can be determined by agreement between the purchaser and the supplier.					
^a Tensile strength and breaking load should be measured fresh and may increase above the upper limit after natural ageing.					
^b The breaking load range is calculated based on 6 sigma method.					

Table 1 (continued)

Diameter, d mm	Tensile strength class ^a MPa	Breaking load range ^b N	Elongation at rupture A_r , %, min.	Reverse bends (N_b) on r2,5 mm min.	Torsion (N_t) ($l=200d$) min.
0,80	2 450 to 2 750	1 235 to 1 378	2,2	20	30
High tensile strength (HT)					
0,20	2 750 to 3 050	82 to 100	1,3	160	80
0,22	2 750 to 3 050	100 to 121	1,6	145	80
0,25	2 750 to 3 050	130 to 155	1,6	120	76
0,28	2 750 to 3 050	164 to 193	1,6	100	74
0,295	2 750 to 3 050	183 to 214	1,6	85	72
0,30	2 750 to 3 050	189 to 221	1,6	85	72
0,33	2 750 to 3 050	230 to 266	1,6	74	66
0,35	2 750 to 3 050	259 to 299	1,6	66	64
0,38	2 750 to 3 050	306 to 352	1,6	60	61
0,40	2 750 to 3 050	340 to 389	1,6	50	57
0,45	2 750 to 3 050	432 to 491	1,8	40	50
0,50	2 750 to 3 050	535 to 604	1,9	25	45
0,56	2 750 to 3 050	673 to 756	2,0	25	41
0,60	2 750 to 3 050	774 to 866	2,0	20	39
0,65	2 750 to 3 050	910 to 1 015	2,2	20	35
0,71	2 750 to 3 050	1 087 to 1 209	2,2	15	32
0,80	2 750 to 3 050	1 384 to 1 532	2,2	15	25
Super tensile strength (ST)					
0,20	3 050 to 3 350	91 to 110	1,3	110	70
0,25	3 050 to 3 350	144 to 170	1,6	80	65
0,28	3 050 to 3 350	182 to 212	1,6	75	62
0,295	3 050 to 3 350	202 to 235	1,6	60	60
0,30	3 050 to 3 350	209 to 243	1,6	60	60
0,33	3 050 to 3 350	254 to 293	1,6	50	58
0,38	3 050 to 3 350	339 to 387	1,6	40	50
0,40	3 050 to 3 350	376 to 428	1,6	35	45
0,50	3 050 to 3 350	592 to 664	2,0	25	35
0,56	3 050 to 3 350	754 to 831	2,0	20	30
Super tensile strength (ST)					
0,60	3 050 to 3 350	857 to 953	2,0	15	21
0,71	3 050 to 3 350	1 204 to 1 330	2,0	12	15
Ultra tensile strength (UT)					
0,25	3 350 to 3 650	158 to 186	1,6	55	54
0,295	3 350 to 3 650	221 to 257	1,6	40	52
0,30	3 350 to 3 650	229 to 265	1,6	40	52

NOTE Special requirement can be determined by agreement between the purchaser and the supplier.

^a Tensile strength and breaking load should be measured fresh and may increase above the upper limit after natural ageing.

^b The breaking load range is calculated based on 6 sigma method.