

---

---

**Rubber, raw natural — Determination  
of the gel content of technically  
specified rubber (TSR)**

*Caoutchouc naturel brut — Détermination de la teneur en gel des  
caoutchoucs spécifiés techniquement (TSR)*

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

[ISO 17278:2020](https://standards.iteh.ai/catalog/standards/sist/dc214db4-4c8b-4654-be8a-ed0e126da0fb/iso-17278-2020)

[https://standards.iteh.ai/catalog/standards/sist/dc214db4-4c8b-4654-be8a-  
ed0e126da0fb/iso-17278-2020](https://standards.iteh.ai/catalog/standards/sist/dc214db4-4c8b-4654-be8a-ed0e126da0fb/iso-17278-2020)



**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

ISO 17278:2020

<https://standards.iteh.ai/catalog/standards/sist/dc214db4-4c8b-4654-be8a-ed0e126da0fb/iso-17278-2020>



**COPYRIGHT PROTECTED DOCUMENT**

© ISO 2020

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office  
CP 401 • Ch. de Blandonnet 8  
CH-1214 Vernier, Geneva  
Phone: +41 22 749 01 11  
Fax: +41 22 749 09 47  
Email: [copyright@iso.org](mailto:copyright@iso.org)  
Website: [www.iso.org](http://www.iso.org)

Published in Switzerland

# Contents

	Page
Foreword.....	iv
<b>1 Scope</b> .....	<b>1</b>
<b>2 Normative references</b> .....	<b>1</b>
<b>3 Terms and definitions</b> .....	<b>1</b>
<b>4 Principle</b> .....	<b>1</b>
<b>5 Reagent</b> .....	<b>1</b>
<b>6 Apparatus</b> .....	<b>2</b>
<b>7 Conditions</b> .....	<b>2</b>
<b>8 Procedure</b> .....	<b>2</b>
8.1 Number of test samples.....	2
8.2 Procedure.....	2
<b>9 Expression of the result</b> .....	<b>3</b>
<b>10 Precision</b> .....	<b>4</b>
<b>11 Test report</b> .....	<b>4</b>
<b>Annex A (informative) Precision</b> .....	<b>5</b>
<b>Bibliography</b> .....	<b>7</b>

**iTeh STANDARD PREVIEW**  
(standards.iteh.ai)

[ISO 17278:2020](https://standards.iteh.ai/catalog/standards/sist/dc214db4-4c8b-4654-be8a-ed0e126da0fb/iso-17278-2020)

<https://standards.iteh.ai/catalog/standards/sist/dc214db4-4c8b-4654-be8a-ed0e126da0fb/iso-17278-2020>

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see [www.iso.org/directives](http://www.iso.org/directives)).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see [www.iso.org/patents](http://www.iso.org/patents)).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see [www.iso.org/iso/foreword.html](http://www.iso.org/iso/foreword.html).

This document was prepared by Technical Committee ISO/TC 45, *Rubber and rubber products*, Subcommittee SC 3, *Raw materials (including latex) for use in the rubber industry*.

This second edition cancels and replaces the first edition (ISO 17278:2013), which has been technically revised.

The main changes compared to the previous edition are as follows:

- to solve the ambiguity with the scope, the term “LoV-TSR sample” in [Clause 4](#) has been replaced by the term “TSR sample”;
- in [8.1](#), the words “two samples” have been replaced by “two test samples”;
- in [5.2](#), acetone has been added.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at [www.iso.org/members.html](http://www.iso.org/members.html).

# Rubber, raw natural — Determination of the gel content of technically specified rubber (TSR)

**WARNING** — Persons using this document should be familiar with normal laboratory practice. This document does not purport to address all of the safety problems, if any, associated with its use. It is the responsibility of the user to establish appropriate safety and health practices.

## 1 Scope

This document specifies a method for the determination of gel content for technically specified rubbers (TSR).

## 2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 2000:2014, *Rubber, raw natural — Guidelines for the specification of technically specified rubber (TSR)*

ISO 23529, *Rubber — General procedures for preparing and conditioning test pieces for physical test methods*

## 3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <http://www.electropedia.org/>

### 3.1

#### technically specified rubber

#### TSR

natural rubber obtained from the latex of *Hevea brasiliensis* (typically processed into block rubber), and having properties complying with the criteria for the grade concerned

## 4 Principle

A TSR sample is dissolved in toluene under specified conditions, and the gel content is calculated as the percentage mass fraction of the insoluble part of the rubber.

## 5 Reagent

Use only reagents of recognized analytical grade.

### 5.1 Toluene, analytical grade.

**CAUTION** — The solvent might evaporate from the flask or tube when it is handled. Therefore, handling this solvent should be done only when permitted and only in a well-ventilated appropriate place.

5.2 **Acetone**, analytical grade.

## 6 Apparatus

6.1 **Laboratory centrifuge**, capable of rotating at a minimum of 14 000 r/min (revolutions per minute).

If the above speed cannot be attained a minimum speed of 8 000 r/min may be used with a longer running time (8.2.4).

NOTE When the centrifugal rotational frequency (rotational speed) is 14 000 r/min, the gravitational acceleration is 22 000*g*. When the centrifugal rotation speed is 8 000 r/min, the gravitational acceleration is 7 000*g*.

6.2 **Screw-cap centrifuge tubes**, with a minimum capacity of 30 cm<sup>3</sup>, capable of withstanding the centrifuge conditions and of being heated to a temperature greater than 110 °C.

6.3 **Balance**, capable of accurately weighing to ± 0,1 mg.

6.4 **Laboratory oven**, gravity convection type, capable of controlling the temperature to ± 10 °C.

6.5 **Weighing container**, i.e. an aluminium box or plate for weighing.

## 7 Conditions

iTeh STANDARD PREVIEW  
(standards.iteh.ai)

Laboratory conditions shall be controlled in accordance with ISO 23529.

## 8 Procedure

ISO 17278:2020  
<https://standards.iteh.ai/catalog/standards/sist/dc214db4-4c8b-4654-be8a-ed0e126da0fb/iso-17278-2020>

### 8.1 Number of test samples

Two test samples shall be taken in accordance with Clause 7 of ISO 2000:2014.

### 8.2 Procedure

8.2.1 Take a test sample from a bale without milling of mass calculated at the ratio of 0,1 g per 30 cm<sup>3</sup> of toluene.

NOTE When the volume of a centrifuge tube is 50 cm<sup>3</sup>, the volume of toluene is 30 cm<sup>3</sup> (see 8.2.3), and the sample weight is 0,1 g.

8.2.2 Cut the test sample into approximately 1 mm<sup>3</sup>-sized pieces using clean scissors. Weigh the prepared test pieces to the nearest 0,1 mg ( $m_0$ ). Place the pieces in a clean centrifuge tube (6.2), which has previously been heated at 100 °C for 1 h and stored in a desiccator.

8.2.3 Add toluene to the tube until it is 60 % full. Cap it and shake by hand for a few seconds. Then, allow it to stand for 16 h to 20 h in dark conditions without stirring at (25 ± 2) °C.

**8.2.4** After this period, shake the tube up and down for 60 s to disperse the jelly-like precipitate on the bottom.

Before placing the tubes in the centrifuge machine, all tubes shall be filled up with fresh toluene, so that the volume of solution is the same in all tubes.

NOTE A centrifuge tube is usually filled up with solution to minimize the dead space created at the top of the tube because of the vacuum-pressured environment during rotation.

Place the tubes in the centrifuge machine and operate the machine at 14 000 r/min for 2 h.

If the rotating capacity of the centrifuge machine is below 14 000 r/min, operate the machine at 8 000 r/min for 6 h.

A set temperature of centrifuge is usually indicated in the operation manual for safety reasons. If not, it may be set to between 0 °C and 25 °C.

**8.2.5** Remove the tube from the machine and pipette the liquid from the tube held at approximately 45°. Caution shall be taken to prevent pipetting the precipitate.

**8.2.6** Add 1 ml to 3 ml of acetone to the precipitate so that it can be easily peeled from the bottom of the tube. Leave to stand for over 30 s and then pipette the liquid from the tube.

**8.2.7** Peel off the precipitate remaining at the bottom of the tube with a spatula or a spatula-like stick and move it into the container (6.5) which has been cleaned and weighed to the nearest 1 mg ( $m_1$ ). A limited amount of acetone may be used to rinse the spatula, if necessary.

**8.2.8** Store the container in a fume cupboard for 30 min to allow the solvent to evaporate, in order to prevent flashing of the solvent during heating. Place the container containing the precipitate in the oven and dry it at the temperature of 110 °C for 1 h.

**8.2.9** Take the container out of the oven and allow it to cool in a desiccator for 30 min.

**8.2.10** Weigh the container containing the dry precipitate to the nearest 0,1 mg ( $m_2$ ).

**8.2.11** Repeat the procedure in 8.2.8, 8.2.9 and 8.2.10 until the loss in mass between two successive weighings is less than 0,2 mg. Note the period of drying time for the first test piece and use it for the next test piece for the series of testing. Record the final mass ( $m_2$ ).

## 9 Expression of the result

To determine the gel content, use [Formula \(1\)](#) and round the result to one decimal place.

$$G = \frac{(m_2 - m_1)}{m_0} \times 100 \quad (1)$$

where

$G$  is the gel content, as a percentage (%);

$m_0$  is the mass of the original test piece (8.2.2), in grams (g);

$m_1$  is the mass of the empty container (8.2.7), in grams (g);

$m_2$  is the mass of the container containing dry precipitate (8.2.10), in grams (g).

Take an average of two gel content values.

## 10 Precision

See [Annex A](#).

## 11 Test report

The test report shall include the following information:

- a) a reference to this document including its year of publication, i.e. ISO 17278:2020;
- b) all details necessary for identification of the test sample;
- c) the test method;
- d) the laboratory temperature;
- e) the centrifuge diameter, the temperature, the speed and the running time of the test;
- f) details of any operation not specified in this document;
- g) the results;
- h) the number of test pieces tested;
- i) the individual test results;
- j) the mean result;
- k) the details of any unusual features noted during the determination;
- l) the date of the test.

**iTeh STANDARD PREVIEW**  
(standards.iteh.ai)  
<https://standards.iteh.ai/catalog/standards/sist/dc214db4-4c8b-4654-be8a-ed0e126da0fb/iso-17278-2020>



## Annex A (informative)

### Precision

#### A.1 General

An interlaboratory test program (ITP) for the precision evaluation of the test method for TSR gel content was planned and conducted in January and February 2011. The calculations were carried out in accordance with ISO/TR 9272<sup>1)</sup>. Ten laboratories from five countries participated in this ITP.

Three TSR samples with different levels of gel content were prepared for this ITP as shown in [Table A.1](#). They were sent out to each laboratory with instructions to carry out the test as soon as the samples were received. The test was carried out on two different days at one-week intervals with two tests each day ( $n = 2$ ).

The precision results as determined by this ITP should not be used for acceptance/rejection testing of any group of materials or products without documentation that the results are applicable to those particular materials or products and the specific test protocol of this test method.

**Table A.1 — TSR sample**

	Sample A	Sample B	Sample C
Gel content level	Low	Medium	High
NOTE Each sample should be appropriately stored in a conditioned place until all the tests are completed.			

The precision results are given in [Table A.2](#). These results were obtained using outlier deletion procedures as described in ISO/TR 9272.

#### A.2 Repeatability

The repeatability,  $r$ , of the test method was established as the appropriate value tabulated in [Table A.2](#) for each material. Two single test results that differ by more than the value shall be considered suspect, and it is recommended that some appropriate investigative action be taken.

#### A.3 Reproducibility

The reproducibility,  $R$ , of the test method was established as the appropriate value tabulated in [Table A.2](#) for each material. Two single test results that differ by more than the value shall be considered suspect, and it is recommended that some appropriate investigative action be taken.

<sup>1)</sup> Withdrawn. Now replaced by ISO 19983.