
Železniške naprave - Varjenje železniških vozil in elementov - 3. del: Zahteve za projektiranje (vključuje dopolnilo A1)

Railway applications - Welding of railway vehicles and components - Part 3: Design requirements

Bahnanwendungen - Schweißen von Schienenfahrzeugen und -fahrzeugteilen - Teil 3: Konstruktionsvorgaben

Applications ferroviaires - Soudage des véhicules ferroviaires et des pièces - Partie 3 : Exigences de conception

Ta slovenski standard je istoveten z: EN 15085-3:2022+A1:2023

ICS:

25.160.10	Varilni postopki in varjenje	Welding processes
45.060.01	Železniška vozila na splošno	Railway rolling stock in general

SIST EN 15085-3:2023+A1:2023 **en,fr,de**

EUROPEAN STANDARD
NORME EUROPÉENNE
EUROPÄISCHE NORM

EN 15085-3:2022+A1

April 2023

ICS 25.160.10; 45.060.01

Supersedes EN 15085-3:2022

English Version

Railway applications - Welding of railway vehicles and
components - Part 3: Design requirements

Applications ferroviaires - Soudage des véhicules
ferroviaires et des pièces - Partie 3 : Exigences de
conception

Bahnanwendungen - Schweißen von
Schienenfahrzeugen und -fahrzeugteilen - Teil 3:
Konstruktionsvorgaben

This European Standard was approved by CEN on 5 September 2022 and includes Amendment 1 approved by CEN on 1 February 2023.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Türkiye and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels

Contents

Page

European foreword	4
Introduction	6
1 Scope.....	7
2 Normative references.....	7
3 Terms and definitions	9
4 Design requirements	9
4.1 General.....	9
4.2 Dimensioning of welded joints	10
4.3 Stress categories and stress factors	10
4.4 Safety categories	10
4.5 Weld performance classes.....	10
4.6 Weld inspection classes.....	11
5 Quality levels for imperfections	12
5.1 General.....	12
5.2 Quality levels for imperfections for fusion welded joints (beam welding excluded)	12
5.3 Quality levels for imperfections for beam welded joints	13
5.3.1 General.....	13
5.3.2 Quality levels for imperfection for friction stir welding.....	14
5.3.3 Quality levels for imperfections for stud welding related to the weld performance class.....	14
5.3.4 Quality requirements for resistance spot welding, projection welding and resistance seam welding related to the weld performance class	14
5.3.5 Quality requirements for flash welding.....	15
5.3.6 Defining quality requirements for other welding processes	15
6 Selection of parent metals and welding consumables	15
6.1 Selection of parent metals	15
6.2 Selection of welding consumables	15
7 Weld joint design	16
7.1 General.....	16
7.2 Design guidelines.....	16
7.2.1 Fabricated box sections	16
7.2.2 Butt welds on parts of dissimilar thickness	17
7.2.3 Plug welds and slot welds	18
7.2.4 Proximity of two joints.....	19
7.2.5 Stiffeners welded across a butt weld	19
7.2.6 Openings	20
7.2.7 Design guidelines for stiffeners and gussets ends	20
7.2.8 Gusset shape	20
7.2.9 Weld return.....	21
7.2.10 Fillet weld	22
7.2.11 Use of run-on and run-off plates.....	23
7.2.12 Highly restrained joints.....	23
7.2.13 Mixing of joining techniques.....	24

7.2.14	Prevention of corrosion problems	25
7.2.15	Intermittent welds.....	25
7.3	Joint preparation.....	26
7.4	Methods to improve the fatigue strength (Post weld improvement)	26
7.4.1	General.....	26
7.4.2	Improvement of shape of weld toe	27
7.4.3	Post Weld Heat Treatment (PWHT) — stress relief.....	27
7.4.4	Introduction of compressive stress.....	28
8	Design documentation related to welding.....	28
8.1	Information on design drawings or documentation linked to the drawings	28
8.2	Design review of welded components.....	29
8.3	Use of existing drawings not according to EN 15085.....	30
Annex A	(informative) List of welded joints (example)	31
Annex B	(informative) Joint preparation of welds	32
Annex C	(informative) Joint preparation for plug welds	40
Annex D	(informative) Types of joints in relation to stresses and inspection classes.....	41
Annex E	(informative) Flash welding.....	42
Annex F	(normative) Resistance spot, seam and projection welding	45
F.1	General.....	45
F.2	Minimum shear pull forces.....	50
Annex G	(informative) Determination of safety category for welded joints	52
Annex ZA	(informative) Relationship between this European Standard and the Essential requirements of Directive (EU) 2016/797 aimed to be covered.....	53
Bibliography	55

EN 15085-3:2022+A1:2023 (E)

European foreword

This document (EN 15085-3:2022+A1:2023) has been prepared by Technical Committee CEN/TC 256 “Railway applications”, the secretariat of which is held by DIN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by October 2023, and conflicting national standards shall be withdrawn at the latest by October 2023.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

This document includes Amendment 1 approved by CEN on 1 February 2023.

This document supersedes A1 EN 15085-3:2022 A1.

The start and finish of text introduced or altered by amendment is indicated in the text by tags A1 A1.

This series of European Standards EN 15085 “*Railway applications — Welding of railway vehicles and components*” consists of the following parts:

- *Part 1: General*
- *Part 2: Requirements of the organization of welding manufacturer*
- *Part 3: Design requirements*
- *Part 4: Production requirements*
- *Part 5: Inspection, testing and documentation*
- *Part 6: Maintenance*

EN 15085-3:2022 includes the following changes with respect to EN 15085-3:2007.

- The weld performance class CP B has been divided into CP B1 and CP B2 (see Table 2);
- Terms and definitions have been updated;
- The following annexes have been reworked accordingly;
 - Annex H has been deleted and part of its content has been integrated into the main text (see 6.2 and 7.1);
 - Annex ZA has been added.

This document has been prepared under a Standardization Request given to CEN by the European Commission and the European Free Trade Association, and supports essential requirements of EU Directive(s) / Regulation(s).

For relationship with EU Directive(s) / Regulation(s), see informative Annex ZA, which is an integral part of this document.

Any feedback and questions on this document should be directed to the users' national standards body. A complete listing of these bodies can be found on the CEN website.

According to the CEN-CENELEC Internal Regulations, the national standards organisations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Türkiye and the United Kingdom.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN 15085-3:2023+A1:2023

<https://standards.iteh.ai/catalog/standards/sist/0a4b913c-3538-40bc-84c2-8e0f84eb1c24/sist-en-15085-3-2023a1-2023>

EN 15085-3:2022+A1:2023 (E)**Introduction**

Welding is a special process in the manufacture of railway vehicles and their parts. The required provisions for this process are laid down in the standards series EN ISO 3834. The basis of these provisions is the basic technical welding standards with respect to the special requirements for the construction of railway vehicles.

This series of standards applies to welding of metallic materials in the manufacture and maintenance of railway vehicles and their parts.

It describes the control for the welding process for railway vehicles and their components for new manufacture and maintenance.

With respect to the railway environment, this series of standards defines the quality requirements for the welding manufacturer to undertake new building and repair work.

Components, parts and subassemblies are assigned a classification level, based on their safety relevance.

According to these levels, qualifications for welding personnel of the manufacturer are specified.

This series provides an essential link between the weld performance class defined during design, the quality of the weld, and the demonstration of the required quality by inspection.

This series of standards does not deal with product qualification.

NOTE This series of standard can also be used by internal and external parties, including certification bodies, to assess the organization's ability to meet customer, regulatory and the organization's own requirements.

ITEH STANDARD PREVIEW
(standards.iteh.ai)

SIST EN 15085-3:2023+A1:2023

<https://standards.iteh.ai/catalog/standards/sist/0a4b913c-3538-40bc-84c2-8e0f84eb1e24/sist-en-15085-3-2023a1-2023>

1 Scope

This document applies to welding of metallic materials in the manufacture and maintenance of railway vehicles and their components.

This document specifies applicable design and classification rules.

This document does not specify parameters for the dimensioning.

NOTE Requirements for structures can be found in other standards (e.g. EN 12663).

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 1011-2:2001, *Welding - Recommendations for welding of metallic materials - Part 2: Arc welding of ferritic steels*

EN 12663-1:2010+A1:2014, *Railway applications - Structural requirements of railway vehicle bodies - Part 1: Locomotives and passenger rolling stock (and alternative method for freight wagons)*

EN 12663-2:2010, *Railway applications - Structural requirements of railway vehicle bodies - Part 2: Freight wagons*

EN 13749:2021, *Railway applications - Wheelsets and bogies - Method of specifying the structural requirements of bogie frames*

EN 15085-1:—,¹ *Railway applications — Welding of railway vehicles and components — Part 1: General*

EN 15085-2:2020, *Railway applications - Welding of railway vehicles and components - Part 2: Requirements for welding manufacturer*

EN 15085-4:—,² *Railway applications — Welding of railway vehicles and components — Part 4: Production requirements*

EN 15085-5:—,³ *Railway applications — Welding of railway vehicles and components — Part 5: Inspection, testing and documentation*

EN 15085-6:—,⁴ *Railway applications — Welding of railway vehicles and components — Part 6: Maintenance welding requirements*

EN 15827:2011, *Railway applications - Requirements for bogies and running gears*

¹ Under preparation. Stage at the time of publication: prEN 15085-1:2021

² Under preparation. Stage at the time of publication: prEN 15085-4:2020

³ Under preparation. Stage at the time of publication: FprEN 15085-5:2021

⁴ Under preparation. Stage at the time of publication: FprEN 15085-6:2021

EN 15085-3:2022+A1:2023 (E)

EN ISO 2553:2019, *Welding and allied processes - Symbolic representation on drawings - Welded joints (ISO 2553:2019, Corrected version 2021-09)*

EN ISO 3452-1:2021, *Non-destructive testing - Penetrant testing - Part 1: General principles (ISO 3452-1:2021)*

EN ISO 4063:2010, *Welding and allied processes - Nomenclature of processes and reference numbers (ISO 4063:2009, Corrected version 2010-03-01)*

EN ISO 5817:2014, *Welding - Fusion-welded joints in steel, nickel, titanium and their alloys (beam welding excluded) - Quality levels for imperfections (ISO 5817:2014)*

EN ISO 6520-1:2007, *Welding and allied processes - Classification of geometric imperfections in metallic materials - Part 1: Fusion welding (ISO 6520-1:2007)*

EN ISO 6520-2:2013, *Welding and allied processes - Classification of geometric imperfections in metallic materials - Part 2: Welding with pressure (ISO 6520-2:2013)*

EN ISO 10042:2018, *Welding - Arc-welded joints in aluminium and its alloys - Quality levels for imperfections (ISO 10042:2018)*

EN ISO 10675-2:2021, *Non-destructive testing of welds — Acceptance levels for radiographic testing — Part 2: Aluminium and its alloys (ISO 10675-2:2021)*

EN ISO 13919-1:2019, *Electron and laser-beam welded joints - Requirements and recommendations on quality levels for imperfections - Part 1: Steel, nickel, titanium and their alloys (ISO 13919-1:2019)*

EN ISO 13919-2:2021, *Electron and laser-beam welded joints - Requirements and recommendations on quality levels for imperfections - Part 2: Aluminium, magnesium and their alloys and pure copper (ISO 13919-2:2021)* <https://standards.iteh.ai/catalog/standards/sist/0a4b913c-3538-40bc-84c2-8e0f84eb1e24/sist-en-15085-3-2023a1-2023>

EN ISO 13920:1996, *Welding - General tolerances for welded constructions - Dimensions for lengths and angles - Shape and position (ISO 13920:1996)*

EN ISO 14555:2017, *Welding - Arc stud welding of metallic materials (ISO 14555:2017)*

EN ISO 15614-1:2017,⁵ *Specification and qualification of welding procedures for metallic materials — Welding procedure test — Part 1: Arc and gas welding of steels and arc welding of nickel and nickel alloys (ISO 15614-1:2017)*

EN ISO 15614-12:2021, *Specification and qualification of welding procedures for metallic materials - Welding procedure test - Part 12: Spot, seam and projection welding (ISO 15614-12:2021)*

EN ISO 17636-1:2022, *Non-destructive testing of welds — Radiographic testing — Part 1: X- and gamma-ray techniques with film (ISO 17636-1:2022)*

EN ISO 17637:2016, *Non-destructive testing of welds - Visual testing of fusion-welded joints (ISO 17637:2016)*

⁵ Document impacted by A1:2019.

EN ISO 17653:2012, *Resistance welding - Destructive tests on welds in metallic materials - Torsion test of resistance spot welds (ISO 17653:2012)*

EN ISO 17663:2009, *Welding - Quality requirements for heat treatment in connection with welding and allied processes (ISO 17663:2009)*

EN ISO 23277:2015, *Non-destructive testing of welds - Penetrant testing - Acceptance levels (ISO 23277:2015)*

EN ISO 25239-5:2020, *Friction stir welding - Aluminium - Part 5: Quality and inspection requirements (ISO 25239-5:2020)*

EN ISO 10447:2015, *Resistance welding - Testing of welds - Peel and chisel testing of resistance spot and projection welds (ISO 10447:2015)*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in EN 15085-1:-¹ apply.

ISO and IEC maintain terminology databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <https://www.electropedia.org/>

3.1

stress factor

ratio of the calculated / measured fatigue stress to the admissible fatigue stress of the joint type, adjusted by the appropriate safety factor

3.2

admissible fatigue stress

maximum fatigue stress applicable to the welded joint according to the applicable standard / specification

4 Design requirements

4.1 General

All welded joints produced under the scope of the EN 15085 series shall be designed according to the requirements of this document unless more stringent product / project specific requirements are defined.

A stress assessment shall be done for new designs. For existing designs not according to EN 15085, the requirements of EN 15085-6:-⁴ shall apply.

Results of the stress assessment shall be used in combination with the safety category to define the weld performance class (CP) according to Table 2. The weld performance class for each weld shall be identified on the manufacturing drawing or associated technical documentation.

If the strength assessment procedure already considers the weld performance class (i.e. the quality levels for imperfections and the weld inspection class), and the safety category according to the definition given in this document, then Table 1 and 2 do not need to be applied.

EN 15085-3:2022+A1:2023 (E)

NOTE EN 17149-3:-⁵ provides such a procedure.

Irrespective of the method of assessment, for welded joints with high safety category the weld performance classes according to this document (CP A, CP B1, CP C1) shall be chosen.

CP D is only allowed for low safety category.

4.2 Dimensioning of welded joints

For dimensioning and preparation of different types of welded joints see Annexes B and C.

4.3 Stress categories and stress factors

The stress category is determined by the stress factor according to Table 1, (see 3.1).

The fatigue strength value can be obtained by calculation according to the appropriate standard / guideline or fatigue tests on representative joint samples.

The statistical evaluation of the fatigue tests shall be done according to an appropriate standard. The verification of strength should be carried out using only one coherent system for calculation.

European standards for structural requirements of railway vehicles, e.g. EN 12663-1:2010+A1:2014, EN 12663-2:2010, EN 13749:2021, EN 15827:2011, shall be applied.

Table 1 — Stress categories

Stress category	Stress factor (S)
High	$\geq 0,9$
Medium	$0,75 \leq S < 0,9$
Low	$\leq 0,75$

4.4 Safety categories

The safety category defines the consequences of failure of a single welded joint with respect to its effect on persons, facilities and the environment.

The safety categories are differentiated as follows:

- Low:** Failure of the welded joint does not lead to any direct impairment of the overall function. Consequential events with personal injuries are unlikely.
- Medium:** Failure of the welded joint leads to an impairment of the overall function or can lead to consequential events with personal injuries.
- High:** Failure of the welded joint leads to consequential events with personal injuries and breakdown of the overall function.

For a more detailed explanation of the safety category, Annex G should also be considered.

4.5 Weld performance classes

Weld performance classes shall be defined in the design phase depending on the safety category and the stress category. A welding coordinator should be consulted with respect to practicability and testing of the welded joints.

Welded joints of railway vehicles are divided into seven weld performance classes (see Table 2).

Table 2 — Weld performance classes

Stress categories	Safety categories		
	High	Medium	Low
High	CP A ^a	CP B2 ^b	CP C2
Medium	CP B1 ^a	CP C2	CP C3
Low	CP C1 ^b	CP C3	CP D
<p>a Weld performance classes CP A and CP B1: CP A and CP B1 are only applicable for welds with full penetration and full accessibility for inspection in production and maintenance.</p> <p>b Weld performance classes CP B2 and CP C1: CP B2 and CP C1 are also applicable for welds where volumetric NDT is not possible. Where this is the case, see EN 15085-5:-³, Table 1, footnote b. This should be noted on the related weld inspection documentation with a note “increase of surface test is required”.</p>			

For new manufacturing, the combination of high safety category and high stress category, which leads to weld performance class CP A, shall be avoided. For application in maintenance see EN 15085-6:-⁴.

The inspection of all welded joints shall be performed according to EN 15085-5:-³, Table 1 as a minimum.

When the weld performance class assessment leads to CP B1, CP B2 or CP C1, and the weld is inaccessible for inspection or repair during maintenance, one of the following actions shall be performed:

- Increase the weld inspection class to CT 1.
- change the design:
 - to reduce the stress category;
 - to allow access for inspection and repair in maintenance.

If it is not possible to fulfil the requirements of a weld performance class, the designer shall reduce the stress category or change the design, see Annex D.

Different post weld treatment methods to increase the fatigue strength are possible. These methods can lead to a downgrading of the stress category.

4.6 Weld inspection classes

The weld inspection class is determined based on the weld performance class.

The correlation between the weld performance class, weld inspection class and inspection requirements is defined in Table 3. Details of weld inspection are further defined in EN 15085-5:-³, Table 1.

EN 15085-3:2022+A1:2023 (E)

Table 3 — Correlation between weld performance classes and weld inspection classes

Stress category	Safety category	Weld performance class	Quality levels for imperfections EN ISO 5817:2014 EN ISO 10042:2018 EN ISO 13919-1:2019 EN ISO 13919-2:2021	Weld inspection class Minimum requirements	Volumetric tests min.	Surface tests min.	Visual examination min.
High	High	CP A	B ^a	CT 1	100 %	100 %	100 %
High	Medium	CP B2	B ^a	CT 2	10 %	10 %	100 %
High	Low	CP C2	C ^a	CT 3	Not required	Not required	100 %
Medium	High	CP B1	B ^a	CT 2	10 %	10 %	100 %
Medium	Medium	CP C2	C ^a	CT 3	Not required	Not required	100 %
Medium	Low	CP C3	C ^a	CT 4	Not required	Not required	100 %
Low	High	CP C1	C ^a	CT 2	10 %	10 %	100 %
Low	Medium	CP C3	C ^a	CT 4	Not required	Not required	100 %
Low	Low	CP D	D ^a	CT 4	Not required	Not required	100 %
^a For detail see Table 4 to 6							

In case of higher weld inspection class than that defined in Table 3 it shall be shown on drawings or in other documents, e.g. parts lists.

5 Quality levels for imperfections

5.1 General

The definition and classification of weld imperfections in accordance with EN ISO 6520-1:2007 and EN ISO 6520-2:2013, are applicable.

5.2 Quality levels for imperfections for fusion welded joints (beam welding excluded)

The quality levels for imperfections related to the weld performance class are described below.

The quality levels for imperfection for fusion welding of steel and aluminium alloys are listed in Table 4 in accordance to EN ISO 5817:2014 and EN ISO 10042:2018.

EN ISO 5817:2014, Annex C, is not applicable in the production and maintenance of railway vehicles and components.

Table 4 — Quality levels for imperfections for steel and aluminium alloys related to weld performance classes

Imperfection No. according to EN ISO 6520-1:2007	Weld performance classes			
	CP A	CP B1 / CP B2	CP C1 / CP C2 / CP C3	CP D
	Level of Imperfections according to EN ISO 5817:2014 and EN ISO 10042:2018			
Group 100	B	B	C	D
Group 200	B	B	C	D
Group 300	B	B	C	D
Group 400	B	B	C	D
5011, 5012, 5013, 502, 504, 506, 509, 511, 510, 515, 516, 517	Not permitted	B	C	D
5071, 5072, 601	B	B	C	D
503, 5213, 512 ^a , 617	Not applicable	B	C	D
505 and Multiple Imperfections	B	These imperfections are not assessed		
5214 [steel]	Not applicable	B	C	D
5214 [aluminium]	Not applicable	refer to geometrical dimension defined into design documentation (e.g. avoid interference during assembly)		
602, 610 [steel]	B	B	C	D
602 [aluminium]	Acceptance depends on application, e.g. material, corrosion protection			
610 [aluminium]	Not applicable			

a 512: Excessive asymmetry of fillet weld (unequal leg length) is not assessed if the fillet weld is an addition on a HY-weld or HV-weld at T-joint (see Annex B, No. 10c and 11c). The throat thickness of these fillet welds depends on the shorter leg length.

5.3 Quality levels for imperfections for beam welded joints

5.3.1 General

The quality levels for imperfections related to the weld performance class are described below.

Quality levels for imperfections shall be according to EN ISO 13919-1:2019 and EN ISO 13919-2:2021 and are given in Table 5 and Table 6.