



Designation: ~~E1826-05~~ Designation: E1826 - 11

# Standard Specification for Low Volatile Organic Compound (VOC) Corrosion-Inhibiting Adhesive Primer for Aluminum Alloys to Be Adhesively Bonded<sup>1</sup>

This standard is issued under the fixed designation E1826; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

*This standard has been approved for use by agencies of the Department of Defense.*

## 1. Scope

1.1 This specification covers pigmented, sprayable, low volatile organic compound (VOC) corrosion-inhibiting adhesive primers for use on aluminum alloys that are to be adhesively bonded in the fabrication of panels for tactical shelters. When applied to a properly prepared surface of aluminum alloy, the primer imparts corrosion resistance and forms a surface suitable for structural bonding and for coating with shelter paint finishes.

~~1.2 The values stated in SI units are to be regarded as the standard. The values given in parentheses are for information only.~~

1.2 The values stated in SI units are to be regarded as standard. The values given in parentheses are mathematical conversions to inch-pound units that are provided for information only and are not considered standard.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

## 2. Referenced Documents

### 2.1 ASTM Standards:<sup>2</sup>

B117 Practice for Operating Salt Spray (Fog) Apparatus

B209 Specification for Aluminum and Aluminum-Alloy Sheet and Plate

D1002 Test Method for Apparent Shear Strength of Single-Lap-Joint Adhesively Bonded Metal Specimens by Tension Loading (Metal-to-Metal)

D3167 Test Method for Floating Roller Peel Resistance of Adhesives

E864 Practice for Surface Preparation of Aluminum Alloys to Be Adhesively Bonded in Honeycomb Shelter Panels

E865 Specification for Structural Film Adhesives for Honeycomb Sandwich Panels

E874 Practice for Adhesive Bonding of Aluminum Facings to Nonmetallic Honeycomb Core for Shelter Panels

### 2.2 Federal Specifications:<sup>3</sup>

QQ-A-250/8d Aluminum Alloy 5052 H34 Plate and Sheet

QQ-A-250/11d Aluminum Alloy 6061 T6 Plate and Sheet

### 2.3 Government Document:<sup>4</sup>

Rule 1124 Aerospace Assembly and Component Manufacturing Operations, South Coast Air Quality Management District

## 3. Materials and Manufacturer

3.1 The primer shall be a pigmented liquid composed of a modified epoxy phenolic or other resin system compounded to be spray-applied to produce a continuous, uniform coating without dilution.

## 4. Physical Properties

4.1 The uncured primer shall be tested as specified in 5.1 and meet the requirement of Table 1.

<sup>1</sup> This specification is under the jurisdiction of ASTM Committee E06 on Performance of Buildings and is the direct responsibility of Subcommittee E06.53 on Materials and Processes for Durable Rigidwall Relocatable Structures.

Current edition approved May 1, 2005-2011. Published May 2005-2011. Originally approved in 1996. Last previous edition approved in 2000-2005 as E1826 - 005. DOI: 10.1520/E1826-05.10.1520/E1826-11.

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For Annual Book of ASTM Standards volume information, refer to the standard's Document Summary page on the ASTM website.

<sup>3</sup> Available from Standardization Documents Order Desk, DODSSP, Bldg. 4, Section D, 700 Robbins Ave., Philadelphia, PA 19111-5098, <http://dodssp.daps.dla.mil>.

<sup>4</sup> Available from South Coast Air Quality Management District, 9150 Flair Dr., El Monte, CA 91731.

<sup>4</sup> Available from South Coast Air Quality Management District, 21865 Copley Dr. Diamond Bar, CA 91765, <http://www.aqmd.gov>.

**TABLE 1 Physical Properties of Uncured Liquid Polymer**

Test	Requirement
Solids content, %	Report only
Ash content, %	Report only
Color	Easily visible film
VOC content	250 g/L max

4.2 *Properties of Cured Film*—When applied and cured in accordance with 5.1.8, the cured film shall meet the requirements of Tables 2 and 3 when tested as specified in 5.2 and 5.3.

4.3 *Storage Stability*—Primer stored in accordance with 5.1.3 shall meet the requirements for normal- and low-temperature floating roller peel in Table 3 when cured in accordance with 5.1.8 and tested as specified in 5.3.7 and 5.3.8.

4.4 *Shelf Life*—The shelf life of the primer at  $25 \pm 7^\circ\text{C}$  ( $77 \pm 12^\circ\text{F}$ ) shall be at least four days. After four days, when tested according to 5.1.4, the primer shall meet the requirements for normal- and low-temperature floating roller peel in Table 3 when cured in accordance with 5.1.8 and tested as specified in 5.3.7 and 5.3.8.

4.5 *Film Thickness*—The average, minimum, and maximum film thicknesses shall be between 0.0025 and 0.010 mm (0.0001 and 0.0004 in.)  $\pm 15\%$  coefficient of variation. At least five thickness readings shall be made with no more than one in any  $645\text{ mm}^2$  ( $1\text{ in.}^2$ ) area.

4.6 *VOC Content*—The volatile organic compound (VOC) is any volatile compound containing the element of carbon, excluding methane, carbon monoxide, carbon dioxide, carbonic acid, metallic carbides or carbonates, and ammonium carbonates, as stated in Rule 1124. The VOC content shall meet the requirement in Table 1 when determined in accordance with 5.1.9.

## 5. Test Methods

### 5.1 *Uncured Primer:*

5.1.1 *Solids Content*—Determine the solids content by heating a 2-g sample of thoroughly mixed primer in an ignition-loss crucible with cover at  $121 \pm 5^\circ\text{C}$  ( $250 \pm 9^\circ\text{F}$ ) for not less than 90 min. Cool the crucible to room temperature in a desiccator. Weighings before and after heating shall be accurate to  $\pm 0.001\text{ g}$ . Calculate the mass of solids remaining as a percentage of the initial sample mass as follows:

$$\text{Percent solids content} = \frac{\text{mass of nonvolatile residue}}{\text{initial sample mass}} \times 100 \quad (1)$$

5.1.2 *Ash Content*—Place the crucibles containing the solids content samples in a furnace at  $565 \pm 28^\circ\text{C}$  ( $1050 \pm 82^\circ\text{F}$ ) for not less than 60 min. Cool the crucible to room temperature in a desiccator. Weighings before and after heating shall be accurate to  $\pm 0.001\text{ g}$ . Calculate the ash content remaining as a percentage of the solids content as follows:

$$\text{Percent ash content} = \frac{\text{mass of ash residue}}{\text{mass of nonvolatile residue}} \times 100 \quad (2)$$

5.1.3 *Storage Stability*—Store a sample of the primer for three months from the date of manufacture at a temperature recommended by the manufacturer. The stored sample shall meet the requirements for normal- and low-temperature floating roller peel in Table 3 when cured in accordance with 5.1.8 and tested as specified in 5.3.7 and 5.3.8.

5.1.4 *Shelf Life*—Store a sample of the primer for four days at  $25 \pm 7^\circ\text{C}$  ( $77 \pm 13^\circ\text{F}$ ). The aged sample shall meet the requirements for normal- and low-temperature floating roller peel in Table 3 when cured in accordance with 5.1.8 and tested as specified in 5.3.7 and 5.3.8.

5.1.5 *Film Thickness*—The cured primer film thickness shall be determined with an eddy-current instrument as specified in 5.2.2.

5.1.6 *Color*—During spray application, there shall be a discernible color change for the primer thickness specified in 4.5.

5.1.7 *Sprayability*—The primer shall be capable of being readily applied in accordance with the manufacturer's instructions to all test panels of either 6061 T6 or 5052 H34 aluminum alloy (Fed. Spec. QQ-A-250/11d or QQ-A-250/8d, respectively, or Specification B209) and cleaned in accordance with Practice E864 for each of the tests described in 5.1.8-5.3.8.

5.1.8 *Curing Properties*—Test the cured film for the ability to meet the requirements listed in Tables 2 and 3. Spray the primer onto the test panels and air dry at least 20 min at  $24 \pm 5^\circ\text{C}$  ( $77 \pm 9^\circ\text{F}$ ); then heat in air for  $65 \pm 5\text{ min}$  at  $121 \pm 5^\circ\text{C}$  ( $250 \pm 9^\circ\text{F}$ ).

5.1.9 *VOC Content*—The grams of VOC per litre of primer, less water and exempt compounds per Rule 1124, shall be determined by the adhesive primer manufacturer in accordance with Rule 1124 and meet the requirement for VOC content in Table 1.

### 5.2 *Cured Film:*

**TABLE 2 Physical Property of Cured Film on Primed Surfaces**

Test	Requirement
Smooth uniform coating	0.0025 to 0.010 mm (0.0001 to 0.0004 in.) $\pm 15\%$ coefficient of variation