



Designation: A230/A230M – 05 (Reapproved 2011)^{ε1}

Standard Specification for Steel Wire, Oil-Tempered Carbon Valve Spring Quality¹

This standard is issued under the fixed designation A230/A230M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the Department of Defense.

^{ε1} NOTE—Changes were made editorially throughout in July 2011.

1. Scope*

1.1 This specification covers the highest quality of round carbon steel spring wire, uniform in quality and temper, intended especially for the manufacture of valve springs and other springs requiring high-fatigue properties.

1.2 The values stated in either SI units or inch-pound units are to be regarded separately as standard. The values stated in each system may not be exact equivalents; therefore, each system shall be used independently of the other. Combining values from the two systems may result in non-conformance with the standard.

2. Referenced Documents

2.1 ASTM Standards:²

[A370 Test Methods and Definitions for Mechanical Testing of Steel Products](#)

[A510 Specification for General Requirements for Wire Rods and Coarse Round Wire, Carbon Steel](#)

[A510M Specification for General Requirements for Wire Rods and Coarse Round Wire, Carbon Steel \(Metric\)](#)

[A700 Practices for Packaging, Marking, and Loading Methods for Steel Products for Shipment](#)

[A751 Test Methods, Practices, and Terminology for Chemical Analysis of Steel Products](#)

[E29 Practice for Using Significant Digits in Test Data to Determine Conformance with Specifications](#)

2.2 ANSI Standard:³

[B 32.4M Preferred Metric Sizes for Round, Square, Rectangle, and Hexagon Metal Products](#)

2.3 Military Standard:⁴

[MIL-STD-163 Steel Mill Products, Preparation for Shipment and Storage](#)

2.4 Federal Standard:⁴

[Fed. Std. No. 123 Marking for Shipment \(Civil Agencies\)](#)

2.5 AIAG Standard:⁵

[AIAG B-5 02.00 Primary Metals Identification Tag Application Standard](#)

3. Ordering Information

3.1 Material furnished under this specification shall conform to the applicable requirements of the current edition of either Specification [A510](#) or Specification [A510M](#).

3.2 Orders for material under this specification should include the following information for each ordered item:

3.2.1 Quantity (mass or weight),

3.2.2 Name of material (oil-tempered carbon steel valve spring quality wire),

3.2.3 Dimensions (Section 8),

3.2.4 Chemical composition (Table 1), if required,

3.2.5 Packaging (Section 14),

3.2.6 Cast or heat analysis report, if desired (see 5.2),

3.2.7 Certification or test report, or both, if specified (Section 13), and

3.2.8 ASTM designation and date of issue.

NOTE 1—A typical metric ordering description is as follows: For inch-pound units, 40 000 lb oil-tempered carbon steel valve spring quality wire, 0.250 in. diameter in 350-lb coils to ASTM A230 dated _____, or for SI units 20 000 kg oil-tempered carbon steel valve spring quality wire, 6.00 mm diameter in 125-kg coils to ASTM A230M dated _____.

4. Materials and Manufacture

4.1 The steel may be made by any commercially accepted steel-making process. The steel shall be continuously cast.

4.2 The finished wire shall be free of detrimental pipe and undue segregation.

¹ This specification is under the jurisdiction of ASTM Committee A01 on Steel, Stainless Steel and Related Alloys and is the direct responsibility of Subcommittee A01.03 on Steel Rod and Wire.

Current edition approved July 1, 2011. Published July 2011. Originally approved in 1939. Last previous edition approved in 2005 as A230/A230M – 05. DOI: 10.1520/A0230_A0230M-05R11E01.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

³ Available from American National Standards Institute (ANSI), 25 W. 43rd St., 4th Floor, New York, NY 10036.

⁴ Available from Standardization Documents Order Desk, DODSSP, Bldg. 4, Section D, 700 Robbins Ave., Philadelphia, PA 19111-5098.

⁵ Available from Automotive Industry Action Group (AIAG), 26200 Lahser Rd., Suite 200, Southfield, MI 48034.

*A Summary of Changes section appears at the end of this standard

TABLE 1 Chemical Requirements

Element	Composition, %	
	min	max
Carbon	0.60–0.75 ^A	
Manganese	0.60–0.90 ^A	
Phosphorus, max	0.025	
Sulfur, max	0.030	
Silicon	0.15–0.35	

^A Carbon and manganese may be varied by the manufacturer at his discretion, provided the mechanical properties specified are maintained and provided the purchaser does not specifically stipulate otherwise.

4.3 The wire shall be hardened and tempered to produce the desired mechanical properties.

5. Chemical Composition

5.1 The steel shall conform to the requirements for chemical composition prescribed in **Table 1**.

5.2 *Cast or Heat Analysis*—Each cast or heat of steel shall be analyzed by the manufacturer to determine the percentage of elements prescribed in **Table 1**. This analysis shall be made from a test specimen preferably taken during the pouring of the cast or heat. When requested, this shall be reported to the purchaser and shall conform to the requirements of **Table 1**.

5.3 *Product Analysis*—An analysis may be made by the purchaser from finished wire representing each cast or heat of steel. The chemical composition thus determined, as to elements required or restricted, shall conform to the product analysis requirements specified in **Table 10** of Specification **A510** or Specification **A510M**.

5.4 For referee purposes, **Test Methods, Practices, and Terminology A751** shall be used.

6. Mechanical Properties

6.1 Tension Test:

6.1.1 *Requirements*—The material as represented by tension test specimens shall conform to the requirements prescribed in **Table 2** or **Table 3**.

TABLE 2 Tensile Requirements, SI Units

Diameter, mm	Tensile Strength, MPa		Reduction of Area, min, % ^A
	min	max	
Less than 1.50	1700	1850	...
1.50 to 2.50, incl	1650	1800	...
Over 2.50 to 3.50, incl	1600	1750	40
Over 3.50 to 4.00, incl	1580	1720	40
Over 4.00 to 4.80, incl	1550	1700	40
Over 4.80 to 5.50, incl	1520	1680	40
Over 5.50 to 6.50, incl	1500	1650	40
Over 6.50	1450	1600	40

^A The reduction of area test is not applicable to wire diameters under 2.34 mm.

TABLE 3 Tensile Requirements, Inch-Pound Units

Diameter, in.	Tensile Strength, ksi		Reduction of Area, min, % ^A
	min	max	
Less than 0.062	245	265	...
0.062 to 0.092, incl	240	260	...
Over 0.092 to 0.128, incl	235	255	40
Over 0.128 to 0.162, incl	230	250	40
Over 0.162 to 0.192, incl	225	245	40
Over 0.192 to 0.225, incl	220	240	40
Over 0.225 to 0.250, incl	215	235	40
Over 0.250	210	230	40

^A The reduction of area test is not applicable to wire diameters under 0.092 in.

6.1.2 *Number of Tests*—One test specimen shall be taken for each five coils, or fraction thereof, in a lot. Each cast or heat in a given lot shall be tested.

6.1.3 *Location of Tests*—Test specimens shall be taken from either end of the coil.

6.1.4 *Test Method*—The tension test shall be made in accordance with **Test Methods and Definitions A370**.

6.2 Wrap Test:

6.2.1 *Requirements*—Wire 0.162 in. [4.00 mm] and smaller in diameter shall wind on itself as an arbor without breakage. Larger diameter wire, up to and including 0.250 in. [6.50 mm], shall wind, without breakage, on a mandrel twice the diameter of the wire.

6.2.2 *Number of Tests*—One test specimen shall be taken for each five coils, or fraction thereof, in a lot. Each cast or heat in a given lot shall be tested.

6.2.3 *Location of Test*—Test specimens shall be taken from either end of the coil.

6.2.4 *Test Method*—The wrap test shall be made in accordance with **Test Methods and Definitions A370**, Supplement IV.

6.3 *Twist Test*—A 10 in. [250 mm] specimen of wire slowly twisted four revolutions in one direction and then twisted in the other direction until failure shall show a square break normal to the axis of the wire without splits or cracks.

6.4 *Special Surface Inspection*—When specified, the entire length of every coil shall be inspected for surface imperfections with a magnetic or eddy current defect analyzer, or both, or equivalent. The defect depth of this surface inspection shall be agreed upon between the manufacturer and the purchaser. All detected defects shall be properly marked so the purchaser has the ability to identify and discard that length of wire.

7. Metallurgical Properties

7.1 Decarburization:

7.1.1 *Requirements*—Transverse sections of the wire properly mounted, polished and etched shall show no completely decarburized (carbon free) areas when examined at 100× magnification. Partial decarburization shall not exceed a depth of 0.001 in. [0.025 mm] on wire 0.192 in. [4.90 mm] and smaller or 0.0015 in. [0.038 mm] on wire larger than 0.192 in. [4.90 mm]. Measure the worst area present excluding decarburization associated with seams or other surface imperfections. Complete decarburization exists when only free ferrite is present. Partial decarburization exists when ferrite is found