# INTERNATIONAL STANDARD

ISO 1403

Fifth edition 2019-07

# Rubber hoses, textile-reinforced, for general-purpose water applications — Specification

Tuyaux en caoutchouc à armature textile d'usage général pour l'eau — Spécifications

iTeh Standards (https://standards.iteh.ai) Document Preview

ISO 1403:2019

https://standards.iteh.ai/catalog/standards/iso/f6c1bd2e-8691-4a50-8417-4bff6e0f0100/iso-1403-2019



## iTeh Standards (https://standards.iteh.ai) Document Preview

ISO 1403:2019

https://standards.iteh.ai/catalog/standards/iso/f6c1bd2e-8691-4a50-8417-4bff6e0f0100/iso-1403-2019



#### **COPYRIGHT PROTECTED DOCUMENT**

© ISO 2019

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office CP 401 • Ch. de Blandonnet 8 CH-1214 Vernier, Geneva Phone: +41 22 749 01 11 Fax: +41 22 749 09 47 Email: copyright@iso.org Website: www.iso.org

Published in Switzerland

Contents			Page
Fore			
1	Scop	pe	1
2	Nori	mative references	1
3	Tern	ms and definitions	1
4	Clas	ssification	2
5	Materials and construction		2
6	<b>Dim</b> 6.1 6.2 6.3 6.4	Inside diameters and tolerances	2 2 2
7		Rubber compounds Finished hose	3 3
8	Mar	king	4

### iTeh Standards (https://standards.iteh.ai) Document Preview

ISO 1403:2019

https://standards.iteh.ai/catalog/standards/iso/f6c1bd2e-8691-4a50-8417-4bff6e0f0100/iso-1403-2019

#### **Foreword**

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see <a href="www.iso.org/directives">www.iso.org/directives</a>).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see <a href="https://www.iso.org/patents">www.iso.org/patents</a>).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see <a href="https://www.iso.org/iso/foreword.html">www.iso.org/iso/foreword.html</a>.

This document was prepared by Technical Committee ISO/TC 45, *Rubber and rubber products*, Subcommittee SC 1, *Rubber and plastics hoses and hose assemblies*.

This fifth edition cancels and replaces the fourth edition (ISO 1403:2005), of which it constitutes a minor revision.

The main changes compared to the previous edition are as follows: 450-8417-4bff6e0f0100/iso-1403-2019

- In <u>Clause 2</u>, normative references have been updated.
- The unit MPa has been added for all the pressures accordingly.
- In <u>Clause 8</u>, the year of publication has been deleted.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at <a href="https://www.iso.org/members.html">www.iso.org/members.html</a>.

## Rubber hoses, textile-reinforced, for general-purpose water applications — Specification

WARNING — Persons using this document should be familiar with normal laboratory practice. This document does not purport to address all of the safety problems, if any, associated with its use. It is the responsibility of the user to establish appropriate safety and health practices.

#### 1 Scope

This document specifies the requirements for three types of general-purpose textile-reinforced rubber water hose with an operating temperature range of -25 °C to +70 °C and a maximum working pressure of up to 2,5 MPa (25 bar).

These hoses are not intended to be used for conveyance of potable (drinking) water, for washing-machine inlets, as firefighting hoses, for special agricultural machines or as collapsible water hoses.

These hoses can be used with additives which lower the freezing point of water.

#### 2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 37, Rubber, vulcanized or thermoplastic — Determination of tensile stress-strain properties

ISO 188:2011, Rubber, vulcanized or thermoplastic — Accelerated ageing and heat resistance tests

ISO 1307, Rubber and plastics hoses — Hose sizes, minimum and maximum inside diameters, and tolerances on cut-to-length hoses

ISO 1402, Rubber and plastics hoses and hose assemblies — Hydrostatic testing

ISO 4671, Rubber and plastics hoses and hose assemblies — Methods of measurement of the dimensions of hoses and the lengths of hose assemblies

ISO 7326:2016, Rubber and plastics hoses — Assessment of ozone resistance under static conditions

ISO 8033, Rubber and plastics hoses — Determination of adhesion between components

ISO 8330, Rubber and plastics hoses and hose assemblies — Vocabulary

ISO 10619-1:2017, Rubber and plastics hoses and tubing — Measurement of flexibility and stiffness — Part 1: Bending tests at ambient temperature

ISO 10619-2:2017, Rubber and plastics hoses and tubing — Measurement of flexibility and stiffness — Part 2: Bending tests at sub-ambient temperatures

#### 3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 8330 apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

ISO Online browsing platform: available at <a href="https://www.iso.org/obp">https://www.iso.org/obp</a>

IEC Electropedia: available at <a href="http://www.electropedia.org/">http://www.electropedia.org/</a>

#### 4 Classification

Hoses are designated as one of the following types depending on their pressure rating:

- Type 1: Low pressure Designed for a maximum working pressure of 0,6 MPa (6 bar).
- Type 2: Medium pressure Designed for a maximum working pressure of 1,0 MPa (10 bar).
- Type 3: High pressure Designed for a maximum working pressure of 2,5 MPa (25 bar).

#### 5 Materials and construction

The hose shall consist of:

- a rubber lining;
- a reinforcement of natural or synthetic textile, applied by any suitable technique;
- a rubber cover.

The lining and cover shall be of uniform thickness, concentric to comply with the minimum thickness specified, and free from holes, porosity and other defects. The cover finish may be smooth, fluted or fabric-marked.

#### 6 Dimensions

#### 6.1 Inside diameters and tolerances ment Preview

When measured in accordance with ISO 4671, the inside diameters and their tolerances shall conform to the values specified in Table 1. ISO 1403:2019

https://standards.iteh.ai/catalog/standards/iso/f6c1bd2e-8691-4a50-8417-4bff6e0f0100/iso-1403-2019

#### 6.2 Concentricity

When determined in accordance with ISO 4671, the concentricity, based on a total indicator reading between the inside diameter and the outside surface of the cover, shall be no greater than 1,0 mm for hoses of inside diameter up to and including 76 mm, and no greater than 1,5 mm for hoses of inside diameter greater than 76 mm.

#### 6.3 Tolerance on length

When measured in accordance with ISO 4671, the tolerance on cut lengths shall be as specified in ISO 1307.

#### 6.4 Minimum thickness of lining and cover

When measured in accordance with ISO 4671, the minimum thickness of the lining plus cover shall be 1,5 mm. If the cover is fluted, the depth of the flutes shall not be greater than 50 % of the cover thickness.