INTERNATIONAL STANDARD

ISO 24023-2

First edition 2020-05

Plastics — Plasticized poly(vinyl chloride) (PVC-P) moulding and extrusion materials —

Part 2:

Preparation of test specimens and determination of properties

Plastiques — Matériaux à base de poly(chlorure de vinyle) plastifié (PVC-P) pour moulage et extrusion —

Partie 2: Préparation des éprouvettes et détermination des propriétés

ISO 24023-2:2020

https://standards.iteh.ai/catalog/standards/iso/db776c99-1a06-4f54-9c83-47cc8748c9eb/iso-24023-2-2020



iTeh Standards (https://standards.iteh.ai) Document Preview

ISO 24023-2:2020

https://standards.iteh.ai/catalog/standards/iso/db776c99-1a06-4f54-9c83-47cc8748c9eb/iso-24023-2-2020



COPYRIGHT PROTECTED DOCUMENT

© ISO 2020

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office CP 401 • Ch. de Blandonnet 8 CH-1214 Vernier, Geneva Phone: +41 22 749 01 11 Fax: +41 22 749 09 47 Email: copyright@iso.org Website: www.iso.org

Published in Switzerland

Coi	ntent	cs ·	Page	
Fore	word		iv	
1	Scop	e	1	
2	Norr	native references	1	
3	Terms and definitions			
4	Preparation of test specimens 4.1 General			
	4.1	General	2	
	4.2	Treatment of the material before moulding	2	
	4.3	Treatment of the material before moulding	2	
5	Cond	litioning of test specimens	3	
6	Dete	rmination of properties	3	
Ann	ex A (no	ormative) Detailed description of the preparation of test specimens	5	

iTeh Standards (https://standards.iteh.ai) Document Preview

ISO 24023-2:2020

https://standards.iteh.ai/catalog/standards/iso/db776c99-1a06-4f54-9c83-47cc8748c9eb/iso-24023-2-2020

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 61, *Plastics*, Subcommittee SC 9, *Thermoplastic materials*, in collaboration with the European Committee for Standardization (CEN) Technical Committee CEN/TC 249, *Plastics*, in accordance with the Agreement on technical cooperation between ISO and CEN (Vienna Agreement).

This first edition of ISO 24023-2 cancels and replaces ISO 2898-2:2008, which has been technically revised.

The main changes compared to the previous edition are as follows:

- ISO 3167 has been replaced by ISO 20753;
- IEC 60093 has been replaced by the new editions of IEC 62631-3-1 and IEC 62631-3-2.

A list of all parts in the ISO 24023 series can be found on the ISO website.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

Plastics — Plasticized poly(vinyl chloride) (PVC-P) moulding and extrusion materials —

Part 2:

Preparation of test specimens and determination of properties

1 Scope

This document specifies the methods of preparation of test specimens and the test methods to be used in determining the properties of PVC-P moulding and extrusion materials. It gives the requirements for handling test materials and for conditioning both the test material before moulding and the specimens before testing.

This document gives procedures and conditions for the preparation of test specimens and procedures for measuring properties of the materials from which these specimens are made. It lists properties and test methods which are suitable and necessary to characterize PVC-P moulding and extrusion materials.

The properties have been selected from the general test methods in ISO 10350-1. Other test methods in wide use for, or of particular significance to, these moulding and extrusion materials are also included in this document, as are the designatory properties specified in ISO 24023 (all parts).

2 Normative references Cument Preview

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 176, Plastics — Determination of loss of plasticizers — Activated carbon method

ISO 291, Plastics — Standard atmospheres for conditioning and testing

ISO 293, Plastics — Compression moulding of test specimens of thermoplastic materials

ISO 458-2, Plastics — Determination of stiffness in torsion of flexible materials — Part 2: Application to plasticized compounds of homopolymers and copolymers of vinyl chloride

ISO 527-1, Plastics — Determination of tensile properties — Part 1: General principles

ISO 527-2, Plastics — Determination of tensile properties — Part 2: Test conditions for moulding and extrusion plastics

ISO 868, Plastics and ebonite — Determination of indentation hardness by means of a durometer (Shore hardness)

ISO 1183-1, Plastics — Methods for determining the density of non-cellular plastics — Part 1: Immersion method, liquid pycnometer method and titration method

ISO 2818, Plastics — Preparation of test specimens by machining

ISO 3451-5, *Plastics* — *Determination of ash* — *Part 5: Poly(vinyl chloride)*

ISO 10350-1, Plastics — Acquisition and presentation of comparable single-point data — Part 1: Moulding materials

ISO 24023-1, Plastics — Plasticized polyvinyl chloride) (PVC-P) moulding and extrusion materials — Part 1: Designation system and basis for specifications

ISO 20753, Plastics — Test specimens

IEC 62631-3-1, Dielectric and resistive properties of solid insulating materials — Part 3-1: Determination of resistive properties (DC methods) — Volume resistance and volume resistivity — General method

Terms and definitions 3

No terms and definitions are listed in this document.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at https://www.iso.org/obp
- IEC Electropedia: available at http://www.electropedia.org/

Preparation of test specimens

4.1 General

In order to obtain reproducible and comparable test results, it is necessary to use the methods of preparation and conditioning, the specimen dimensions and the test procedures specified herein. Values determined are not necessarily identical to those obtained using specimens of different dimensions or prepared using different procedures.

It is essential that specimens are always prepared by the same procedure (compression moulding), using the same processing conditions.

The material shall be kept in moisture-proof containers until it is required for use.

Treatment of the material before moulding 4.2

Before processing, no pretreatment of the material sample is normally necessary.

4.3 Compression moulding

Before compression moulding, the material shall be plasticized using a two-roll mill under the conditions specified in Table 1.

Unless it constitutes a variable under study, the required number of milled sheets shall be placed cross layered in the preheated mould and prepare compression-moulded sheets in accordance with ISO 293, using the conditions specified in Table 2.

Table 1 — Conditions for milling of material before compression moulding

Shore hardness of	Roll surface temperature	Milling time ^a	Roll surface	Speed ratio	Roll nip width	Roll diameter	Re

hardness of material	Roll surface temperature	Milling time ^a	surface speed	Speed ratio	Roll nip width	Roll diameter	Roll length
	°C	min	m/min		mm	mm	mm
Up to A 80	130 to 160	Approxi mately 5	Approxi mately 10	1:1,2	Approxi mately 1	e.g. 150	e.g. 300
D 35 to D 50	145 to 170	Approxi mately 5	Approxi mately 10	1:1,2	Approxi mately 1	e.g. 150	e.g. 300
a Measured f	rom the moment w	hen a sheet is forn	ned.				