
**Fine ceramics (advanced ceramics,
advanced technical ceramics) —
Methods of tests for reinforcements
— Determination of the tensile
properties of resin-impregnated yarns**

*Céramiques techniques (céramique technique, céramique technique
avancée) — Méthodes d'essais pour renforts — Détermination des
propriétés en traction des fils imprégnés de résine*

iTeh STANDARDS (standards.iteh.ai)

ISO 24046:2022

<https://standards.iteh.ai/catalog/standards/sist/2b33fe27-9f2f-4a8f-b6d1-d3342d38bdfb/iso-24046-2022>



iTeh STANDARD PREVIEW (standards.iteh.ai)

ISO 24046:2022

<https://standards.iteh.ai/catalog/standards/sist/2b33fe27-9f2f-4a8f-b6d1-d3342d38bdfb/iso-24046-2022>



COPYRIGHT PROTECTED DOCUMENT

© ISO 2022

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Contents

Page

Foreword	iv
Introduction	v
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Principle	3
5 Apparatus and material	3
5.1 Resin	3
5.2 Impregnation apparatus	3
5.3 Curing oven with temperature control	4
5.4 Tensile-testing machine and extensometer	4
5.4.1 Tensile-testing machine	4
5.4.2 Extensometer	4
5.5 Balance	4
5.6 Ruler	4
6 Test specimens	4
6.1 Number of test specimens	4
6.2 Impregnation of test specimens	4
6.3 Determination of other fibre properties	5
6.3.1 General	5
6.3.2 Linear density of the yarn	5
6.3.3 Size content of the yarn	5
6.3.4 Density of the ceramic fibre	5
6.4 Criteria for selection of the test specimens	5
6.4.1 Specimens	5
6.4.2 Resin content of the specimens	5
6.4.3 Impregnated yarn	6
7 Atmospheres for conditioning and testing	6
8 Procedure for tensile testing	6
8.1 Procedure	6
8.2 Determination of load train compliance	6
8.3 Test validity	6
9 Calculation of results	7
9.1 Tensile strength	7
9.2 Calculation of the load train compliance	7
9.3 Calculation of instantaneous total compliance and longitudinal deformation of resin-impregnated yarn	8
9.4 Tensile modulus of elasticity	9
9.5 Tensile strain at maximum force (percentage elongation at failure)	10
9.5.1 Calculation method (1)	10
9.5.2 Calculation method (2)	11
10 Statistics	11
11 Test report	11
Annex A (informative) Examples of heat-curable epoxy-resin systems	13
Annex B (informative) Examples of resin-impregnating apparatus	14
Annex C (informative) Example of extensometer	15
Bibliography	17

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 206, *Fine ceramics*.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

Introduction

Fine ceramics are widely used in various fields, such as machinery, electronics, chemistry, construction, energy, aerospace and the nuclear industry, and in environmental applications. Fibre-reinforced ceramic matrix composites (CMCs) have been the subject of extensive research and development. CMCs are lightweight, have suitable chemical and thermal stability, and exhibit high strength, elastic modulus and creep resistance. These composites have been applied in devices and components in the aerospace industry and in high-temperature applications.

CMCs have been put to practical use as components in the jet engines of passenger planes and are also being developed as components of gas turbines for electric power generation.

The reliability of CMCs is influenced by the properties of the reinforcing fibre. High reliability is particularly important for jet engine parts. The mechanical properties of these fibres also require fixed values and distribution.

This document establishes a method for the measurement of mechanical properties such as tensile strength, elastic modulus and strain at the maximum force of a resin-impregnated yarn specimen prepared from the reinforcing ceramic fibre in CMCs.

Fibre and CMC manufacturers will be able to use this method to perform quality control and relative comparison of ceramic fibres used as the reinforcement of CMCs.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

ISO 24046:2022

<https://standards.iteh.ai/catalog/standards/sist/2b33fe27-9f2f-4a8f-b6d1-d3342d38bdfb/iso-24046-2022>

Fine ceramics (advanced ceramics, advanced technical ceramics) — Methods of tests for reinforcements — Determination of the tensile properties of resin-impregnated yarns

1 Scope

This document specifies a method for the determination of the tensile strength, tensile modulus of elasticity and strain at the maximum force of a resin-impregnated yarn specimen at ambient temperature. This method is applicable to yarns of ceramic fibres that are used as reinforcements in composite materials. The test results obtained by this method are applicable for quality control and comparison of the ceramic fibres.

The outputs of this method are not to be mixed up with the strength of filaments derived from tensile tests on dry tows specified in ISO 22459.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 1889, *Reinforcement yarns — Determination of linear density*

ISO 7500-1, *Metallic materials — Calibration and verification of static uniaxial testing machines — Part 1: Tension/compression testing machines — Calibration and verification of the force-measuring system*

ISO 10119, *Carbon fibre — Determination of density*

ISO 10548, *Carbon fibre — Determination of size content*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminology databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <https://www.electropedia.org/>

3.1 gauge length

L

distance between reference points on the test specimen during the tensile test

3.2 initial gauge length

L_0

distance between reference points on the test specimen at zero load

[SOURCE: ISO 22459:2020, 3.1, modified — term and definition revised and Note 1 to entry removed.]

3.3
longitudinal deformation

A

increase of the *initial gauge length* (3.2) during the tensile test

[SOURCE: ISO 19630:2017, 3.7, modified — definition revised.]

3.4
maximum tensile force

F_m

greatest tensile force applied to the test specimen when tested to failure

[SOURCE: ISO 19630:2017, 3.4, modified — definition revised.]

3.5
tensile strength

σ_f

maximum tensile force (3.4) divided by the *initial total cross-sectional area of the dry yarn* (3.9)

[SOURCE: ISO 19630:2017, 3.6, modified — definition revised.]

3.6
total compliance

C_t

ratio of the measured displacement to the corresponding force during the tensile test

[SOURCE: ISO 22459:2020, 3.4.1]

3.7
load train compliance

C_l

ratio of the load train elongation, excluding the specimen contribution, to the corresponding force during the tensile test

[SOURCE: ISO 22459:2020, 3.4.2]

3.8
tensile modulus of elasticity

E_f

slope of the force–deformation curve divided by the *initial total cross-sectional area of the dry yarn* (3.9)

3.9
initial total cross-sectional area of the dry yarn

S_f

linear density of the dry yarn (3.11) divided by the *density of the dry yarn* (3.13)

[SOURCE: ISO 22459:2020, 3.2, modified — term and definition revised.]

3.10
strain at maximum force

$\varepsilon_{t,m}$

ratio of the greatest *longitudinal deformation* (3.3) to the *initial gauge length* (3.2)

3.11
linear density of the dry yarn

T_{tf}

mass of the dry yarn without a sizing agent divided by its length

[SOURCE: ISO 1889:2009, 3.1, modified — term and definition revised and Note 1 to entry removed.]

3.12**linear density of the impregnated yarn** T_{ti}

mass of the test specimen divided by its length

3.13**density of the dry yarn** ρ_f

mass of the dry yarn without a sizing agent divided by its volume

4 Principle

A fibre yarn impregnated with an epoxy resin is used as the specimen. A tensile force is applied to the specimen at a constant displacement rate by a suitable mechanical testing machine and grip system until failure. The longitudinal deformation of resin-impregnated yarn is measured directly by using an extensometer or is determined from the displacement between two grips using a compliance correction. The correction takes into account the contributions of the loading train, the grips and the tabbing materials.

The tensile strength, tensile modulus of elasticity and the strain at maximum force are calculated from the force–deformation relationship. For ceramic fibre yarns in epoxy matrix, the relation between force and longitudinal deformation is linear and, hence, the tensile modulus of elasticity is calculated from the slope of the force–deformation curve.

5 Apparatus and material**5.1 Resin**

The impregnating resin shall be compatible with the sizing agent and the type of yarn. The viscosity of the resin or resin solution shall be such that sufficient resin pick-up and uniform impregnation are achieved. The failure strain of the cured resin should be at least twice as large, preferably more than three times as large, as that of the specimen. In this respect, thermosetting epoxy-resin systems are suitable (see [Annex A, Table A.1](#) for an example) as is any formulation capable of giving test specimens that fulfil the requirements of this document.

5.2 Impregnation apparatus

Test specimens can be prepared by any method that produces a uniformly impregnated, smooth specimen.

An impregnation apparatus consists of a yarn bobbin holder, an impregnation bath, rollers for resin impregnation and removal of excess resin, and an impregnated yarn winder.

An impregnation apparatus may consist of:

5.2.1 Yarn bobbin holder for the sample yarn bobbin, with yarn-tensioning devices.

5.2.2 Impregnation bath with temperature-control devices and impregnation rollers or yarn-tensioning bars.

5.2.3 Roller for removal of excess resin from the impregnated yarn, that passes its rollers covered with fabric, paper or felt through a die.

5.2.4 Impregnated yarn winder to wind up the impregnated yarn, preferably made of wood or metal coated with rubber. Examples of impregnation apparatuses are given in [Annex B, Figure B.1](#).

5.3 Curing oven with temperature control

A fan circulation oven is preferable to ensure uniform curing of the resin.

5.4 Tensile-testing machine and extensometer

5.4.1 Tensile-testing machine

Use a tensile-testing machine (with a constant cross-head speed) equipped with force- and extension-recording devices. The machine shall conform to grade 1 or better in ISO 7500-1. The accuracy of the force indicated shall be better than 1 % of the recorded value. The specimen-gripping system shall ensure that the test specimen is aligned with the axis of the test machine. A suitable example is shown in [Annex C, Figure C.1](#).

5.4.2 Extensometer

Use an extensometer linked to a continuous-recording device that automatically records the extension within the gauge length of the extensometer as a function of force on the test specimen. The extensometer should be sufficiently light to induce only negligible stresses in the test specimen. For the specimens with long gauge section lengths, it is recommended that the weight of the extensometer is supported, for example by using a thread, in order to prevent bending of the specimen and contact forces.

The gauge length of the extensometer shall be at least 25 mm. The gauge length shall be determined with a tolerance of ± 1 %. The use of an extensometer with a gauge length as long as possible is recommended to increase the accuracy of the measurement.

The extensometer shall have a tolerance on deviation from linearity of not more than 0,1 % over the required extension measurement range.

Examples of suitable extensometers are given in [Annex C](#). Other strain-measuring instruments, such as optical or laser instruments, may be used if suitable.

5.5 Balance

Use a balance readable to 0,1 mg to weigh the test specimens to determine the linear density of the impregnated yarn.

5.6 Ruler

Use a graduated ruler or other measuring device with a precision of $\pm 0,5$ mm to determine the initial distance between two grips, i.e. the gauge length of the specimen.

6 Test specimens

6.1 Number of test specimens

Prepare a sufficient number of test specimens to perform five determinations. If any of the specimens fails within the grips at the tabs, or because of damage caused by the extensometer, discard the result and carry out a repeat determination on a fresh test specimen.

6.2 Impregnation of test specimens

The procedure for using the impregnation apparatus described in [5.2](#) is as follows:

- a) Place the yarn bobbin on the holder.

- b) Pour the impregnating-resin mixture into the resin bath (see 5.2.2) and adjust the temperature and viscosity to the desired values.
- c) Draw the yarn from the bobbin holder through the rollers, resin bath and system designed to remove the excess resin while ensuring adequate resin impregnation (see 5.2.3).
- d) Adjust the unwinding tension by applying a force of 80 gram-force (gf) to 130 gf.
- e) Wind the impregnated yarn onto the frame (see 5.2.4).
- f) Place the frame in the oven (see 5.3).
- g) Cure the resin in accordance with the resin manufacturer's instructions.
- h) When the resin has been cured, remove the frame from the oven. After removing the impregnated yarn from the frame, cut off a sufficient number of test specimens.
- i) Select the test specimens according to the criteria given in 6.4.1.

6.3 Determination of other fibre properties

6.3.1 General

In order to perform the calculations of tensile strength and tensile modulus given in [Clause 9](#) the properties specified from 6.3.2 to 6.3.4 shall be determined.

6.3.2 Linear density of the yarn

Determine the linear density of the yarn using the method given in ISO 1889 for carbon fibre.

6.3.3 Size content of the yarn

Determine the size content of the yarn using the method given in ISO 10548, method C.

6.3.4 Density of the ceramic fibre

Determine the density of the ceramic fibre using one of the methods given in ISO 10119.

6.4 Criteria for selection of the test specimens

6.4.1 Specimens

Each test specimen shall be confirmed as straight by checking with a metallic measuring ruler. The specimen shall be uniform in appearance and without any of the following defects:

- broken filaments;
- resin droplets;
- fibre misalignment.

6.4.2 Resin content of the specimens

The resin content shall be at least 30 % by mass. The resin content of the specimens is calculated from the linear densities of the specimen and dry yarn using [Formula \(1\)](#):

$$m_r = 100 \times \frac{T_{ti} - T_{tf}}{T_{ti}} \quad (1)$$