
Embalaža za končno sterilizirane medicinske pripomočke - 3. del: Papir za izdelavo papirnatih vrečk (specifikacija EN 868-4) in papir za izdelavo vrečk in zvitkov (specifikacija EN 868-5) - Zahteve in preskusne metode

Packaging for terminally sterilized medical devices - Part 3: Paper for use in the manufacture of paper bags (specified in EN 868-4) and in the manufacture of pouches and reels (specified in EN 868-5) - Requirements and test methods

Verpackungen für in der Endverpackung zu sterilisierende Medizinprodukte - Teil 3: Papier zur Herstellung von Papierbeuteln (festgelegt in EN 868-4) und zur Herstellung von Klarsichtbeuteln und -schläuchen (festgelegt in EN 868-5) - Anforderungen und Prüfverfahren

Emballage des dispositifs médicaux stérilisés au stade terminal - Partie 3 : Papier utilisé dans la fabrication de sacs en papier (spécifiés dans l'EN 868-4) et dans la fabrication de sachets et gaines (spécifiés dans l'EN 868-5) - Exigences et méthodes d'essai

Ta slovenski standard je istoveten z: prEN 868-3

ICS:

11.080.30	Sterilizirana embalaža	Sterilized packaging
55.080	Vreče. Vrečke	Sacks. Bags

oSIST prEN 868-3:2024

en,fr,de

EUROPEAN STANDARD
NORME EUROPÉENNE
EUROPÄISCHE NORM

DRAFT
prEN 868-3

April 2024

ICS 11.080.30

Will supersede EN 868-3:2017

English Version

**Packaging for terminally sterilized medical devices - Part
3: Paper for use in the manufacture of paper bags
(specified in EN 868-4) and in the manufacture of pouches
and reels (specified in EN 868-5) - Requirements and test
methods**

Emballage des dispositifs médicaux stérilisés au stade terminal - Partie 3 : Papier utilisé dans la fabrication de sacs en papier (spécifiés dans l'EN 868-4) et dans la fabrication de sachets et gaines (spécifiés dans l'EN 868-5) - Exigences et méthodes d'essai

Verpackungen für in der Endverpackung zu sterilisierende Medizinprodukte - Teil 3: Papier zur Herstellung von Papierbeuteln (festgelegt in EN 868-4) und zur Herstellung von Klarsichtbeuteln und -schläuchen (festgelegt in EN 868-5) - Anforderungen und Prüfverfahren

This draft European Standard is submitted to CEN members for enquiry. It has been drawn up by the Technical Committee CEN/TC 102.

If this draft becomes a European Standard, CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration.

This draft European Standard was established by CEN in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Türkiye and United Kingdom.

Recipients of this draft are invited to submit, with their comments, notification of any relevant patent rights of which they are aware and to provide supporting documentation.

Warning : This document is not a European Standard. It is distributed for review and comments. It is subject to change without notice and shall not be referred to as a European Standard.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels

Contents	Page
European foreword	3
Introduction	5
1 Scope	6
2 Normative references	6
3 Terms and definitions	7
4 General requirements	7
5 Performance requirements and test methods	7
5.1 General	7
6 Sterilization compatibility	8
7 Labelling	9
7.1 Transport packaging	9
7.2 Labelling of individual units	9
8 Environmental declarations	9
Annex A (normative) Method for the determination of water repellency	11
Annex B (normative) Method for the determination of pore size	14
Annex C (informative) Repeatability and reproducibility of test methods	19
Annex D (informative) Environmental aspects	21
Bibliography	24

[oSIST prEN 868-3:2024](https://standards.iteh.ai/catalog/standards/sist/361c1292-5ff3-4fd4-be25-9c2fac80c594/osist-pren-868-3-2024)

<https://standards.iteh.ai/catalog/standards/sist/361c1292-5ff3-4fd4-be25-9c2fac80c594/osist-pren-868-3-2024>

European foreword

This document (prEN 868-3:2024) has been prepared by Technical Committee CEN/TC 102 “Sterilizers and associated equipment for processing of medical devices”, the secretariat of which is held by DIN.

This document is currently submitted to the CEN Enquiry.

This document will supersede EN 868-3:2017.

This document includes the following significant technical changes with respect to EN 868-3:2017:

- a) The document was renumbered to limit the list numbering to 3 levels only for better readability.
- b) Clause 4 “General requirements” was slightly revised for clarity aligned with the other parts of EN 868 series and a statement was added clarifying when acceptance criteria apply.
- c) Clause 6 “Sterilization compatibility” was added, aligned with the other parts of EN 868 series.
- d) Clause 8 “Environmental declarations” was added and aligned with the other parts of EN 868 series.
- e) List of major changes were moved to Foreword, thus Annex A was deleted.
- f) New Clause “Environmental aspects for testing” was added to each test method in Annexes A – B.
- g) New Annex D regarding environmental aspects was added.

EN 868 consists of the following parts, under the general title *Packaging for terminally sterilized medical devices*:

- *Part 2: Sterilization wrap — Requirements and test methods;*
- *Part 3: Paper for use in the manufacture of paper bags (specified in EN 868-4) and in the manufacture of pouches and reels (specified in EN 868-5) — Requirements and test methods;*
- *Part 4: Paper bags — Requirements and test methods;*
- *Part 5: Sealable pouches and reels of porous materials and plastic film construction — Requirements and test methods;*
- *Part 6: Paper for low temperature sterilization processes — Requirements and test methods;*
- *Part 7: Adhesive coated paper for low temperature sterilization processes — Requirements and test methods;*
- *Part 8: Re-usable sterilization containers for steam sterilizers conforming to EN 285 — Requirements and test methods;*
- *Part 9: Uncoated nonwoven materials of polyolefines — Requirements and test methods;*
- *Part 10: Adhesive coated nonwoven materials of polyolefines — Requirements and test methods.*

In addition, ISO/TC 198 “Sterilization of health care products” in collaboration with CEN/TC 102 “Sterilizers and associated equipment for processing of medical devices” has prepared the EN ISO 11607 series “Packaging for terminally sterilized medical devices”. The EN ISO 11607 series specifies general

prEN 868-3:2024 (E)

requirements for materials, sterile barrier systems and packaging systems (Part 1) and validation requirements for forming, sealing and assembly processes (Part 2).

iTeh Standards
(<https://standards.iteh.ai>)
Document Preview

[oSIST prEN 868-3:2024](https://standards.iteh.ai/catalog/standards/sist/361c1292-5ff3-4fd4-be25-9c2fac80c594/osist-pren-868-3-2024)

<https://standards.iteh.ai/catalog/standards/sist/361c1292-5ff3-4fd4-be25-9c2fac80c594/osist-pren-868-3-2024>

Introduction

The EN ISO 11607 series of standards consists of two parts under the general title “Packaging for terminally sterilized medical devices”. Part 1 of this series specifies general requirements and test methods for materials, preformed sterile barrier systems, sterile barrier systems and packaging systems that are intended to maintain sterility of terminally sterilized medical devices to the point of use. Part 2 of this series specifies validation requirements for forming, sealing and assembly processes.

General requirements for all types of sterile barrier systems are provided by EN ISO 11607-1.

The EN 868 series of standards have been developed mainly for materials and sterile barrier systems used in health care facilities sterilization processes. The EN 868 series of standards can be used to demonstrate compliance with one or more of the requirements specified in EN ISO 11607-1.

Considering CEN guide 4 [1] and the CEN environmental checklists, this revision has been complemented with a new annex with guidance to encourage users to also include environmental aspects when applying the EN 868 series of standards with the objective to minimize the environmental impact. Environmental aspects have also been included into the description of test methods with the same objective.

iTeh Standards (<https://standards.iteh.ai>) Document Preview

[oSIST prEN 868-3:2024](https://standards.iteh.ai/catalog/standards/sist/361c1292-5ff3-4fd4-be25-9c2fac80c594/osist-pren-868-3-2024)

<https://standards.iteh.ai/catalog/standards/sist/361c1292-5ff3-4fd4-be25-9c2fac80c594/osist-pren-868-3-2024>

prEN 868-3:2024 (E)**1 Scope**

This document specifies test methods and values for paper used in the manufacture of single-use paper bags (specified in EN 868-4) and in the manufacture of single-use pouches and reels (specified in EN 868-5) used as sterile barrier systems and/or packaging systems for terminally sterilized medical devices by means of sterilization processes that require properties specific to higher temperature sterilization, such as moist heat sterilization used in healthcare facilities.

Other than the general requirements as specified in EN ISO 11607-1 and EN ISO 11607-2 [2], this part of EN 868 specifies materials, test methods and values that are specific to the products covered by this document.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN ISO 187, *Paper, board and pulps — Standard atmosphere for conditioning and testing and procedure for monitoring the atmosphere and conditioning of samples (ISO 187)*

EN ISO 535, *Paper and board — Determination of water absorptiveness — Cobb method (ISO 535)*

EN ISO 536, *Paper and board — Determination of grammage (ISO 536)*

EN ISO 1924-2, *Paper and board — Determination of tensile properties — Part 2: Constant rate of elongation method (20 mm/min) (ISO 1924-2)*

EN ISO 1974, *Paper — Determination of tearing resistance — Elmendorf method (ISO 1974)*

EN ISO 2758, *Paper — Determination of bursting strength (ISO 2758)*

EN ISO 11607-1:2020, *Packaging for terminally sterilized medical devices — Part 1: Requirements for materials, sterile barrier systems and packaging systems (ISO 11607-1:2019)*

<https://standards.iteh.ai/catalog/standards/sist/361e1292-5ff3-4fd4-be25-9c2fac80c594/osist-pren-868-3-2024>

EN ISO 14021, *Environmental labels and declarations — Self-declared environmental claims (Type II environmental labelling) (ISO 14021)*

EN ISO 14025, *Environmental labels and declarations — Type III environmental declarations — Principles and procedures (ISO 14025)*

ISO 2470-2, *Paper, board and pulps — Measurement of diffuse blue reflectance factor — Part 2: Outdoor daylight conditions (D65 brightness)*

ISO 3689, *Paper and board — Determination of bursting strength after immersion in water*

ISO 3781, *Paper and board — Determination of tensile strength after immersion in water*

ISO 5636-3, *Paper and board — Determination of air permeance (medium range) — Part 3: Bendtsen method*

ISO 6588-2:2021, *Paper, board and pulps — Determination of pH of aqueous extracts — Part 2: Hot extraction*

ISO 8601-1, *Date and time — Representations for information interchange — Part 1: Basic rules*

ISO 9197, *Paper, board and pulps — Determination of water-soluble chlorides*

ISO 9198, *Paper, board and pulp — Determination of water-soluble sulfates*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in EN ISO 11607-1:2020 apply.

ISO and IEC maintain terminology databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp/>
- IEC Electropedia: available at <https://www.electropedia.org/>

4 General requirements

4.1 For any material, preformed sterile barrier system or sterile barrier system, the requirements of EN ISO 11607-1 shall apply.

NOTE When additional materials are used inside the sterile barrier system in order to ease the organization, drying or aseptic presentation (e.g. inner wrap, container filter, indicators, packing lists, mats, instrument organizer sets, tray liners or an additional envelope around the medical device), then other requirements, including the determination of the acceptability of these materials during validation activities, can apply.

4.2 This part of EN 868 only introduces performance requirements and test methods that are specific to the products covered by this part of EN 868 but does not add or modify the general requirements specified in EN ISO 11607-1.

As such, the particular requirements in Clause 5 can be used to demonstrate compliance with one or more but not all of the requirements of EN ISO 11607-1.

NOTE Compliance to EN 868-3 does not automatically mean compliance to EN ISO 11607-1.

4.3 All acceptance criteria in Clause 5 shall be applied for testing materials before sterilization.

4.4 A confirmation of compliance to EN 868-3 shall contain a statement whether EN ISO 11607-1 is covered.

5 Performance requirements and test methods

5.1 General

NOTE See Annex C for repeatability and reproducibility of the test methods: pore diameters, sulphate content, chloride content and water repellency. For information on statement of precision and/or bias, repeatability and reproducibility of other test methods, see EN ISO 11607-1:2020, Table B.1.

5.2 The requirements of 5.13 and 5.17 do not apply to materials solely used in irradiation sterilization packaging.

5.3 No colour shall leach out of the paper. Compliance shall be tested by visual examination of a hot aqueous extract prepared in accordance with the method given in ISO 6588-2.

5.4 The average mass of 1 m² of the conditioned paper when tested in accordance with EN ISO 536 shall be within ± 5 % of the nominal value stated by the manufacturer.

prEN 868-3:2024 (E)

5.5 The pH of an aqueous extract of the paper shall be not less than 5 or greater than 8 when tested in accordance with ISO 6588-2, hot extraction method.

5.6 The chloride content of the paper, calculated as sodium chloride, shall not exceed 0,05 % when tested in accordance with ISO 9197 using a hot extract prepared in accordance with ISO 6588-2:2021, 7.2 except that 2 ml of potassium chloride solution is not added.

5.7 The sulphate content of the paper, calculated as sodium sulphate, shall not exceed 0,25 % when tested in accordance with ISO 9198, using a hot extract prepared in accordance with ISO 6588-2:2021, 7.2 except that 2 ml of potassium chloride solution is not added.

5.8 When tested in accordance with ISO 2470-2 the material shall not exhibit an increase in D65 brightness, due to the optical brightener agents, of more than 1 %; calculated as the ratio of the D65 brightness measured with the 420 nm UV-cut-off filter in place to the D65 brightness measured without 420 nm UV-cut-off filter.

5.9 When exposed at $(25,0 \pm 1,0)$ cm from a UV light source, the material shall not have per 0,01 m² more than five fluorescent spots, each having an axis greater than 1 mm.

The UV light to be used is the one described as per Annex A.

5.10 The internal tearing resistance of the conditioned paper shall be not less than 550 mN in both machine and cross direction when tested in accordance with EN ISO 1974.

5.11 The air permeance of the conditioned paper shall be not less than 3,4 µm/Pa × s at an air pressure of 1,47 kPa when tested in accordance with ISO 5636-3.

5.12 The bursting strength of the conditioned paper shall be not less than 230 kPa when tested in accordance with EN ISO 2758.

5.13 The wet bursting strength of the paper shall be not less than 35 kPa when tested in accordance with ISO 3689 using an immersion time of 10 min.

5.14 The water repellency of the paper shall be such that the penetration time is not less than 20 s when tested in accordance with Annex A.

5.15 When tested in accordance with Annex B, the average of the pore diameters of the ten test pieces shall be lower than or equal to 35 µm. No value shall be greater than 50 µm.

5.16 The tensile strength of the conditioned paper shall be not less than 4,40 kN/m in machine direction and not less than 2,20 kN/m in cross direction when tested in accordance with EN ISO 1924-2.

5.17 The wet tensile strength of the paper shall be not less than 0,90 kN/m in machine direction and not less than 0,45 kN/m in cross direction when tested in accordance with ISO 3781.

5.18 The surface absorbency of each side of the paper shall be not more than 20 g/m² when tested in accordance with EN ISO 535 using a 60 s exposure time (COBB method).

6 Sterilization compatibility

6.1 The sterilization processes applicable to the packaging materials under the scope of this document shall be defined by the manufacturer of the packaging material.