



Designation: B977 – 11

Standard Specification for Titanium and Titanium Ingots¹

This standard is issued under the fixed designation B977; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This specification covers titanium and titanium alloy ingots as follows:

- 1.1.1 *Grade 1*—Unalloyed titanium,
- 1.1.2 *Grade 2*—Unalloyed titanium,
- 1.1.3 *Grade 3*—Unalloyed titanium,
- 1.1.4 *Grade 4*—Unalloyed titanium,
- 1.1.5 *Grade 5*—Titanium alloy (6 % aluminum, 4 % vanadium),
- 1.1.6 *Grade 6*—Titanium alloy (5 % aluminum, 2.5 % tin),
- 1.1.7 *Grade 7*—Unalloyed titanium plus 0.12 to 0.25 % palladium,
- 1.1.8 *Grade 9*—Titanium alloy (3 % aluminum, 2.5 % vanadium),
- 1.1.9 *Grade 11*—Unalloyed titanium plus 0.12 to 0.25 % palladium,
- 1.1.10 *Grade 12*—Titanium alloy (0.3 % molybdenum, 0.8 % nickel),
- 1.1.11 *Grade 13*—Titanium alloy (0.5 % nickel, 0.05 % ruthenium),
- 1.1.12 *Grade 14*—Titanium alloy (0.5 % nickel, 0.05 % ruthenium),
- 1.1.13 *Grade 15*—Titanium alloy (0.5 % nickel, 0.05 % ruthenium),
- 1.1.14 *Grade 16*—Unalloyed titanium plus 0.04 to 0.08 % palladium,
- 1.1.15 *Grade 17*—Unalloyed titanium plus 0.04 to 0.08 % palladium,
- 1.1.16 *Grade 18*—Titanium alloy (3 % aluminum, 2.5 % vanadium) plus 0.04 to 0.08 % palladium,
- 1.1.17 *Grade 19*—Titanium alloy (3 % aluminum, 8 % vanadium, 6 % chromium, 4 % zirconium, 4 % molybdenum),
- 1.1.18 *Grade 20*—Titanium alloy (3 % aluminum, 8 % vanadium, 6 % chromium, 4 % zirconium, 4 % molybdenum) plus 0.04 to 0.08 % palladium,
- 1.1.19 *Grade 21*—Titanium alloy (15 % molybdenum, 3 % aluminum, 2.7 % niobium, 0.25 % silicon),

1.1.20 *Grade 23*—Titanium alloy (6 % aluminum, 4 % vanadium with extra low interstitials, ELI),

1.1.21 *Grade 24*—Titanium alloy (6 % aluminum, 4 % vanadium) plus 0.4 to 0.8 % palladium,

1.1.22 *Grade 25*—Titanium alloy (6 % aluminum, 4 % vanadium) plus 0.3 to 0.8 % nickel and 0.04 to 0.08 % palladium,

1.1.23 *Grade 26*—Unalloyed titanium plus 0.08 to 0.14 % ruthenium,

1.1.24 *Grade 27*—Unalloyed titanium plus 0.08 to 0.14 % ruthenium,

1.1.25 *Grade 28*—Titanium alloy (3 % aluminum, 2.5 % vanadium) plus 0.08 to 0.14 % ruthenium,

1.1.26 *Grade 29*—Titanium alloy (6 % aluminum, 4 % vanadium, extra low interstitial elements, ELI) plus 0.08 to 0.14 % ruthenium,

1.1.27 *Grade 30*—Titanium alloy (0.3 % cobalt, 0.05 % palladium),

1.1.28 *Grade 31*—Titanium alloy (0.3 % cobalt, 0.05 % palladium),

1.1.29 *Grade 32*—Titanium alloy (5 % aluminum, 1 % tin, 1 % zirconium, 1 % vanadium, 0.8 % molybdenum),

1.1.30 *Grade 33*—Titanium alloy (0.4 % nickel, 0.015 % palladium, 0.025 % ruthenium, 0.15 % chromium),

1.1.31 *Grade 34*—Titanium alloy (0.4 % nickel, 0.015 % palladium, 0.025 % ruthenium, 0.15 % chromium),

1.1.32 *Grade 35*—Titanium alloy (4.5 % aluminum, 2 % molybdenum, 1.6 % vanadium, 0.5 % iron, 0.3 % silicon),

1.1.33 *Grade 36*—Titanium alloy (45 % niobium),

1.1.34 *Grade 37*—Titanium alloy (1.5 % aluminum), and

1.1.35 *Grade 38*—Titanium alloy (4 % aluminum, 2.5 % vanadium, 1.5 % iron).

1.2 The values stated in either SI units or inch-pound units are to be regarded separately as standard. The values stated in each system may not be exact equivalents; therefore, each system shall be used independently of the other. Combining values from the two systems may result in non-conformance with the standard.

1.3 *The following caveat pertains only to the test method portions of this specification: This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

¹ This specification is under the jurisdiction of ASTM Committee B10 on Reactive and Refractory Metals and Alloys and is the direct responsibility of Subcommittee B10.01 on Titanium.

Current edition approved July 1, 2011. Published August 2011. DOI:10.1520/B0977-11.

2. Referenced Documents

2.1 *ASTM Standards*:²

- E29 Practice for Using Significant Digits in Test Data to Determine Conformance with Specifications
- E178 Practice for Dealing With Outlying Observations
- E539 Test Method for Analysis of Titanium Alloys by X-Ray Fluorescence Spectrometry
- E1409 Test Method for Determination of Oxygen and Nitrogen in Titanium and Titanium Alloys by the Inert Gas Fusion Technique
- E1447 Test Method for Determination of Hydrogen in Titanium and Titanium Alloys by Inert Gas Fusion Thermal Conductivity/Infrared Detection Method
- E1941 Test Method for Determination of Carbon in Refractory and Reactive Metals and Their Alloys by Combustion Analysis
- E2371 Test Method for Analysis of Titanium and Titanium Alloys by Atomic Emission Plasma Spectrometry
- E2626 Guide for Spectrometric Analysis of Reactive and Refractory Metals

3. Terminology

3.1 *Lot Definitions*:

- 3.2 *ingot, n*—a quantity of metal cast into a shape suitable for subsequent processing to various mill products.

4. Ordering Information

4.1 Orders for material under this specification shall include the following information as required to describe adequately the desired material:

- 4.1.1 Grade number (1.1),
- 4.1.2 Nominal weight in the unit system regarded as standard (inch-pound or SI),
- 4.1.3 Nominal size (width and gauge or diameter, length) in the unit system regarded as standard (inch-pound or SI),
- 4.1.4 ASTM designation and year of issue.

4.2 Orders for material under this specification may include (at the discretion of the purchaser) the following additional information:

- 4.2.1 Method of manufacture (5.1),
- 4.2.2 Surface condition (7.1 and 7.2),
- 4.2.3 Product analysis (6.2),
- 4.2.4 Additional chemical analysis (6.1.3),
- 4.2.5 Requirements for purchaser inspection/witness (11.1), and
- 4.2.6 Packaging (Section 15).

5. Materials and Manufacture

5.1 Materials covered by this specification are produced by one of the following methods:

- 5.1.1 double vacuum arc melting,
- 5.1.2 triple vacuum arc melting,

5.1.3 electron beam cold hearth melting followed by vacuum arc melting,

5.1.4 plasma arc cold hearth melting followed by vacuum arc melting,

5.1.5 electron beam cold hearth melting,

5.1.6 plasma arc cold hearth melting or

5.1.7 other melting process as agreed upon by the purchaser and producer.

5.2 The melting method used to produce the ingot shall be reported to the purchaser on the certification.

5.3 The melting method shall be at the discretion of the producer, unless specified in the purchase order.

6. Chemical Composition

6.1 The chemistry of titanium and titanium alloy ingot covered by this specification shall conform to the requirements for the specified grade as prescribed in Table 1.

6.1.1 The elements listed for each grade in Table 1 are intentional alloy additions or elements that are inherent to the manufacture of titanium sponge or ingot.

6.1.2 Elements intentionally added to the melt, including additions made via revert additions, must be identified, analyzed and reported in the chemical analysis. Elements not listed in Table 1 for the specified grade shall not be required.

6.1.3 When agreed upon by the producer and purchaser and requested by the purchaser in the written purchase order, chemical analysis shall be completed for specific elements not listed in this specification.

6.2 The chemical analysis shall normally be conducted using the ASTM standard test methods referenced in 2.1. Other industry standard methods may be used where the ASTM test methods in 2.1 do not adequately cover the elements in the material or by other methods acceptable to the purchaser. Alternate techniques are discussed in Guide E2626.

6.3 *Product Check Analysis*—Product check analysis is an analysis made by or for the purchaser for the purpose of verifying the composition of the ingot. The check analysis tolerances reflect the variation between laboratories in the measurement of chemical composition. The permissible variation in the product check analysis from the specified range is as prescribed in Table 2.

7. Condition

7.1 *Surface Finish*—The surface finish shall be at the discretion of the producer, unless specified in the purchase order.

7.2 When specified, the ingots shall be conditioned on the surface to standards agreed upon between the manufacturer and the purchaser.

7.3 Titanium and titanium alloy ingots shall be free of imperfections that would be deemed injurious by the standards of acceptability agreed upon between the purchaser and the manufacturer.

7.3.1 The manufacturer shall be permitted to remove minor surface imperfections. Surface imperfections may be removed up to 1 in. (25 mm) deep from the ingot surface. Areas adjacent

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.