

FINAL
DRAFT

INTERNATIONAL
STANDARD

ISO/FDIS
18219-1

IULTCS
IUC 30-1

IULTCS

Voting begins on:
2021-02-09

Voting terminates on:
2021-04-06

**Leather — Determination of
chlorinated hydrocarbons in
leather —**

Part 1:
**Chromatographic method for short-
chain chlorinated paraffins (SCCPs)**

iTeh STANDARD PREVIEW
(standards.iteh.ai)

Cuir — Dosage des hydrocarbures chlorés dans le cuir —

*Partie 1: Méthode chromatographique pour les paraffines chlorées à
chaîne courte (PCCC)*

<https://standards.iteh.ai/catalog/standards/sist/1f6bd224-2f63-40cc-bfbc-1a601b21bccc/iso-fdis-18219-1>

ISO/CEN PARALLEL PROCESSING

RECIPIENTS OF THIS DRAFT ARE INVITED TO SUBMIT, WITH THEIR COMMENTS, NOTIFICATION OF ANY RELEVANT PATENT RIGHTS OF WHICH THEY ARE AWARE AND TO PROVIDE SUPPORTING DOCUMENTATION.

IN ADDITION TO THEIR EVALUATION AS BEING ACCEPTABLE FOR INDUSTRIAL, TECHNOLOGICAL, COMMERCIAL AND USER PURPOSES, DRAFT INTERNATIONAL STANDARDS MAY ON OCCASION HAVE TO BE CONSIDERED IN THE LIGHT OF THEIR POTENTIAL TO BECOME STANDARDS TO WHICH REFERENCE MAY BE MADE IN NATIONAL REGULATIONS.



Reference numbers
ISO/FDIS 18219-1:2021(E)
IULTCS/IUC 30-1:2021(E)

© ISO 2021

iTeh STANDARD PREVIEW (standards.iteh.ai)

[ISO/FDIS 18219-1](https://standards.iteh.ai/catalog/standards/sist/1f6bd224-2f63-40cc-bfbc-1a601b21bccc/iso-fdis-18219-1)

<https://standards.iteh.ai/catalog/standards/sist/1f6bd224-2f63-40cc-bfbc-1a601b21bccc/iso-fdis-18219-1>



COPYRIGHT PROTECTED DOCUMENT

© ISO 2021

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Contents

Page

Foreword	iv
Introduction	vi
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Principle	1
5 Apparatus and materials	1
6 Reagents	2
7 Sampling	2
8 Sample preparation and analysis	2
8.1 Preparation of the SCCPs calibration solution (50 µg/ml) with 59 % chlorine content.....	2
8.2 Extraction of leather.....	3
8.3 Sulfuric acid clean-up.....	3
8.4 GC-ECNI-MS determination.....	3
9 Expression of results	3
9.1 Evaluation.....	3
9.2 Ions used for quantification.....	3
9.3 Interference to SCCPs determination.....	3
9.4 Calculation.....	4
9.5 Precision.....	4
10 Test report	4
Annex A (informative) Gas chromatographic (GC-ECNI-MS) analysis operating parameters	5
Annex B (informative) Liquid chromatographic (LC-MS/MS) analysis operating parameters	6
Annex C (informative) Integration using peak shape evaluation (PSE) with GC-ECNI-MS	9
Bibliography	12

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see www.iso.org/iso/foreword.html.

This document prepared by the Chemical Test Commission of the International Union of Leather Technologists and Chemists Societies (IUC Commission, IULTCS) in collaboration with the European Committee for Standardization (CEN) Technical Committee CEN/TC 289, *Leather*, the secretariat of which is held by UNI, in accordance with the agreement on technical co-operation between ISO and CEN (Vienna Agreement).

IULTCS, originally formed in 1897, is a world-wide organization of professional leather societies to further the advancement of leather science and technology. IULTCS has three Commissions, which are responsible for establishing international methods for the sampling and testing of leather. ISO recognizes IULTCS as an international standardizing body for the preparation of test methods for leather.

This first edition of ISO 18219-1, together with ISO 18219-2, cancels and replaces ISO 18219:2015, which has been technically revised.

The main changes to ISO 18219:2015 are as follows:

- a modification of the ISO number and the title;
- Introduction revised and updated;
- a new [Clause 3](#);
- technical changes to [Clause 4](#);
- in [6.2](#), a new internal standard;
- in [8.3](#), the SPE clean-up changed to a procedure using sulfuric acid;
- new [9.2](#), [9.3](#), [9.4](#) and [9.5](#) to improve the method;
- a new [Annex B](#) with a LC-MS/MS procedure;

— a new [Annex C](#) explaining how to interpret the chromatograms with peak shape evaluation (PSE).

A list of all parts in the ISO 18219 series can be found on the ISO website.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

ISO/FDIS 18219-1

<https://standards.iteh.ai/catalog/standards/sist/1f6bd224-2f63-40cc-bfbc-1a601b21bccc/iso-fdis-18219-1>

Introduction

Short-chain chlorinated paraffins (SCCPs) are a mixture of chlorinated hydrocarbons with a chain length of 10 to 13 carbon atoms and a chlorine content of 40 % to 70 %. SCCPs are classified as dangerous to the environment, since they are very toxic to aquatic organisms and can cause long-term adverse effects in the aquatic environment.

In 2002, the European Directive 2002/45/EC restricted the sale and use of SCCPs (C_{10} to C_{13}) in product preparations for the fatliquoring of leather. Preparations containing concentrations equal to or higher than 1 % of SCCPs were forbidden. This directive is included as part of the EU Regulation 1907/2006 (REACH). Within this EU Regulation, in October 2008, the SCCPs were added to the candidate list of substances of very high concern (SVHC)^[2].

The EU Commission Regulation 2015/2030^[3] in November 2015 prohibited alkanes C_{10} to C_{13} , chloro (SCCPs) (CAS No 85535-84-8), as constituents of articles. Articles containing SCCPs in concentrations lower than 0,15 % by mass are allowed.

In 2017, the SCCPs were listed in [Annex A](#) of the Stockholm Convention on Persistent Organic Pollutants (POP)^[4].

The analysis of chlorinated paraffins is a challenge. The technical compounds are mixtures of up to 200 congeners with different chain lengths and degrees of chlorination. GC chromatograms of these complex mixtures typically show a lot of overlapping peaks that can be difficult to separate. In particular, the responses to the various chlorination degrees can vary over a large range.

In addition, the presence of sulfochlorinated paraffins and equivalent chain-length chloroalkenes in such technical compounds can cause interference.

This document describes a procedure to compare the chromatogram results for SCCPs compounds from a test sample with the chromatogram results of a defined calibration standard of the most typically used mixture (59 % chlorination for SCCPs). With this gas chromatography negative ion chemical ionization mass spectrometry (GC-ECNI-MS) procedure it uses four ion traces for identifying the SCCPs.

Leather — Determination of chlorinated hydrocarbons in leather —

Part 1: Chromatographic method for short-chain chlorinated paraffins (SCCPs)

1 Scope

This document specifies a chromatographic method to determine the amount of short-chain chlorinated paraffins (SCCPs) C₁₀ to C₁₃ in processed and unprocessed leathers.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 2418, *Leather — Chemical, physical and mechanical and fastness tests — Sampling location*

ISO 4044, *Leather — Chemical tests — Preparation of chemical test samples*

3 Terms and definitions

No terms and definitions are listed in this document.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <http://www.electropedia.org/>

4 Principle

The test sample is extracted using n-hexane at 60 °C in an ultrasonic bath for 60 min. After sulfuric acid clean-up, an aliquot is then analysed using a gas chromatograph fitted to a mass selective detector with chemical ionization (GC-ECNI-MS).

A liquid chromatography system with single quad (LC-MS) or triple quad mass spectrometry (LC-MS/MS), as described in [Annex B](#), can also be used if the user has demonstrated that the accuracy of measurement is equivalent to that of the GC-ECNI-MS method.

In some cases when determining SCCPs using the GC-ECNI-MS method, the presence of sulfochlorinated paraffins and equivalent chain-length chloroalkenes causes interference. The [Annex B](#) procedure with a LC-MS/MS method aims to give a better resolution and eliminate possible false positives determined with the GC-ECNI-MS method.

5 Apparatus and materials

Use normal laboratory apparatus and, in particular, the following.

- 5.1 **Analytical balance**, weighing to an accuracy of 0,1 mg.
- 5.2 **Sealable vessel**, with lid, 20 ml, suitable for extraction with n-hexane.
- 5.3 **Ultrasonic bath**, with controllable heating capable of maintaining a temperature of (60 ± 5) °C.

NOTE A frequency of 40 KHz is suitable.

- 5.4 **Pipette**, 1 ml to 10 ml capacity.
- 5.5 **Volumetric flask**, 2 ml.
- 5.6 **Gas chromatograph and mass selective detector with chemical ionization**, (GC-ECNI-MS).

NOTE An example of GC-ECNI-MS equipment is given in [Annex A](#).

- 5.7 **Shaker or agitator**, ensuring an efficient mixing of the phases.

6 Reagents

If not otherwise defined, analytical reagent grade chemicals shall be used.

- 6.1 **n-hexane**, Chemical Abstracts Service (CAS) CAS No 110-54-3.
- 6.2 **Internal standard solution, lindane**, CAS No 58-89-9, 1 000 µg/ml.
- 6.3 **Standard solutions, SCCPs, C₁₀ to C₁₃**, with different chlorination degree, each 100 µg/ml.
- 6.3.1 **SCCPs C₁₀ to C₁₃, 55,5 % Cl**, technical grade.
- 6.3.2 **SCCPs C₁₀ to C₁₃, 63 % Cl**, technical grade, CAS No 85535-84-8.

NOTE These SCCPs calibration solutions are available commercially.

- 6.4 **Concentrated sulfuric acid**, ($\rho = 1,84$ g/ml at 20 °C).

7 Sampling

Take a sample in accordance with ISO 2418. If sampling in accordance with ISO 2418 is not possible (e.g. leathers from finished products like shoes, garments), provide details about sampling together with the test report. Glue residuals shall be mechanically removed from leather samples.

Prepare the leather samples in accordance with ISO 4044.

8 Sample preparation and analysis

8.1 Preparation of the SCCPs calibration solution (50 µg/ml) with 59 % chlorine content

Transfer 533 µl of SCCPs C₁₀ to C₁₃ 55,5 % Cl standard solution (6.3.1) and 467 µl SCCPs C₁₀ to C₁₃ 63 % Cl standard solution (6.3.2) into a 2 ml volumetric flask (5.5). Add 20 µl of internal standard solution (6.2). Fill the flask up to the volume with n-hexane (6.1).

The calibration standard with 59 % chlorine content shall be used for the quantification of all samples, independent of their chlorination degree (if known).

8.2 Extraction of leather

Weigh 0,5 g ± 0,001 g test leather sample with the analytical balance (5.1) into the sealable vessel (5.2). Add 9,9 ml n-hexane (6.1) and 100 µl internal standard (6.2) and seal the vessel. Extract the sample at (60 ± 5) °C in an ultrasonic bath (5.3) for (60 ± 2) min. Cool down to room temperature (less than 27 °C).

8.3 Sulfuric acid clean-up

Add a 5 ml aliquot of the extracted hexane solution to a tight sealable vessel (5.2) and add 1 ml sulfuric acid (6.4). Shake the vessel (5.7) for 10 min. After separating of the phases (optionally with centrifugation), 1 ml of the hexane phase shall be taken for analysis.

8.4 GC-ECNI-MS determination

Analyse the solution using GC-ECNI-MS (5.6). An example of a suitable GC-ECNI-MS method is given in Annex A.

9 Expression of results

9.1 Evaluation

The peak shape evaluation (PSE) has been successfully tested and used. The integration shall be done with PSE in accordance with examples presented in Annex C.

Peak areas from the four quantification masses of the standard are summed up and equated with standard concentration. Peak areas of the samples are summed up too and the concentration is calculated with the response of the standard.

To check the linearity of the analytical system, a calibration standard as reference standard is analysed after each ten samples and at the end of the sequence. The deviation in reference to the calibration standard should be within ± 20 %, otherwise the analytical system has to be checked before retrying the analysis.

Sample extract should always be diluted in the concentration range of the standard.

The integration of the samples shall only be done in the retention time window of the standard.

9.2 Ions used for quantification

Table A.1 lists the ions used for the quantification of SCCPs and the ions used for the internal standard lindane.

Sum up the quantifier peak areas from the standard and equate with the standard concentration. Sum up the quantifier peak areas of the sample, too, and calculate the concentration with responses of the calibration standards.

To get a quantitative result, each peak area of the extract chromatogram has to be below the highest calibration point. If not, dilute the extract with IS solution (8.2) in the range or specify that the result is bigger than the calculated result.

9.3 Interference to SCCPs determination

C₁₁Cl₇ qualifier m/z (mass-to-charge ratio) ion 363 can show a large interference if there is a high middle-chain chlorinated paraffins (MCCPs) content. If the peak shape and retention time fits it is possible to ignore the divergent quantifier/qualifier ratio. Note in test report.

C₁₂Cl₇ quantifier m/z ion 375 can also show interference if there is a high MCCPs content. In this case the quantifier and qualifier can be switched. Note in test report.

9.4 Calculation

Set up the linear regression function by using the ratio ($A_{\text{SCCP-S}}/A_{\text{int.Std-S}}$) and ($C_{\text{SCCP-S}}/C_{\text{int.Std-S}}$) as shown in [Formula \(1\)](#).

$$\frac{A_{\text{SCCP-S}}}{A_{\text{int.Std-S}}} = \frac{C_{\text{SCCP-S}}}{C_{\text{int.Std-S}}} \cdot a + b \quad (1)$$

where

$A_{\text{SCCP-S}}$ is the sum of the peak areas of SCCPs in the calibration standard;

$A_{\text{int.Std-S}}$ is the area of the internal standard in the calibration standard;

a is the slope of the linear function;

b is the intercept of the linear function;

$C_{\text{SCCP-S}}$ is the concentration of SCCPs in the calibration standard, $\mu\text{g/ml}$;

$C_{\text{int.Std-S}}$ is the concentration of the internal standard in the calibration standard, $\mu\text{g/ml}$.

The content of the SCCPs in leather is calculated according to [Formula \(2\)](#) as a mass fraction, w , in mg/kg .

$$w = \left(\frac{A_{\text{SCCP-Sample}}}{A_{\text{int.Std-Sample}}} - b \right) \cdot \frac{V}{m} \cdot C_{\text{int.Std-Sample}} \quad (2)$$

where

$A_{\text{SCCP-Sample}}$ is the sum of the peak areas of SCCPs in the sample;

$A_{\text{int.Std-Sample}}$ is the peak area of internal standard in the sample;

V is the final volume, ml ;

m is the mass of the sample, g ;

$C_{\text{int.Std-Sample}}$ is the concentration of internal standard in the sample, $\mu\text{g/ml}$.

9.5 Precision

With this method it is feasible to reach quantification limits of 100 mg/kg .

10 Test report

The test report shall include at least the following:

- a reference to this document, i.e. ISO 18219-1:—;
- all details necessary for complete identification of the sample tested;
- the date of the test;
- declaration of analytical techniques used for detection and confirmation;
- amount of extracted SCCPs (C_{10} to C_{13}) in mg/kg ;
- any deviation by agreement or otherwise from the procedure specified.

Annex A (informative)

Gas chromatographic (GC-ECNI-MS) analysis operating parameters

A.1 Suggested GC-ECNI-MS conditions

Column:	non-polar (5 % phenyl methyl siloxane, length: 25 m, internal diameter: 0,25 mm, film thickness: 0,25 µm)
Carrier gas:	helium, flow rate: 1,2 ml/min
Injector temperature:	250 °C, mode splitless, splitless time: 1,5 min
Injection volume:	1 µl
Temperature programme:	120 °C, up to 300 °C at 12 °C/min, 300 °C for 5 min solvent delay: 4 min total run time: 20 min
MS conditions:	transfer line: 280 °C ion source: 150 °C quadrupole: 120 °C
Chemical ionization (CI) conditions:	CI gas: methane 5,5 (i.e. > 99,999 5 % CH ₄) CI valve: 40 %

iTeh STANDARD PREVIEW
(standards.iteh.ai)

<https://standards.iteh.ai/catalog/standards/sist/1f6bd224-2f63-40cc-bfbc-150116136136/iso-18219-1>

A.2 GC-ECNI-MS system optimization

The system should be optimized for good signal or noise ratio. If the scan rate is not chosen correctly, a noisy baseline can prevent peak shape interpretation. In this case scan rate should be changed to faster settings, e.g. 2[^]3.

A.3 Calibration and calculation

Table A.1 — m/z ion signals for quantification and qualification

No.	Substance	Quantifier/qualifier
1	lindane	325/327
		255/253
		255/257
2	SCCPs (C ₁₀ to C ₁₃)	347/349
		361/363
		375/377
		389/391