
Glass — Hydrolytic resistance of glass grains at 98 °C — Method of test and classification

*Verre — Résistance hydrolytique du verre en grains à 98 °C —
Méthode d'essai et classification*

iTeh Standards
(<https://standards.iteh.ai>)
Document Preview

ISO 719:2020

<https://standards.iteh.ai/catalog/standards/iso/df886ace-f0ae-431f-b340-6444fc2deda4/iso-719-2020>



iTeh Standards
(<https://standards.iteh.ai>)
Document Preview

ISO 719:2020

<https://standards.iteh.ai/catalog/standards/iso/df886ace-f0ae-431f-b340-6444fc2deda4/iso-719-2020>



COPYRIGHT PROTECTED DOCUMENT

© ISO 2020

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Contents

Page

Foreword	iv
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Principle	2
5 Reagents	2
6 Apparatus	2
7 Preparation of sample	5
7.1 Crushing.....	5
7.2 Manual preparation.....	5
7.3 Mechanical preparation.....	5
7.4 Cleaning.....	5
8 Procedure	6
9 Expression of results	6
9.1 Calculation.....	6
9.2 Classification.....	6
9.3 Designation.....	6
10 Test report	7
Bibliography	8

iTeh Standards
(<https://standards.iteh.ai>)
Document Preview

ISO 719:2020

<https://standards.iteh.ai/catalog/standards/iso/df886ace-f0ae-431f-b340-6444fc2deda4/iso-719-2020>

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 76, *Transfusion, infusion and injection, and blood processing equipment for medical and pharmaceutical use*.

This third edition cancels and replaces the second edition (ISO 719:1985), which has been technically revised.

The main changes compared to the previous edition are as follows:

- a more precise definition of the field of application by means of glass types was added;
- wherever possible a harmonization with the identical paragraphs in the European Pharmacopoeia, chapter 3.2.1, and the USP, chapter 660, was established to simplify the application in the laboratories globally. This concerns, e.g. sample size, mesh size;
- the usage of acetone was restricted to always fresh, new acetone, since re-usage might lead to deviating test results;
- the maximum temperature and its tolerance field was simplified and oriented on the technical conditions of a water basin.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

Glass — Hydrolytic resistance of glass grains at 98 °C — Method of test and classification

1 Scope

This document specifies

- a) a method for determining the hydrolytic resistance of glass grains at 98 °C. The resistance is measured and expressed by the volume of acid required for titration of the alkali extracted from the unit mass of glass, and can also be expressed by the amount of sodium oxide equivalent to this volume of acid, and
- b) a classification of glass according to the hydrolytic resistance determined by the method of this document.

This document is intended for use on the less resistant types of glass, such as soda-lime glass.

NOTE 1 For the more resistant glasses, e.g. borosilicate glass, the method specified in ISO 720 is more suited.

NOTE 2 It is emphasized that there is no exact correlation between the classification laid down in this document and that laid down in ISO 720, and it is, therefore, essential to identify which classification is being used.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 385, *Laboratory glassware — Burettes*

ISO 565, *Test sieves — Metal wire cloth, perforated metal plate and electroformed sheet — Nominal sizes of openings*

ISO 648, *Laboratory glassware — Single-volume pipettes*

ISO 720, *Glass — Hydrolytic resistance of glass grains at 121 °C — Method of test and classification*

ISO 1042, *Laboratory glassware — One-mark volumetric flasks*

ISO 1773, *Laboratory glassware — Narrow-necked boiling flasks*

ISO 3819, *Laboratory glassware — Beakers*

ISO 13130, *Laboratory glassware — Desiccators*

3 Terms and definitions

No terms and definitions are listed in this document.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <http://www.electropedia.org/>

4 Principle

The method of testing is a test for glass as a material applied on glass grains. Extraction of 2 g of grains, of particle size between 300 µm and 500 µm, with grade 2 water for 60 min at 98 °C. Measurement of the degree of the hydrolytic attack by analysis of the extraction solutions.

The test method shall not be applied to glasses with extreme low alkaline contents or that are essentially free of alkaline species as this method measures only the alkaline release as the indication for chemical durability.

The density of the glass to be tested should, preferably, be $2,4 \text{ g/cm}^3 \pm 0,2 \text{ g/cm}^3$ at 20 °C.

5 Reagents

During the test, unless otherwise stated, use only reagents of recognized analytical grade.

5.1 Test water, to be prepared as follows: prepare the test water from distilled water (5.6) by multiple distillations. Remove the carbon dioxide by boiling for at least 15 min before use in a boiling flask (6.6) of fused silica or borosilicate glass and cool. Any other suitable method may be used, e.g. preparation of carbon dioxide-free water according to USP 660^[4].

When tested immediately before use, water prepared as described above shall produce an orange-red (not violet-red or yellow) colour corresponding to the neutral point of methyl red indicator of $\text{pH } 5,5 \pm 0,1$ when 0,05 ml of methyl red indicator solution (5.4) is added to 50 ml of the water to be examined. This water may also be used as the reference solution (see Clause 8). The conductivity of the water shall not exceed 1 µS/cm , determined at 25 °C by an in-line conductivity meter.

NOTE 1 This description is based on the European Pharmacopoeia 3.2.1^[3]. In the European Pharmacopoeia, water prepared as described above is designated water R1.

NOTE 2 Water of Grade 2 according to ISO 3696^[2] is suitable for this test.

5.2 Hydrochloric acid, standard volumetric solution, $c(\text{HCl}) = 0,01 \text{ mol/l}$.

5.3 Hydrochloric acid, solution, $c(\text{HCl}) = 1 \text{ mol/l}$.

5.4 Methyl red, indicator solution.

Dissolve 25 mg of the sodium salt of methyl red ($\text{C}_{15}\text{H}_{14}\text{N}_3\text{NaO}_2$) in 100 ml of the grade 2 water (5.1). Alternatively, the indicator solution may be prepared as described in, e.g. USP 42 [6.60] or Ph.Eur. 10 [3.2.1] (this method is based on dissolution of methyl red in 0,1 M sodium hydroxide, ethanol and distilled water).

5.5 Acetone (CH_3COCH_3).

5.6 Purified water, prepared by distillation, by ion exchange, by reverse osmosis or by any other suitable method from water having drinking water quality.

NOTE 1 See national or regional regulation for information on water intended for human consumption.

NOTE 2 Water that corresponds to Grade 3 according to ISO 3696^[2] is suitable.

NOTE 3 In the European Pharmacopoeia 3.2.1^[3], water as described above is designated water R.

6 Apparatus

Ordinary laboratory apparatus and, in particular, the following: