



Standard Specification for Crosslinked Chlorinated Polyolefin Heat-Shrinkable Tubing for Electrical Insulation¹

This standard is issued under the fixed designation D2903; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope*

1.1 This specification covers flexible crosslinked chlorinated polyolefin heat-shrinkable tubing used for electrical insulating purposes. It is supplied in an expanded form and will shrink to the specified diameter when heated.

NOTE 1—This standard does not have a similar or equivalent IEC standard.

~~1.2 The values stated in inch-pound units are to be regarded as the standard accept for temperature, which is stated in degrees Celsius. SI values in parentheses are for information only.~~

1.2 The values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units that are provided for information only and are not considered standard.

1.2.1 In some cases, temperatures are described in degrees Celsius only.

2. Referenced Documents

2.1 ASTM Standards:²

D412 Test Methods for Vulcanized Rubber and Thermoplastic Elastomers Tension

D1711 Terminology Relating to Electrical Insulation

D2671 Test Methods for Heat-Shrinkable Tubing for Electrical Use

D3636 Practice for Sampling and Judging Quality of Solid Electrical Insulating Materials

E176 Terminology of Fire Standards

2.2 Military Standards:³

MIL-H-5606 Hydraulic Fluid Petroleum Base, Aircraft, Missile and Ordnance

MIL-T-5624 Turbine Fuel, Aviation, Grades JP4 and JP5

MIL-L-7808 Lubrication Oil, Aircraft, Turbine Engine, Synthetic Base

MIL-L-23699 Lubrication Oil, Aircraft, Turbine Engines, Synthetic Base

MIL-A-8243 Anti-Icing and De-Icing Defrosting Fluid

MIL-G-5572 Fuel, Aviation, Grades 100 and 130

2.3 Federal Standards:

SS-S-550 Sodium Chloride, Technical, for Water Softening Units³

3. Terminology

3.1 Definitions:

3.1.1 For definitions pertaining to electrical insulation, refer to Terminology D1711.

3.1.2 For definitions pertaining to fire issues, refer to Terminology E176.

3.2 Definitions of Terms Specific to This Standard:

3.2.1 *chlorinated polyolefin, n*—a polymer or polymer blend based on chlorinated polyolefin(s), chlorinated olefin copolymer(s) or chlorinated polybutadiene polymer(s).

¹ This specification is under the jurisdiction of ASTM Committee D09 on Electrical and Electronic Insulating Materials and is the direct responsibility of Subcommittee D09.07 on Flexible and Rigid Insulating Materials.

~~Current edition approved March 10, 2003. Published April 2003. Originally approved in 1970. Last previous edition approved in 1998 as D2903-93 (1998). DOI: 10.1520/D2903-03.~~

Current edition approved Aug. 1, 2011. Published August 2011. Originally approved in 1970. Last previous edition approved in 2003 as D2903-03. DOI: 10.1520/D2903-11.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

³ Available from Naval Publications and Forms Center, 5801 Tabor Ave., Philadelphia, PA 19120.

*A Summary of Changes section appears at the end of this standard.

4. Classification

- 4.1 *Type I*—Normal operating temperature.
 4.2 *Type II*—Extended operating temperature.

5. Ordering Information

- 5.1 When ordering to this specification the purchaser must state the type, class, and size of the tubing required.

6. Materials and Manufacture

6.1 The compound used in the manufacture of this heat-shrinkable tubing shall be based on chlorinated polyolefin as defined in Section 3, Terminology. The finished compound shall be free of foreign matter other than antioxidants, flame retardants, processing aids, crosslinking agents, pigments or other additives as appropriate.

- 6.2 The tubing shall be extruded, crosslinked and then expanded to the required dimensions.

7. Chemical Property Requirements

7.1 The material shall conform to the chemical requirements specified in Tables 1 and 2.

7.2 Every lot of material manufactured requires testing for flammability, but testing for all the other chemical property requirements may shall be tested conducted less frequently or with at a frequency agreed upon by the purchaser and seller.

8. Other Property Requirements

8.1 The material shall conform to the mechanical, thermal, and electrical requirements of Table 3.

8.2 Every lot of material manufactured shall be tested for heat shock, tensile strength, and elongation, but testing for all other requirements may shall be tested conducted less frequently or with at a frequency agreed upon by the purchaser and seller.

9. Dimensional Requirements

- 9.1 Both Type I and Type II tubing shall conform to the dimensional requirements of Tables 4 and 5.

10. Workmanship

10.1 Chlorinated polyolefin heat-shrinkable tubing shall be homogeneous and free from flaws and defects and from foreign matter that may have the potential to compromise its performance.

11. Sampling

11.1 A lot is defined as that material which is processed at the same time and under essentially the same conditions in accordance with this specification and submitted for inspection at one time.

- 11.2 Inspect a quantity of the end item selected at random from each lot in accordance with Practice D3636 and Table 1.

12. Tests and Retests

12.1 If the results of any test do not conform to the requirements prescribed in this specification, make two additional tests on different specimens from the same lot.

12.2 If the results of either of the two additional tests do not conform to the requirements, ~~the lot of material may be rejected at purchaser is entitled to reject the option lot of the purchaser material.~~ A notice of nonconformance of material based on tests made according to this specification should shall be reported to the manufacturer promptly and in writing.

~~12.3 Rejected tubing may be replaced~~ 12.3 It is acceptable to replace or rework rejected tubing to correct the nonconformances and resubmitted then resubmit for inspection. Before resubmitting, furnish to the inspector full particulars concerning previous rejection and action taken to correct the nonconformances.

13. Test Methods

- 13.1 Use the test methods described in Test Methods D2671 unless stated otherwise in Table 2 or Table 3.

TABLE 1 Sampling Table for Lot Acceptance Tests

Property	Requirement	Inspection Level	AQL	Sampling Unit of Sleeving, ft (m)
Inside diameter as supplied	Table 4	S-3	1.0	4 (1.2)
Inside diameter after unrestricted shrinkage	Table 4	S-3	1.0	4 (1.2)
Wall thickness after shrinkage	Table 4	S-3	1.0	4 (1.2)
Longitudinal change	Table 4	S-2	1.0	4 (1.2)
Straight length size, min	16.1 herein	S-3	1.0	single straight length
Workmanship	10.1 herein	I	4.0	4 (1.2)