



SLOVENSKI STANDARD
oSIST prEN ISO 20433:2023
01-september-2023

Usnje - Preskušanje obstojnosti barve - Obstojnost barve proti drgnjenju (ISO/DIS 20433:2023)

Leather - Tests for colour fastness - Colour fastness to crocking (ISO/DIS 20433:2023)

Leder - Farbechtheitsprüfungen - Farbechtheit gegen Reiben (ISO/DIS 20433:2023)

Cuir - Essais de solidité des coloris - Solidité des coloris au dégorgeement par frottement (ISO/DIS 20433:2023)

Ta slovenski standard je istoveten z: prEN ISO 20433

ICS:

59.140.30 Usnje in krzno

Leather and furs

oSIST prEN ISO 20433:2023

en,fr,de

DRAFT INTERNATIONAL STANDARD

ISO/DIS 20433

IULTCS

IULTCS

Secretariat: ISO

Voting begins on:
2023-07-03Voting terminates on:
2023-09-25

Leather — Tests for colour fastness — Colour fastness to crocking

Cuir — Essais de solidité des coloris — Solidité des coloris au dégorge ment par frottement

ICS: 59.140.30

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[oSIST prEN ISO 20433:2023](https://standards.iteh.ai/catalog/standards/sist/7c3c8537-3a8b-4fe8-817d-f6041d436548/osist-pren-iso-20433-2023)

<https://standards.iteh.ai/catalog/standards/sist/7c3c8537-3a8b-4fe8-817d-f6041d436548/osist-pren-iso-20433-2023>

This document is circulated as received from the committee secretariat.

THIS DOCUMENT IS A DRAFT CIRCULATED FOR COMMENT AND APPROVAL. IT IS THEREFORE SUBJECT TO CHANGE AND MAY NOT BE REFERRED TO AS AN INTERNATIONAL STANDARD UNTIL PUBLISHED AS SUCH.

IN ADDITION TO THEIR EVALUATION AS BEING ACCEPTABLE FOR INDUSTRIAL, TECHNOLOGICAL, COMMERCIAL AND USER PURPOSES, DRAFT INTERNATIONAL STANDARDS MAY ON OCCASION HAVE TO BE CONSIDERED IN THE LIGHT OF THEIR POTENTIAL TO BECOME STANDARDS TO WHICH REFERENCE MAY BE MADE IN NATIONAL REGULATIONS.

RECIPIENTS OF THIS DRAFT ARE INVITED TO SUBMIT, WITH THEIR COMMENTS, NOTIFICATION OF ANY RELEVANT PATENT RIGHTS OF WHICH THEY ARE AWARE AND TO PROVIDE SUPPORTING DOCUMENTATION.

ISO/CEN PARALLEL PROCESSING



Reference numbers
ISO/DIS 20433:2023(E)
IULTCS/IUF 452:2023(E)

© ISO 2023

iTeh STANDARD PREVIEW (standards.iteh.ai)

[oSIST prEN ISO 20433:2023](https://standards.iteh.ai/catalog/standards/sist/7c3c8537-3a8b-4fe8-817d-f6041d436548/osist-pren-iso-20433-2023)

<https://standards.iteh.ai/catalog/standards/sist/7c3c8537-3a8b-4fe8-817d-f6041d436548/osist-pren-iso-20433-2023>



COPYRIGHT PROTECTED DOCUMENT

© ISO 2023

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Contents

	Page
Foreword	iv
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Principle	1
5 Apparatus and materials	2
6 Test specimens	2
7 Procedure	2
8 Evaluation	2
9 Test report	3
Annex A (informative) Apparatus and materials	4
Bibliography	5

iTeh STANDARD PREVIEW (standards.iteh.ai)

[oSIST prEN ISO 20433:2023](https://standards.iteh.ai/catalog/standards/sist/7c3c8537-3a8b-4fe8-817d-f6041d436548/osist-pren-iso-20433-2023)

<https://standards.iteh.ai/catalog/standards/sist/7c3c8537-3a8b-4fe8-817d-f6041d436548/osist-pren-iso-20433-2023>

ISO/DIS 20433:2023(E)
IULTCS/IUF 452:2023(E)**Foreword**

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

ISO draws attention to the possibility that the implementation of this document may involve the use of a patent. ISO takes no position concerning the evidence, validity or applicability of any claimed patent rights in respect thereof. As of the date of publication of this document, ISO had not received notice of a patent which may be required to implement this document. However, implementers are cautioned that this may not represent the latest information, which may be obtained from the patent database available at www.iso.org/patents. ISO shall not be held responsible for identifying any or all such patent rights.

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see www.iso.org/iso/foreword.html.

This document was prepared by the Fastness Tests Commission of the International Union of Leather Technologists and Chemists Societies (IUF Commission, IULTCS) in collaboration with the European Committee for Standardization (CEN) Technical Committee CEN/TC 289, *Leather*, the secretariat of which is held by UNI, in accordance with the Agreement on technical cooperation between ISO and CEN (Vienna Agreement). It is based on IUF 452 published in *J. Soc. Leather Tech. Chem.*, **86**, pp. 333-335, 2002, and declared an official method of the IULTCS in May 2003.

IULTCS, originally formed in 1897, is a world-wide organization of professional leather societies to further the advancement of leather science and technology. IULTCS has three Commissions, which are responsible for establishing international methods for the sampling and testing of leather. ISO recognizes IULTCS as an international standardizing body for the preparation of test methods for leather.

This second edition cancels and replaces the first edition (ISO 20433:2005), which has been technically revised.

The main changes are as follows:

- in [clauses 2](#) and [4](#) the leather specific reference, ISO 7906, has been included.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

Leather — Tests for colour fastness — Colour fastness to crocking

1 Scope

This International Standard specifies a method for determining the amount of colour transferred from the surface of coloured leather to other surfaces by rubbing.

Two tests are carried out, one with a dry rubbing cloth and one with a wet rubbing cloth.

The method is applicable to all types of coloured leather. Since after-treatments of the leather as well as surface finishes can affect the degree of colour transfer, the test can be made before and/or after such treatment.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 105-A03, *Textiles — Tests for colour fastness — Part A03: Grey scale for assessing staining*

ISO 105-A04, *Textiles — Tests for colour fastness — Part A04: Method for the instrumental assessment of the degree of staining of adjacent fabrics*

ISO 2418, *Leather — Chemical, physical, mechanical and fastness tests — Position and preparation of specimens for testing*

ISO 2419, *Leather — Physical and mechanical tests — Sample preparation and conditioning*

ISO 7906, *Leather — Tests for colour fastness — General principles of testing*

3 Terms and definitions

No terms and definitions are listed in this document.

ISO and IEC maintain terminology databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <https://www.electropedia.org/>

4 Principle

Specimens of leather are rubbed with a dry or wet rubbing cloth attached to a cylindrical finger that is moved to and fro under controlled conditions. Colour transferred to the white rubbing cloth is assessed with the grey scale for staining.

The general principles of testing for colour fastness shall be in accordance with those described in ISO 7906.

5 Apparatus and materials

5.1 Suitable test device, for determining the colour fastness to crocking. The device shall have a rubbing finger consisting of a cylinder of 16 mm diameter which is driven to carry out a linear reciprocating motion along a 100 mm \pm 5 mm track on the specimen, exerting a downward force of 9 N.

NOTE An example of a suitable apparatus available commercially is given in [Annex A](#).

5.2 White cotton rubbing cloth, desized, bleached, without finish, cut into squares measuring approximately 50 mm \times 50 mm, for the finger used in [5.1](#).

NOTE An example of a suitable commercial source is given in [Annex A](#).

5.3 Grey scale for assessing staining, complying with ISO 105-A03.

6 Test specimens

If the piece of leather available for testing is a whole hide or skin, then first take a sample in accordance with ISO 2418.

Two representative leather specimens, each measuring not less than 140 mm \times 50 mm, are required. One specimen is required for dry rubbing and the other for wet rubbing. Prior to testing, condition the specimens and dry rubbing cloth for at least 24 h under standard conditions in accordance with ISO 2419.

7 Procedure

7.1 Fasten each test specimen securely to the baseboard of the test device so that the surface to be tested is uppermost and the long direction of the specimen follows the track of the device.

Test the specimen by the procedures in [7.2](#) and [7.3](#).

7.2 Dry rubbing: Fix the dry rubbing cloth ([5.2](#)) in place over the end of the cylindrical finger of the test device ([5.1](#)). At a rate of one turn per second, complete 10 turns of the crank to slide the rubbing finger to and fro (10 times to and 10 times fro) in a straight line along a track 100 mm long on a dry specimen, exerting a downward force of 9 N. After rubbing, remove the cloth.

7.3 Wet rubbing: Establish a technique for preparing a wet rubbing cloth by weighing a conditioned piece of cloth, thoroughly wetting it out in distilled water and squeezing or wringing it until the water pick-up is approximately 100 %.

Follow the directions for rubbing given in [7.2](#) with a fresh leather specimen. After rubbing, remove the cloth and dry it at room temperature.

8 Evaluation

Remove dust and fibrous matter retained on the surface of both cotton rubbing cloths by light brushing or by careful use of the sticky side of clear adhesive tape. Consider only the coloration due to staining by the dye.

Back each of the rubbing cloths used in the test with three layers of unused white rubbing cloth and, under suitable illumination, visually assess the staining of the rubbing cloths using the grey scale for staining in accordance with ISO 105-A03 ([5.3](#)).

Alternatively, provided the staining on the rubbing cloth is even, the grey scale colour difference can be assessed instrumentally in accordance with ISO 105-A04.

9 Test report

The test report shall include the following information:

- a) a reference to this International Standard, i.e. ISO 20433:2023;
- b) a description of the type of leather tested;
- c) the numerical grey scale ratings obtained for the staining of the dry rubbing cloth and the wet rubbing cloth;
- d) details of any deviations from the procedure specified;
- e) the date of the test.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[oSIST prEN ISO 20433:2023](https://standards.iteh.ai/catalog/standards/sist/7c3c8537-3a8b-4fe8-817d-f6041d436548/osist-pren-iso-20433-2023)

<https://standards.iteh.ai/catalog/standards/sist/7c3c8537-3a8b-4fe8-817d-f6041d436548/osist-pren-iso-20433-2023>

Annex A (informative)

Apparatus and materials

A.1 Crockmeter

A suitable apparatus, the AATCC Crockmeter, is described in the *Technical Manual of the American Association of Textile Chemists and Colorists*, Test Method 8-2016.

Available from: <https://www.aatcc.org/2020-technical-manual-global/>.

A Crockmeter can be obtained, for example, from James Heal/PPT Group, Lake View, Halifax, West Yorkshire HX3 6EP, United Kingdom.

Available from: <https://www.jamesheal.com/instrument/crockmaster>.

Other crocking devices can be used, provided that the same results are obtained as with the apparatus described in [5.1](#).

A.2 Rubbing cloth

The white cotton rubbing cloth can be obtained, for example, from Swisstatest Testmaterialien AG, Mövenstrasse 12, CH-9015 St. Gallen, Switzerland. Available from: <https://www.swisstatest.ch/en/>.

A.3 Abnormal crock images

If the crocking apparatus is not correctly maintained, poor, circular images of the rubbing finger can be obtained. Details on possible causes and corrective actions are contained in AATCC Test Method 8-2016.