



Designation: E1877 – 11

Standard Practice for Calculating Thermal Endurance of Materials from Thermogravimetric Decomposition Data¹

This standard is issued under the fixed designation E1877; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reappraisal. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reappraisal.

1. Scope

1.1 This practice covers additional treatment of the Arrhenius activation energy data determined by Test Method E1641 to develop a thermal endurance curve and derive a relative thermal index for materials.

1.2 This practice is generally applicable to materials with a well-defined decomposition profile, namely a smooth, continuous mass change with a single maximum rate.

1.3 The values stated in SI units are to be regarded as standard. No other units of measurement are included in this standard.

1.4 There is no ISO standard equivalent to this practice.

1.5 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 *ASTM Standards:*²

E1641 Test Method for Decomposition Kinetics by Thermogravimetry

3. Terminology

3.1 *Definitions of Terms Specific to This Standard:*

3.1.1 *failure, n*—change in some chemical, physical, mechanical, electrical or other property of sufficient magnitude to make it unsuitable for a particular use.

3.1.2 *failure temperature (T_f), n*—the temperature at which a material fails after a selected time.

¹ This practice is under the jurisdiction of Committee E37 on Thermal Measurements and is the direct responsibility of Subcommittee E37.10 on Fundamental, Statistical and Mechanical Properties.

Current edition approved Aug. 1, 2011. Published September 2011. Originally approved in 1997. Last previous edition approved in 2010 as E1877 – 00 (2010). DOI: 10.1520/E1877-11.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

3.1.3 *relative thermal index (RTI), n*—a measure of the thermal endurance of a material when compared with that of a control with proven thermal endurance characteristics.

3.1.3.1 *Discussion*—The RTI is also considered to be the maximum temperature below which the material resists changes in its properties over a defined period of time. In the absence of comparison data for a control material, a time-to-failure of 60 000 h has been arbitrarily selected for measuring RTI. The RTI is therefore, the failure temperature, T_f , obtained from the thermal endurance curve.

4. Summary of Practice

4.1 The Arrhenius activation energy obtained from Test Method E1641 is used to construct the thermal endurance curve of a material from which an estimate of lifetime at certain temperatures may be obtained.

5. Significance and Use

5.1 Thermogravimetry provides a rapid method for the determination of the temperature-decomposition profile of a material.

5.2 This practice is useful for quality control, specification acceptance, and research.

5.3 This practice shall not be used for product lifetime predications unless a correlation between test results and actual lifetime has been demonstrated. In many cases, multiple mechanisms occur during the decomposition of a material, with one mechanism dominating over one temperature range, and a different mechanism dominating in a different temperature range. Users of this practice are cautioned to demonstrate for their system that any temperature extrapolations are technically sound.

6. Calculation

6.1 The following values obtained by Test Method E1641 are used to calculate thermal endurance, estimated thermal life and failure temperature.

6.1.1 The following definitions apply to 6.1 and 6.3:

6.1.1.1 E = Arrhenius activation energy (J/mol),

6.1.1.2 R = Universal gas constant (= 8.314 510 J/(mol K)),

6.1.1.3 β = Heating rate (K/min),

