INTERNATIONAL STANDARD

ISO 25239-3

Second edition 2020-06

Friction stir welding — Aluminium —

Part 3: **Qualification of welding operators**

Soudage par friction-malaxage — Aluminium — Partie 3: Qualification des opérateurs soudeurs

iTeh STANDARD PREVIEW (standards.iteh.ai)

ISO 25239-3:2020 https://standards.iteh.ai/catalog/standards/sist/4bce5fl d-d8d1-4463-a3e6-66fb5a44d60b/iso-25239-3-2020



iTeh STANDARD PREVIEW (standards.iteh.ai)

ISO 25239-3:2020 https://standards.iteh.ai/catalog/standards/sist/4bce5fl d-d8d1-4463-a3e6-66fb5a44d60b/iso-25239-3-2020



COPYRIGHT PROTECTED DOCUMENT

© ISO 2020

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office CP 401 • Ch. de Blandonnet 8 CH-1214 Vernier, Geneva Phone: +41 22 749 01 11 Email: copyright@iso.org Website: www.iso.org

Published in Switzerland

COII	itent	1.5	Page		
Forev	word		iv		
Intro	ductio	on	v		
1	Scon	oe	1		
2	•				
Z	Normative references				
3	Tern	ms and definitions	1		
4	Requirements				
	4.1	Welding operator qualification			
	4.2	Essential variables and ranges of qualification	2		
		4.2.1 General			
		4.2.2 Friction stir welding methods			
		4.2.3 Welding equipment			
		4.2.4 Parent materials			
		4.2.5 Weld joint geometry			
		4.2.6 Quality acceptance levels			
	4.3	Qualification methods			
		4.3.1 Qualification based on standard welding test			
		4.3.2 Qualification based on welding procedure test			
		4.3.3 Qualification based on pre-production welding test			
	4.4	4.3.4 Qualification based on production sample welding test	3		
		Test welds en STANDARD PREVIEW 4.4.1 General			
		4.4.1 General 4.4.2 Testing and acceptance levels of test welds			
		4.4.3 Re-testing			
	4.5	Test report			
5	Certificate https://standards.iteh.ai/catalog/standards/sist/4bce5f1d-d8d1-4463-a3e6-5.1 General 66fb5a44d60b/iso-25239-3-2020				
	5.2	Period of validity			
		5.2.1 Initial qualification			
		5.2.2 Confirmation of the validity			
		5.2.3 Prolongation of qualification			
Anne	x A (no	ormative) Knowledge of the welding unit and its operation	7		
Anne	x B (no	ormative) Knowledge of welding technology	9		
		nformative) Example of a qualification test certificate for FSW v			
Rihli	norani	hv	13		

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see www.iso.org/iso/foreword.html. (standards.iteh.ai)

This document was prepared by IIW, *International Institute of Welding*, Commission III, *Resistance Welding*, *Solid State Welding and Allied Joining Process*, in collaboration with the European Committee for Standardization (CEN) Technical Committee CEN/TC 121, *Welding and allied processes*, in accordance with the Agreement on technical cooperation between ISO and CEN (Vienna Agreement).

This second edition cancels and replaces the first edition (ISO 25239-3:2011), which has been technically revised.

The main changes compared to the previous edition are as follows:

- the qualification of the welding operator has been changed for reference to the acceptance levels of ISO 25239-5;
- the definitions for testing and acceptance levels of test welds have been updated;
- NDT is no longer accepted as an alternative to bend test to qualify welding operator;
- the period of welding operator qualification has been extended to three years with possible prolongation for another three years;
- Annex A has been reworded to focus on the knowledge of the welding unit and its operation;
- Annex B has been reworded to focus on the knowledge of the welding technology;
- Annex C has been modified to fit to the extended validity of the qualification.

A list of all parts in the ISO 25239 series can be found on the ISO website.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

Introduction

Welding processes are widely used in the fabrication of engineered structures. During the second half of the twentieth century, fusion welding processes, wherein fusion is obtained by the melting of parent material and usually a filler metal, dominated the welding of large structures. In 1991, Wayne Thomas at TWI invented friction stir welding (FSW), which is carried out entirely in the solid phase (no melting).

The increasing use of FSW has created the need for this document in order to ensure that welding is carried out in the most effective way and that appropriate control is exercised over all aspects of the operation. This document focuses on the FSW of aluminium because, at the time of publication, the majority of commercial applications for FSW involved aluminium. Examples include railway carriages, consumer products, food processing equipment, aerospace structures, and marine vessels.

iTeh STANDARD PREVIEW (standards.iteh.ai)

ISO 25239-3:2020 https://standards.iteh.ai/catalog/standards/sist/4bce5fl d-d8d1-4463-a3e6-66fb5a44d60b/iso-25239-3-2020

iTeh STANDARD PREVIEW (standards.iteh.ai)

ISO 25239-3:2020

 $https://standards.iteh.ai/catalog/standards/sist/4bce5fl\,d-d8d1-4463-a3e6-66fb5a44d60b/iso-25239-3-2020$

Friction stir welding — Aluminium —

Part 3:

Qualification of welding operators

1 Scope

This document specifies requirements for the qualification of welding operators for friction stir welding (FSW) of aluminium. In this document, the term "aluminium" refers to aluminium and its alloys.

This document does not apply to "operators" as defined in ISO 25239-1.

This document does not apply to friction stir spot welding which is covered by the ISO 18785 series.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 25239-1, Friction stir welding — Aluminium — Part 1: Vocabulary **Standards. Iten. al**

ISO 25239-4:2020, Friction stir welding — Aluminium — Part 4: Specification and qualification of welding procedures ISO 25239-3:2020

ISO 25239-5:2020, https://standards.iteh.ai/catalog/standards/sist/4bce5fl d-d8d1-4463-a3e6-Aluminium — Part 5: Quality and inspection requirements

3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 25239-1 apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at https://www.iso.org/obp
- IEC Electropedia: available at http://www.electropedia.org/

4 Requirements

4.1 Welding operator qualification

Welding operators shall be qualified by one of the following tests, as detailed in 4.3:

- standard welding test, see 4.3.1;
- welding procedure test, see <u>4.3.2</u>;
- pre-production welding test or production welding test, see 4.3.3;
- production welding sample test, see 4.3.4.

In addition, the welding operator's knowledge of the welding unit to be used for the qualification test and the knowledge of the welding technology shall be tested and documented as shown in <u>Annexes A</u> and <u>B</u>.

ISO 25239-3:2020(E)

The essential variables and ranges of qualification are specified in <u>4.2</u> and the validity is specified in <u>Clause 5</u>. Provided that the welding operator works in accordance with a welding procedure specification (WPS), the range of qualification shall be limited only as specified in <u>4.2</u>.

A suggested form for the welding operator's qualification certificate is shown in Annex C.

4.2 Essential variables and ranges of qualification

4.2.1 General

The qualification of welding operators is based on essential variables, as specified in <u>4.2.2</u> to <u>4.2.5</u>. For each essential variable, a range of qualification is defined. If a welding operator is required to weld outside the range of qualification, then a new qualification test is required.

NOTE Friction stir welding is a mechanized process. However, because it is also a solid-state welding process, the essential variables are different from those applicable to fusion welding processes.

4.2.2 Friction stir welding methods

A successful welding operator qualification test made with any type of FSW method qualifies an operator only for that welding method. This subclause applies to FSW methods that include, but are not limited to, robotic, single spindle, multiple spindle, bobbin tool, adjustable tool probe, or any other FSW method defined in the WPS used for that qualification test.

4.2.3 Welding equipment iTeh STANDARD PREVIEW

The following changes require a new qualification ards.iteh.ai)

- a change from welding with a joint sensor to welding without, although welding without a joint sensor also qualifies an operator to weld with a joint sensor (i.e., location, height mismatch, ...);
- a change from one type of welding machine to another type of welding machine that requires additional training to operate;
- a test made with any type of machine qualifies only that type of machine, although the addition or removal of jigs and fixtures, feeding units and other ancillary equipment does not change the type of machine;
- addition, removal or change of control system.

4.2.4 Parent materials

A successful test weld made in any aluminium alloy qualifies an operator for all aluminium alloys.

A successful test weld of any parent material thickness qualifies an operator for all parent material thicknesses.

A successful test weld of any parent material form (including, but not limited to, sheet, tube, castings, forgings or extrusions) qualifies an operator for all parent material forms and for all tube diameters.

4.2.5 Weld joint geometry

A successful test weld made in any weld joint geometry qualifies an operator for all weld joint geometries.


4.2.6 Quality acceptance levels

A welding operator qualified to one weld quality acceptance level in accordance with ISO 25239-5:2020, Annex A, shall be qualified for all acceptance levels.

4.3 Qualification methods

4.3.1 Qualification based on standard welding test

The test piece shown in Figure 1 shall be used for the standard welding test. A welding operator who has successfully completed the welding test in accordance with 4.4 shall be considered qualified for the method and type of welding machine used for the test.



Key	190.252	20. 2.2020			
1	weld https://standards.iteh.ai/catalog/standards	<u>39-3:2020</u> ards/sist/4bo	minimum 50 mm or three times the weld		
2	area for root bend test specimen6fb5a44d60b/iso-25239-3-2penetration whichever is greater				
3	area for face bend test specimen	l_2	minimum 50 mm		
4	area for test specimen for macroscopic	l_3	minimum 500 mm		
	examination	a	Weld direction.		

The width of the test piece shall be sufficient for extracting the bend test specimens.

NOTE Not to scale. Start and stop of the weld are not shown in this figure.

Figure 1 — Location of destructive test specimens

4.3.2 Qualification based on welding procedure test

A welding operator shall have successfully completed a welding procedure test in accordance with ISO 25239-4:2020, Clause 6, to be considered qualified for the method and type of welding machine used.

4.3.3 Qualification based on pre-production welding test

A welding operator shall have successfully completed a pre-production welding test in accordance with ISO 25239-4:2020, Clause 7, to be considered qualified for the FSW method and type of welding machine used for the test.

4.3.4 Qualification based on production sample welding test

A welding operator having successfully set up a production part shall be considered qualified if representative samples of the items that are produced are approved by the examiner or the examining

ISO 25239-3:2020(E)

body. This testing of production samples shall be in accordance with the requirements of <u>4.4</u> or the requirements of the contracting parties, whichever is more stringent.

4.4 Test welds

4.4.1 General

Test welds shall be made in accordance with a WPS, except when <u>4.3.2</u> or <u>4.3.3</u> applies. The welding and testing of test pieces shall be witnessed by the examiner.

The test welds used for qualification of a welding operator shall have a length of at least 500 mm. If the qualification is based on pre-production tests, production tests or production sample tests and the product used has a shorter weld length than 500 mm, then the number of products tested shall be such that the required weld length is met. However, no more than three products shall be tested.

The test piece and test specimens shall be marked with the identification of the examiner or the examining body and the welding operator before welding starts.

The examiner may stop the test if the welding conditions are not correct or if it appears that the welding operator does not have the skill to fulfil the requirements of this part of ISO 25239.

4.4.2 Testing and acceptance levels of test welds

4.4.2.1 General

iTeh STANDARD PREVIEW

The acceptance levels for the test welds shall be the same as those used to qualify the WPS. (**Standards.iteh.ai**)

The following tests, as a minimum, shall be performed:

visual testing 100 %;

https://standards.iteh.ai/catalog/standards/sist/4bce5f1d-d8d1-4463-a3e6-

- macroscopic examination; 66fb5a44d60b/iso-25239-3-2020
- bend tests (only applies to a qualification based on a standard welding test in accordance with 4.3.1).

4.4.2.2 Visual testing

Visual testing shall be carried out in accordance with ISO 25239-4:2020, 6.3.2, except in the case of 4.4.1 where, if the length of weld is less than 500 mm, the length of weld to be tested shall be specified in the WPS.

4.4.2.3 Macroscopic examination

Macroscopic examination shall be carried out in accordance with ISO 25239-4:2020, 6.3.3.5. The location of the test specimen blank shall be in accordance with Figure 1.

4.4.2.4 Bend test

Bend testing shall be performed in accordance with ISO 25239-4:2020, 6.3.3.4. The location of the test specimen blanks shall be in accordance with Figure 1.

If a partial penetration weld is specified in the WPS, the specimen shall be machined from the root side to a thickness equal to the specified minimum weld penetration before testing.

4.4.3 Re-testing

If the welded assembly fails to meet the requirements of <u>4.4.1</u> and <u>4.4.2</u>, then the test shall be rejected. A duplicate assembly may be welded using the same procedure and subjected to examination. If the

second assembly fails to meet the requirements, then the welding operator shall be required to have additional training before a new test is made.

If a bend test specimen fails to meet the requirements, then two additional test specimens shall be prepared from the same welded assembly and tested. If both retests are acceptable, the welding operator shall be qualified. If one or both retests are not acceptable, the welding operator is not qualified.

4.5 Test report

The results of all testing shall be documented. The format of the documentation shall be decided by the fabricator.

NOTE The documentation can be on paper or electronic media.

5 Certificate

5.1 General

It shall be verified that the welding operator passed the qualification test. All essential variables shall be recorded on the certificate. If the test piece(s) fail(s) any of the required tests, no certificate shall be issued.

The certificate shall be issued under the sole responsibility of the examiner or examining body and shall contain all the information detailed in <u>Annex C</u>. It is recommended that the format of <u>Annex C</u> be used as the welding operator's qualification test certificate. If a different welding operator qualification test certificate is used, it is recommended that it contains the information as in <u>Annex C</u>.

NOTE In some countries, an examiner can be employed by the company performing welding.

5.2 Period of validity

<u>ISO 25239-3;2020</u>

https://standards.iteh.ai/catalog/standards/sist/4bce5fld-d8d1-4463-a3e6-

66fb5a44d60b/iso-25239-3-2020

5.2.1 Initial qualification

The welding operator's qualification is valid from the date of welding of the test pieces, provided the required tests have been carried out and acceptable test results are available.

The welding operator's qualification test certificate is valid for a period of 3 years, the period of validity ending on the last day of the month.

5.2.2 Confirmation of the validity

The welding coordinator or the person responsible from the employer shall confirm that the welding operator has been working within the initial range of qualification. This shall be confirmed every 6 months. If such a confirmation is not given and the qualification expires, the welding operator shall be required to pass a new qualification test before resuming welding.

5.2.3 Prolongation of qualification

The welding operator's qualification test certificates can be prolonged every 3 years by an examiner or examining body.

Before prolongation of the certification takes place, the specifications of 5.2.2 shall be satisfied and the following conditions shall be confirmed:

— all records and evidence used to support prolongation shall be traceable to the welding operator and shall identify the WPS(s) used in production;