
**Friction stir welding — Aluminium —
Part 5:
Quality and inspection requirements**

*Soudage par friction-malaxage — Aluminium —
Partie 5: Exigences de qualité et de contrôle*

iTeh Standards
(<https://standards.iteh.ai>)
Document Preview

ISO 25239-5:2020

<https://standards.iteh.ai/catalog/standards/iso/65767689-cc79-4f2a-8e3b-416a8079e72e/iso-25239-5-2020>



Reference number
ISO 25239-5:2020(E)

iTeh Standards
(<https://standards.iteh.ai>)
Document Preview

[ISO 25239-5:2020](https://standards.iteh.ai/catalog/standards/iso/65767689-cc79-4f2a-8e3b-416a8079e72e/iso-25239-5-2020)

<https://standards.iteh.ai/catalog/standards/iso/65767689-cc79-4f2a-8e3b-416a8079e72e/iso-25239-5-2020>



COPYRIGHT PROTECTED DOCUMENT

© ISO 2020

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Contents

Page

Foreword	iv
Introduction	v
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Quality requirements	2
4.1 General	2
4.2 Welding personnel	2
4.2.1 General	2
4.2.2 Welding operator	2
4.3 Inspection and testing personnel	2
4.3.1 General	2
4.3.2 Personnel performing non-destructive testing (including visual testing)	2
4.3.3 Destructive testing personnel	2
4.4 Equipment	2
4.4.1 Suitability of equipment	2
4.4.2 Reproducibility tests for qualified machine welding settings	3
4.4.3 Equipment maintenance	3
4.5 Welding procedure specification	3
4.6 Friction stir welding tool	3
4.6.1 Identification	3
4.6.2 Friction stir welding tool inspection	3
4.7 Pre-weld joint preparation and fit-up	4
4.7.1 Joint preparation	4
4.7.2 Pre-weld cleaning	4
4.8 Preheating and interpass temperature control	4
4.9 Tack welds	4
4.10 Welding	4
4.11 Postweld heat treatment	4
4.12 Inspection and testing	4
4.12.1 General	4
4.12.2 Inspection and testing before welding	4
4.12.3 Inspection and testing during welding	5
4.12.4 Inspection and testing after welding	5
4.12.5 Damaged and non-conforming welds	6
4.12.6 Weld geometry correction	6
4.13 Identification and traceability	6
Annex A (normative) Imperfections, testing and examination, acceptance levels, and ISO 6520-1 reference number	7
Bibliography	12

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see www.iso.org/iso/foreword.html.

This document was prepared by IIW, *International Institute of Welding*, Commission III, *Resistance Welding, Solid State Welding and Allied Joining Process*, in collaboration with the European Committee for Standardization (CEN) Technical Committee CEN/TC 121, *Welding and allied processes*, in accordance with the Agreement on technical cooperation between ISO and CEN (Vienna Agreement).

This second edition cancels and replaces the first edition (ISO 25239-5:2011), which has been technically revised.

The main changes compared to the previous edition are as follows:

- the concept of three different acceptance levels for the assessment of weld quality has been added to [Annex A](#);
- the following imperfections have been added to [Table A.1](#): angular misalignment, joint area deformation, surface breaking cavity, solid inclusion, joint remnants and multiple imperfections;
- the requirements for personnel performing non-destructive testing and visual testing have been aligned with ISO 17637

A list of all parts in the ISO 25239 series can be found on the ISO website.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

Introduction

Welding processes are widely used in the fabrication of engineered structures. During the second half of the twentieth century, fusion welding processes, wherein fusion is obtained by the melting of parent material and usually a filler metal, dominated the welding of large structures. In 1991, Wayne Thomas at TWI invented friction stir welding (FSW), which is carried out entirely in the solid phase (no melting).

The increasing use of FSW has created the need for this document in order to ensure that welding is carried out in the most effective way and that appropriate control is exercised over all aspects of the operation. This document focuses on the FSW of aluminium because, at the time of publication, the majority of commercial applications for FSW involved aluminium. Examples include railway carriages, consumer products, food processing equipment, aerospace structures, and marine vessels.

iTeh Standards
(<https://standards.iteh.ai>)
Document Preview

[ISO 25239-5:2020](https://standards.iteh.ai/catalog/standards/iso/65767689-cc79-4f2a-8e3b-416a8079e72e/iso-25239-5-2020)

<https://standards.iteh.ai/catalog/standards/iso/65767689-cc79-4f2a-8e3b-416a8079e72e/iso-25239-5-2020>

Friction stir welding — Aluminium —

Part 5: Quality and inspection requirements

1 Scope

This document specifies a method for determining the capability of a manufacturer to use the friction stir welding (FSW) process for the production of products of the specified quality. It specifies quality requirements, but does not assign those requirements to any specific product group.

In this document, the term “aluminium” refers to aluminium and its alloys.

This document does not apply to friction stir spot welding which is covered by the ISO 18785 series.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 3452-1, *Non-destructive testing — Penetrant testing — Part 1: General principles*

ISO 4136, *Destructive tests on welds in metallic materials — Transverse tensile test*

ISO 9015-1, *Destructive tests on welds in metallic materials — Hardness testing — Part 1: Hardness test on arc welded joints*

<https://standards.iso.org/iso/25239-5:2020/> ISO 9015-2, *Destructive tests on welds in metallic materials — Hardness testing — Part 2: Microhardness testing of welded joints*

ISO 9017, *Destructive tests on welds in metallic materials — Fracture test*

ISO 9712, *Non-destructive testing — Qualification and certification of NDT personnel*

ISO 17636 (all parts), *Non-destructive testing of welds — Radiographic testing*

ISO 17637, *Non-destructive testing of welds — Visual testing of fusion-welded joints*

ISO 17640, *Non-destructive testing of welds — Ultrasonic testing — Techniques, testing levels, and assessment*

ISO 25239-1, *Friction stir welding — Aluminium — Part 1: Vocabulary*

ISO 25239-3, *Friction stir welding — Aluminium — Part 3: Qualification of welding operators*

ISO 25239-4, *Friction stir welding — Aluminium — Part 4: Specification and qualification of welding procedures*

ISO/TR 25901 (all parts), *Welding and allied processes — Vocabulary*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 25239-1 and ISO/TR 25901 (all parts) apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <http://www.electropedia.org/>

4 Quality requirements

4.1 General

These requirements relate only to those aspects of product quality that can be influenced by FSW.

4.2 Welding personnel

4.2.1 General

Manufacturers shall have at their disposal sufficient competent personnel for the planning, performance and supervision of FSW production operations in accordance with specified requirements.

4.2.2 Welding operator

Welding operators shall be qualified in accordance with ISO 25239-3. Qualification records shall be kept up to date.

4.3 Inspection and testing personnel

4.3.1 General

Manufacturers shall have sufficient competent personnel for the planning, performance, and supervision of inspection and testing operations during the production of friction stir welded parts in accordance with specified requirements.

<https://standards.iteh.ai/catalog/standards/iso/65767689-cc79-4f2a-8e3b-416a8079e72e/iso-25239-5-2020>

4.3.2 Personnel performing non-destructive testing (including visual testing)

Non-destructive testing of welds (including visual testing) and the evaluation of results for final acceptance shall be performed by qualified and capable personnel. It is recommended that the personnel be qualified in accordance with ISO 9712 or an equivalent standard at an appropriate level in the relevant industry sector.

4.3.3 Destructive testing personnel

Personnel performing destructive testing shall be trained for those test methods.

4.4 Equipment

4.4.1 Suitability of equipment

The equipment shall be adequate for the application concerned.

Welding equipment (e.g. welding machines and FSW tools) shall be capable of producing welds that meet the acceptance levels specified in [Annex A](#). Welding equipment shall be maintained in good condition and shall be repaired or adjusted when a welding operator, inspector or welding coordinator is concerned about the capability of the equipment to operate satisfactorily.

4.4.2 Reproducibility tests for qualified machine welding settings

Reproducibility tests shall be performed to demonstrate that the welding equipment can repeatedly produce welds that meet the acceptance levels in [Annex A](#). Reproducibility tests shall be carried out when any of the following occurs:

- after installation of new or refurbished welding equipment;
- a critical component of the FSW machine is repaired or replaced after being damaged or after failing to operate properly;
- equipment is dislodged or moved in a manner for which it was not designed;
- stationary equipment is moved from one location to another.

The reproducibility test shall be performed in accordance with a WPS that is used in production for that machine.

A minimum of three satisfactory test welds shall be made and documented.

4.4.3 Equipment maintenance

The manufacturer shall have a documented plan for equipment maintenance. The plan shall ensure that maintenance checks are performed on the equipment that controls variables listed in the relevant WPSs. The maintenance plan may be limited to those items that are essential for producing welds that meet the quality requirements of this document.

Examples of these items are as follows:

- condition of guides and mechanized fixtures;
- condition of meters and gauges that are used for the operation of the welding equipment;
- condition of cables, hoses, and connectors;
- condition of the control systems in mechanized or automatic welding equipment;
- condition of thermocouples and other temperature measurement instruments;
- condition of clamps, jigs, and fixtures.

Before welding, clamps, jigs, and fixtures that contact the workpieces shall be clean and sufficiently free of contaminants (e.g. oil, grease, and dirt) that can have a detrimental effect on the weld.

Defective equipment shall not be used.

4.5 Welding procedure specification

The manufacturer shall ensure the WPS is used correctly in production.

4.6 Friction stir welding tool

4.6.1 Identification

The FSW tool that is used in production shall be permanently marked for identification prior to use.

4.6.2 Friction stir welding tool inspection

The correct tool geometry is critical for producing a quality friction stir weld. Therefore upon first use, the FSW tool shall be clean and sufficiently free of contaminants (e.g. oil, grease or dirt) that can have a

detrimental effect on weld quality. Because the FSW tool wears with use, it shall be inspected for wear at appropriate intervals and in accordance with a written procedure.

4.7 Pre-weld joint preparation and fit-up

4.7.1 Joint preparation

The edge of each joint member shall be prepared in accordance with the WPS.

The joint condition shall be set in accordance with the WPS.

4.7.2 Pre-weld cleaning

Pre-weld cleaning shall be carried out in accordance with the WPS. Parent material shall be clean and sufficiently free of contaminants (e.g. oil, grease or dirt) that can have a detrimental effect on weld quality.

4.8 Preheating and interpass temperature control

Requirements for preheating and interpass temperature control shall be in accordance with a WPS.

4.9 Tack welds

If tack welds are required, they shall be made in accordance with a WPS.

4.10 Welding

All welding shall be done in accordance with a WPS.

4.11 Postweld heat treatment

If postweld heat treatment is required, it shall be done in accordance with a WPS.

The manufacturer shall be fully responsible for the specification and performance of any postweld heat treatment (e.g. solution heat-treating, stress relieving, or ageing). The procedure shall be compatible with the parent material, welded joint, and weldment, in accordance with the product standard or specified requirements. A record of the heat treatment shall be made. The record shall demonstrate that this document has been followed and shall be traceable to the heat-treated part.

4.12 Inspection and testing

4.12.1 General

The location and frequency of applicable inspections and tests depends on the product standard and the type of construction.

4.12.2 Inspection and testing before welding

Before the start of welding, the following shall be verified:

- suitability and validity of the welding operator's qualification certificate;
- suitability of the WPS;
- parent material alloy and temper;
- joint preparation (e.g. shape and dimensions);