



Standard Test Method for Effect of Water on Compressive Strength of Compacted Bituminous Mixtures¹

This standard is issued under the fixed designation D1075; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the Department of Defense.

1. Scope

1.1 This test method covers measurement of the loss of compressive strength resulting from the action of water on compacted bituminous mixtures containing asphalt cement. A numerical index of reduced compressive strength is obtained by comparing the compressive strength of freshly molded and cured specimens with the compressive strength of duplicate specimens that have been immersed in water under prescribed conditions.

1.2 *Units*—The values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units that are provided for information only and are not considered standard.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 ASTM Standards:²

- [C670 Practice for Preparing Precision and Bias Statements for Test Methods for Construction Materials](#)
- [D1074 Test Method for Compressive Strength of Bituminous Mixtures](#)
- [D2726 Test Method for Bulk Specific Gravity and Density of Non-Absorptive Compacted Bituminous Mixtures](#)
- [D3666 Specification for Minimum Requirements for Agencies Testing and Inspecting Road and Paving Materials](#)

¹ This test method is under the jurisdiction of ASTM Committee D04 on Road and Paving Materials and is the direct responsibility of Subcommittee D04.22 on Effect of Water and Other Elements on Bituminous Coated Aggregates.

Current edition approved Aug. 15, 2011. Published August 2011. Originally approved in 1949. Last previous edition approved in 2007 as D1075 – 07. DOI: 10.1520/D1075-11.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

[D6752 Test Method for Bulk Specific Gravity and Density of Compacted Bituminous Mixtures Using Automatic Vacuum Sealing Method](#)

[E2251 Specification for Liquid-in-Glass ASTM Thermometers with Low-Hazard Precision Liquids](#)

3. Significance and Use

3.1 This test method is useful as an indicator of the susceptibility to moisture of compacted bitumen-aggregate mixtures.

NOTE 1—The quality of the results produced by this standard are dependent on the competence of the personnel performing the procedure and the capability, calibration, and maintenance of the equipment used. Agencies that meet the criteria of Standard Practice D3666 are generally considered capable of competent and objective testing/sampling/inspection/etc. Users of this standard are cautioned that compliance with D3666 alone does not completely assure reliable results. Reliable results depend on many factors; following the suggestions of D3666 or some similar acceptable guideline provides a means of evaluating and controlling some of those factors.

4. Apparatus

4.1 One or more automatically controlled water baths shall be provided for immersing the specimens. The baths shall be of sufficient size to permit total immersion of the test specimens. They shall be so designed and equipped as to permit accurate and uniform control of the immersion temperature within $\pm 1.8^\circ\text{F}$ (1°C). They shall be constructed of or lined with copper, stainless steel, or other nonreactive material. The water used for the wet storage of the specimens shall be either distilled or otherwise treated to eliminate electrolytes and the bath shall be emptied, cleaned, and refilled with fresh water for each series of tests.

4.2 A manually or automatically controlled water bath also shall be provided for bringing the immersed specimens to the temperature of $77 \pm 1.8^\circ\text{F}$ ($25 \pm 1^\circ\text{C}$) for the compression test. Any convenient pan or tank may be used provided it is of sufficient size to permit total immersion of the specimens.

4.3 A balance and a water bath with suitable accessory equipment will be required for weighing the test specimens in air and in water in order to determine their densities, the