



Designation: E 1070 – 00

Standard Test Method for Determination of Phosphorus in Iron Ores by Photometric Method¹

This standard is issued under the fixed designation E 1070; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This test method covers the determination of phosphorus in iron ores, concentrates, and agglomerates in the concentration range from 0.005 to 1.0 % phosphorus.

1.2 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 *ASTM Standards:*

D 1193 Specification for Reagent Water²

E 50 Practices for Apparatus, Reagents, and Safety Precautions for Chemical Analysis of Metals³

E 60 Practice for Analysis of Metals, Ores, and Related Materials by Molecular Absorption Spectrometry³

E 135 Terminology Relating to Analytical Chemistry for Metals, Ores, and Related Materials³

E 877 Practice for Sampling and Sample Preparation of Iron Ores and Related Materials⁴

E 882 Guide for Accountability and Quality Control in the Chemical Analysis Laboratory⁴

3. Terminology

3.1 *Definitions*—For definitions of terms used in this test method, refer to Terminology **E 135**.

4. Summary of Test Method

4.1 The sample is fused in a zirconium crucible with sodium peroxide. The melt is dissolved in water and hydrochloric acid. In a suitable aliquot, the molybdenum blue complex is formed by the addition of ammonium molybdate-hydrazine sulfate

solution. The absorbance of the phospho-molybdenum-blue complex is measured at 725 nm.

5. Significance and Use

5.1 This test method for the analysis of iron ore concentrates and agglomerates is primarily intended as a referee method to test for compliance with compositional specifications. It is assumed that users of this test method will be trained analysts capable of performing common laboratory procedures skillfully and safely. It is expected that work will be performed in a properly-equipped laboratory and that proper waste disposal procedures will be followed. Appropriate quality control practices shall be followed, such as those described in Guide **E 882**.

5.2 The determination of this element is needed for international trade and primary iron and steel making.

6. Interferences

6.1 Elements normally found in iron ores do not interfere excepting arsenic giving positive interference (0.01 % As = 0.001 % P).

7. Apparatus

7.1 *Zirconium Crucible*, 50 mL capacity.

7.2 *Spectrophotometer*—Visible spectrophotometer capable of measuring absorbance at the 725 nm wavelength using a 1-cm path length cell in accordance with Practices **E 60**.

8. Reagents and Materials

8.1 *Purity of Reagents*—Reagent grade chemicals shall be used in all tests. Unless otherwise indicated, it is intended that all reagents conform to the specifications of the Committee on Analytical Reagents of the American Chemical Society, where such specifications are available.⁵ Other grades may be used, provided it is first ascertained that the reagent is of sufficient high purity to permit its use without lessening the accuracy of the determination.

⁵ *Reagent Chemicals, American Chemical Society Specifications*, American Chemical Society, Washington, DC. For suggestions on the testing of reagents not listed by the American Chemical Society, see *Analar Standards for Laboratory Chemicals*, BDH Ltd., Poole, Dorset, U.K., and the *United States Pharmacopeia and National Formulary*, U.S. Pharmacopeial Convention, Inc. (USPC), Rockville, MD.

¹ This test method is under the jurisdiction of ASTM Committee E01 on Analytical Chemistry for Metals, Ores, and Related Materials and is the direct responsibility of Subcommittee E01.02 on Ores, Concentrates, and Related Metallurgical Materials.

Current edition approved Nov. 10, 2000. Published January 2001. Originally published as E 1070 – 85. Last previous edition E 1070 – 95.

² *Annual Book of ASTM Standards*, Vol 11.01.

³ *Annual Book of ASTM Standards*, Vol 03.05.

⁴ *Annual Book of ASTM Standards*, Vol 03.06.