



SLOVENSKI STANDARD
oSIST prEN 603-2:2024
01-januar-2024

Aluminij in aluminijeve zlitine - Valjani material za kovanje - 2. del: Mehanske lastnosti

Aluminium and aluminium alloys - Wrought forging stock - Part 2: Mechanical properties

Aluminium und Aluminiumlegierungen - Stranggepresstes oder gewalztes Schmiedevormaterial - Teil 2: Mechanische Eigenschaften

Aluminium et alliages d'aluminium - Produits corroyés destinés à la forge - Partie 2: Caractéristiques mécaniques

Ta slovenski standard je istoveten z: prEN 603-2

<https://standards.iteh.ai/catalog/standards/sist/7a41aa12-2b00-4ac5-8509-8980d9c91471/osist-pren-603-2-2024>

ICS:

77.150.10 Aluminijski izdelki Aluminium products

oSIST prEN 603-2:2024

en,fr,de

EUROPEAN STANDARD
NORME EUROPÉENNE
EUROPÄISCHE NORM

DRAFT
prEN 603-2

November 2023

ICS 77.150.10

Will supersede EN 603-2:1996

English Version

Aluminium and aluminium alloys - Wrought forging stock - Part 2: Mechanical properties

Aluminium et alliages d'aluminium - Produits corroyés
destinés à la forge - Partie 2: Caractéristiques
mécaniques

Aluminium und Aluminiumlegierungen -
Stranggepreßtes oder gewalztes Schmiedevormaterial
- Teil 2: Mechanische Eigenschaften

This draft European Standard is submitted to CEN members for enquiry. It has been drawn up by the Technical Committee CEN/TC 132.

If this draft becomes a European Standard, CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration.

This draft European Standard was established by CEN in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Türkiye and United Kingdom.

Recipients of this draft are invited to submit, with their comments, notification of any relevant patent rights of which they are aware and to provide supporting documentation.

Warning : This document is not a European Standard. It is distributed for review and comments. It is subject to change without notice and shall not be referred to as a European Standard.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels

Contents	Page
European foreword	3
1 Scope	4
2 Normative references	4
3 Terms and definitions	4
4 Tensile testing	4
5 Mechanical properties	4
5.1 Extruded forging stock	4
5.2 Rolled forging stock	7
6 Electrical conductivity	7
Annex A (normative) Rules for rounding	8
Bibliography	9

iTeh Standards
(<https://standards.iteh.ai>)
Document Preview

[oSIST prEN 603-2:2024](https://standards.iteh.ai/catalog/standards/sist/7a41aa12-2b00-4ac5-8509-8980d9c91471/osist-pren-603-2-2024)

<https://standards.iteh.ai/catalog/standards/sist/7a41aa12-2b00-4ac5-8509-8980d9c91471/osist-pren-603-2-2024>

European foreword

This document (prEN 603-2:2023) has been prepared by Technical Committee CEN/TC 132 “Aluminium and aluminium alloys”, the secretariat of which is held by AFNOR.

This document is currently submitted to the Formal Vote.

This document will supersede EN 603-2:1996.

prEN 603-2:2023 includes the following significant technical changes with respect to EN 603-2:1996:

- application of last CEN template to the introductory text of Clause 2 Normative references;
- replacement of withdrawn Standard EN 10002-1 by EN ISO 6892-1 in Clause 2 Normative references;
- application of last CEN template to Clause 3 Terms and definitions;
- introduction of Standard EN ISO 6892-1 instead of withdrawn Standard EN 10002-1 in Clause 4 Tensile testing;
- move of former text from Note in Table 9 to Clause 6;
- introduction of mechanical properties for alloy EN AW-2033 in new Table 3;
- introduction of mechanical properties for alloy EN AW-2077 in new Table 4;
- introduction of mechanical properties for alloy EN AW-6026 in new Table 7;
- minor text changes.

EN 603 comprises the following parts under the general title *Aluminium and aluminium alloys - Wrought forging stock*:

- *Part 1: Technical conditions for inspection and delivery;*
- *Part 2: Mechanical properties;*
- *Part 3: tolerances on dimensions and form.*

prEN 603-2:2023 (E)

1 Scope

This document, part of EN 603 series of Standards, specifies the mechanical properties of wrought forging stock in aluminium and aluminium alloys for general engineering applications.

The chemical composition and temper designations for these alloys are specified in EN 573-3 and EN 515 respectively.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 2004-1, *Aerospace series - Test methods for aluminium and aluminium alloy products - Part 1: Determination of electrical conductivity of wrought aluminium alloys*

EN ISO 6892-1, *Metallic materials - Tensile testing - Part 1: Method of test at room temperature (ISO 6892-1)*

3 Terms and definitions

For the purposes of this document, the following definition applies.

ISO and IEC maintain terminology databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp/>
- IEC Electropedia: available at <https://www.electropedia.org/>

3.1

section size

minor sectional dimension, ie. diameter for extruded round bar, width across flats for extruded square bar and thickness for extruded rectangular section, designated as t

4 Tensile testing

For the selection of specimens and preparation of test pieces, see EN 603-1.

Tensile testing shall be carried out in accordance with EN ISO 6892-1.

5 Mechanical properties

5.1 Extruded forging stock

Extruded forging stock is normally supplied in the F or H112 temper condition.

Testing to determine mechanical properties of extruded forging stock shall be undertaken only when requested by the purchaser and specified on the order (see EN 603-1).

In instances where tensile testing is specified on extruded forging stock in heat treatable alloys, the specimen selected for test shall be heat treated in accordance with the recommended practice for the temper condition of final use.

The mechanical properties of aluminium alloys are specified in Tables 1 to 9.

Test results shall be rounded in accordance with the rules given in Annex A.