



Designation: A1035/A1035M – 11

Standard Specification for Deformed and Plain, Low-carbon, Chromium, Steel Bars for Concrete Reinforcement¹

This standard is issued under the fixed designation A1035/A1035M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope*

1.1 This specification covers low-carbon, chromium, steel bars, deformed and plain for concrete reinforcement in cut lengths and coils. The standard sizes and dimensions of deformed bars and their number designations are given in [Table 1](#). The text of this specification references notes and footnotes which provide explanatory material. These notes and footnotes (excluding those in tables and figures) shall not be considered as requirements of the specification.²

1.2 Bars are of two minimum yield strength levels as defined in [9.2](#): namely, 100 000 psi [690 MPa], and 120 000 [830 MPa] designated as Grade 100 [690] and Grade 120 [830], respectively.

NOTE 1—**Caution:** Designers need to be aware that typical design standards limit the design strength to 80 000 psi [550 MPa], except for prestressing steel and for spiral transverse reinforcement. Members reinforced with bars with yield strengths that are considerably above 80 000 psi [550 MPa] may exhibit behavior that differs from that expected of conventional reinforced concrete members or may require special detailing to ensure adequate performance at service and factored loads.

1.3 Deformed bars shall have a minimum yield strength and other tensile properties in accordance with [Table 2](#). Hot-rolled plain rounds in sizes up to and including 2.25 in. [57.2 mm] in diameter in coils or cut lengths when specified for dowels, spirals, structural ties or bar supports shall be furnished under this specification and shall also meet the tensile properties requirements of [Table 2](#). Ductility properties for plain rounds shall be those of the nearest smaller nominal diameter deformed bar size in [Table 2](#). Requirements covering deformation dimensions and marking are not applicable to plain rounds.

NOTE 2—Welding of the material in this specification should be

¹ This specification is under the jurisdiction of ASTM Committee A01 on Steel, Stainless Steel and Related Alloys and is the direct responsibility of Subcommittee A01.05 on Steel Reinforcement.

Current edition approved Sept. 1, 2011. Published October 2011. Originally approved in 2004. Last previous edition approved in 2009 as A1035/A1035M – 09. DOI: 10.1520/A1035_A1035M-11.

² MMFX Technologies Corporation has several patented materials (US Patents #6,273,968, #6,709,534, #7,118,637, #7,214,278) that meet this specification. Interested parties are invited to submit information regarding the identification of an alternative(s) to this patented item to the ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee,¹ which you may attend.

approached with caution since no specific provisions have been included to enhance its weldability. When this steel is to be welded, a welding procedure suitable for the chemical composition and intended use or service should be used.

1.4 This specification is applicable for orders in either inch-pound units (as Specification A1035) or in SI units (as Specification A1035M).

1.5 The values stated in either inch-pound units or SI units are to be regarded as standard. Within the text, the SI units are shown in brackets. The values stated in each system are not exact equivalents; therefore, each system must be used independently of the other. Combining values from the two systems may result in nonconformance with the specification.

2. Referenced Documents

2.1 ASTM Standards:³

[A6/A6M Specification for General Requirements for Rolled Structural Steel Bars, Plates, Shapes, and Sheet Piling](#)
[A370 Test Methods and Definitions for Mechanical Testing of Steel Products](#)

[A510 Specification for General Requirements for Wire Rods and Coarse Round Wire, Carbon Steel](#)

[A510M Specification for General Requirements for Wire Rods and Coarse Round Wire, Carbon Steel \(Metric\)](#)

[A700 Practices for Packaging, Marking, and Loading Methods for Steel Products for Shipment](#)

[A751 Test Methods, Practices, and Terminology for Chemical Analysis of Steel Products](#)

[E29 Practice for Using Significant Digits in Test Data to Determine Conformance with Specifications](#)

2.2 U.S. Military Standard:⁴

[MIL-STD-129 Marking for Shipment and Storage](#)

2.3 U.S. Federal Standard:⁴

[Fed. Std. No. 123 Marking for Shipment \(Civil Agencies\)](#)

³ For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

⁴ Available from Standardization Documents Order Desk, Bldg. 4 Section D, 700 Robbins Ave., Philadelphia, PA 19111-5094, Attn: NPODS. Or visit: <http://assist.daps.dla.mil/online>.

*A Summary of Changes section appears at the end of this standard

TABLE 1 Deformed Bar Designation Numbers, Nominal Weights [Masses], Nominal Dimensions, and Deformation Requirements

Bar Designation No.	Nominal Weight, lb/ft [Nominal Mass, kg/m]	Nominal Dimensions ^A			Deformation Requirements, in. [mm]		
		Diameter, in. [mm]	Cross-Sectional Area, in. ² [mm ²]	Perimeter in. [mm]	Maximum Average Spacing	Minimum Average Height	Maximum Gap (Chord of 12.5 % of Nominal Perimeter)
3 [10]	0.376 [0.560]	0.375 [9.5]	0.11 [71]	1.178 [29.9]	0.262 [6.7]	0.015 [0.38]	0.143 [3.6]
4 [13]	0.668 [0.994]	0.500 [12.7]	0.20 [129]	1.571 [39.9]	0.350 [8.9]	0.020 [0.51]	0.191 [4.9]
5 [16]	1.043 [1.552]	0.625 [15.9]	0.31 [199]	1.963 [49.9]	0.437 [11.1]	0.028 [0.71]	0.239 [6.1]
6 [19]	1.502 [2.235]	0.750 [19.1]	0.44 [284]	2.356 [59.8]	0.525 [13.3]	0.038 [0.97]	0.286 [7.3]
7 [22]	2.044 [3.042]	0.875 [22.2]	0.60 [387]	2.749 [69.8]	0.612 [15.5]	0.044 [1.12]	0.334 [8.5]
8 [25]	2.670 [3.973]	1.000 [25.4]	0.79 [510]	3.142 [79.8]	0.700 [17.8]	0.050 [1.27]	0.383 [9.7]
9 [29]	3.400 [5.060]	1.128 [28.7]	1.00 [645]	3.544 [90.0]	0.790 [20.1]	0.056 [1.42]	0.431 [10.9]
10 [32]	4.303 [6.404]	1.270 [32.3]	1.27 [819]	3.990 [101.3]	0.889 [22.6]	0.064 [1.63]	0.487 [12.4]
11 [36]	5.313 [7.907]	1.410 [35.8]	1.56 [1006]	4.430 [112.5]	0.987 [25.1]	0.071 [1.80]	0.540 [13.7]
14 [43]	7.65 [11.38]	1.693 [43.0]	2.25 [1452]	5.32 [135.1]	1.185 [30.1]	0.085 [2.16]	0.648 [16.5]
18 [57]	13.60 [20.24]	2.257 [57.3]	4.00 [2581]	7.09 [180.1]	1.58 [40.1]	0.102 [2.59]	0.864 [21.9]

^A The nominal dimensions of a deformed bar are equivalent to those of a plain round bar having the same weight [mass] per foot [metre] as the deformed bar.

TABLE 2 Tensile Properties Requirements

	Grade 100 [690]	Grade 120 [830]
Tensile strength, min, psi [MPa]	150 000 [1030]	150 000 [1030]
Yield strength (0.2 % offset), min, psi [MPa]	100 000 [690]	120 000 [830]
Stress corresponding to an extension under load of 0.0035 in./in. (0.0035 mm/mm), min, psi [MPa]	80 000 [550]	90 000 [620]
Elongation in 8 in. [200 mm], min, %:		
Bar Designation No.		
3 through 11 [10 through 36]	7	7
14, 18 [43, 57]	6	—

3. Terminology

3.1 Definitions of Terms Specific to This Standard:

3.1.1 *deformations, n*—protrusions on a deformed bar.

3.1.2 *deformed bar, n*—steel bar with protrusions; a bar that is intended for use as reinforcement in reinforced concrete construction.

3.1.2.1 *Discussion*—The surface of the bar is provided with lugs or protrusions that inhibit longitudinal movement of the bar relative to the concrete surrounding the bar in such construction. The lugs or protrusions conform to the provisions of this specification.

3.1.3 *lot, n*—all the bars of one bar size or pattern of deformation contained in an individual shipping release or shipping order.

3.1.4 *plain bar, n*—steel bar without protrusions.

3.1.5 *rib, n*—longitudinal protrusion on a deformed bar.

4. Ordering Information

4.1 It shall be the responsibility of the purchaser to specify all requirements that are necessary for material ordered to this specification. Such requirements shall include but are not limited to the following:

4.1.1 Quantity (weight) [mass],

4.1.2 Name of material: low-carbon, chromium, steel bars for concrete reinforcement,

4.1.3 Size,

4.1.4 Cut lengths or coils,

4.1.5 Deformed or plain,

4.1.6 Grade,

4.1.7 Packaging (see Section 21),

4.1.8 ASTM designation and year of issue, and

4.1.9 Certified mill test reports.

5. Materials and Manufacture

5.1 The bars shall be rolled from properly identified heats of mold cast or strand cast steel using the basic oxygen, electric-furnace, or open-hearth process.

6. Chemical Composition

6.1 The chemical analysis of each heat shall be determined in accordance with Test Methods, Practice, and Terminology A751. The manufacturer shall make the analysis on test samples taken preferably during the pouring of the heat. The percentages of carbon, manganese, phosphorus, sulfur, silicon, chromium, and nitrogen, shall be determined and reported as required in Section 16.

6.2 The chemical composition as shown by heat analysis shall be limited by the following:

Element	max, % ^A
Carbon	0.15 %
Chromium	8.0 to 10.9 %
Manganese	1.5 %
Nitrogen	0.05 %
Phosphorus	0.035 %
Sulfur	0.045 %
Silicon	0.50 %

^A Maximum unless range is indicated percentages refer to weight percentages.

7. Requirements for Deformation

7.1 Deformations shall be spaced along the bar at substantially uniform distances. The deformations on opposite sides of the bar shall be similar in size, shape, and pattern.

7.2 The deformations shall be placed with respect to the axis of the bar so that the included angle is not less than 45°. Where the line of deformations forms an included angle with the axis of the bar from 45 to 70° inclusive, the deformations shall alternately reverse in direction on each side, or those on one