
**Urine-absorbing aids for
incontinence — Polyacrylate
superabsorbent powders —
Part 7:
Test method for gravimetric
determination of absorption against
pressure**

*Aides pour absorption d'urine — Méthodes d'essai pour caractériser
les matériaux absorbants à base de polymères —*

*Partie 7: Détermination gravimétrique du pouvoir d'absorption sous
pression*

ISO 17190-7:2020

<https://standards.iteh.ai/catalog/standards/iso/455b9bd7-8f55-43dc-950f-5dda41babf08/iso-17190-7-2020>



iTeh Standards
(<https://standards.iteh.ai>)
Document Preview

ISO 17190-7:2020

<https://standards.iteh.ai/catalog/standards/iso/455b9bd7-8f55-43dc-950f-5dda41babf08/iso-17190-7-2020>



COPYRIGHT PROTECTED DOCUMENT

© ISO 2020

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Contents

Page

Foreword	iv
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Principle	1
5 Reagents and materials	2
6 Apparatus	2
7 Conditioning	4
8 Sampling	4
9 Procedure	4
10 Calculation	5
11 Report	6
12 Precision	6
Annex A (informative) Apparatus for measuring absorbency under pressure	8
Bibliography	10

iTeh Standards
(<https://standards.iteh.ai>)
Document Preview

ISO 17190-7:2020

<https://standards.iteh.ai/catalog/standards/iso/455b9bd7-8f55-43dc-950f-5dda41babf08/iso-17190-7-2020>

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 173, *Assistive products*, Subcommittee SC 3, *Aids for ostomy and incontinence*.

This second edition cancels and replaces the first edition (ISO 17190-7:2001), which has been technically revised. The main changes compared to the previous edition are as follows:

- full text review and new laboratory analysis with statistical evaluation;
- descriptions of the equipment required and the handling procedure improved.

A list of all parts in the ISO 17190 series can be found on the ISO website.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

Urine-absorbing aids for incontinence — Polyacrylate superabsorbent powders —

Part 7:

Test method for gravimetric determination of absorption against pressure

WARNING — This document does not claim to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this document to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use. It is expected that the person performing this test has been fully trained in all aspects of this procedure.

1 Scope

This document provides a test method that determines the capacity of polyacrylate superabsorbent powders to absorb saline solution under a specified enclosing pressure.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 187, *Paper, board and pulps — Standard atmosphere for conditioning and testing and procedure for monitoring the atmosphere and conditioning of samples* ¹²⁰

ISO 3696, *Water for analytical laboratory use — Specification and test methods*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <http://www.electropedia.org/>

3.1

sample

product or portion of a product taken from a production lot for testing purposes and identifiable and traceable back to its origin

3.2

specimen

specific portion of the identified *sample* (3.1) upon which a test is performed

4 Principle

The test sample is weighed and spread evenly on the bottom filter screen closing a specified cylinder. A uniform pressure is applied on the test portion. The cylinder is then placed on a filter plate, which

is placed in a Petri dish filled with saline solution. After an absorption time of 1 hour, the cylinder is removed from the filter plate and weighed to determine the amount of fluid absorbed.

5 Reagents and materials

Use only reagents of recognized analytical grade, unless otherwise specified.

5.1 Water.

Grade 1 water in accordance with ISO 3696, with the exception that the conductivity can be as high as 30 $\mu\text{S}/\text{cm}$.

5.2 Sodium chloride solution.

5.2.1 0,9 % mass fraction of sodium chloride solution in water. Weigh $(9,00 \pm 0,01)$ g of sodium chloride into a 1 l beaker and add $(991,0 \pm 0,1)$ g of deionized water (grade 3). Stir until dissolved.

5.2.2 The conductivity of the solution should be checked prior to each use using properly calibrated measuring equipment. The expected conductivity of a 0,9 % saline solution is of the order of 1600 S/m at 25 °C. Each testing lab shall determine the correct conductivity for the conditions obtaining in the lab. It is also recommended that the temperature of the solution be maintained at (23 ± 2) °C for the duration of the test. As this matches the required laboratory temperature, it is not necessary to record the solution temperature.

6 Apparatus

The apparatus for measuring absorbency under pressure is illustrated on [Figures A.1](#) and [A.2](#). It comprises the following elements:

6.1 Petri dish or tray, large enough to accommodate the apparatus and supply sufficient saline solution to meet the absorption capacity of the sample for the duration of the test.

It is necessary to minimize evaporation of water, as this leads to increasing saline concentration during the test, without compromising the availability of sufficient saline to be absorbed by the polymer.

A practical solution is to use a circular Petri dish of 20 cm diameter, which gives an area of about 314 cm², or a square dish of 20 cm per side, which gives an area of about 400 cm².

6.2 Ceramic filter plate, at least 80 mm in diameter and at least 5 mm in thickness/height, centred and bi-plane ground, with the outside edge not fused. The porosity shall be 0 (nominal pore size 160 μm to 250 μm), in accordance with ISO 4793.

NOTE For example, VitraPOR®¹⁾ filter discs (ROBU®¹⁾).

A filter paper with a diameter of at least 70 mm, but not larger than the ceramic filter plate may be employed to reduce contamination of the filter plate by water soluble extracts from the polymer.

6.3 Polymethylmethacrylate (PMMA, or equivalent) cylinder, with an internal diameter of $d_1 = (60,0 \pm 0,2)$ mm, a height equal to $(50,0 \pm 0,5)$ mm with a nylon cloth filter screen or stainless-steel screen in the bottom (400 mesh = 36 μm). For other diameters and materials, see [Annex A](#). It is recommended that this cylinder be machined from a solid block rather than cut from a tube.

1) VitraPOR® and ROBU® are examples of suitable products available commercially. This information is given for the convenience of users of this document and does not constitute an endorsement by ISO of this product.