

DRAFT INTERNATIONAL STANDARD

ISO/DIS 17190-10

ISO/TC 173/SC 3

Secretariat: SIS

Voting begins on:
2019-08-15

Voting terminates on:
2019-11-07

Urine-absorbing aids for incontinence — Polyacrylate superabsorbent powders —

Part 10:

Test method for determination of extractable polymer content by potentiometric titration

Aides pour absorption d'urine — Méthodes d'essai pour caractériser les matériaux absorbants à base de polymères —

Partie 10: Détermination de la teneur en polymère extractible par titrage potentiométrique

ICS: 11.180.20

ITeH STANDARD PREVIEW
(standards.iteh.ai)
Full standard:
<https://standards.iteh.ai/catalog/standards/sist/b260-4981-897a-296112bbd96d/iso-dis-17190-10>

THIS DOCUMENT IS A DRAFT CIRCULATED FOR COMMENT AND APPROVAL. IT IS THEREFORE SUBJECT TO CHANGE AND MAY NOT BE REFERRED TO AS AN INTERNATIONAL STANDARD UNTIL PUBLISHED AS SUCH.

IN ADDITION TO THEIR EVALUATION AS BEING ACCEPTABLE FOR INDUSTRIAL, TECHNOLOGICAL, COMMERCIAL AND USER PURPOSES, DRAFT INTERNATIONAL STANDARDS MAY ON OCCASION HAVE TO BE CONSIDERED IN THE LIGHT OF THEIR POTENTIAL TO BECOME STANDARDS TO WHICH REFERENCE MAY BE MADE IN NATIONAL REGULATIONS.

RECIPIENTS OF THIS DRAFT ARE INVITED TO SUBMIT, WITH THEIR COMMENTS, NOTIFICATION OF ANY RELEVANT PATENT RIGHTS OF WHICH THEY ARE AWARE AND TO PROVIDE SUPPORTING DOCUMENTATION.

This document is circulated as received from the committee secretariat.



Reference number
ISO/DIS 17190-10:2019(E)

© ISO 2019

iTeh STANDARD PREVIEW
(standards.iteh.ai)
Full standard:
<https://standards.iteh.ai/catalog/standards/sist/912c64cf-b260-4981-897a-296112bbd96d/iso-dis-17190-10>



COPYRIGHT PROTECTED DOCUMENT

© ISO 2019

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Fax: +41 22 749 09 47
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Contents

Page

Foreword.....	iv
1 Scope.....	1
2 Normative references.....	1
3 Terms and definitions.....	1
4 Principle.....	2
5 Reagents and Materials.....	2
6 Apparatus.....	3
7 Conditioning.....	4
8 Sampling.....	4
9 Procedure.....	4
10 Calculation.....	5
11 Report.....	6
12 Precision.....	7
Annex A (informative) Modification Track Sheet.....	8
Bibliography.....	9

iTeh STANDARD PREVIEW
 (standards.iteh.ai)

Full standard:
<https://standards.iteh.ai/catalog/standards/sist/912c64cf-b260-4981-897a-296112bbd96d/iso-dis-17190-10>

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee [or Project Committee] ISO/TC [or ISO/PC] ###, [name of committee], Subcommittee SC ##, [name of subcommittee].

This second/third/... edition cancels and replaces the first/second/... edition (ISO #####:#####), which has been technically revised.

The main changes compared to the previous edition are as follows:

— xxx xxxxxxxx xxx xxxxx

A list of all parts in the ISO ##### series can be found on the ISO website.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

Urine-absorbing aids for incontinence — Polyacrylate superabsorbent powders —

Part 10:

Test method for determination of extractable polymer content by potentiometric titration

1 Scope

This test method is used to determine the mass fraction of soluble polymers present in crosslinked polyacrylate superabsorbent powders that may be extracted into saline solution.

NOTE - This standard does not claim to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use. It is expected that the person performing this test has been fully trained in all aspects of this procedure.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 187, *Paper, board and pulps — Standard atmosphere for conditioning and testing and procedure for monitoring the atmosphere and conditioning of samples*

ISO 3696, *Water for analytical laboratory use — Specification and test methods*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <http://www.electropedia.org/>

3.1

acid groups

carboxylic acid group

3.2

extractables

sum of the soluble acid and salt groups of monomeric, oligomeric and polymeric carboxylates extracted from the superabsorbent polymer

3.3

salt group

Alkali metal salt of carboxylic acid group also referred to as neutralized carboxylic acid or carboxylate

**3.4
sample**

product or portion of a product taken from a production lot for testing purposes and identifiable and traceable back to its origin

**3.5
specimen**

specific portion of the identified sample upon which a test is performed

4 Principle

The amount of extractable polymer in polyacrylate superabsorbent powders is determined by mixing the polymer in saline solution for 1 hour. The resulting saline suspension is filtered in its entirety through a paper filter of <12- μ m pore size. An aliquot of the filtrate is titrated against a standard base solution (NaOH) to pH 10.0 to determine the concentration of free carboxylic acid groups. The resulting solution is then back-titrated against a standard acid solution (HCl) to pH 2.7 to determine the concentration of neutralised carboxylate groups. The titration data are used to calculate the total amount of extractables present in the superabsorbent powder.

5 Reagents and Materials

Use only reagents of recognized analytical grade, unless otherwise specified.

5.1 Water

Grade 3 water according to **ISO 3696**, with the exception that the conductivity can be as high as 30 μ S/cm.

5.2 Sodium hydroxide solution

c(NaOH) = 0.1 mol/l. Obtained as ready-made analytical grade solution.

5.3 Hydrochloric acid solution

c(HCl) = 0.1 mol/l. Obtained as ready-made analytical grade solution.

5.4 Sodium Chloride solution

5.4.1 0.9% by mass (m/m) Weigh 9.00 ± 0.01 g of sodium chloride into a 1 l beaker and add 991.0 ± 0.1 g of deionised water (grade 3). Stir until dissolved.

5.4.2 The conductivity of the solution should be checked prior to each use using properly calibrated measuring equipment. The expected conductivity of a 0,9% saline solution is of the order of 16mS/cm at 25 °C. Each testing lab must determine the correct conductivity for the conditions obtaining in the lab. It is also recommended that the temperature of the solution be maintained at (23 +/- 2) °C for the duration of the test.

5.5 Standard buffer solutions

Prepare 3 buffer solutions according to ISO 10523 (or equivalent national standards) with pH values suitable to work in a range from pH 2,7 till pH 10. For instance

- 3.0 \pm 0.02
- 7.0 \pm 0.02
- 10.0 \pm 0.02

6 Apparatus

6.1 Analytical balance capable of weighing a mass of 1.000 ± 0.001 g of polymer powder in combination with the mass of the weighing vessel or laboratory paper employed.

6.2 Analytical balance, capable of weighing a mass of 9.00 ± 0.01 g of sodium chloride in combination with the mass of the weighing vessel or laboratory paper employed

6.3 Analytical balance, capable of weighing a mass of 1000.00 ± 1.00 g of sodium chloride solution in combination with the mass of the vessel employed

6.4 pH meter with a combined glass pH-responsive electrode, referred to in the text as the pH electrode, which is suitable for titrating polymer solutions and capable of accurately measuring pH in the range 2.7 to 10.0. For example, a large membrane surface increases the electrode sensitivity for high pH measurement and a leaky sleeve electrode is less likely to suffer contamination from the polymer in the titration solution.

6.5 Volumetric flask, grade "A" of 1 l capacity

6.6 Weighing vessel or laboratory paper

6.7 Titration vessels - glass beakers or conical flasks

6.8 Conical flask of 250 ml capacity

6.9 Beaker of 250 ml capacity. A tall form is recommended to allow better gel separation.

6.10 Metal spatula to accommodate 1.0 g of superabsorbent powder

6.11 Paraffin film or suitable cover for glass beakers

6.12 Filter papers to accommodate 100 ml supernatant, with a pore size $<12 \mu\text{m}$

6.13 Measuring cylinder of 200 ml capacity and accurate to $\pm 0.5\%$

6.14 Magnetic stirrer having the capability of stirring at a rate of 250 ± 50 r.min⁻¹

6.15 Magnetic stirrer and stirring bar

6.16 Cylindrical stirring bars can be unstable when used on a multipoint magnetic stirring block. The mixture of magnetic fluxes can cause the bar to freeze periodically. Both cylindrical and star-shaped stirrers can tear the gel. It is recommended to use a cross-centered circular bar, which provides more stable stirring and minimum tearing of the gel. It is also important to make sure that the cross is properly centred in the circle. Cheaply made versions can be off-centre and this increases variability in the test.



Figure 1 — Cowie double cross-head stir bar (typical dimensions: $20 < d < 25$ mm, $12 < h < 18$ mm)

6.17 Analytical burette of 10 ml to 20 ml volume, with an accuracy to ± 0.01 ml or automated titration equipment of similar or better accuracy.

7 Conditioning

Samples shall be delivered in a closed container, to prevent absorption of atmospheric moisture. Allow the closed container to equilibrate to the laboratory conditions. The preferred test conditions are (23 ± 2) °C and (45 ± 15) % relative humidity. If these conditions are not available, test at ambient conditions and report the temperature and relative humidity. Measure these laboratory conditions in accordance with ISO 187.

8 Sampling

SAFETY WARNING Power Handling - The German MAK has provided a guideline value for long-term exposure to the respirable portion of superabsorbent polyacrylate dust of $0.05 \text{ mg}\cdot\text{m}^{-3}$. The respirable portion is defined as those particles of less than $10\text{-}\mu\text{m}$ diameter. Commercial superabsorbent polymers typically contain less than 0.1% of such particles. Precautions should be taken to avoid routine exposure to atmospheric respirable particles above this guideline MAK value.

8.1 Before taking a test portion out of the container to run the test, move the container five to ten times in a figure of eight motion, so as to obtain a homogeneous product. For that matter, sample bottles should not be filled more than 80% of their nominal capacity.



Figure 2 — Sense of motion of the container

8.2 Make sure the test portion is substantially free of lumps of size greater than 1 mm in diameter before proceeding with testing.

9 Procedure

9.1 Electrode Calibration

Calibrate the pH electrode using three buffer solutions with pH values between pH 2.00 and pH 10.00. Monitor the accuracy and precision of the electrode according to the manufacturers' instructions.

9.2 Accurately add 200.0 ± 0.1 ml of saline solution to a 250 ml beaker or conical flask, using the measuring cylinder.

9.3 Place a clean, dry weighing vessel or laboratory paper onto a balance and tare the balance.

9.4 Add 0.95 to 1.05 g of a test portion of superabsorbent powder test sample to the weighing vessel or laboratory paper and tare the balance again.

NOTE 1 Transfer the sample portion from the sample bottle to the weighing vessel or laboratory paper in one spatula portion. Discard any excess material on the spatula. Do not return it to the sample bottle. Keep the sample container closed as much as possible during this process.

9.5 Carefully distribute the test portion into the flask containing the 200.0 ± 0.1 ml of saline.

9.6 Place the weighing vessel or laboratory paper back on the balance. The negative weight displayed is the mass of the sample transferred. Record this as M_{sam} .

9.7 Stopper/Cover/Seal the beaker or conical flask, and stir the solution at a rate of 250 ± 50 r.min⁻¹ for 1 hour.

9.8 Prepare a titration blank by treating 200.0 ± 0.1 ml of the same batch of saline solution as used for the sample preparation in the same way.

9.9 Stop stirring the solutions, and allow the gel to completely settle to the bottom of the beaker; 10 minutes is recommended.

9.10 Filter 100 ml of the solution supernatant through a filter paper.

NOTE 2 Blank Filtration: It is possible that filter papers change the pH of the blank saline solution. If filtration is used it must be shown that the pH of the blank is not changed by filtration. Or simply do not filter the blank saline solution.

9.11 Take a volume of this filtrate appropriate for the titration system used. In this method, 50-ml is used as an example in the procedure and the calculations.

9.12 Using a burette or automated titration system, titrate 50 ml of the blank saline to pH 10.0 against the standard sodium hydroxide solution, and then to pH 2.7 against the standard hydrochloric acid solution. Record each titrant volume used to reach the end point.

9.13 Using a burette or automated titration system, titrate 50 ml of the sample filtrate to pH 10.0 against the standard sodium hydroxide solution, and then to pH 2.7 against the standard hydrochloric acid solution. Record each titrant volume used to reach the end point.

10 Calculation

The amount of carboxylic acid (e.g. polycarboxylic acid), expressed in moles, in the supernatant aliquot, n_{COOH} , is given by [equation \(1\)](#):

$$n_{COOH} = (V_{NaOH,s} - V_{NaOH,b}) C_{NaOH} \quad (1)$$

where

$V_{NaOH,s}$ Is the volume, expressed in millilitres, of the NaOH titrant necessary to titrate the sample filtrate to pH 10.0

$V_{NaOH,b}$ Is the volume, expressed in millilitres, of the NaOH titrant necessary to titrate the blank to pH 10.0

C_{NaOH} Is the concentration, expressed in moles per litre, of the NaOH titrant used for the titration to pH 10.0

The total amount of carboxylate, n_{tot} , expressed in moles, in the supernatant aliquot is given by [equation \(2\)](#):

$$n_{tot} = (V_{HCl,s} - V_{HCl,b}) C_{HCl} \quad (2)$$

where