

INTERNATIONAL
STANDARD

ISO
24260

First edition
2022-06

**Thermal insulation products — Hemp
fiber mat and board — Specification**

*Produits d'isolation thermique — Panneaux et tapis en fibres de
chanvre — Spécifications*

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[ISO 24260:2022](#)

[https://standards.iteh.ai/catalog/standards/sist/8b52a481-9c66-4db9-b4d3-
286fd4ea7efb/iso-24260-2022](https://standards.iteh.ai/catalog/standards/sist/8b52a481-9c66-4db9-b4d3-286fd4ea7efb/iso-24260-2022)



Reference number
ISO 24260:2022(E)

© ISO 2022

iTeh STANDARD PREVIEW (standards.iteh.ai)

[ISO 24260:2022](#)

<https://standards.iteh.ai/catalog/standards/sist/8b52a481-9c66-4db9-b4d3-286fd4ea7efb/iso-24260-2022>



COPYRIGHT PROTECTED DOCUMENT

© ISO 2022

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Contents

	Page
Foreword	iv
1 Scope	1
2 Normative references	1
3 Terms and definitions	2
4 Symbols, units and abbreviated terms	2
4.1 Symbols and units	2
4.2 Abbreviated terms and symbols used in designations	3
5 Requirements	3
5.1 General	3
5.2 Material properties	3
5.2.1 Thermal resistance and thermal conductivity	3
5.2.2 Length and width	4
5.2.3 Thickness	4
5.2.4 Service Temperature	5
5.2.5 Reaction to fire	5
5.2.6 Moisture content	5
5.3 Specific requirements	5
5.3.1 Apparent density	5
5.3.2 Sound absorption	5
5.3.3 Formaldehyde release	5
6 Test methods	6
6.1 Sampling	6
6.2 Conditioning	6
6.3 Procedure	6
6.3.1 General	6
6.3.2 Thermal resistance and thermal conductivity	7
7 Designation code	7
8 Product conformity	8
8.1 General	8
8.2 Initial type testing (ITT)	8
8.3 Factory production control (FPC)	8
9 Marking and labelling	8
Annex A (normative) Determination of the declared values of thermal resistance and thermal conductivity	10
Annex B (normative) Factory production control (FPC)	12
Annex C (normative) Determination of the thermal conductivity in relation to moisture content	13
Bibliography	15

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 163, *Thermal performance and energy use in the built environment*, Subcommittee SC 3, *Thermal insulation products, components and systems*.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

Thermal insulation products — Hemp fiber mat and board — Specification

1 Scope

This document specifies requirements for factory-made products of hemp fibre, which are used for the thermal insulation of buildings. This document applies to material containing more than 50 % (by mass) natural hemp fibre, with or without the other natural fibre and the balance being polymeric material. The products are delivered as a mat or board with or without facings.

This document describes product characteristics and testing methods, marking, labelling and packaging.

Products covered in this document are also used in prefabricated thermal insulation systems and composite panels. The performance of systems incorporating these products is not covered.

The use of moth proof agent residues is outside the scope of this document.

This document does not address the health and safety aspects associated with its use. It is the responsibility of the user of this document to establish appropriate health and safety practices.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

<https://standards.iteh.ai/catalog/standards/sist/8b52a481-9c66-4db9-b4d3->
ISO 354, *Acoustics — Measurement of sound absorption in a reverberation room*

ISO 8301, *Thermal insulation — Determination of steady-state thermal resistance and related properties — Heat flow meter apparatus*

ISO 8302, *Thermal insulation — Determination of steady-state thermal resistance and related properties — Guarded hot plate apparatus*

ISO 9229, *Thermal insulation — Vocabulary*

ISO 11654, *Acoustics — Sound absorbers for use in buildings — Rating of sound absorption*

ISO 11925-2, *Reaction to fire tests — Ignitability of products subjected to direct impingement of flame — Part 2: Single-flame source test*

ISO 12460-1, *Wood-based panels — Determination of formaldehyde release — Part 1: Formaldehyde emission by the 1-cubic-metre chamber method*

ISO 12570, *Hygrothermal performance of building materials and products — Determination of moisture content by drying at elevated temperature*

ISO 12576-1, *Thermal insulation — Insulating materials and products for buildings — Conformity control systems — Part 1: Factory-made products*

ISO 29465, *Thermal insulating products for building applications — Determination of length and width*

ISO 29466, *Thermal insulating products for building applications — Determination of thickness*

ISO 29470, *Thermal insulating products for building applications — Determination of the apparent density*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 9229 and the following apply.

ISO and IEC maintain terminology databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <https://www.electropedia.org/>

3.1

production line

equipment that produces products in a continuous process

Note 1 to entry: For initial type test (ITT) and factory production control (FPC), each production line is considered separately.

3.2

production unit

equipment that produces products in a discontinuous process

Note 1 to entry: For initial type test (ITT) and factory production control (FPC), units using the same process in one factory are considered together [as one *production line* (3.1)].

3.3

hemp fibre mat

HFM

soft matted material made from natural hemp fibre as the main (>50 % by mass) material with or without the other natural fibre and the balance being polymeric material.

3.4

hemp fibre board

HFB

plate type products with certain degree of rigidity made from natural hemp fibre as the main (>50 % by mass) material with or without the other natural fibre and the balance being polymeric material.

4 Symbols, units and abbreviated terms

4.1 Symbols and units

b	width, mm
d	thickness, mm
l	length, mm
d_N	nominal thickness of the product, mm
λ	thermal conductivity, W/(m·K)
λ_D	declared thermal conductivity, W/(m·K)
λ_i	Specimen's one test result of thermal conductivity, W/(m·K)
$\lambda_{90/90}$	90 % fractile with a confidence level of 90 % for the thermal conductivity, W/(m·K)
λ_{mean}	Specimens' mean thermal conductivity, W/(m·K)
H	moisture content, %

k	factor related to the number of test results available
R_D	declared thermal resistance, $\text{m}^2 \cdot \text{K}/\text{W}$
R_i	specimen's one test result of thermal resistance, $\text{m}^2 \cdot \text{K}/\text{W}$
R_{mean}	mean thermal resistance, $\text{m}^2 \cdot \text{K}/\text{W}$
$R_{90/90}$	90 % fractile with a confidence level of 90 % for the thermal resistance, $\text{m}^2 \cdot \text{K}/\text{W}$
ρ_a	apparent density, kg/m^3
L	declared class or level for length tolerances
T	declared class or level for thickness tolerances
W	declared class or level for width tolerances

4.2 Abbreviated terms and symbols used in designations

HFM hemp fibre mat

HFB hemp fibre board

ITT initial type test

FPC factory production control

ITEH STANDARD PREVIEW
(standards.iteh.ai)

5 Requirements

[ISO 24260:2022](#)

5.1 General //standards.iteh.ai/catalog/standards/sist/8b52a481-9c66-4db9-b4d3-286fd4ea7efb/iso-24260-2022

Product properties shall be determined in accordance with [Clause 6](#).

The test methods to be used for determination of each property are given in [Table 4](#), which also shows the required test specimen dimensions and the minimum number of test specimens required to give one test result.

One test result for a product property is the average of the measured values on the number of test specimens given in [Table 4](#).

NOTE For FPC, see [Annex B](#).

5.2 Material properties

5.2.1 Thermal resistance and thermal conductivity

For thermal conductivity testing, the specimen shall be conditioned at $(23 \pm 2)^\circ\text{C}$ and $(50 \pm 5)\%$ relative humidity to constant mass.

Thermal resistance and thermal conductivity shall be based upon measurements carried out in accordance with ISO 8301 or ISO 8302 for thick products.

The thermal resistance and thermal conductivity shall be determined in accordance with the procedures given in [Annex A](#) and declared by the manufacturer according to the following:

- The reference mean temperature shall be either 10°C or 23°C , or both.
- The measured values shall be expressed with three significant figures.

- For products of uniform thickness, the thermal resistance, R_D , shall always be declared. The thermal conductivity, λ_D , shall be declared where possible. Where appropriate, for products of non-uniform thickness (i.e. for sloped and tapered products), only the thermal conductivity, λ_D , shall be declared.
- The declared thermal resistance, R_D , and the declared thermal conductivity, λ_D , shall be given as limit values representing at least 90 % of the production, determined with a confidence level of 90 %.
- The value of the thermal conductivity, $\lambda_{D\ 90/90}$, shall be rounded up to the nearest 0,001 W/(m·K) and declared as λ_D in levels with steps of 0,001 W/(m·K).
- The declared thermal resistance, R_D , shall be calculated from the nominal thickness, d_N , and the corresponding thermal conductivity, $\lambda_{90/90}$.
- The value of the thermal resistance, $R_{90/90}$ (when calculated from the nominal thickness, d_N , and the corresponding thermal conductivity, $\lambda_{D\ 90/90}$), shall be rounded down to the nearest 0,05 m²·K/W and declared as R_D in levels with steps of 0,05 m²·K/W.
- The value of $R_{90/90}$, for those products for which only the thermal resistance is measured directly, shall be rounded down to the nearest 0,05 m²·K/W and declared as R_D in levels with steps of 0,05 m²·K/W.

Determination of declared values of thermal resistance, R_D , and thermal conductivity, λ_D , shall be in accordance with [Annex A](#).

Determination of declared values of thermal conductivity in relation to moisture content shall be in accordance with [Annex C](#).

5.2.2 Length and width

(standards.iteh.ai)

The length, l , and width, b , shall be determined in accordance with ISO 29465. No test result shall deviate from the nominal values by more than the tolerances given in [Table 1](#) and [Table 2](#).

<https://standards.iteh.ai/catalog/standards/sist/8b52a481-9c66-4db9-b4d3-286f11e73b/ce23603022>

Table 1 — Products for length tolerances

Product	Tolerances
	mm
HFM	±5 or ±0,4 % ^a
HFB	±3 or ±0,4 % ^a

^a Whichever gives the greatest numerical tolerance.

Table 2 — Products for width tolerances

Product	Tolerances
	mm
HFM	±2 or ±0,4 % ^a
HFB	±2 or ±0,4 % ^a

^a Whichever gives the greatest numerical tolerance.

5.2.3 Thickness

The thickness, d , shall be determined in accordance with ISO 29466, under a pressure of 50 Pa. No test result shall deviate from the nominal thickness, d_N , by more than the tolerances given in [Table 3](#).

5.2.4 Service Temperature

Hemp fibre mat (HFB) and hemp fibre board (HFB) thermal insulation shall not be used on a substrate outside a continuous service temperature of -60°C to $+80^{\circ}\text{C}$.

Table 3 — Products for thickness tolerances

Product	Tolerances
	mm
HFM	+5
	0
HFB	+3
	-2

5.2.5 Reaction to fire

The reaction to fire characteristics of the product as placed on the market shall be measured according to ISO 11925-2.

5.2.6 Moisture content

Moisture content, H , shall be determined in accordance with ISO 12570 ($80 \pm 2^{\circ}\text{C}$). No test result shall exceed a mass fraction of 30 %.

5.3 Specific requirements (standards.iteh.ai)

5.3.1 Apparent density

Apparent density, ρ_a , is a useful identification parameter. Apparent density of mat and board shall be determined in accordance with ISO 29470. No mean value of a product shall deviate by more than $\pm 15\%$ from the declared value given in the manufacturer's literature.

5.3.2 Sound absorption

Sound absorption coefficient shall be determined in accordance with ISO 354. The sound absorption characteristics shall be calculated in accordance with ISO 11654 using the values for the practical sound absorption coefficient, α_p , at the frequencies 125 Hz, 250 Hz, 500 Hz, 1 000 Hz, 2 000 Hz and 4 000 Hz and the single number value for the weighted sound absorption coefficient, α_w . α_p and α_w shall be rounded to the nearest 0,05 (α_p larger than 1 shall be expressed as $\alpha_p = 1$) and declared in levels with steps of 0,05.

The weighted sound absorption coefficient, α_w , shall be declared. No result of α_w shall be lower than the declared level.

5.3.3 Formaldehyde release

The formaldehyde release amount shall be measured and declared according to ISO 12460-1. The formaldehyde release shall be declared.

6 Test methods

6.1 Sampling

Test specimens shall be taken from the same sample with a total area not less than 1 m² and sufficient to cover the needed tests. The shorter side of the sample shall not be less than 300 mm or full size of the product, whichever is the smaller.

6.2 Conditioning

Condition the test specimen at (23 ± 2) °C and (50 ± 5) % relative humidity or (27 ± 5) °C and (65 ± 5) % relative humidity for 6 h.

For thermal conductivity testing, the conditioning shall be according to [5.2.1](#).

6.3 Procedure

6.3.1 General

[Table 4](#) gives the dimensions of the test specimens, the minimum number of measurements required to get one test result and any specific conditions which are necessary.

The test may be performed on the faced product, if the facing is known to have no relevance to the test result.

Table 4 — Test methods, test specimens and specific conditions

Sub-clause		Test method ISO 286614ca7d118c9a42603203	Test speci-men length and width (mm) ISO 286614ca7d118c9a42603203	Minimum number of specimens for one test result ISO 286614ca7d118c9a42603203	Specific con-ditions ISO 286614ca7d118c9a42603203	Material re-quirements ISO 286614ca7d118c9a42603203
No.	Title ISO 286614ca7d118c9a42603203					
5.2.1	Thermal resistance and thermal conductivity	ISO 8301 or ISO 8302	Required in ISO 8301 or ISO 8302	3	(23 ± 2) °C and (50 ± 5) % relative humidity to constant mass.	Declared
5.2.2	Length and width	ISO 29465	Full-size	3	-	Table 1 and Table 2
5.2.3	Thickness	ISO 29466	Full size	3	Method in Annex B ; pressure at 50 Pa	Table 3
5.2.4	Reaction to fire	ISO 11925-2	250 x 90	6	-	Declared
		EN 13823	1 500 × 1 000 1 500 × 495	3	-	Declared
5.2.5	Moisture content	ISO 12570	200 × 200	3	(80 ± 2) °C to constant mass	30 % maximum
5.3.1	Apparent density	ISO 29470	Full size	3	(23 ± 2) °C and (50 ± 5) % relative humidity to constant mass	Declared

Table 4 (continued)

Sub-clause		Test method	Test specimen length and width (mm)	Minimum number of specimens for one test result	Specific conditions	Material requirements
No.	Title					
5.3.2	Sound absorption	ISO 354	10 m ² minimum	3	-	Declared in steps of 0,05
5.3.3	Formaldehyde release	ISO 12460-1	Required in ISO 12460-1	3	-	Declared

6.3.2 Thermal resistance and thermal conductivity

For thermal conductivity testing, the specimen shall be conditioned (23 ± 2) °C and (50 ± 5) % relative humidity to constant mass.

Thermal resistance and thermal conductivity shall be determined in accordance with ISO 8301 or ISO 8302 for thick products and under the following conditions:

- at a mean temperature of (10 ± 0,30) °C or at a mean temperature of (23 ± 0,30) °C.

Thermal resistance and thermal conductivity can also be measured at other mean temperatures, providing that the accuracy of the relationship between temperature and thermal properties is well documented.

Thermal resistance and thermal conductivity shall be determined directly at measured thickness. In the event that this is not possible, they shall be determined by measurements on other thicknesses of the product providing that

- the product is of similar chemical and physical characteristics and is produced on the same production unit, and
<https://standards.iteh.ai/catalog/standards/sist/8b52a481-9c66-4db9-b4d3->
- it can be demonstrated that the thermal conductivity, λ , does not vary more than 2 % over the range of thicknesses where the calculation is applied.

When measured thickness is used for testing of thermal resistance and thermal conductivity, the test thickness shall be the smallest of the measured points on the test specimen (and not the mean) as far as possible to avoid any air gabs during testing.

Determination of declared values of thermal conductivity in relation to moisture content λ shall be in accordance with [Annex C](#).

7 Designation code

A designation code for the product shall be given by the manufacturer. The following shall be included except when there is no requirement for a property described in [5.3](#):

- the hemp fibre mat and hemp fibre board abbreviated term, HFM and HFB;
- this document number, i.e. ISO 24260:2022;
- thickness, d_N ;
- width and length, b and l ;
- thermal resistance and/or thermal conductivity, λ_D and/or R_D .

The designation code for an HFM product is illustrated by the following example:

EXAMPLE HFM — ISO 24260 — d_N 90 — b395 — l10600, λ_D 0,044 W/(m·K), R_D 2,05 (m²·K/W)