



Designation: E1745 – 11

Standard Specification for Plastic Water Vapor Retarders Used in Contact with Soil or Granular Fill under Concrete Slabs¹

This standard is issued under the fixed designation E1745; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This specification covers flexible, preformed sheet membrane materials to be used as vapor retarders in contact with soil or granular fill under concrete slabs.

1.1.1 This specification does not cover bituminous vapor retarders. See Specification E1993 for information on bituminous vapor retarders.

1.2 The specified tests are conducted on new materials and materials that have been conditioned or exposed to simulate potential service conditions.

1.3 The values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units that are provided for information only and are not considered standard.

2. Referenced Documents

2.1 *ASTM Standards*:²

C168 Terminology Relating to Thermal Insulation

D828 Test Method for Tensile Properties of Paper and Paperboard Using Constant-Rate-of-Elongation Apparatus (Withdrawn 2009)³

D882 Test Method for Tensile Properties of Thin Plastic Sheeting

D1709 Test Methods for Impact Resistance of Plastic Film by the Free-Falling Dart Method

E96/E96M Test Methods for Water Vapor Transmission of Materials

E154 Test Methods for Water Vapor Retarders Used in Contact with Earth Under Concrete Slabs, on Walls, or as Ground Cover

E631 Terminology of Building Constructions

E1643 Practice for Selection, Design, Installation, and Inspection of Water Vapor Retarders Used in Contact with Earth or Granular Fill Under Concrete Slabs

E1993 Specification for Bituminous Water Vapor Retarders Used in Contact with Soil or Granular Fill Under Concrete Slabs

F1249 Test Method for Water Vapor Transmission Rate Through Plastic Film and Sheeting Using a Modulated Infrared Sensor

3. Terminology

3.1 *Definitions*—For definitions of terms used in this specification, see Terminologies C168 and E631.

3.2 *Definitions of Terms Specific to This Standard*:

3.2.1 *perm, n*—the time rate of water vapor migration through a material or a construction of one grain per hour, square foot, inch of mercury pressure difference.

3.2.1.1 *Discussion*—If a specification states that a one perm limit is required, the same flow rate will be obtained from the following relationships:

$$\begin{aligned} 1 \text{ perm} &= 1 \text{ grain/h} \cdot \text{ft}^2 \text{ in.} \cdot \text{Hg (inch-pound)} \\ &= 57.2 \cdot 10^{-12} \text{ kg}/(\text{Pa} \cdot \text{s} \cdot \text{m}^2) \text{ (SI fundamental units)} \\ &= 57.2 \text{ ng}/(\text{Pa} \cdot \text{s} \cdot \text{m}^2) \text{ (SI frequently used)} \\ &= 0.66 \text{ g}/24 \text{ h} \cdot \text{m}^2 \cdot \text{mm Hg (SI has been used but is now} \\ &\quad \text{obsolete)} \end{aligned}$$

3.2.2 *vapor retarder, n*—(formerly vapor barrier) a material or construction that impedes the transmission of water vapor under specified conditions.

3.2.3 *water vapor permeability, n*—a property of material which is water vapor permeance through unit thickness. Since materials that provide resistance to vapor flow are never used in unit thickness, the preferred evaluation of both materials and constructions is the permeance.

3.2.4 *water-vapor permeance, n*—the time rate of water vapor flow through unit area of the known thickness of a flat material or a construction normal to two specific parallel

¹ This specification is under the jurisdiction of ASTM Committee E06 on Performance of Buildings and is the direct responsibility of Subcommittee E06.21 on Serviceability.

Current edition approved Oct. 1, 2011. Published October 2011. Originally approved in 1996. Last previous edition approved in 2009 as E1745 – 09. DOI: 10.1520/E1745-11.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

³ The last approved version of this historical standard is referenced on www.astm.org.