



Designation: ~~A266/A266M-03a (Reapproved 2008)~~ Designation: A266/A266M – 11

Standard Specification for Carbon Steel Forgings for Pressure Vessel Components¹

This standard is issued under the fixed designation A266/A266M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the Department of Defense.

1. Scope*

1.1 This specification² covers four grades of carbon steel forgings for boilers, pressure vessels, and associated equipment.

NOTE 1—Designations have been changed as follows:

| | |
|---------|----------|
| Current | Formerly |
| Grade 1 | Class 1 |
| Grade 2 | Class 2 |
| Grade 3 | Class 3 |
| Grade 4 | Class 4 |

1.2 Supplementary requirements are provided for use when additional testing or inspection is desired. These shall apply only when specified individually by the purchaser in the order.

1.3 The values stated in either SI units or inch-pound units are to be regarded separately as standard. The values stated in each system may not be exact equivalents; therefore, each system shall be used independently of the other. Combining values from the two systems may result in non-conformance with the standard.

1.4 Unless the order specifies the applicable “M” specification designation, the material shall be furnished to the inch-pound units.

2. Referenced Documents

2.1 *ASTM Standards:*³

A275/A275M [Practice for Magnetic Particle Examination of Steel Forgings](#)

A370 [Test Methods and Definitions for Mechanical Testing of Steel Products](#)

A788/A788M [Specification for Steel Forgings, General Requirements](#)

A1058 [Test Methods for Mechanical Testing of Steel Products](#)

E112 [Test Methods for Determining Average Grain Size](#)

E165 [Practice for Liquid Penetrant Examination for General Industry](#)

E381 [Method of Macroetch Testing Steel Bars, Billets, Blooms, and Forgings](#)

2.2 *Other Standard:*

ASME Boiler and Pressure Vessel Code, Section IX, Welding Qualifications⁴

3. Ordering Information and General Requirements

3.1 In addition to the ordering information required by Specification A788/A788M, the purchaser shall include with the inquiry and order a detailed drawing, sketch, or written description of the forging.

3.2 Material supplied to this specification shall conform to the requirements of Specification A788/A788M, which outlines additional ordering information, manufacturing requirements, testing and retesting methods and procedures, marking, certification, product analysis variations, and additional supplementary requirements.

3.3 If the requirements of this specification are in conflict with the requirements of Specification A788/A788M, the requirements of this specification shall prevail.

¹ This specification is under the jurisdiction of ASTM Committee A01 on Steel, Stainless Steel and Related Alloys and is the direct responsibility of Subcommittee A01.06 on Steel Forgings and Billets.

Current edition approved March 1, 2008. Published April 2008. Originally approved in 1943. Last previous edition approved in 2003 as A266/A266M-03a. DOI: 10.1520/A0266_A0266M-03AR08.

Current edition approved Oct. 1, 2011. Published October 2011. Originally approved in 1943. Last previous edition approved in 2008 as A266/A266M – 03a (2008). DOI: 10.1520/A0266_A0266M-11.

² For ASME Boiler and Pressure Vessel Code applications, see related Specification SA-266/ SA-266M in Section II of that code.

³ For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For Annual Book of ASTM Standards volume information, refer to the standard's Document Summary page on the ASTM website.

⁴ Available from the American Society of Mechanical Engineers, 345 East 47th St., New York, NY 10017.

*A Summary of Changes section appears at the end of this standard.

3.4 For hubbed flanges and tube sheets ordered for ASME Boiler and Pressure Vessel Code application, Supplementary Requirement S12 of Specification A788/A788M shall be specified in addition to Supplementary Requirement S8 of this specification.

4. Materials and Manufacture

4.1 The steel shall be made in accordance with the Melting Process Section of Specification A788/A788M. A sufficient discard shall be made to secure freedom from injurious pipe and undue segregation.

4.2 The material shall be forged as close as practical to the specified shape and size.

4.3 The finished product shall be a hot-worked forging as defined by Specification A788/A788M.

5. Machining

5.1 Surfaces shall be machined as designated by the purchaser. Unmachined surfaces shall be sufficiently free of scale to permit inspection.

5.2 Machining may be performed either prior to or after heat treatment at the option of the manufacturer unless specified in accordance with Supplementary Requirement S1.

6. Heat Treatment

6.1 After forging and before reheating for heat treatment, the forgings shall be cooled in such a manner as to prevent injury and to accomplish transformation.

6.2 All forgings shall be annealed, normalized, or normalized and tempered, but alternatively may be liquid quenched and tempered when mutually agreed upon between the manufacturer and the purchaser. When tempering is performed, it shall be at a subcritical temperature, but no less than 1100°F [595°C].

6.3 A multiple stage austenitizing procedure may be used whereby the forging is first fully austenitized and liquid quenched, followed by reheating within the intercritical temperature range to partially reaustenitize, and again liquid quenched. On completion of the austenitizing/quenching cycles, tempering at a temperature between 1100°F [595°C] and the lower critical temperature shall follow.

NOTE 2—Although liquid quenching from the austenitizing temperatures is more effective in enhancing impact properties, air cooling from the austenitizing temperatures is also beneficial and may be used instead of the normalizing procedure in 6.2.

7. Chemical Composition

7.1 *Heat Analysis*—The heat analysis obtained from sampling in accordance with Specification A788/A788M shall comply with Table 1 except that the additional features of Supplementary Requirements S11 and S12 shall also apply as individually specified in the ordering information.

7.2 *Product Analysis*—The purchaser may use the product analysis provision of Specification A788/A788M to obtain a product analysis from a forging representing each heat or multiple heat.

8. Mechanical Properties

8.1 *General Requirements*—Except when otherwise specified in accordance with Supplementary Requirement S2, the material shall conform to the requirements for mechanical properties prescribed in Table 2 when tested in accordance with the latest issue of Test Methods and Definitions A370. ~~The largest obtainable tension test specimen as specified in Test Methods and Definitions or Test Methods A1058 when the M suffix standard has been specified. The largest obtainable tension test specimen as specified in Test Methods and Definitions A370 shall be used, or Test Methods A1058, as applicable, shall be used.~~

8.1.1 Except when otherwise specified in accordance with Supplementary Requirement S2, the longitudinal axis of the specimens shall be parallel to the direction of major working of the forging. For upset-disc forgings, the longitudinal axis of the test specimen shall be in the tangential direction.

8.1.1.1 The longitudinal axis of the specimen shall be located midway between the parallel surfaces of the test extension if added to the periphery of disks or midway between the center and surface of solid forgings. For hollow forgings, the longitudinal axis of the specimens shall be located midway between the center and outer surfaces of the wall. When separately forged test blocks are employed as defined in 8.1.3, the tension test specimens shall be taken from a location that represents the midwall of the heaviest section of the production forgings. When specimens are required from opposite ends, they shall be taken from the diagonal corners of an axial plane.

TABLE 1 Chemical Requirements

| | Composition, % | | |
|-----------------|----------------|-----------|-----------|
| | Grades 1 and 2 | Grade 3 | Grade 4 |
| Carbon, max | 0.30 | 0.35 | 0.30 |
| Manganese | 0.40–1.05 | 0.80–1.35 | 0.80–1.35 |
| Phosphorus, max | 0.025 | 0.025 | 0.025 |
| Sulfur, max | 0.025 | 0.025 | 0.025 |
| Silicon | 0.15–0.35 | 0.15–0.35 | 0.15–0.35 |