



SLOVENSKI STANDARD
SIST EN 13445-2:2021+A1:2023

01-november-2023

Nadomešča:

SIST EN 13445-2:2021

SIST EN 13445-2:2021/A1:2023

Nekurjene tlačne posode - 2. del: Materiali (vključuje dopnilo A1)

Unfired pressure vessels - Part 2: Materials

Unbefeuerte Druckbehälter - Teil 2: Werkstoffe

Réipients sous pression non soumis à la flamme - Partie 2: Matériaux

Ta slovenski standard je istoveten z: EN 13445-2:2021+A1:2023

[SIST EN 13445-2:2021+A1:2023](https://standards.iteh.ai/catalog/standards/sist/1a3289a3-bebd-40de-befb-589c05cbd788/sist-en-13445-2-2021a1-2023)

<https://standards.iteh.ai/catalog/standards/sist/1a3289a3-bebd-40de-befb-589c05cbd788/sist-en-13445-2-2021a1-2023>

ICS:

23.020.32 Tlačne posode Pressure vessels

SIST EN 13445-2:2021+A1:2023 **en,fr,de**

EUROPEAN STANDARD

EN 13445-2:2021+A1

NORME EUROPÉENNE

EUROPÄISCHE NORM

August 2023

ICS 23.020.30

English Version

Unfired pressure vessels - Part 2: Materials

Réceptifs sous pression non soumis à la flamme -
Partie 2: Matériaux

Unbefeuerte Druckbehälter - Teil 2: Werkstoffe

This European Standard was approved by CEN on 24 February 2021 and includes Amendment 1 approved by CEN on 21 February 2023 and Amendment 1 approved by CEN on 13 June 2023.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Türkiye and United Kingdom.

(<https://standards.iteh.ai>)

Document Preview

[SIST EN 13445-2:2021+A1:2023](https://standards.iteh.ai/catalog/standards/sist/1a3289a3-bebd-40de-befb-589c05cbd788/sist-en-13445-2-2021a1-2023)

<https://standards.iteh.ai/catalog/standards/sist/1a3289a3-bebd-40de-befb-589c05cbd788/sist-en-13445-2-2021a1-2023>



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels

Contents

	Page
European foreword.....	4
1 Scope.....	4
2 Normative references.....	6
3 Terms, definitions, symbols and units	8
3.1 Terms and définitions	8
3.2 Symbols and units	10
4 Requirements for materials to be used for pressure-bearing parts	12
4.1 General.....	12
4.2 Special provisions	15
4.2.1 Special properties	15
4.2.2 Design temperature above 20 °C	15
4.2.3 Prevention of brittle fracture	15
4.2.4 Design properties in the creep range	16
4.2.5 Specific requirements for steels for fasteners.....	16
4.3 Technical delivery conditions	17
4.3.1 European Standards.....	17
4.3.2 European Approval for Materials.....	17
4.3.3 Particular material appraisals	17
4.3.4 Clad products.....	17
4.3.5 Welding consumables.....	17
4.4 Marking.....	17
5 Requirements for materials to be used for non-pressure parts	18
Annex A (normative) Grouping system for steels for pressure equipment.....	19
Annex B (normative) Requirements for prevention of brittle fracture at low temperatures.....	21
B.1 General.....	21
B.2 Material selection and impact energy requirements.....	22
B.2.1 Introduction	22
B.2.2 Method 1	22
B.2.3 Method 2	32
B.2.4 Method 3 — Fracture mechanics analysis.....	44
B.3 General test requirements.....	45
B.3.1 General.....	45
B.3.2 Sub-sized specimens	46
B.4 Welds	47
B.4.1 General.....	47
B.4.2 Welding procedure qualification	47
B.4.3 Production test plates	47
B.5 Materials for use at elevated temperatures	47
B.5.1 General.....	47
B.5.2 Materials.....	48
B.5.3 Welding procedure qualification and production test plates.....	48
B.5.4 Start up and shut down procedure	48
B.5.5 Pressure test	48

Annex C (informative) Procedure for determination of the weld creep strength reduction factor (WCSRF)	56
Annex D (informative) Technical delivery conditions for clad products for pressure purposes	57
D.1 Introductory note	57
D.2 Requirements for the material	57
D.3 Requirements for the deposited material	57
D.4 Qualification of the cladding procedure.....	58
D.5 Production tests	59
Annex E (informative) European steels for pressure purposes.....	61
E.1 European Standards for steels and steel components for pressure purposes.....	61
E.2 European standardised steels grouped according to product forms	62
Annex F (normative) Special provisions for materials and components	85
F.1 General	85
F.2 Mechanical properties and technical delivery conditions for fasteners in accordance with EN ISO 3506.....	85
F.2.1 Mechanical properties for austenitic bolts in accordance with EN ISO 3506-1	85
F.2.2 Delivery conditions for austenitic fasteners.....	86
Annex Y (informative) History of EN 13445-2.....	87
Y.1 Differences between EN 13445-2:2014 and EN 13445-2:2021.....	87
Annex ZA (informative) Relationship between this European Standard and the essential requirements of Directive 2014/68/EU aimed to be covered	88
Bibliography	89

iTech Standards
(<https://standards.iteh.ai>)
Document Preview

[SIST EN 13445-2:2021+A1:2023](https://standards.iteh.ai/catalog/standards/sist/1a3289a3-bebd-40de-befb-589c05cbd788/sist-en-13445-2-2021a1-2023)

<https://standards.iteh.ai/catalog/standards/sist/1a3289a3-bebd-40de-befb-589c05cbd788/sist-en-13445-2-2021a1-2023>

EN 13445-2:2021+A1:2023 (E)

European foreword

This document (EN 13445-2:2021+A1:2023) has been prepared by Technical Committee CEN/TC 54 “Unfired pressure vessels”, the secretariat of which is held by BSI.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by February 2024, and conflicting national standards shall be withdrawn at the latest by February 2024.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

This document supersedes A1 EN 13445-2:2021 A1.

This document includes Amendment 1 approved by CEN on 21 February 2023.

The start and finish of text introduced or altered by amendment is indicated in the text by tags A1 A1.

This document has been prepared under a standardisation request addressed to [the relevant ESO] by the European Commission. The Standing Committee of the EFTA States subsequently approves these requests for its Member States.

For the relationship with EU Legislation, see informative Annex ZA, which is an integral part of this document.

The list of all parts in the EN 13445 series can be found on the CEN website.

Although these Parts may be obtained separately, it should be recognised that the Parts are inter-dependant. As such the manufacture of unfired pressure vessels requires the application of all the relevant Parts in order for the requirements of the Standard to be satisfactorily fulfilled.

Corrections to the standard interpretations where several options seem possible are conducted through the Migration Help Desk (MHD). Information related to the Help Desk can be found at <http://www.unm.fr> (en13445@unm.fr). A form for submitting questions can be downloaded from the link to the MHD website. After subject experts have agreed an answer, the answer will be communicated to the questioner. Corrected pages will be given specific issue number and issued by CEN according to CEN Rules. Interpretation sheets will be posted on the website of the MHD.

This document supersedes EN 13445-2:2014. This new edition incorporates the Amendments which have been approved previously by CEN members, and the corrected pages up to Issue 5 without any further technical change. Annex Y provides details of significant technical changes between this European Standard and the previous edition.

Amendments to this new edition may be issued from time to time and then used immediately as alternatives to rules contained herein. It is intended to deliver a new Issue of EN 13445:2021 each year, starting with the precedent as Issue 1, consolidating these Amendments and including other identified corrections.

Any feedback and questions on this document should be directed to the users' national standards body. A complete listing of these bodies can be found on the CEN website.

According to the CEN-CENELEC Internal Regulations, the national standards organisations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

iTeh Standards
(<https://standards.iteh.ai>)
Document Preview

[SIST EN 13445-2:2021+A1:2023](https://standards.iteh.ai/catalog/standards/sist/1a3289a3-bebd-40de-befb-589c05cbd788/sist-en-13445-2-2021a1-2023)

<https://standards.iteh.ai/catalog/standards/sist/1a3289a3-bebd-40de-befb-589c05cbd788/sist-en-13445-2-2021a1-2023>

EN 13445-2:2021+A1:2023 (E)

1 Scope

This document specifies the requirements for steel products used for unfired pressure vessels.

For some metallic materials other than steel, such as spheroidal graphite cast iron, aluminium, nickel, copper, titanium, requirements are or will be formulated in separate parts of this document.

For metallic materials which are not covered by a harmonized material standard and are not likely to be in near future, specific rules are given in this part or the above cited parts of this document.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 764-1:2015+A1:2016, *Pressure equipment — Terminology — Part 1: Pressure, temperature, volume, nominal size*

EN 764-2:2012, *Pressure equipment — Part 2: Quantities, symbols and units*

A1 Deleted reference **A1**

EN 764-4:2014, *Pressure equipment — Part 4: Establishment of technical delivery conditions for metallic materials*

EN 764-5:2014, *Pressure equipment — Part 5: Inspection documentation of metallic materials and compliance with the material specification*

EN 1092-1:2018, *Flanges and their joints — Circular flanges for pipes, valves, fittings and accessories, PN designated — Part 1: Steel flanges*

A1 EN 10028-2:2017 **A1**, *Flat products made of steels for pressure purposes — Part 2: Non-alloy and alloy steels with specified elevated temperature properties*

A1 EN 10028-3:2017 **A1**, *Flat products made of steels for pressure purposes — Part 3: Weldable fine grain steels, normalized*

A1 EN 10028-4:2017 **A1**, *Flat products made of steels for pressure purposes — Part 4: Nickel alloy steels with specified low temperature properties*

A1 EN 10028-5:2017 **A1**, *Flat products made of steels for pressure purposes — Part 5: Weldable fine grain steels, thermomechanically rolled*

A1 EN 10028-6:2017 **A1**, *Flat products made of steels for pressure purposes — Part 6: Weldable fine grain steels, quenched and tempered*

A1 EN 10028-7:2016 **A1**, *Flat products made of steels for pressure purposes — Part 7: Stainless steels*

EN 10204:2004, *Metallic products — Types of inspection documents*

EN 10216-3:2013, *Seamless steel tubes for pressure purposes — Technical delivery conditions — Part 3: Alloy fine grain steel tubes*

EN 10216-4:2013, *Seamless steel tubes for pressure purposes — Technical delivery conditions — Part 4: Non-alloy and alloy steel tubes with specified low temperature properties*

EN 10217-3:2019, *Welded steel tubes for pressure purposes — Technical delivery conditions — Part 3: Electric welded and submerged arc welded alloy fine grain steel tubes with specified room, elevated and low temperature properties* ^{A1}

EN 10217-4:2019 ^{A1}, *Welded steel tubes for pressure purposes — Technical delivery conditions — Part 4: Electric welded non-alloy steel tubes with specified low temperature properties*

EN 10217-6:2019 ^{A1}, *Welded steel tubes for pressure purposes — Technical delivery conditions — Part 6: Submerged arc welded non-alloy steel tubes with specified low temperature properties*

EN 10222-3:2017 ^{A1}, *Steel forgings for pressure purposes — Part 3: Nickel steels with specified low temperature properties*

EN 10222-4:2017+A1:2021 ^{A1}, *Steel forgings for pressures purposes — Part 4: Weldable fine grain steels with high proof strength*

EN 10269:2013, *Steels and nickel alloys for fasteners with specified elevated and/or low temperature properties*

EN 10273:2016 ^{A1}, *Hot rolled weldable steel bars for pressure purposes with specified elevated temperature properties*

EN 12074:2000, *Welding consumables — Quality requirements for manufacture, supply and distribution of consumables for welding and allied processes*

EN 13445-1:2021, *Unfired pressure vessels — Part 1: General*

EN 13445-3:2021, *Unfired pressure vessels — Part 3: Design*

EN 13445-4:2021, *Unfired pressure vessels — Part 4: Fabrication*

EN 13445-5:2021, *Unfired pressure vessels — Part 5: Inspection and testing*

EN 13479:2017 ^{A1}, *Welding consumables — General product standard for filler metals and fluxes for fusion welding of metallic materials*

EN ISO 148-1:2016, *Metallic materials — Charpy pendulum impact test — Part 1: Test method (ISO 148-1:2016)* ^{A1}

EN ISO 204:2018 ^{A1}, *Metallic materials — Uniaxial creep testing in tension — Method of test (ISO 204:2009)*

EN ISO 898-1:2013, *Mechanical properties of fasteners made of carbon steel and alloy steel — Part 1: Bolts, screws and studs with specified property classes — Coarse thread and fine pitch thread (ISO 898-1:2013)*

EN ISO 898-2:2012, *Mechanical properties of fasteners made of carbon steel and alloy steel — Part 2: Nuts with specified property classes — Coarse thread and fine pitch thread (ISO 898-2:2012)*

EN 13445-2:2021+A1:2023 (E)

EN ISO 2566-1:2021, Steel — Conversion of elongation values — Part 1: Carbon and low alloy steels (ISO 2566-1:2021)

EN ISO 2566-2:2021, Steel — Conversion of elongation values — Part 2: Austenitic steels (ISO 2566-2:2021)

EN ISO 3506-1:2020, *Mechanical properties of corrosion-resistant stainless-steel fasteners — Part 1: Bolts, screws and studs with specified grades and property classes* (ISO 3506-1:2020)

EN ISO 3506-2:2020, *Mechanical properties of corrosion-resistant stainless-steel fasteners — Part 2: Nuts with specified grades and property classes* (ISO 3506-2:2020)

EN ISO 6892-1:2019, *Metallic materials — Tensile testing — Part 1: Method of test at room temperature* (ISO 6892-1:2019)

CEN ISO/TR 15608:2017, *Welding — Guidelines for a metallic materials grouping system* (ISO/TR 15608:2017)

3 Terms, definitions, symbols and units

3.1 Terms and definitions

For the purposes of this document, the terms and definitions given in EN 13445-1:2021, EN 764-1:2015+A1:2016, deleted reference and the following apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- IEC Electropedia: available at <http://www.electropedia.org/>
- ISO Online browsing platform: available at <http://www.iso.org/obp>

3.1.1

minimum metal temperature T_M

the lowest temperature determined for any of the following conditions (also see 3.1.2, 3.1.3):

- normal operations;
- start up and shut down procedures;
- possible process upsets, such as flashings of fluid, which have an atmospheric boiling point below 0 °C;
- during pressure or leak testing.

3.1.2

temperature adjustment term T_A

relevant to the calculation of the design reference temperature T_R and is dependent on the calculated tensile membrane stress at the appropriate minimum metal temperature

Note 1 to entry: Values for T_A are given in Table B.2-12.

Note 2 to entry: For tensile membrane stress reference is made to EN 13445-3:2021, Annex C.

3.1.3

design reference temperature T_R

the temperature used for determining the impact energy requirements and is determined by adding the temperature adjustment T_A to the minimum metal temperature T_M :

$$T_R = T_M + T_A$$

3.1.4

impact test temperature T_{KV}

the temperature at which the required impact energy has to be achieved (see B.2).

3.1.5

impact energy KV

the energy absorbed by a sample of material when subjected to a Charpy-V-notch test in accordance with EN ISO 148-1:2016

3.1.6

reference thickness e_B

thickness of a component to be used to relate the design reference temperature T_R of the component with its required impact test temperature T_{KV} , (see Tables B.2-2 to B.2-7 and Figures B.2-1 to B.2-11). For unwelded parts the reference thickness e_B is equal to the nominal wall thickness (including corrosion allowance). For welded parts the reference thickness is defined in Table B.4-1.

3.1.7

weld creep strength reduction factor (WCSRf)

factor to account for creep strength reduction at the weldment

(<https://standards.iteh.ai>)
Document Preview

[SIST EN 13445-2:2021+A1:2023](https://standards.iteh.ai/catalog/standards/sist/1a3289a3-bebd-40de-befb-589c05cbd788/sist-en-13445-2-2021a1-2023)

<https://standards.iteh.ai/catalog/standards/sist/1a3289a3-bebd-40de-befb-589c05cbd788/sist-en-13445-2-2021a1-2023>

EN 13445-2:2021+A1:2023 (E)

3.2 Symbols and units

For the purpose of this part, the symbols and units of EN 764-2:2012 apply together with those given in Table 3.2-1 and Table 3.2-2.

Table 3.2-1 — Quantities for space and time

Quantity	Symbol	Unit
time	t	s, min, h, d, a
frequency	f	Hz
dimension	any Latin letter a	mm
length	l	mm
thickness	e	mm
corrosion allowance	c	mm
diameter	d, D	mm
radius	r, R	mm
area	A, S	mm ²
volume, capacity	V	mm ³ b, c
weight	W	N, kN
density	ρ	kg/mm ³ d
second moment of area	I	mm ⁴
section modulus	Z	mm ³
acceleration	γ	m/s ²
plane angle	any Greek letter a	rad, °
<p>^a Symbols may use any lower-case letter, except for those defined elsewhere in this table.</p> <p>^b Volume may also be given in m³ or L.</p> <p>^c Litre "L" is a non-SI unit which may be used with SI units and their multiples.</p> <p>^d Density may also be given in kg/m³.</p>		

Table 3.2-2 — Mechanical quantities

Quantity ^a	Symbol ^b	Unit
force	F	N
moment	M	N·mm
pressure	p, P	bar ^c , MPa
Temperature	T	°C
linear expansion coefficient	α	$\mu\text{m}/\text{m}^\circ\text{C}$
normal stress	σ	MPa
shear stress	τ	MPa
nominal design stress	f	MPa
tensile strength	R_m	MPa
ultimate tensile strength at temperature T	$R_{m/T}$	MPa
yield strength	R_e	MPa
yield strength at temperature T	$R_{e/T}$	MPa
upper yield strength	R_{eH}	MPa
1 % proof strength	$R_{p1,0}$	MPa
0,2 % proof strength	$R_{p0,2}$	MPa
0,2 % proof strength at temperature T	$R_{p0,2/T}$	MPa
modulus of elasticity	E	MPa
shear modulus	G	MPa
Poisson's ratio	ν	-
strain	ε	%
elongation after fracture	A	%
impact energy	KV	J
hardness	HB, HV	-
Joint coefficient	z	-
safety factor	S	-
Mean 1 % creep strain limit at calculation temperature T and lifetime t	$R_{p1,0/T/t}$	MPa
Mean creep rupture strength at calculation temperature T and lifetime t	$R_{m/T/t}$	MPa
Weld creep strength reduction factor	z_c	-

^a Quantities without a temperature index normally refer to room temperature.

^b Some of these symbols, such as R, f , are not part of ISO 31.

^c "bar" is a non-SI unit which may be used with SI units and their multiples. The unit bar shall be used on nameplates, certificates, drawings, pressure gauges and instrumentation and is always used as a gauge pressure. This is in line with the requirements of the Pressure Equipment Directive 97/23/EC.

EN 13445-2:2021+A1:2023 (E)

4 Requirements for materials to be used for pressure-bearing parts

4.1 General

4.1.1 Materials to be used for pressure-bearing parts shall meet the general requirements of 4.1 and the special provisions of 4.2, if applicable. Materials for pressure bearing parts shall be ordered complying with the technical delivery conditions in 4.3.

Marking of materials for pressure-bearing parts shall be performed in accordance with 4.4.

Materials shall be selected to be compatible with anticipated fabrication steps and to be suitable for the internal fluid and external environment. Both normal operating conditions and transient conditions occurring during fabrication transport, testing and operation shall be taken into account when specifying the materials.

NOTE 1 The requirements of 4.1 and 4.2 should also be fulfilled when technical delivery conditions are developed for European material standards, European approval of materials or particular material appraisals.

NOTE 2 When technical delivery conditions for pressure-bearing parts are developed, the structure and requirements of EN 764-4:2014 should be met. Exceptions should be technically justified.

The materials shall be grouped in accordance with A1 CEN ISO/TR 15608:2017 A1 to relate manufacturing and inspection requirements to generic material types.

NOTE 3 Materials have been allocated into these groups in accordance with their chemical composition and properties in view of manufacture and heat treatment after welding.

4.1.2 Materials for pressure-bearing parts compliant with the requirements of this document shall be accompanied by inspection documents in accordance with EN 10204:2004. Certificate of specific control (3.1 or 3.2 certificate) shall be required for all steels if Design by Analysis – Direct Route according to Annex B of EN 13445-3:2021 is used.

The type of inspection document shall be in accordance with EN 764-5:2014 and include a declaration of compliance to the material specification.

4.1.3 The materials shall be free from surface and internal defects which can impair their intended usability.

4.1.4 Steels shall have a specified minimum elongation after fracture measured on a gauge length

$$L_o = 5,65 \sqrt{S_o} \quad (4.1-1)$$

where

S_o is the original cross sectional area within the gauge length.

The minimum elongation after fracture in any direction shall be ≥ 14 %.

When measured on a gauge length other than that stated here, the minimum elongation after fracture shall be determined by converting the elongation in accordance with

— A1 EN ISO 2566-1:2021 A1 for carbon and low alloy steels;