
Usnje - Kemijski preskusi za določevanje nekaterih azo barvil na barvanem usnju - 1. del: Določevanje nekaterih aromatskih aminov, izvirajočih iz azo barvil (ISO/DIS 17234-1:2023)

Leather - Chemical tests for the determination of certain azo colourants in dyed leathers - Part 1: Determination of certain aromatic amines derived from azo colourants (ISO/DIS 17234-1:2023)

Leder - Chemische Prüfungen zur Bestimmung bestimmter Azofarbstoffe in gefärbten Ledern - Teil 1: Bestimmung bestimmter aromatischer Amine aus Azofarbstoffen (ISO/DIS 17234-1:2023)

Cuir - Essais chimiques pour le dosage de certains colorants azoïques dans les cuirs teints - Partie 1: Dosage de certaines amines aromatiques dérivées des colorants azoïques (ISO/DIS 17234-1:2023)

Ta slovenski standard je istoveten z: prEN ISO 17234-1

ICS:

59.140.30	Usnje in krzno	Leather and furs
71.040.40	Kemijska analiza	Chemical analysis

oSIST prEN ISO 17234-1:2023**en,fr,de**

DRAFT INTERNATIONAL STANDARD

ISO/DIS 17234-1

IULTCS

IULTCS

Secretariat: ISO

 Voting begins on:
 2023-09-26

 Voting terminates on:
 2023-12-19

Leather — Chemical tests for the determination of certain azo colourants in dyed leathers —

Part 1:

Determination of certain aromatic amines derived from azo colourants

Cuir — Essais chimiques pour le dosage de certains colorants azoïques dans les cuirs teints —

Partie 1: Dosage de certaines amines aromatiques dérivées des colorants azoïques

ICS: 59.140.30

iTeh Standards
 (<https://standards.iteh.ai>)
 Document Preview

[oSIST prEN ISO 17234-1:2023](https://standards.iteh.ai/catalog/standards/sist/f5d875eb-2329-45d5-9dd9-bbcb681cc7df/osist-pren-iso-17234-1-2023)

<https://standards.iteh.ai/catalog/standards/sist/f5d875eb-2329-45d5-9dd9-bbcb681cc7df/osist-pren-iso-17234-1-2023>

This document is circulated as received from the committee secretariat.

THIS DOCUMENT IS A DRAFT CIRCULATED FOR COMMENT AND APPROVAL. IT IS THEREFORE SUBJECT TO CHANGE AND MAY NOT BE REFERRED TO AS AN INTERNATIONAL STANDARD UNTIL PUBLISHED AS SUCH.

IN ADDITION TO THEIR EVALUATION AS BEING ACCEPTABLE FOR INDUSTRIAL, TECHNOLOGICAL, COMMERCIAL AND USER PURPOSES, DRAFT INTERNATIONAL STANDARDS MAY ON OCCASION HAVE TO BE CONSIDERED IN THE LIGHT OF THEIR POTENTIAL TO BECOME STANDARDS TO WHICH REFERENCE MAY BE MADE IN NATIONAL REGULATIONS.

RECIPIENTS OF THIS DRAFT ARE INVITED TO SUBMIT, WITH THEIR COMMENTS, NOTIFICATION OF ANY RELEVANT PATENT RIGHTS OF WHICH THEY ARE AWARE AND TO PROVIDE SUPPORTING DOCUMENTATION.

ISO/CEN PARALLEL PROCESSING



Reference numbers
 ISO/DIS 17234-1:2023(E)
 IULTCS/IUC 20-1:2023(E)

© ISO 2023

iTeh Standards
(<https://standards.iteh.ai>)
Document Preview

[oSIST prEN ISO 17234-1:2023](https://standards.iteh.ai/catalog/standards/sist/f5d875eb-2329-45d5-9dd9-bbcb681cc7df/osist-pren-iso-17234-1-2023)

<https://standards.iteh.ai/catalog/standards/sist/f5d875eb-2329-45d5-9dd9-bbcb681cc7df/osist-pren-iso-17234-1-2023>



COPYRIGHT PROTECTED DOCUMENT

© ISO 2023

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Contents

	Page
Foreword.....	iv
1 Scope.....	1
2 Normative references.....	1
3 Terms and definitions.....	1
4 General.....	1
5 Principle.....	3
6 Safety precautions.....	3
7 Apparatus.....	3
8 Reagents.....	4
9 Sampling and preparation of samples.....	5
10 Procedure.....	5
10.1 Degreasing.....	5
10.2 Reductive cleavage.....	5
10.3 Liquid-liquid extraction.....	6
10.4 Check of the analytical system.....	6
11 Chromatographic analyses.....	6
12 Calibration.....	6
13 Evaluation.....	7
13.1 Calculation of amine in the sample.....	7
13.2 Reliability of the method.....	7
14 Test report.....	7
Annex A (informative) Chromatographic analyses.....	9
Annex B (informative) Reliability of the method.....	13
Annex C (informative) Assessment guide — Interpretation of analytical results.....	14
Annex D (informative) Procedure for liquid/liquid extraction without diatomaceous earth.....	20
Annex E (normative) Colorants - Method for the determination of certain aromatic amines.....	23
Annex F (normative) Leather and colorants Method for the determination of free aromatic amines.....	24
Bibliography.....	27

ISO/DIS 17234-1:2023(E)
IULTCS/IUC 20-1:2023(E)

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see www.iso.org/iso/foreword.html.

This document was prepared by the Chemical Test Commission of the International Union of Leather Technologists and Chemists Societies (IUC Commission, IULTCS) in collaboration with the European Committee for Standardization (CEN) Technical Committee CEN/TC 289, *Leather*, the secretariat of which is held by UNI, in accordance with the Agreement on technical cooperation between ISO and CEN (Vienna Agreement). This method is technically similar to the method in IUC 20, which was declared an official method at the IULTCS Delegates meeting on 31st May 2003 in Cancun, Mexico.

IULTCS, originally formed in 1897, is a world-wide organization of professional leather societies to further the advancement of leather science and technology. IULTCS has three Commissions, which are responsible for establishing international methods for the sampling and testing of leather. ISO recognizes IULTCS as an international standardizing body for the preparation of test methods for leather.

This fourth edition cancels and replaces the third edition (ISO 17234-1:2020), which has been technically revised.

The changes to the previous edition are as follows:

- two new normative [Annexes E](#) and [F](#) are added.

A list of all parts in the ISO 17234 series can be found on the ISO website.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

Leather — Chemical tests for the determination of certain azo colourants in dyed leathers —

Part 1: Determination of certain aromatic amines derived from azo colourants

1 Scope

This document specifies a method for determining the use of certain azo colourants which can release certain aromatic amines.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 2418, *Leather — Chemical, physical and mechanical and fastness tests — Sampling location*

ISO 3696, *Water for analytical laboratory use — Specification and test methods*

ISO 4044, *Leather — Chemical tests — Preparation of chemical test samples*

ISO 17234-2, *Leather — Chemical tests for the determination of certain azo colorants in dyed leathers — Part 2: Determination of 4-aminoazobenzene*

3 Terms and definitions oSIST prEN ISO 17234-1:2023

No terms and definitions are listed in this document.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <https://www.electropedia.org/>

4 General

Certain azo colourants can release, by reductive cleavage of azo group(s), one or more of the aromatic amines listed in EU Regulation 1907/2006, Annex XVII, Appendix 8^[2] and GB 20400-2006^[3] (see [Table 1](#)).

ISO/DIS 17234-1:2023(E)
IULTCS/IUC 20-1:2023(E)
Table 1 — Aromatic amines listed in EU Regulation 1907/2006, Annex XVII, Appendix 8^[2] and GB 20400-2006^[3]

No.	CAS number	Index number	EC number	Substances
1	92-67-1	612-072-00-6	202-177-1	biphenyl-4-ylamine 4-aminobiphenyl xenylamine
2	92-87-5	612-042-00-2	202-199-1	benzidine
3	95-69-2	612-196-00-0	202-441-6	4-chloro- <i>o</i> -toluidine
4	91-59-8	612-022-00-3	202-080-4	2-naphthylamine
5 ^a	97-56-3	611-006-00-3	202-591-2	<i>o</i> -aminoazotoluene 4-amino-2',3-dimethylazobenzene 4- <i>o</i> -tolylazo- <i>o</i> -toluidine
6 ^a	99-55-8	612-210-00-5	202-765-8	5-nitro- <i>o</i> -toluidine 2-amino-4-nitrotoluene
7	106-47-8	612-137-00-9	203-401-0	4-chloroaniline
8	615-05-4	612-200-00-0	210-406-1	4-methoxy- <i>m</i> -phenylenediamine 2,4-diaminoanisole
9	101-77-9	612-051-00-1	202-974-4	4,4'-methylenedianiline 4,4'-diaminodiphenylmethane
10	91-94-1	612-068-00-4	202-109-0	3,3'-dichlorobenzidine 3,3'-dichlorobiphenyl-4,4'-ylenedi- amine
11	119-90-4	612-036-00-X	204-355-4	3,3'-dimethoxybenzidine <i>o</i> -dianisidine
12	119-93-7	612-041-00-7	204-358-0	3,3'-dimethylbenzidine 4,4'-bi- <i>o</i> -toluidine
13	838-88-0	612-085-00-7	212-658-8	4,4'-methylenedi- <i>o</i> -toluidine
14	120-71-8	612-209-00-X	204-419-1	6-methoxy- <i>m</i> -toluidine <i>p</i> -cresidine
15	101-14-4	612-078-00-9	202-918-9	4,4'-methylene-bis-(2-chloro-aniline) 2,2'-dichloro-4,4'-methylene-dianiline
16	101-80-4	612-199-00-7	202-977-0	4,4'-oxydianiline
17	139-65-1	612-198-00-1	205-370-9	4,4'-thiodianiline
18	95-53-4	612-091-00-X	202-429-0	<i>o</i> -toluidine 2-aminotoluene
19	95-80-7	612-099-00-3	202-453-1	4-methyl- <i>m</i> -phenylenediamine 2,4-toluylendiamine 2,4-diaminotoluene
20	137-17-7	612-197-00-6	205-282-0	2,4,5-trimethylaniline
21	90-04-0	612-035-00-4	201-963-1	<i>o</i> -anisidine 2-methoxyaniline
22 ^b	60-09-3	611-008-00-4	200-453-6	4-aminoazobenzene
23 ^c	95-68-1	612-027-00-0	202-440-0	2,4-xylidine 2,4-dimethylbenzene-1-amine

^a The CAS-numbers 97-56-3 (no. 5) and 99-55-8 (no. 6) are further reduced to CAS-numbers 95-53-4 (no. 18) and 95-80-7 (no. 19).

^b Azo colourants that are able to form 4-aminoazobenzene generate under the condition of this method aniline CAS-number 62-53-3) and 1,4-phenylenediamine (CAS number 106-50-3). The presence of these colourants shall be tested using ISO 17234-2.

^c Additional aromatic amines in GB 20400-2006.

Table 1 (continued)

No.	CAS number	Index number	EC number	Substances
24 ^c	87-62-7	612-161-00-X	201-758-7	2,6-xylydine 2,6-dimethylbenzene-1-amine
<p>^a The CAS-numbers 97-56-3 (no. 5) and 99-55-8 (no. 6) are further reduced to CAS-numbers 95-53-4 (no. 18) and 95-80-7 (no. 19).</p> <p>^b Azo colourants that are able to form 4-aminoazobenzene generate under the condition of this method aniline CAS-number 62-53-3) and 1,4-phenylenediamine (CAS number 106-50-3). The presence of these colourants shall be tested using ISO 17234-2.</p> <p>^c Additional aromatic amines in GB 20400-2006.</p>				

5 Principle

After degreasing, the leather sample is treated with sodium dithionite in an aqueous buffer solution (pH 6) at 70 °C in a closed vessel. The amines released in the process of reductive cleavage are transferred to a *t*-butyl methyl ether (8.5) phase by means of liquid-liquid extraction using diatomaceous earth columns. The *t*-butyl methyl ether (8.5) extract is then concentrated under mild conditions in a rotary vacuum evaporator and the residue is dissolved in a suitable solvent, depending on the method used to determine the amines (see Annex A).

Determination of the amines is performed by means of high-performance liquid chromatography (HPLC) using a diode array detector (DAD) or mass selective detector (HPLC-MS), capillary gas chromatography with a mass selective detector (GC-MS) or by capillary electrophoresis with a diode array detector (CE-DAD), or qualitatively with thin layer chromatography (TLC, HPTLC).

The amines shall be identified by means of at least two different chromatographic separation methods in order to avoid any possible misinterpretations caused by interfering substances (such as position isomers of the amines to be identified) and hence any incorrect statements. Amine quantification shall be performed by HPLC-DAD or GC-MS.

A screening method using liquid-liquid extraction without diatomaceous earth columns is described in Annex D.

If it is required to analyse the colorant itself, the method in Annex E shall be used.

If it is required to analyse for residual free aromatic amines in the leather or colorant, the method in Annex F shall be used.

6 Safety precautions

WARNING — The aromatic amines listed in Clause 4 are classified as substances known to be or suspected to be human carcinogens.

6.1 It is the user's responsibility to use safe and proper techniques when handling materials in this test method. Consult manufacturers for specific details, such as material safety data sheets and other recommendations.

6.2 Good laboratory practice should be followed. Wear safety glasses in all laboratory areas and a dust respirator and single-use gloves while handling powder colourants and aromatic amines.

6.3 National and local safety regulations can apply.

7 Apparatus

The usual laboratory equipment and, in particular, the following:

ISO/DIS 17234-1:2023(E)
IULTCS/IUC 20-1:2023(E)

- 7.1 Suitable reaction vessel**, of temperature-resistant glass with a gas-tight closure.
- 7.2 Suitable heating system**, at (70 ± 2) °C.
- 7.3 Polypropylene or glass column**, inside diameter 25 mm to 30 mm, length 130 mm to 150 mm, packed with 20 g of diatomaceous earth, fitted with glass fibre filter at the outlet.
- The diatomaceous earth columns are either bought pre-packed and used as is, or 20 g of diatomaceous earth can be packed into a glass or polypropylene column of the dimensions given.
- 7.4 Vacuum rotary evaporator with vacuum control and water bath.**
- 7.5 Pipettes**, in required sizes or variables pipettes.
- 7.6 Ultrasonic bath with thermostat.**
- 7.7 Chromatographic equipment**, selected from the following:
- 7.7.1 High-performance liquid chromatography (HPLC)** and DAD or MS.
- 7.7.2 Capillary gas chromatography (GC)**, with MS.
- 7.7.3 Capillary electrophoresis (CE)**, with DAD.
- 7.7.4 Thin layer chromatography (TLC) or high-performance thin layer chromatography (HPTLC).**

NOTE A description of the chromatographic equipment (7.7) is given in [Annex A](#).

8 Reagents

Unless otherwise specified, analytical grade chemicals shall be used.

- 8.1 *n*-hexane.**
- 8.2 Citrate buffer solution**, 0,06 mol/l, pH = 6, preheated to (70 ± 2) °C.
- 8.3 Aqueous sodium dithionite solution**, $\rho = 200$ mg/ml¹⁾, freshly prepared, to be used immediately after resting for 1 h in a closed vessel.
- 8.4 Sodium hydroxide aqueous solution**, a mass fraction of 40 %.
- 8.5 *t*-butyl methyl ether.**
- 8.6 Methanol.**
- 8.7 Acetonitrile.**
- 8.8 Amines**, listed in [Table 1](#) (highest available purity standard).

1) ρ = mass concentration.

8.9 Standard solutions.

8.9.1 Stock solution of the amines (8.8), 400 µg/ml in ethyl acetate for TLC.

8.9.2 Stock solution of the amines (8.8), 200 µg/ml of each amine in an appropriate solvent.

NOTE Acetonitrile is an appropriate solvent for this stock solution, resulting in good stability of amines.

8.9.3 Standard solution for amine process control, 30 µg amine per millilitre solvent, freshly prepared from stock solutions (8.9.1 or 8.9.2) depending on the analytical method

8.9.4 Internal standard in solution (IS), $\rho = 10$ µg of IS/ml of *t*-butyl methyl ether (8.5).

In the case of GC-MS analysis, one of the following internal standards can be used:

- IS1: naphthalene-d8, CAS no.: 1146-65-2;
- IS2: 2,4,5-trichloroaniline (TCA), CAS no.: 636-30-6;
- IS3: anthracene-d10, CAS no.: 1719-06-8.

8.10 Water, Grade 3 according to ISO 3696.

9 Sampling and preparation of samples

The leather shall be sampled in accordance with ISO 2418 and prepared in accordance with ISO 4044. If sampling in accordance with ISO 2418 is not possible (e.g. in the case of leathers from finished products such as shoes or garments), details about sampling shall be given in the test report. Any traces of adhesives shall be removed mechanically.

In the case of leather patchwork fabrics with varicoloured patterns, the various colours shall be taken into account separately as far as possible. For commodities consisting of various leather qualities, specimens of the various qualities shall be analysed separately.

For the analytical procedure, accurately weigh a representative specimen of 1,0 g of this leather sample in the reaction vessel (7.1).

10 Procedure

10.1 Degreasing

Treat 1,0 g of the leather in a closed 50 ml vessel (7.1) with 40 ml *n*-hexane (8.1) in an ultrasonic bath (7.6) at (40 ± 2) °C for 40 min.

Decant the *n*-hexane layer from the leather specimen. Any loss of leather particles during decanting shall be avoided. Evaporate the residual *n*-hexane at least overnight in the open vessel.

10.2 Reductive cleavage

Add a quantity of 15 ml buffer solution (8.9) preheated to (70 ± 2) °C to the sample.

Close the reaction vessel tightly and treat for (30 ± 1) min at (70 ± 2) °C.

Subsequently, add 3 ml aqueous sodium dithionite solution (8.3) for the reductive cleavage of the azo groups to the reaction vessel, then shake vigorously and immediately keep at (70 ± 2) °C for another (30 ± 1) min. Then cool to room temperature (20 °C to 25 °C) within 2 min with a cooling mixture of ice, water and salt.