

FINAL  
DRAFT

INTERNATIONAL  
STANDARD

ISO/FDIS  
4518

ISO/TC 107

Secretariat: KATS

Voting begins on:  
2020-12-30

Voting terminates on:  
2021-02-24

---

---

## Metallic coatings — Measurement of coating thickness — Profilometric method

*Revêtements métalliques — Mesurage de l'épaisseur — Méthode profilométrique*

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

[ISO/FDIS 4518](https://standards.iteh.ai/catalog/standards/sist/ff4dbaad-b20c-4d86-b895-4528dc1133d/iso-fdis-4518)

<https://standards.iteh.ai/catalog/standards/sist/ff4dbaad-b20c-4d86-b895-4528dc1133d/iso-fdis-4518>

RECIPIENTS OF THIS DRAFT ARE INVITED TO SUBMIT, WITH THEIR COMMENTS, NOTIFICATION OF ANY RELEVANT PATENT RIGHTS OF WHICH THEY ARE AWARE AND TO PROVIDE SUPPORTING DOCUMENTATION.

IN ADDITION TO THEIR EVALUATION AS BEING ACCEPTABLE FOR INDUSTRIAL, TECHNOLOGICAL, COMMERCIAL AND USER PURPOSES, DRAFT INTERNATIONAL STANDARDS MAY ON OCCASION HAVE TO BE CONSIDERED IN THE LIGHT OF THEIR POTENTIAL TO BECOME STANDARDS TO WHICH REFERENCE MAY BE MADE IN NATIONAL REGULATIONS.

**ISO/CEN PARALLEL PROCESSING**



Reference number  
ISO/FDIS 4518:2020(E)

© ISO 2020

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

ISO/FDIS 4518

<https://standards.iteh.ai/catalog/standards/sist/ff4dbaad-b20c-4d86-b895-4528dc1133d/iso-fdis-4518>



**COPYRIGHT PROTECTED DOCUMENT**

© ISO 2020

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office  
CP 401 • Ch. de Blandonnet 8  
CH-1214 Vernier, Geneva  
Phone: +41 22 749 01 11  
Email: [copyright@iso.org](mailto:copyright@iso.org)  
Website: [www.iso.org](http://www.iso.org)

Published in Switzerland

# Contents

	Page
Foreword .....	iv
<b>1 Scope .....</b>	<b>1</b>
<b>2 Normative references .....</b>	<b>1</b>
<b>3 Terms and definitions .....</b>	<b>1</b>
<b>4 Principle .....</b>	<b>1</b>
<b>5 Instrumentation — Operational parameters and measurement characteristics .....</b>	<b>1</b>
5.1 Types of profile recording instruments .....	1
5.2 Stylus instruments .....	2
5.3 Inductive measuring probes or displacement sensors .....	2
5.4 Optical profilometers .....	3
<b>6 Factors relating to accuracy .....</b>	<b>4</b>
6.1 Profile record .....	4
6.2 Vertical magnification (only for instruments with chart recorders) .....	4
6.3 Graphical measurements .....	4
6.4 Applied force (only for profilometers with stylus) .....	4
6.5 Stylus diameter and surface roughness .....	4
6.6 Surface roughness .....	4
6.7 Vibrations .....	5
6.8 Surface curvature .....	5
6.9 Cleanliness .....	5
6.10 Temperature .....	5
6.11 Step configuration .....	5
6.12 Datum reference (only for profilometers with stylus) .....	5
6.13 Calibration .....	5
<b>7 Calibration .....</b>	<b>5</b>
<b>8 Measuring procedure .....</b>	<b>6</b>
8.1 Preparation of step .....	6
8.2 Recording of profiles .....	7
8.3 Measurement of thickness .....	7
8.4 Measurement accuracy .....	7
<b>9 Test report .....</b>	<b>7</b>
<b>Bibliography .....</b>	<b>8</b>

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see [www.iso.org/directives](http://www.iso.org/directives)).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see [www.iso.org/patents](http://www.iso.org/patents)).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see [www.iso.org/iso/foreword.html](http://www.iso.org/iso/foreword.html).

This document was prepared by Technical Committee ISO/TC 107, *Metallic and other inorganic coatings*, in collaboration with the European Committee for Standardization (CEN) Technical Committee CEN/TC 262, *Metallic and other inorganic coatings, including for corrosion protection and corrosion testing of metals and alloys*, in accordance with the Agreement on technical cooperation between ISO and CEN (Vienna Agreement).

This second edition cancels and replaces the first edition (ISO 4518:1980), which has been technically revised. The main changes compared with the previous edition are as follows:

- optical profilometers such as confocal microscopes or interference microscopes have been added as alternatives to stylus instruments for the measurement of the step height;
- a description of more modern stylus profilometers has been added.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at [www.iso.org/members.html](http://www.iso.org/members.html).

# Metallic coatings — Measurement of coating thickness — Profilometric method

## 1 Scope

This document specifies a method for the measurement of metal coating thickness by first forming a step between the surface of the coating and the surface of its substrate and then measuring the step height using a profile recording instrument. It covers the instrumentation characteristics and the procedure appropriate to this specific application of profilometric methods.

The method is applicable to the measurement of thicknesses of metal coatings from 0,01 µm to 1 000 µm on flat surfaces and, if appropriate precautions are taken, on cylindrical surfaces. It is highly suitable for the measurement of minute thicknesses but, for thicknesses of less than 0,01 µm, surface flatness and surface smoothness are very critical and, accordingly, the method is not suitable for use down to the lowest level of measurement usual for electronic stylus instruments. The method is suitable for measuring coating thicknesses when preparing coating thickness reference standards.

## 2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 2177, *Metallic coatings — Measurement of coating thickness — Coulometric method by anodic dissolution*

<https://standards.iteh.ai/catalog/standards/sist/f4d8baad-b20c-4d86-b895-4528dc1133d/iso-fdis-4518>

## 3 Terms and definitions

No terms and definitions are listed in this document.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <http://www.electropedia.org/>

## 4 Principle

Formation of a step either by dissolving part of the coating (acceptance testing) or by masking a portion of the substrate prior to coating (production inspection). Measurement of the height of the step using a profile recording instrument.

## 5 Instrumentation — Operational parameters and measurement characteristics

### 5.1 Types of profile recording instruments

Any of the following three types may be used:

- a) contact stylus instruments, known as “surface analysers” and “surface profile recorders”, generally used to measure surface roughness but which, for the purposes of this document, are used to record the profile of a step;

- b) inductive measuring probe or displacement sensor (incremental or absolute) capable of recording the profile of a step;
- c) optical profilometers, i.e. white-light interference microscopes or confocal microscopes (ordinary, laser scanning or chromatic), which are generally used to measure surface topographic information and 3D surface roughness but which, for the purposes of this document, are used to record and evaluate the profile of a step.

Stylus instruments can have a greater utility, being suitable for roughness and form measurements, while measuring probes or displacement sensors can be simpler in construction. Stylus instruments designed only for roughness generally cover a range of coating thicknesses from 0,005 µm to 250 µm. Other contact instruments cover up to approximately 1 000 µm.

## 5.2 Stylus instruments

These instruments are used to record the profile of a surface and have the following components.

**5.2.1 A pick-up with a conical or pyramidal stylus**, having an included angle of 1,05 rad (60°) or 1,57 rad (90°) and a nominal tip radius, in the direction of the traverse, of 2 µm, 5 µm, 10 µm or 50 µm. The force of contact on the test surface shall not exceed the appropriate value given in [Table 1](#).

**Table 1 — Maximum force on stylus**

Nominal value of stylus tip radius, µm	2	5	10	50 <sup>b</sup>
Maximum static force at the mean level of the stylus, mN <sup>a</sup>	0,7	4	16	10 <sup>b</sup>
<sup>a</sup> 1 mN ≈ 0,1 gf. <sup>b</sup> Values useful for low-hardness metals such as tin.				

**5.2.2 A traverse unit**, that moves the pick-up relative to a datum skid or, in those cases where the skid can result in damage to the surface or introduce distortion of the step to be measured, a datum surface having nominal form of the profile.

**5.2.3 A component that unites the amplifier and the recording instrument**, in an electronic controller and a computer software, which can display and print the digitized data at any desirable vertical and horizontal magnification (zoom).

Old-fashioned instruments with purely analogous measuring value processing are equipped with an amplifier with firm amplifying steps and a recording instrument that plots the amplified values ( $V_v$ ) over the amplified values of the horizontal movement of the traverse unit ( $V_h$ ).

### 5.2.4 Profile recording instruments with the following properties:

- traverse length: 1 mm to 100 mm;
- range of thickness measurement: 0,005 µm to 250 µm;
- height resolution (dependent on the range of measurement): 0,000 5 µm to 1 µm.

## 5.3 Inductive measuring probes or displacement sensors

**5.3.1** The design of inductive measuring probes or displacement sensors is very similar to that of the electronic stylus instruments (see [5.2](#)), the principal difference being that the large-radius stylus does not plot the microprofile of the surface.

**5.3.2** Typical examples of the operational parameters and the measuring characteristics of an inductive measuring probe or a displacement sensor are as follows.

Operational parameters:

- a linearity of not less than 0,5 %;
- a table providing a rectilinear motion to the surface to be traversed;
- suitable amplifiers;
- using the following operational parameters:
  - radius of stylus: 250  $\mu\text{m}$ ;
  - maximum magnification:  $\times 50\,000$ ;
  - static stylus force: 0,12 N.

Measurement characteristics:

- traverse length: 100 mm;
- range of thickness measurement: 1  $\mu\text{m}$  to 1 000  $\mu\text{m}$ ;
- height resolution (dependent on the range of measurement): 0,02  $\mu\text{m}$  to 20  $\mu\text{m}$ .

## 5.4 Optical profilometers

Optical profilometers are based on the technology of optical microscopes, use similar objectives and thus have similar lateral resolution but, due to the interference or confocal technique and digital data evaluation, they have a good height resolution.

Typical examples of the measuring characteristics of optical profilometers are as follows.

For white-light interference microscopes:

- range of thickness measurement:  $10 \times R_a$  to 50 % of the maximum measurable height difference (depending on the instrument);
- height resolution: 0,5 nm.

For confocal microscopy:

- range of thickness measurement:  $10 \times R_a$  to 50 % of the maximum measurable height difference (depending on the instrument);
- height resolution: 0,5 nm.

For laser-scanning confocal microscopes:

- range of thickness measurement:  $10 \times R_a$  to 50 % of the maximum measurable height difference (depending on the instrument);
- height resolution: 0,5 nm.

For chromatic confocal microscopes:

- range of thickness measurement:  $10 \times R_a$  to 50 % of the maximum measurable height difference (e.g. 0,15 mm or 0,5 mm);
- the height resolution depends on the selected sensor and the measurable height difference: the larger the working range, the worse the resolution.

## 6 Factors relating to accuracy

### 6.1 Profile record

Because the thickness measurement is made from the recorded profile, errors will arise if the recording does not give a faithful reproduction of the step at a suitable magnification. Inaccurate recordings can reflect the quality or improper adjustment of the recording instrument.

### 6.2 Vertical magnification (only for instruments with chart recorders)

If the vertical magnification is too low, measurement precision will be poor. It should be set to take maximum advantage of the chart width.

### 6.3 Graphical measurements

If the test surface is not parallel to the reference (datum) surface, the recording of the horizontal surface is sloped with respect to the chart grid. The vertical portion of the step is also sloped but it can still be vertical on the chart grid, depending on the vertical and horizontal magnifications, on the radius of the stylus and finally on the height of the step (i.e. thickness). When the profile is sloped, a common error is to measure the perpendicular distance between the mean lines of the profile without correcting for the differences between the horizontal and vertical magnifications.

Modern instruments with software-based evaluation can correct for such effects.

To avoid these errors or additional mathematical calculations, the datum and test surfaces shall be parallel. This may be accomplished using an appropriate jig or fitting.

### 6.4 Applied force (only for profilometers with stylus)

If the force on the stylus is too high, the stylus produces a scratch or deformation that can introduce a measurement error. The force should be kept to a minimum and generally should not exceed the appropriate values given in [Table 1](#).

### 6.5 Stylus diameter and surface roughness

If a small diameter stylus is used on a rough surface, the step height can be difficult to measure accurately because of poor definition of the extremes of the recorded step. A large diameter stylus minimizes this difficulty.

If the substrate and coating surfaces are of different roughness, the recorded step profile can be misleading to the extent that the stylus rides the high spots more on one surface than the other because of different peak to peak spacings. A small diameter stylus tends to reduce this error.

A small diameter stylus equipped with an electronic filter to smooth out the profile can be advantageous but can round the corners of the step profile.

### 6.6 Surface roughness

In principle, the roughness of a recorded substrate (peak to valley height of the surface profile) should not exceed 10 % of the step height.

When optical profilometers are used, the lateral dimensions of the surface profile elements (e.g. RSm) shall exceed a few times the wavelength of the light, otherwise a plane cannot be determined.



## 6.7 Vibrations

Vibrations can cause irregularities or noise in the recorded profile, making accurate measurement difficult. This effect should be minimized by insulating the equipment from vibrations. In principle, the peak to valley height should not exceed 10 % of the step height.

## 6.8 Surface curvature

Surface curvature can interfere with accurate measurement of the recorded step profile. The measurement should be carried out on as flat a surface as practicable. If it must be carried out on a curved surface, the traverse of the stylus should be in the direction of least curvature, e.g. parallel to the axis of a cylinder. (This implies that the step should be parallel to the direction of maximum curvature.)

## 6.9 Cleanliness

Any foreign matter such as dirt, grease and corrosion products can lead to erroneous measurements. The surfaces to be measured should be cleaned, and the laboratory air should be reasonably free of dust and dirt.

## 6.10 Temperature

Temperature variations can affect the measurement. Therefore, the temperature should be uniform and reasonably stable.

## 6.11 Step configuration

A poorly defined step (e.g. excessive rounding of edges) can make an accurate measurement difficult by obscuring the levels of the upper and lower portions of the steps. The steps should be reasonably well defined.

<https://standards.iteh.ai/catalog/standards/sist/f4dbaad-b20c-4d86-b895-4528dc1133d/iso-fdis-4518>

## 6.12 Datum reference (only for profilometers with stylus)

The stylus holder rides on a datum skid or on a datum surface, and the vertical motion of the stylus relative to the datum skid or surface is recorded. The datum skid is a rounded surface that rides over the surface of the test specimen, and the datum surface is part of the equipment independent of the test specimen.

The faithfulness of a recording will depend on the quality (smoothness and straightness) of the datum reference.

## 6.13 Calibration

The thickness measurement will be not better than the uncertainty of the instrument calibration and that of the step height standard used to calibrate the instrument. The calibration can change, and the frequency with which calibration is required has to be learned by experience. Though the instrument can be carefully calibrated, an error of 2 % can exist because of nonlinearity of the instrument response. To minimize this error, the instrument can be calibrated at two points closely bracketing the step height to be measured.

## 7 Calibration

**7.1** Calibrate the instrument in accordance with the manufacturer's instructions, paying appropriate attention to the factors listed in [Clause 6](#).