



Designation: ~~D6336-98~~ (Reapproved 2004) Designation: D6336 – 11

Standard Practice for Evaluation of Flushing Vehicles for Pigment Wetting Using a Vacuum Modified Sigma Blade Mixer¹

This standard is issued under the fixed designation D6336; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This practice covers guidelines for the evaluations of flushing vehicles for pigment dispersion using a vacuum modified sigma blade mixer, or vacuum flusher.

1.2 The values stated in SI units are to be regarded as the standard. The values given in parentheses are for information only.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 ASTM Standards:²

D280 Test Methods for Hygroscopic Moisture (and Other Matter Volatile Under the Test Conditions) in Pigments

D387 Test Method for Color and Strength of Chromatic Pigments with a Mechanical Muller

D1316 Test Method for Fineness of Grind of Printing Inks By the NPIRI Grindometer

D2066 Test Methods for Relative Tinting Strength of Paste-Type Printing Ink Dispersions

D2067 Test Method for Coarse Particles in Printing Ink Dispersions

D4017 Test Method for Water in Paints and Paint Materials by Karl Fischer Method

D4040 Test Method for Rheological Properties of Paste Printing and Vehicles by the Falling-Rod Viscometer

D4361 Test Method for Apparent Tack of Printing Inks and Vehicles by a Three-Roller Tackmeter

3. Terminology

3.1 Definitions of Terms Specific to This Standard:

3.1.1 *additives, n*—various materials that are used in relatively small quantities to condition the pigment or vehicle.

3.1.2 *break, n*—the action that takes place when water is separated from the pigment in a presscake.

3.1.3 *flushed color, n*—a color base in paste form prepared by flushing.

3.1.4 *flusher, n*—a mixing device that has two sigma shaped agitator blades parallel to each other, turning in opposing directions at different speeds.

3.1.4.1 *Discussion*—The mixing action of a flusher is that of kneading.

3.1.5 *flushing, n*—a method of transferring pigments from dispersions in water to dispersions in oil by the displacement of the water by oil.

3.1.5.1 *Discussion*—The resulting dispersions of flushing are known as flushed colors.

3.1.6 *pigment, n*—the fine solid particles of colorant used to give color to printing inks.

3.1.6.1 *Discussion*—The pigment particles are substantially insoluble in the vehicle and in water.

3.1.7 *presscake, n*—a mixture of pigment and water formed into a cake by passing through a filter press under pressure.

3.1.8 *vacuum cycle, n*—the time a flush is under vacuum to remove entrapped water.

3.1.9 *vehicle, n*—the liquid portion of an ink that holds and carries the pigment, provides workability and drying properties and binds the pigment to the substrate after the ink has dried.

¹ This practice is under the jurisdiction of ASTM Committee D01 on Paint and Related Coatings, Materials, and Applications and is the direct responsibility of Subcommittee D01.37 on Ink Vehicles.

Current edition approved Nov. 1, 2004. Published November 2004. Originally approved in 1998. Last previous edition approved in 1998 as D6336-98. DOI: 10.1520/D6336-98R04.

Current edition approved Nov. 1, 2011. Published November 2011. Originally approved in 1998. Last previous edition approved in 2004 as D6336-98 (2004) which was withdrawn in 2010 and reinstated in November 2011. DOI: 10.1520/D6336-11.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

4. Summary of Practice

4.1 Vehicle, pigment presscake, and additives are added into a sigma blade mixer and mixed until the water is displaced from the pigment presscake.

4.2 Step 4.1 is repeated two or three times until the capacity of the flusher has been reached.

4.3 The flusher is then sealed and a vacuum applied until the dispersion (flush) is free of moisture.

NOTE 1—Lithol rubine pigment undergoes a color conversion when essentially all water is removed.

4.4 Vehicle solvent and additives are added to adjust the strength, shade and body of the dispersion (flush) to that of a standard dispersion (flush).

5. Significance and Use

5.1 By following this practice it is possible to make reproducible flushes when using the same raw materials. Therefore, if someone wishes to evaluate the effect a different raw material has on a flush, it is possible to evaluate this effect by noting the change that occurs from a control flush to the experimental flush. This change can be, but is not limited to; such things as strength after vacuum, grind, grit, gloss etc. This practice can be used by ink companies, pigment companies or varnish companies. This practice is not meant to give absolute values but is meant to be used as a relative practice in which a control flush is made using a standard formula and the experimental flush is compared to the control flush. This practice is not meant to determine the absolute performance of a formula in production. Again it can be used to give a relative idea of how a formula will perform in production when a correlation has been established between laboratory flushing and production flushing.

6. Apparatus

6.1 *Laboratory Sigma Blade Flusher*, typically 1-L (1-qt) to 4-L (1-gal) capacity.

6.2 *Vacuum Pump*, capable of obtaining a vacuum in the flusher of 69 cm (27 in.) to 76 cm (30 in.).

6.3 *Wide Blade Spatula*, typically 5 by 10 cm (2 by 4 in.).

6.4 *Spatula*, typically 2.5 by 7.5 cm (1 by 3 in.).

6.5 *Scale*, capable of weighing up to 3 kg accurate to 1 g.

6.6 *Scale*, capable of weighing up to 1 kg, accurate to 1 g.

7. Materials

7.1 *Presscake*.

7.2 *Flushing Vehicle(s)*.

7.3 *Experimental Vehicle*.

7.4 *Flushing Additives*.

8. Procedure

8.1 Fig. 1 illustrates a typical formula for a 1-L laboratory flusher.

NOTE 2—It is common practice for formulas to be based on the amount of pigment calculated on a dry basis and not on the weight of presscake, since the amount of water in the presscake will vary from batch to batch. For example, a presscake can be referred to as 25 % dry or 25 % solids. This means that for every 100 kg of presscake there are 25 kg of pigment and 75 kg of water. Usually the entire quantity of presscake to be flushed will not fit in the flusher at one time. If this is the case, it is necessary to flush the required amount of pigment in a succession of breaks (see Fig. 1).

NOTE 3—Many formulas call for two or more kinds of oil or varnish or resin solution etc. Directions are usually very specific as to how much should be used, when the various items should be added, and the order in which they are added. It is normal practice to add these items in the same order as shown on the formula. The vehicle having the best pigment wetting property is usually added first. In some formulas, however, judgment is left to the operator, as predictions cannot be made.

NOTE 4—Flushing aids are very effective and should be used with care and good judgment.

8.2 *First Break:*

8.2.1 Add prescribed quantity of presscake to the flusher.

8.2.1.1 The presscake should be analyzed for dry weight or solids according to Test Methods D280.

8.2.1.2 All presscake should be weighed before it is charged to the flusher.

8.2.2 Agitate for 2 to 5 min. If using a multispeed flusher, agitate at low speed for 1 to 2 min then at high speed for 2 to 5 min.

8.2.3 Add flushing additive(s) if required.

8.2.4 Add vehicle in small quantities until break occurs. Remember you can always put vehicle in but never take it out. Therefore, always work the vehicle into the presscake well before adding more.

8.2.5 When the flush mass begins to form (water is flushed out) continue to mix until the water clears, then drain.

8.2.6 Run the flusher on high speed for 30 to 45 s and drain again. Do this until no more water is flushed from the system.

NOTE 5—First breaks generally use 45 to 55 % of the pigment and 55 to 60 % of the vehicle. First breaks are usually soft so it is very important to drain well. Also it is important that the mixer's sides should be scraped down thoroughly during the first break and all subsequent breaks, to make sure all pigment and presscake are mixed in properly. Proper draining will shorten the vacuum cycle.

8.3 *Other Breaks:*

DEVELOPMENT FLUSHING FORM

Date: _____

Project No. _____

Product Code Number 9999
 Presscake Used zyxw
 Percent Solids 28.5%

| I. Flushing Cycle | | Amount used(a) | Break 1 | Break 2 | Break 3 | Break 4 |
|-------------------|------|----------------|---------|---------|---------|---------|
| Presscake No. | zyxw | 160.0g | 77.0g | 37.0g | 25.5g | 20.5g |
| Vehicle No. | 1 | 35.0g | 35.0g | | | |
| Vehicle No. | 2 | 90.0g | 60.5g | 29.5g | | |
| Vehicle No. | | | | | | |
| Additive No. | 1 | 5.0g | 5.0g | | | |
| Additive No. | 2 | .8g | .8g | | | |
| Solvent No. | 1 | 23.0g | | | | |
| Total | | 308.0g(b) | | | | |

II. Reduction Cycle

Vehicle No. _____
 Vehicle No., _____
 Additive No 3 9.0g
 Additive No _____
 Solvent No 1 1.0g
 Solvent No _____

Total 10.0g

ASTM D6336-11
<https://standards.iteh.ai/catalog/standards/sist/41bcd043-d872-48f6-b9f6-e10c0878dde9/astm-d6336-11>

III. Adjustments

Vehicle No. 2 44.0g
 Vehicle No _____
 Solvent No 1 20.0g
 Solvent No _____

Total 64.0g

TOTAL FORMULA 382.0g

By: _____

- (a) These weights are calculated on the dry weight of the presscake. (pigment weight)
- (b) For this formula, it is assumed that additives #1 and #2 are washed out of the system with the water.

FIG. 1 Development Flushing Form