



Designation: B465 – 11

## Standard Specification for Copper-Iron Alloy Plate, Sheet, Strip, and Rolled Bar<sup>1</sup>

This standard is issued under the fixed designation B465; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

*This standard has been approved for use by agencies of the Department of Defense.*

### 1. Scope\*

1.1 This specification establishes Copper Alloy UNS Nos. C19200, C19210, C19400, C19500, C19700, and C19720 plate, sheet, strip, and rolled bar.

1.2 *Units*—Values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units, which are provided for information only and are not considered standard.

### 2. Referenced Documents

2.1 *ASTM Standards*:<sup>2</sup>

**B193** Test Method for Resistivity of Electrical Conductor Materials

**B248** Specification for General Requirements for Wrought Copper and Copper-Alloy Plate, Sheet, Strip, and Rolled Bar

**B601** Classification for Temper Designations for Copper and Copper Alloys—Wrought and Cast

**B846** Terminology for Copper and Copper Alloys

**E8** Test Methods for Tension Testing of Metallic Materials

**E54** Test Methods for Chemical Analysis of Special Brasses and Bronzes (Withdrawn 2002)<sup>3</sup>

**E62** Test Methods for Chemical Analysis of Copper and Copper Alloys (Photometric Methods) (Withdrawn 2010)<sup>3</sup>

**E75** Test Methods for Chemical Analysis of Copper-Nickel and Copper-Nickel-Zinc Alloys (Withdrawn 2010)<sup>3</sup>

**E112** Test Methods for Determining Average Grain Size

**E478** Test Methods for Chemical Analysis of Copper Alloys

**E527** Practice for Numbering Metals and Alloys in the Unified Numbering System (UNS)

<sup>1</sup> This specification is under the jurisdiction of ASTM Committee B05 on Copper and Copper Alloys and is the direct responsibility of Subcommittee B05.01 on Plate, Sheet, and Strip.

Current edition approved Oct. 1, 2011. Published November 2011. Originally approved in 1968. Last previous edition approved in 2009 as B465–09. DOI: 10.1520/B0465-11.

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, [www.astm.org](http://www.astm.org), or contact ASTM Customer Service at [service@astm.org](mailto:service@astm.org). For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

<sup>3</sup> The last approved version of this historical standard is referenced on [www.astm.org](http://www.astm.org).

### 3. General Requirements

3.1 The following sections of Specification B248 constitute a part of this specification:

3.1.1 Terminology,

3.1.2 Materials and Manufacture,

3.1.3 Workmanship, Finish, and Appearance,

3.1.4 Sampling,

3.1.5 Number of Tests and Retests,

3.1.6 Specimen Preparation,

3.1.7 Test Methods (except chemical analysis),

3.1.8 Significance of Numerical Limits,

3.1.9 Inspection,

3.1.10 Rejection and Rehearing,

3.1.11 Certification,

3.1.12 Test Reports (Mill),

3.1.13 Packaging and Package Marking, and

3.1.14 Supplementary Requirements.

3.2 In addition, when a section with a title identical to that referenced in 3.1 appears in this specification, it contains additional requirements which supplement those appearing in Specification B248.

### 4. Terminology

4.1 *Definitions*—For definitions of terms related to copper and copper alloys, refer to Terminology B846.

### 5. Ordering Information

5.1 Include the following information when placing orders for product under this specification:

5.1.1 ASTM designation and year of issue (for example B465–XX),

5.1.2 Copper Alloy UNS No. designation (for example, C19200),

5.1.3 Temper (Section 8),

5.1.4 *Dimensions*—Thickness, width, length, and so forth (Section 13),

5.1.5 *Form*—Plate, sheet, strip, or rolled bar,

5.1.6 *How Furnished*—Coils (rolls), specific lengths or stock lengths, with or without ends,

5.1.7 *Quantity*—total weight each form, temper, and size, and

\*A Summary of Changes section appears at the end of this standard

5.1.8 When material is purchased for agencies of the U.S. government (Section 12).

5.2 The following options are available under this specification and should be specified in the contract or purchase order when required:

5.2.1 *Type of Edge*—Slit, sheared, sawed, square corners, round corners, rounded edges, or full rounded edges,

5.2.2 Width and straightness tolerances (appropriate table in Specification B248),

5.2.3 Heat identification or traceability details,

5.2.4 Certification, and

5.2.5 Mill test report.

## 6. Material and Manufacture

### 6.1 Material:

6.1.1 The material of manufacture shall be a cast bar, cake, or slab, of Copper Alloy UNS No. C19200, C19210, C19400, C19500, C19700, or C19720 as specified in the ordering information, and of such purity and soundness as to be suitable for processing into the products prescribed herein.

6.1.2 In the event heat identification or traceability is required, the purchaser shall specify the details desired.

NOTE 1—Because of the discontinuous nature of the processing of castings into wrought products, it is not practical to identify a specific casting analysis with a specific quantity of finished product.

### 6.2 Manufacture:

6.2.1 The product shall be manufactured by such hot-working, cold-working, and annealing processes as to produce a uniform wrought structure in the finished product.

6.2.2 The product shall be hot- or cold-worked to the finished size, and subsequently annealed, when required, to meet the temper properties specified.

6.2.3 *Edges*—Slit edges shall be furnished unless otherwise specified in the contract or purchase order.

## 7. Chemical Composition

7.1 The material shall conform to the requirements prescribed in Table 1 for the Copper Alloy UNS No. designation specified in the ordering information.

7.1.1 These composition limits do not preclude the presence of other elements. Limits may be established and analysis required for unnamed elements by agreement between the manufacturer and the purchaser.

7.2 Copper, when specified as the remainder, may be taken as the difference between the sum of results for specified elements and 100 %.

7.3 When all elements listed in Table 1 for the designated alloy are determined, the sum of results shall be 99.8 % minimum, except for C19720 which shall be 99.5 % minimum.

## 8. Temper

8.1 As defined in Classification B601, products shall be produced in tempers O60 (soft annealed), O61 (annealed), O50 (light annealed), O82 (annealed to temper - ½ hard), H01 (¼ hard), H02 (½ hard), H03 (¾ hard), H04 (hard), H06 (extra hard), HR02 (½ hard and stress relieved), HR04 (hard and stress relieved), HR06 (extra hard and stress relieved), H08 (spring), H10 (extra spring), and H14 (super spring).

NOTE 2—The purchaser should confer with the manufacturer or supplier for the availability of product in a specific alloy, temper, and form, since all tempers are subject to manufacturing limitations.

NOTE 3—Properties of special tempers not listed in this specification are subject to agreement between the manufacturer and purchaser.

## 9. Grain Size for Annealed Tempers

9.1 *Grain Size*—No grain size requirements have been established for tempers O50, O60, and O61; however, the product material shall be fully recrystallized when examined in accordance with Test Methods E112.

## 10. Physical Property Requirements

### 10.1 Electrical Resistivity Requirement:

10.1.1 The product furnished shall conform to the requirements of Table 2 for the Copper UNS No. designation and temper specified in the ordering information when determined in accordance with Test Method B193.

10.1.1.1 Products produced in temper O60 from Copper Alloy UNS No. C19400 are not required to conform to the resistivity requirement of Table 2.

**TABLE 1 Chemical Requirements**

Element	Composition, %					
	Copper Alloy UNS No.					
	C19200	C19210	C19400	C19500	C19700	C19720
Copper	98.5 min	remainder	97.0 min	96.0 min	remainder	remainder
Iron	0.8 to 1.2	0.05 to 0.15	2.1 to 2.6	1.0 to 2.0	0.30–1.2	0.05–0.50
Phosphorus	0.01 to 0.04	0.025 to 0.04	0.015 to 0.15	0.01 to 0.35	0.10–0.40	0.05–0.15
Zinc	0.20 max	...	0.05 to 0.20	0.20 max	0.20 max	0.20 max
Lead, max	0.03	...	0.03	0.02	0.05	0.05
Tin	...	...	...	0.10 to 1.0	0.20 max	0.20 max
Cobalt	...	...	...	0.30 to 1.3	0.05 max	...
Aluminum	...	...	...	0.02 max	...	...
Magnesium	...	...	...	...	0.01–0.20	0.06–0.20
Nickel, max	...	...	...	...	0.05	0.10
Manganese, max	...	...	...	...	0.05	0.05