

---

---

**Extenders — Specifications and  
methods of test —**

**Part 1:  
Introduction and general test methods**

*Matières de charge — Spécifications et méthodes d'essai —*

*Partie 1: Introduction et méthodes d'essai générales*

*ITeH Standards*  
**(<https://standards.iteh.ai>)**  
**Document Preview**

[ISO 3262-1:2020](https://standards.iteh.ai/catalog/standards/iso/2a36ab46-76fe-4b44-88e4-75add670ac51/iso-3262-1-2020)

<https://standards.iteh.ai/catalog/standards/iso/2a36ab46-76fe-4b44-88e4-75add670ac51/iso-3262-1-2020>



iTeh Standards  
(<https://standards.iteh.ai>)  
Document Preview

[ISO 3262-1:2020](https://standards.iteh.ai/catalog/standards/iso/2a36ab46-76fe-4b44-88e4-75add670ac51/iso-3262-1-2020)

<https://standards.iteh.ai/catalog/standards/iso/2a36ab46-76fe-4b44-88e4-75add670ac51/iso-3262-1-2020>



**COPYRIGHT PROTECTED DOCUMENT**

© ISO 2020

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office  
CP 401 • Ch. de Blandonnet 8  
CH-1214 Vernier, Geneva  
Phone: +41 22 749 01 11  
Fax: +41 22 749 09 47  
Email: [copyright@iso.org](mailto:copyright@iso.org)  
Website: [www.iso.org](http://www.iso.org)

Published in Switzerland

# Contents

|   | Page     |
|---|----------|
| Foreword .....  | iv       |
| <b>1 Scope</b> .....                                      | <b>1</b> |
| <b>2 Normative references</b> .....                       | <b>1</b> |
| <b>3 Terms and definitions</b> .....                      | <b>1</b> |
| <b>4 Sampling</b> .....                                   | <b>2</b> |
| <b>5 Test methods</b> .....                               | <b>2</b> |
| 5.1 Comparison of colour .....                            | 2        |
| 5.2 Determination of loss on ignition .....               | 2        |
| 5.2.1 Apparatus .....                                     | 2        |
| 5.2.2 Procedure .....                                     | 2        |
| 5.2.3 Expression of results .....                         | 3        |
| 5.3 Determination of calcium and magnesium contents ..... | 3        |
| 5.3.1 Reagents .....                                      | 3        |
| 5.3.2 Apparatus .....                                     | 4        |
| 5.3.3 Procedure .....                                     | 4        |
| <b>Bibliography</b> .....                                 | <b>6</b> |

**iTeh Standards**  
**(<https://standards.iteh.ai>)**  
**Document Preview**

[ISO 3262-1:2020](https://standards.iteh.ai/catalog/standards/iso/2a36ab46-76fe-4b44-88e4-75add670ac51/iso-3262-1-2020)

<https://standards.iteh.ai/catalog/standards/iso/2a36ab46-76fe-4b44-88e4-75add670ac51/iso-3262-1-2020>

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see [www.iso.org/directives](http://www.iso.org/directives)).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see [www.iso.org/patents](http://www.iso.org/patents)).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see [www.iso.org/iso/foreword.html](http://www.iso.org/iso/foreword.html).

This document was prepared by Technical Committee ISO/TC 256, *Pigments, dyestuffs and extenders*, in collaboration with the European Committee for Standardization (CEN) Technical Committee CEN/TC 298, *Pigments and extenders*, in accordance with the Agreement on technical cooperation between ISO and CEN (Vienna Agreement).

This second edition cancels and replaces the first edition (ISO 3262-1:1997), which has been technically revised.

The main changes compared to the previous edition are as follows:

- the main title has been changed from “Extenders for paints” to “Extenders”;
- clarification and focus on extenders for all/undefined applications;
- CAS numbers have been added to all reagents used.

A list of all parts in the ISO 3262 series can be found on the ISO website.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at [www.iso.org/members.html](http://www.iso.org/members.html).

# Extenders — Specifications and methods of test —

## Part 1: Introduction and general test methods

### 1 Scope

This document gives the definition for the term extender and specifies test methods that are required for most of the subsequent parts of ISO 3262.

NOTE The subsequent parts of ISO 3262 specify requirements and the corresponding methods of test for extenders for use in paints, related coating materials and other applications.

### 2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 385, *Laboratory glassware — Burettes*

ISO 648, *Laboratory glassware — Single-volume pipettes*

ISO 787-2, *General methods of test for pigments and extenders — Part 2: Determination of matter volatile at 105 °C*

ISO 1042, *Laboratory glassware — One-mark volumetric flasks*

ISO 3696, *Water for analytical laboratory use — Specification and test methods*

ISO 3819, *Laboratory glassware — Beakers*

ISO 15528, *Paints, varnishes and raw materials for paints and varnishes — Sampling*

### 3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

— ISO Online browsing platform: available at <https://www.iso.org/obp>

— IEC Electropedia: available at <http://www.electropedia.org/>

#### 3.1

##### **extender**

material in granular or powder form, practically insoluble to somewhat soluble in the application medium and used to modify or influence certain physical properties

Note 1 to entry: The German terms “Extender”, “Extenderpigment”, “Pigmentextender” or “Verschnittmittel” should be avoided.

Note 2 to entry: Whether a given substance is to be considered as pigment or extender depends on its application.

Note 3 to entry: In some industries, such as rubber industries, “extender” is also called “filler” (see ISO 1382). In coatings industries, the term “extender” is preferred, because in ISO 4618, “filler” is defined as “coating material with a high proportion of extender, intended primarily to even out irregularities in substrates to be painted and to improve surface appearance”.

[SOURCE: ISO 18451-1:2019, 3.34]

## 4 Sampling

Take a representative sample of the product to be tested according to ISO 15528.

## 5 Test methods

NOTE For particular test methods for individual extenders, see the appropriate parts of ISO 3262.

### 5.1 Comparison of colour

NOTE There is no objection to the use of a particular instrumental method, agreed between the interested parties, for comparison of colour. ISO 11664-4 defines procedures for calculating the respective coordinates in the CIE 1976 L\*a\*b\* colour space. However, in view of differences between the results obtained with various instruments, the simple visual method is given as the referee method. A method for the assessment of hue of near-white specimens is described in ISO 18314-1.

Place approximately equal masses of the test sample and the agreed reference sample on to a ground glass plate placed on a piece of white paper.

Place a thin glass plate vertically between the two samples so as to form a partition. Push the samples towards each other until they come into contact with the thin glass plate. Remove the glass plate and flatten the surface of the two heaps with another glass plate, removing the latter before viewing.

Examine the colour of the samples in diffuse daylight or, if good daylight is not available, make the comparison in artificial daylight.

Carefully add a few drops of either white spirit or water (as agreed between the interested parties) in such a way that the two samples are just wetted without being disturbed, then repeat the colour comparison by the same method as before.

### 5.2 Determination of loss on ignition

NOTE For the determination of loss on ignition of aluminium hydroxides, see ISO 3262-16.

#### 5.2.1 Apparatus

Use ordinary laboratory apparatus and glassware, together with the following:

##### 5.2.1.1 Platinum or porcelain dish, shallow.

##### 5.2.1.2 Muffle furnace.

#### 5.2.2 Procedure

Weigh, to the nearest 1 mg, about 0,5 g to 2 g of the test sample, previously dried in accordance with ISO 787-2, into the tared platinum or porcelain dish (5.2.1.1), ignite in the muffle furnace (5.2.1.2) at  $(1\ 000 \pm 25)$  °C to constant mass together with a cover lid, and cool immediately in a desiccator containing a suitable desiccant such as phosphorus pentoxide or orange gel. To avoid uptake of moisture during handling, cover the dish with the lid.

NOTE The mass depends on the specific density of the extender.