

Designation: F1667-11 Designation: F1667 - 11a

Standard Specification for Driven Fasteners: Nails, Spikes, and Staples¹

This standard is issued under the fixed designation F1667; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the Department of Defense. The Commercial and Government Entity (Cage) Code for ASTM: 81346.

1. Scope*

1.1 This specification covers nails, spikes, staples, and other driven fasteners, as listed in Table 1.

Note 1-Fastener ductility information is presented in Table 2 and dimensional information in Tables 3-65.

- 1.2 Fasteners described in this specification are driven by hand tool, power tool, or mechanical device in single or multiple strikes and are positioned by hand, tool, or machine.
- 1.3 The values stated in inch-pound units are to be regarded as standard. No other units of measurement are included in this standard.
- 1.4 Fasteners in this specification are sold in bulk (loose) form and are collated for loading into the magazine of an application tool. Other than as covered in Section 9, Workmanship, cohering materials (including, but not limited to, plastic, adhesive bond, paper tape, plastic strip, plastic carrier, wire, etc.) and relative orientation of collated fasteners are not within the scope of this standard.
- 1.5 This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.

2. Referenced Documents (https://standards.iteh.ai)

2.1 ASTM Standards:²

A153/A153M Specification for Zinc Coating (Hot-Dip) on Iron and Steel Hardware

A510M Specification for General Requirements for Wire Rods and Coarse Round Wire, Carbon Steel (Metric)

A641/A641M Specification for ZincCoated (Galvanized) Carbon Steel Wire

B695 Specification for Coatings of Zinc Mechanically Deposited on Iron and Steel

F547 Terminology of Nails for Use with Wood and Wood-Base Materials

F592 Terminology of Collated and Cohered Fasteners and Their Application Tools 4967b9c7d20/astm-f1667-11a

F680 Test Methods for Nails

F1575 Test Method for Determining Bending Yield Moment of Nails

3. Terminology

3.1 *Definitions*—The definitions used in this specification are those of common commercial acceptance and usage and also appear in Terminologies F547 and F592.

4. Classification

4.1 The fasteners and their Table 1 classification are identified as follows:

Note 2—The identification of fasteners, classified by style and type (alpha indicators) followed by a dash number (numerical code) based on Tables 3-65, identifies dimensions specifically and establishes a PIN (part identifying number) system when preceded by the F1667 ASTM designator of this specification. For example:

¹ This specification is under the jurisdiction of ASTM Committee F16 on Fasteners and is the direct responsibility of Subcommittee F16.05 on Driven and Other Fasteners. Current edition approved Jan. Nov. 1, 2011. Published January November 2011. Originally approved in 1995. Last previous edition approved in 2012 as F1667 – 10. DOI: 10.1520/F1667-11A.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.




TABLE 1 Classification and Identification Index

Type I—Nails (NL)		Style	Style Identification	Table
I—Naiis (INL)		Dan de	DD.	
-	1.	Brads	BR	3
	2. 3.	Barrel Boat	BL BTH/BTL	4
	3. 4.	Box A	BXA	5 6
	٦.	Box B	BXB	7
	5.	Broom	BM	8
	6.	Casing	CN	9
	7.	Cooler	CL	10
	8.	Sinker	SK	11
	9.	Corker	CK	12
	10.	Common	CMA	13
		Common	CMC	14
		Common	CMS	15
		Common	CMM	16
	11.	Concrete	CTS/CTM	17
	12.	Double-headed	DH	18
	13.	Fine	FN	19
	14.	Finishing	FH	20
	15.	Flooring	FL	21
	16.	Lath	LHF	22
	17	Lath	LHH MD/MDU	23
	17.	Masonry	MR/MRH	24
	18.	Pallet	PL	25
	19.	Gypsum wallboard	GWS	26
	00	Gypsum wallboard	GWM	27
	20.	Roofing Roofing	RFA RFS	28 29
		Roofing	RFC	30
		Roofing	RFL	31
		Roofing	RFR	32
		Roofing	RFD	33
		Roofing	RFNS/RFND	34
	21.	Shingle	SHAD/SHAS	35
		Shingle	SHSS/SHNSB	36
	22.	Siding	SDF/SDC/SDK	37
	23.	Slating	SLA/SLC/SLS	38
		Rubber heel	RH	39
	25.	Underlayment	ure vievy	40
	26.	Square-barbed	SB	41
	27.	Masonry drive	MD	42
	28.	Escutcheon	ES	43
	29. 🛕	Glulam rivet	GR	44
/upto lo obstravil a al	30.	Post frame	PF 50453 0453	45
II—Cut nails (CN)	IS/1.1S1	Common e 9a-111	CM+1De-ac53-a4	467
	2.	Basket	BK	47
	3.	Clout	CL	48
	4.	Trunk	TR	49
	5.	Cobblers	CB	50
	6. 7.	Extra-iron clinching Hob	EC HB	51 52
III—Spikes (SP)	7. 1.		СМ	52 53
III —Opines (OF)	2.	Common Gutter	GRF/GRO	54
	3.	Round	RDC/RDF	55
	3. 4.	Barge and boat	BB	56
IV—Staples (ST)	1.	Fence	FN	57
iv Stapics (OT)	2.	Poultry netting	PN	58
	3.	Flat top crown	FC	59
	٥.	Flat top crown	FCC	60
	4.	Round or V crown	RC	61
	5.	Preformed	PC	62
	6.	Electrical	RE	63
	7.	Preformed hoop	PH	64
	8.	Сар	STC	65

TABLE 2 Bend Angles for Fasteners Using the Test Methods F680 Bend Test

	Fastener Material	Bend Angle, °
1.	Steel wire: (low-carbon, medium-low carbon, medium-carbon) (unhardened)	180
2.	Stainless steel wire	180
3.	Hardened steel fasteners	20
4.	Sheet steel for cut nails, Type II, and cut spikes, Type III	90
5.	Copper (min 98 %)	180
6.	Copper clad wire (min 20 %)	180
7.	Aluminum alloy wire	90
8.	Brass wire	180



Identifies a cooler nail with a length of 27/8, a shank diameter of 0.120, and a head diameter of 0.297 (See Table 10).

All dimensions are given in inches.

4.2 The trade designation, S, pennyweight, used in commercial practice is referenced in Tables 3-64 wherever it applies.

5. Ordering Information

- 5.1 Orders for driven fasteners under this specification shall include the following information:
- 5.1.1 Quantity or weight;
- 5.1.2 Part identifying number (PIN) or product description (see 4.1 and appropriate table);
- 5.1.3 Special material requirements, if specified, including coatings or finishes;
- 5.1.4 ASTM designation;
- 5.1.5 Packaging requirements;
- 5.1.6 A producer's or supplier's certification that the material and the finished fastener are in compliance with this specification, furnished only when specified in the purchase order;
 - 5.1.7 Supplementary requirements, if any; and
 - 5.1.8 Any additions agreed upon between the purchaser and the supplier.

6. Material Requirements

- 6.1 Steel wire used in the manufacture of driven fasteners shall be of low carbon, medium-low carbon, or medium-high carbon.
- 6.2 Stainless steel wire used in the manufacture of driven fasteners shall be of Types 302, 304, 305, or 316.
- 6.3 Carbon steel wire for the manufacture of hardened steel nails shall be suitable for heat treatment to a minimum hardness of 37 HRC.
 - 6.4 Sheet steel used in the manufacture of cut nails (Type II) and cut spikes (Type III) shall be a medium-carbon sheet steel.
 - 6.5 Copper used in the manufacture of driven fasteners shall contain a minimum of 98 % pure copper.
- 6.6 Copper-clad steel wire used in the manufacture of driven fasteners shall contain not less than 20 % copper by weight. The average thickness of copper on the steel wire shall be not less than 10 % of the radius of the clad wire; the minimum thickness of copper on the steel wire shall be not less than 8 % of the radius of the clad wire.
- 6.7 Aluminum alloy wire used in the manufacture of fasteners shall conform to Alloy 2024, 5056, 6061, or 6110 and have a minimum ultimate tensile strength of 60 000 psi.

Note 3—Smooth shank nails are sometimes chemically treated to remove grease, oil, and foreign matter and to roughen the surface microscopically. Mechanically deformed nails are sometimes cleaned to remove grease and foreign matter.

6.8 Brass wire used in the manufacture of fasteners shall be of good commercial quality suitable for the purpose.

7. Physical Properties

7.1 Ductility—The fasteners shall be sufficiently ductile to withstand cold bending without fracture, as specified in Table 2 for various materials used in the manufacture of fasteners utilizing the conventional bend test described in Test Methods F680. Mandrel diameter used in this test shall not exceed nail/wire diameter. The cold bend test shall not apply to unhardened nails with deformed shanks.



- 7.2 *Tensile Strength*—Finished driven fasteners are not normally subject to tension testing. However, the wire or sheet used to manufacture the fastener is tested as required for control in the production process during manufacture.
- 7.3 Number per pound—Number per pound figures are not requirements. Number per pound varies (1) as actual dimensions vary within tolerance ranges, (2) between bright and coated nails, and (3) with zinc coating thickness for galvanized nails. No tolerances have been established for these figures. They are for reference only and shall not be used as product acceptance/rejection criteria.

8. Dimensions and Tolerances

8.1 Nominal dimensions of nails and spikes shall be as shown in Tables 3-56. The following dimensional designations shall apply:

S = trade designation (reference in penny weight),

L = length, in.,

H = head diameter or width, in.,

D = shank diameter, in.,

B = head separation, in. (Table 18), and

No./lb = approximate count per pound.

- 8.1.1 The lengths, L, of nails and spikes with flat heads or parallel shoulders under the head shall be measured from under the head or shoulder to the tip of the point. All other nails and spikes shall be measured overall.
- 8.1.2 The diameter, D, of smooth shank nails and spikes shall be measured away from the gripper marks. The diameter, D, of formed or deformed shanks shall be measured before deformation, or, if specified, the thread crest diameter after deformation, or both. All diameter dimensions shall be taken prior to the application of or after the removal of any coatings or finish.
 - 8.2 Tolerances on Nominal Dimensions for Nails and Spikes:
- 8.2.1 Length tolerances shall be $\pm \frac{1}{32}$ in. for lengths up to and including 1 in.; $\pm \frac{1}{16}$ in. for lengths over 1 in., up to and including $2\frac{1}{2}$ in.; $\pm \frac{3}{32}$ for lengths over $2\frac{1}{2}$ in., up to and including 7 in.; and $\pm \frac{1}{8}$ in. for all lengths over 7 in.
- 8.2.2 Shank diameter tolerances shall be ± 0.002 in. for diameters smaller than 0.076 in. and ± 0.004 in. for diameters 0.076 in. and larger.
 - 8.2.3 Head Diameter Tolerances:
- 8.2.3.1 Hand Driven—Tolerances on head diameters of roofing nails shall be ± 0 , -10% of the nominal head diameter (the mean of two readings 90° apart). For other brads, nails, and spikes, the tolerance shall be $\pm 10\%$ of the nominal head diameter (individual measurement). The difference in diameter across the long axis of a roofing nail shall not exceed that across the short axis by more than 20%. For other brads, nails, and spikes, the difference in diameter across the long axis shall not exceed that across the short axis by more than 10%. A fillet shall be provided under the head if not otherwise specified.
- 8.2.3.2 *Power Driven*—Tolerances on head diameters of power-driven nails shall comply with the manufacturer's specifications and shall be suitable for use in the make and model of the tool specified.
 - 8.3 Nominal dimensions of staples shall be as shown in Tables 57-65, and the following dimensional designations shall apply:
 - 8.3.1 Hand Tool–Driven Nominal Dimensions:

L = leg length, inside, in.,

D = round leg diameter, in.,

C = crown width, inside, in., and

No./lb = approximate count per pound.

8.3.2 Power Tool–Driven Nominal Dimensions:

D = round leg diameter, in.,

L = leg length, outside, in.,

T = leg thickness, in. (see Tables 59 and 60),

W = leg width, in. (see Tables 59 and 60),

C = crown width, outside, in., and

G = steel wire gage.

- 8.4 Tolerances on Nominal Dimensions for Staples:
- 8.4.1 Leg length, L, tolerances shall be $+\frac{1}{32}$, $-\frac{1}{64}$ in. for both hand tool–driven and power tool–driven staples.
- 8.4.2 Diameter tolerances for hand tool–driven round staples shall be ± 0.002 in. for diameters smaller than 0.076 in. and ± 0.004 in. for diameters 0.076 in. and larger.
- 8.4.3 Thickness and width tolerances on power-driven staples shall comply with the manufacturer's specification and shall be suitable for use in the make and model tool specified (see Tables 59 and 60).
 - 8.4.4 Crown width tolerances are $\pm \frac{1}{32}$ in. unless otherwise specified.
 - 8.5 Nominal Dimensions for Cut Nails, Type II—Unless otherwise specified, cut nails shall be sheared from medium carbon



sheet steel and shall have a wedge-shaped shank with a sheared square point end narrower than the upset head end. The designation T in Tables 46-51 refers to sheet thickness in finished product. Other designations shall be the same as those for nails in 8.1.

8.6 When gage is used for a nominal diameter dimension in the application of this specification, it shall be in accordance with the decimal equivalents as shown in Specification A510M, unless otherwise specified.

9. Workmanship

9.1 Fasteners covered by this specification shall be true to shape, well-finished, free from imperfections, clean, and free of corrosion. Mechanically driven collated items shall be uniform and aligned properly in their assembled form for use in power tools.

10. Protective Coatings and Finishes

- 10.1 Zinc Coating:
- 10.1.1 Driven fasteners required to be zinc coated shall be cut and formed from hot-dip, hard-wiped, galvanized steel wire, electrogalvanized steel wire, or zinc flake/chromate dispersion-coated steel wire; or they shall be cut from uncoated (bright) steel wire and shall be hot-dip galvanized, electrodeposited zinc coated, mechanically deposited zinc coated, or zinc flake/chromate dispersion coated after forming. Power-driven staples are not normally zinc coated after forming.
- 10.1.2 Hot-dip galvanized or electrogalvanized steel wire for the manufacture of fasteners shall have a coating weight in accordance with Specification A641/A641M, Supplementary Requirements, Class 1.
- 10.1.3 Hot-dip galvanized steel fasteners coated after forming shall have a coating weight in accordance with Specification A153/A153M, Class D, when a heavier coating for exterior use is specified. If not otherwise specified, the coating weight shall be in accordance with Specification A641/A641M, Supplementary Requirements, Class 1.
- 10.1.4 Mechanically deposited zinc coatings applied to fasteners after forming shall have a thickness in accordance with Specification B695, Class 40, unless otherwise specified.
 - 10.2 Other Coatings and Finishes (When Specified):
- 10.2.1 Cement coating shall be applied by tumbling, mechanical dispensing device, or immersion in resin or other similar material and shall not be tacky or gummy. Cement coatings on power-driven fasteners shall be uniform and applied before, during, or after the fasteners are cohered into strips, clips, or coils.
- Note 4—Cement coatings increase the holding strength in withdrawal of a driven fastener, depending on the fastener size, amount of cement coating applied, and method of driving.
 - 10.2.2 Chemical etching shall remove the polish of fabrication and roughen the surface microscopically.
 - 10.2.3 Blued nails shall be heated to form a thin, colored oxide on the surface.
- 10.2.4 Miscellaneous finishes, such as tin plating, liquor, brass plating, copper plating, phosphate coating, or oil coating shall be applied.
 - 10.3 Altered Shapes and Deformations: ASTM F1667-11:
- 10.3.1 Mechanically formed or deformed nail shanks shall have barbs, flutes, threads, or angular serrations formed onto the wire from which the nail is manufactured. Mechanically deformed shanks shall have vertical or helical flutes or screw-type or annular (ring)-type deformations rolled onto the shank. Symmetrical helical shank deformations shall be obtained by twisting square wire. The deformations shall pass entirely around the shank body, resulting in expanded ridges and depressions. Interruptions in shank deformation to facilitate attachment of materials for collating nails is permitted.
- 10.3.2 Mechanically formed or deformed nail heads shall be round or T-headed; or they shall be altered round for suitable use in a given make and model of a power-driving fastening system.
- 10.3.3 Staples manufactured for intended use in power tools shall comply with the tool manufacturer's specification or Type IV, Style 3 (Table 59 or Table 60).

11. Certification

11.1 When specified in the purchase order, a producer's or supplier's certification shall be furnished to the purchaser, indicating that the fasteners are in compliance with this specification and the purchase order.

12. Packaging and Package Marking

- 12.1 Unless otherwise specified, fasteners shall be in substantial commercial containers of the type, size, and kind commonly used for the purpose, so constructed as to preserve the contents in good condition and to ensure acceptance and safe delivery by common or other carriers to the point of delivery. In addition, the containers shall be so made that the contents can be removed partially without destroying the container's ability to serve as a receptacle for the remainder of the contents.
- 12.2 When specified, individual packages and shipping containers shall be marked with the part-identifying number and type, length, diameter (or gage, as applicable) of the fastener, the name of the manufacturer or distributor, and the quantity or net weight.


13. Keywords

13.1 diameter; driven fasteners; head; length; nails; point; spikes; staples;



TABLE 3 Type I, Style 1-Brads^A

Note—Steel wire, brad head, diamond point, round smooth shank, bright finish. When specified, brads shall have a modified brad head with a blunt or chiseled point for use with mechanical drivers.




- Identifies a brad nail with a length of 11/2, a diameter of 0.099, and a diamond point.

Dash No.	L	D	S	No./lb	Dash No.	L	D	S	No./lb
01	3/8	0.035		9520	21	13/4	0.062		670
02	1/2	0.035		7060	22	13/4	0.080		400
03	1/2	0.048		3990	23	13/4	0.099	5d	270
04	5/8	0.035		5680	24	2	0.062		580
05	5/8	0.048		3200	25	2	0.080		350
06	3/4	0.035		4800	26	2	0.113	6d	180
07	3/4	0.048		2620	27	21/4	0.080		320
80	3/4	0.062		1550	28	21/4	0.113	7d	160
09	7/8	0.035		4220	29	21/2	0.080		290
10	7/8	0.048		2220	30	21/2	0.131	8d	110
11	7/8	0.062		1280	31	23/4	0.131	9d	97
12	1	0.054		1500	32	3	0.148	10d	70
13	1	0.062		1120	33	31/4	0.148	12d	65
14	1	0.072	44	904	34	31/2	0.162	16d	50
15	11/4	0.054	lu 0.8.7	1210	35	40	0.192	20d	31
16	11/4	0.062		940	36	41/2	0.207	30d	24
17	11/4	0.080	3d	560	-37	5	0.225	40d	18
18	11/2	0.054	1300	1040	38	51/2	0.244	50d	14
19	11/2	0.080		470	39	6	0.262	60d	11
20	11/2	0.099	4d	320					

^A All dimensions are given in inches.

TABLE 4 Type I, Style 2—Barrel Nails^A

Note-Steel wire, flat head, diamond point, round smooth shank, bright, zinc or cement coated as specified.



- Identifies a barrel nail with a length of 5/8, a diameter of 0.067, a head diameter of 0.148, and a bright finish.

B = bright

C = cement coated

Dash No.	L	D	Н	No./lb	Dash No.	L	D	Н	No./lb
01	5/8	0.067	0.148	1.550	05	11/8	0.076	0.177	670
02	3/4	0.067	0.148	1.300	06	11/4	0.080	0.188	540
03	7/8	0.076	0.177	850	07	13/8	0.092	0.219	380
04	1	0.076	0.177	750	08	11/2	0.092	0.219	350

A All dimensions are given in inches.


TABLE 5 Type I, Style 3—Boat nails^A


 Identifies a heavy boat nail with a length of 3, a diameter of 0.375, a head diameter of

0.750, and zinc coated.

Note—Steel wire, oval countersunk head, chisel point, round smooth shank, bright or zinc coated as specified.

ASTM identifier






F 1667 NLBTL						F 1667 NLBTH							
Dash No.	S	L	D	Н	No./lb	Dash No.	s	L	D	н	No./lb		
01	4d	11/2	0.188	0.406	82	01	4d	11/2	0.250	0.500	47		
02	6d	2	0.188	0.406	62	02	6d	2	0.250	0.500	36		
03	8d	21/2	0.188	0.406	50	03	8d	21/2	0.250	0.500	29		
04	10d	3	0.250	0.500	24	04	10d	3	0.375	0.750	11		
05	12d	31/4	0.250	0.500	22	05	12d	31/4	0.375	0.750	10		
06	16d	31/2	0.250	0.500	20	06	16d	31/2	0.375	0.750	9		
07	20d	4	0.250	0.500	18	07	20d	4	0.375	0.750	8		

^A All dimensions are given in inches.

TABLE 6 Type I, Style 4A—Box Nails^A

Note—Steel wire, flat head, diamond point, round, barbed or smooth shank, bright or cement coated as specified. When specified, box nails shall have an altered or T-head with a diamond, blunt, or chisel point for use with mechanical drivers.



_	
	111 22


					F 1667	7 NLBXA		•			
Dash No.	s	L	D	Н	No./lb	Dash No.	s	L	D	Н	No./lb
01	2d	1	0.067	0.188	940	08	9d	23/4	0.113	0.297	120
02	3d	11/4	0.076	0.219	590	09	10d	3	0.128	0.312	90
03	4d	11/2	0.080	0.219	450	10	12d	31/4	0.128	0.312	83
04	5d	13/4	0.080	0.219	390	11	16d	31/2	0.135	0.344	69
05	6d	2	0.099	0.266	220	12	20d	4	0.148	0.375	50
06	7d	21/4	0.099	0.266	200	13	30d	41/2	0.148	0.375	45
07	8d	21/2	0.113	0.297	140	14	40d	5	0.162	0.406	34

^A All dimensions are given in inches.




TABLE 7 Type I, Style 4B—Box Nails^A

Note—Steel wire, flat head, diamond point, round smooth shank, cement coated.



 Identifies a Style B, box nail with a length of 15/8, a diameter of 0.072, and a head diameter of 0.219.




	F 1667 NLBXB												
Dash No.	S	L	D	Н	No./lb	Dash No.	s	L	D	н	No./lb		
01	2d	1	0.058	0.172	1250	06	7d	21/8	0.086	0.250	280		
02	3d	11/8	0.062	0.188	980	07	8d	2 ³ / ₈	0.099	0.266	190		
03	4d	13/8	0.067	0.203	680	08	9d	25/s	0.099	0.266	170		
04	5d	15/8	0.072	0.219	510	09	10d	27/a	0.113	0.297	120		
05	6d	17/8	0.086	0.250	315								

A All dimensions are given in inches.

TABLE 8 Type I, Style 5—Broom Nails^A

Note—Steel wire, flat or star head, diamond point, round smooth shank, bright finish, as specified.




111

Dash No.	L	D	Н	No./lb
01	5/8	0.072	0.203	1480
02	5/ ₈	0.080	0.219	990
03	3/4	0.072	0.203	1170
04	3/4	0.080	0.219	840

A All dimensions are given in inches.

TABLE 9 Type I, Style 6—Casing Nails^A

Note—Steel wire, flat countersunk cupped head, diamond point, round smooth shank, bright finish.



 Identifies a casing nail with a length of 3½, a diameter of 0.135, and a head diameter of 0.177.


- mii

Dash No.	S	L	D	Н	No./lb	Dash No.	S	L	D	н	No./lb
01	2d	1	0.067	0.099	1090	07	8d	21/2	0.113	0.155	150
02	3d	11/4	0.076	0.113	650	08	9d	23/4	0.113	0.155	135
03	4d	11/2	0.080	0.120	490	09	10d	3	0.128	0.170	95
04	5d	13/4	0.080	0.120	415	10	12d	31/4	0.128	0.170	90
05	6d	2	0.099	0.142	245	11	16d	31/2	0.135	0.177	75
06	7d	21/4	0.099	0.142	215						

^A All dimensions are given in inches.

TABLE 10 Type I, Style 7—Cooler Nails^A

Note—Steel wire, flat head, diamond point, round smooth shank, cement coated. When specified, coolers shall have an altered or T-head for use with mechanical drivers.






Dash No.	S	L	D	Н	No./lb	Dash No.	s	L	D	Н	No./ib
01	2d	1	0.062	0.172	1110	06	7d	21/8	0.099	0.266	210
02	3d	11/8	0.067	0.188	840	07	8d	23/8	0.113	0.281	140
03	4d	13/a	0.080	0.219	490	08	9d	25/a	0.113	0.281	130
04	5d	15/a	0.086	0.234	370	09	10d	27/8	0.120	0.297	100
05	6d	17/a	0.092	0.250	280						

A All dimensions are given in inches.

TABLE 11 Type I, Style 8—Sinker Nails^A

Note—Steel wire, flat countersunk head, diamond point, round smooth shank, bright or cement coated. When specified, sinkers shall have an altered or T-head for use with mechanical drivers.






Dash No.	S	L	D	Н	No./lb	Dash No.	s	L	D	Н	No./lb
01	3d	11/8	0.067	0.172	940	08	12d	31/8	0.135	0.312	81
02	4d	13/8	0.080	0.203	530	09	16d	31/4	0.148	0.344	64
03	5d	15/8	0.086	0.219	390	10	20d	33/4	0.177	0.375	40
04	6d	17/8	0.092	0.234	290	11	30d	41/4	0.192	0.406	30
05	7d	21/8	0.099	0.250	220	12	40d	43/4	0.207	0.438	23
06	8d	23/8	0.113	0.266	150	13	60d	53/4	0.244	0.500	14
07	10d	27/8	0.120	0.281	110						

A All dimensions are given in inches.

TABLE 12 Type I, Style 9—Corker Nails^A

Note—Steel wire, flat countersunk head, diamond point, round smooth shank, cement coated. When specified, corkers shall have an altered or T-head for use with mechanical drivers.






Dash No.	S	L	D	Н	No./lb	Dash No.	S	L	D	Н	No./lb
01	2d	1	0.062	0.156	1220	09	10d	27/8	0.135	0.312	89
02	3d	11/4	0.072	0.188	720	10	12d	31/s	0.135	0.312	81
03	4d	11/2	0.086	0.219	420	11	16d	33/8	0.148	0.344	62
04	5d	15/a	0.086	0.219	320	12	20d	37/a	0.177	0.375	38
05	6d	17/a	0.099	0.250	250	13	30d	43/8	0.192	0.406	29
06	7d	21/8	0.099	0.250	220	14	40d	47/8	0.207	0.438	22
07	8d	23/8	0.120	0.281	130	15	50d	53/s	0.226	0.469	17
08	9d	25/8	0.120	0.281	120	16	60d	57/s	0.244	0.500	13

A All dimensions are given in inches.

TABLE 13 Type I, Style 10—Common Nails^A

Note—Aluminum alloy wire, flat head, diamond point, round smooth shank, or, when specified, square barbed shank.



 Identifies an aluminum common nail with a length of 2, a diameter of 0.120, and a head diameter of 0.266.

———


	F 1667 NLCMA														
Dash No.	S	L	D	Н	No./lb	Dash No.	s	L	D	Н	No./lb				
01	4d	11/2	0.099	0.250	830	04	10d	3	0.162	0.312	170				
02	6d	2	0.120	0.266	430	05	16d	31/2	0.177	0.344	120				
03	8d	21/2	0.148	0.281	220	06	20d	4	0.199	0.406	78				


^A All dimensions are given in inches.

TABLE 14 Type I, Style 10—Common Nails^A

Note—Copper wire, flat head, diamond point, round smooth shank.

ASTM identifier






		· · · · · · · · · · · · · · · · · · ·		F 1667	NLCMC				
Dash No.	L	D	Н	No./lb	Dash No.	L	D	Н	No./lb
01	5/8	0.065	0.156	1380	10	2	0.120	0.266	130
02	3/4	0.065	0.156	1160	11	2	0.134	0.281	
03	3/4	0.072	0.172	960	12	21/2	0.134	0.281	86
04	7/8	0.072	0.172	810	13	3	0.148	0.312	56
05	1	0.072	0.172	700	14	31/2	0.165	0.344	40
06	11/4	0.083	0.203	420	15	4	0.203	0.406	23
07	11/2	0.109	0.250	210	16	41/2	0.220	0.438	18
08	13/4	0.109	0.250	180	17	5	0.238	0.469	14
09	13/4	0.120	0.266	140	18	6	0.284	0.531	8

A All dimensions are given in inches.

TABLE 15 Type I, Style 10—Common Nails^A

Note—Steel wire, flat head, diamond point, round smooth shank, bright, zinc or cement coated as specified.



 Identifies a steel common nail with a length of 2, a diameter of 0.113, a head diameter of 0.266, and a bright finish.
 B = bright
 Z = zinc coated

Z = zinc coated C = cement coated




	F 1667 NLCMS														
Dash No.	S	L	D	Н	No./lb	Dash No.	s	L	D	Н	No./ib				
01	2d	1	0.072	0.172	850	09	10d	3	0.148	0.312	66				
02	3d	11/4	0.080	0.203	540	10	12d	31/4	0.148	0.312	61				
03	4d	11/2	0.099	0.250	290	11	16d	31/2	0.162	0.344	47				
04	5d	13/4	0.099	0.250	250	12	20d	4	0.192	0.406	30				
05	6d	2	0.113	0.266	170	13	30d	41/2	0.207	0.438	23				
06	7d	21/4	0.113	0.266	150	14	40d	5	0.226	0.469	17				
07	8d	21/2	0.131	0.281	100	15	50d	51/2	0.244	0.500	14				
08	9d	23/4	0.131	0.281	92	16	60d	6	0.262	0.531	11				

A All dimensions are given in inches.

Tien Standards

TABLE 16 Type I, Style 10—Common Nails^A

Note—Aluminum alloy wire, <u>stainless steel</u> or steel wire, (bright, zinc coated or cement coated), altered or T-head, diamond or chisel point, round smooth or <u>deformed</u> shank, as <u>specified</u>. For use with mechanical drivers.



 Identifies a mechanically driven, steel common nail with a length of 2, diameter of 0.080, and zinc coated.

MS = mechanically driven steel 907d20/astm-11667-11a
MA = mechanically driven aluminum

For steel only:

B = bright Z = zinc coated

C = cement coated

								F1667 I	NLCMM								
Dash No.	L	D	Dash No.	L	D	Dash No.	L	D	Dash No.	L	D	Dash No.	L	D	Dash No.	L	D
01	11/4	0.080	15	13/4	0.086	29	2	0.148	43	13/4	0.120	57	23/8	0.113	71	3	0.131
02	11/4	0.086	16	13/4	0.092	30	21/4	0.092	44	17/8	0.120	58	23/8	0.120	72	3	0.148
03	11/4	0.092	17	13/4	0.099	31	21/4	0.099	45	17/8	0.131	59	23/8	0.131	73	31/4	0.120
04	11/4	0.099	18	13/4	0.113	32	21/4	0.113	46	17/8	0.148	60	23/8	0.148	74	31/4	0.131
05	11/2	0.080	19	1 7/8	0.080	33	21/2	0.092	47	2	0.120	61	21/2	0.120	75	31/4	0.148
06	11/2	0.086	20	1 7/8	0.086	34	21/2	0.099	48	2	0.131	62	21/2	0.148	76	31/2	0.135
07	11/2	0.092	21	1 7/8	0.092	35	21/2	0.113	49	21/8	0.099	63	21/2	0.162	77	31/2	0.148
08	11/2	0.099	22	1 7/8	0.099	36	21/2	0.131	50	21/8	0.113	64	25/8	0.148	78	31/2	0.162
09	11/2	0.113	23	1 7/8	0.113	37	31/2	0.131	51	21/8	0.120	65	23/4	0.120	79	4	0.148
10	1 5/8	0.080	24	2	0.080	38	11/2	0.120	52	21/8	0.131	66	23/4	0.131	80	4	0.162
11	15/8	0.086	25	2	0.086	39	11/2	0.131	53	21/8	0.148	67	23/4	0.148	81	41/2	0.148
12	1 5/8	0.092	26	2	0.092	40	11/2	0.148	54	21/4	0.120	68	27/8	0.120	82	41/2	0.162
13	1 5/8	0.099	27	2	0.099	41	11/2	0.162	55	21/4	0.131	69	3	0.120			
14	13/4	0.080	28	2	0.113	42	1 5⁄8	0.113	56	21/4	0.148	70	3	0.128			