

# DRAFT INTERNATIONAL STANDARD

## ISO/DIS 11515

ISO/TC 58/SC 3

Secretariat: BSI

Voting begins on:  
2020-09-03

Voting terminates on:  
2020-11-26

---

---

### Gas cylinders — Refillable composite reinforced tubes of water capacity between 450 L and 3000 L — Design, construction and testing

*Bouteilles à gaz — Tubes composites renforcés rechargeables d'une capacité de 450 L à 3000 L —  
Conception, construction et essais*

ICS: 23.020.35

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

[ISO/DIS 11515](#)

[https://standards.iteh.ai/catalog/standards/sist/10535231-9817-4db4-9cdf-  
b56b01e7988f/iso-dis-11515](https://standards.iteh.ai/catalog/standards/sist/10535231-9817-4db4-9cdf-b56b01e7988f/iso-dis-11515)

THIS DOCUMENT IS A DRAFT CIRCULATED FOR COMMENT AND APPROVAL. IT IS THEREFORE SUBJECT TO CHANGE AND MAY NOT BE REFERRED TO AS AN INTERNATIONAL STANDARD UNTIL PUBLISHED AS SUCH.

IN ADDITION TO THEIR EVALUATION AS BEING ACCEPTABLE FOR INDUSTRIAL, TECHNOLOGICAL, COMMERCIAL AND USER PURPOSES, DRAFT INTERNATIONAL STANDARDS MAY ON OCCASION HAVE TO BE CONSIDERED IN THE LIGHT OF THEIR POTENTIAL TO BECOME STANDARDS TO WHICH REFERENCE MAY BE MADE IN NATIONAL REGULATIONS.

RECIPIENTS OF THIS DRAFT ARE INVITED TO SUBMIT, WITH THEIR COMMENTS, NOTIFICATION OF ANY RELEVANT PATENT RIGHTS OF WHICH THEY ARE AWARE AND TO PROVIDE SUPPORTING DOCUMENTATION.

This document is circulated as received from the committee secretariat.



Reference number  
ISO/DIS 11515:2020(E)

© ISO 2020

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

ISO/DIS 11515

<https://standards.iteh.ai/catalog/standards/sist/10535231-9817-4db4-9cdf-b56b01e7988f/iso-dis-11515>



**COPYRIGHT PROTECTED DOCUMENT**

© ISO 2020

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office  
CP 401 • Ch. de Blandonnet 8  
CH-1214 Vernier, Geneva  
Phone: +41 22 749 01 11  
Email: [copyright@iso.org](mailto:copyright@iso.org)  
Website: [www.iso.org](http://www.iso.org)

Published in Switzerland

# Contents

	Page
<b>Foreword</b> .....	<b>v</b>
<b>Introduction</b> .....	<b>vi</b>
<b>1 Scope</b> .....	<b>1</b>
<b>2 Normative references</b> .....	<b>1</b>
<b>3 Terms and definitions</b> .....	<b>2</b>
<b>4 Symbols</b> .....	<b>5</b>
<b>5 Inspection and testing</b> .....	<b>5</b>
<b>6 Materials</b> .....	<b>5</b>
6.1 Liner materials.....	5
6.2 Composite overwrap.....	6
<b>7 Design and manufacture</b> .....	<b>7</b>
7.1 General.....	7
7.2 Design submission.....	7
7.3 Manufacturing.....	9
<b>8 Type approval procedure</b> .....	<b>9</b>
8.1 General.....	9
8.2 Prototype tests.....	9
8.3 New design.....	10
8.4 Design variants.....	11
8.5 Type approval test procedures and criteria.....	16
8.5.1 Hydraulic proof pressure test.....	16
8.5.2 Hydraulic volumetric expansion test.....	16
8.5.3 Liner burst test.....	17
8.5.4 Tube burst test.....	17
8.5.5 Ambient cycle test.....	18
8.5.6 Environmental cycle test.....	19
8.5.7 Flaw test.....	20
8.5.8 Blunt impact test.....	22
8.5.9 Fire resistance test.....	24
8.5.10 Neck strength test.....	25
8.5.11 Leak test.....	26
8.5.12 Accelerated stress rupture test.....	26
8.5.13 Permeability test.....	27
8.5.14 Gas cycle test.....	27
8.5.15 Coatings test.....	29
8.5.16 Salt spray test.....	29
8.5.17 Acid environment test.....	30
8.5.18 Vacuum test.....	30
8.5.19 High velocity impact (gunfire) test.....	31
8.5.20 Glass transition temperature.....	31
8.6 Failure of type approval tests.....	31
<b>9 Inspection and testing at time of manufacture</b> .....	<b>31</b>
9.1 Liners for Type 2 and Type 3 tubes.....	31
9.2 Liners for Type 4 tubes.....	32
9.3 Failure of liner batch tests.....	33
9.4 Overwrap materials.....	33
9.5 Composite tube.....	34
9.6 Failure of batch tests.....	34
<b>10 Tube marking</b> .....	<b>35</b>
10.1 General.....	35

10.2 Additional marking .....	35
<b>Annex A</b> (informative) <b>Examples of design approval certificate</b> .....	<b>36</b>
<b>Annex B</b> (informative) <b>Specimen test reports</b> .....	<b>37</b>
<b>Annex C</b> (normative) <b>Ultrasonic inspection for seamless steel liners and metal tubing</b> .....	<b>39</b>
<b>Annex D</b> (Informative) <b>Guidance for calculating permeation rates when using trace gases</b> .....	<b>44</b>
<b>Bibliography</b> .....	<b>45</b>

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

[ISO/DIS 11515](https://standards.iteh.ai/catalog/standards/sist/10535231-9817-4db4-9cdf-b56b01e7988f/iso-dis-11515)

<https://standards.iteh.ai/catalog/standards/sist/10535231-9817-4db4-9cdf-b56b01e7988f/iso-dis-11515>

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2. [www.iso.org/directives](http://www.iso.org/directives)

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received. [www.iso.org/patents](http://www.iso.org/patents)

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

The committee responsible for this document is ISO/TC 58, *Gas cylinders*, Subcommittee SC 3, *Cylinder design*.

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

[ISO/DIS 11515](https://standards.iteh.ai/catalog/standards/sist/10535231-9817-4db4-9cdf-b56b01e7988f/iso-dis-11515)

<https://standards.iteh.ai/catalog/standards/sist/10535231-9817-4db4-9cdf-b56b01e7988f/iso-dis-11515>

## Introduction

The purpose of ISO 11515 is to provide a specification for the design, manufacture, inspection and testing of composite tubes for worldwide usage. The objective is to balance design and economic efficiency against international acceptance and universal utility.

ISO 11515 aims to eliminate the concern about climate, duplicate inspection and restrictions currently existing because of lack of definitive International Standards and should not be construed as reflecting on the suitability of the practice of any nation or region.

ISO 11515 addresses the general requirements on design, construction and initial inspection and testing of pressure receptacles of the *United Nations Recommendations on the Transport of Dangerous Goods Model Regulations*.

Annexes A and B of ISO 11515 are for information only.

## iTeh STANDARD PREVIEW (standards.iteh.ai)

[ISO/DIS 11515](https://standards.iteh.ai/catalog/standards/sist/10535231-9817-4db4-9cdf-b56b01e7988f/iso-dis-11515)

<https://standards.iteh.ai/catalog/standards/sist/10535231-9817-4db4-9cdf-b56b01e7988f/iso-dis-11515>

# Gas cylinders — Refillable composite reinforced tubes of water capacity between 450 L and 3000 L — Design, construction and testing

## 1 Scope

This document specifies minimum requirements for the materials, design, construction and performance testing for:

- type 2 hoop wrapped composite tubes
- type 3 fully wrapped composite tubes
- type 4 fully wrapped composite tubes
- with water capacities between 450 l and 3 000 l for storage and conveyance of compressed or liquefied gases with test pressures up to and including 1600 bar and a design life of at least 15 years.

The expected service temperatures are between  $-40\text{ °C}$  and  $+65\text{ °C}$ .

Type 4 tubes manufactured and tested to this document are not intended to contain toxic, oxidizing or corrosive gases.

This document is limited to tubes with composite reinforcement of carbon fibre or aramid fibre or glass fibre (or a mixture thereof) in a matrix.

Composite tubes can be used alone or in batteries to equip trailers or skids (ISO modules) or multiple element gas containers (MEGC) for the transportation and distribution of gases. This document does not include consideration of any additional stresses that can occur during service or transport, (e.g. torsional / bending stresses). However, it is important that the stresses associated with mounting the tube are considered by the assembly manufacturer and the tube manufacturer.

## 2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 306, *Plastics — Thermoplastic materials — Determination of Vicat softening temperature (VST)*

ISO 527-1, *Plastics — Determination of tensile properties — Part 1: General principles*

ISO 527-2, *Plastics — Determination of tensile properties — Part 2: Test conditions for moulding and extrusion plastics*

ISO 3341, *Textile glass — Yarns — Determination of breaking force and breaking elongation*

ISO 4624, *Paints and varnishes — Pull-off test for adhesion*

ISO 6506-1, *Metallic materials — Brinell hardness test — Part 1: Test method*

ISO 6508-1, *Metallic materials — Rockwell hardness test — Part 1: Test method*

ISO 6892-1, *Metallic materials — Tensile testing — Part 1: Method of test at room temperature*

ISO 7225, *Gas cylinders — Precautionary labels*

## ISO/DIS 11515:2020(E)

ISO 7866, *Gas cylinders — Refillable seamless aluminium alloy gas cylinders — Design, construction and testing*

ISO 9227:2012, *Corrosion tests in artificial atmospheres — Salt spray tests*

ISO 9712, *Non-destructive testing — Qualification and certification of NDT personnel*

ISO 9809-1, *Gas cylinders — Design, construction and testing of refillable seamless steel gas cylinders and tubes — Part 1: Quenched and tempered steel cylinders and tubes with tensile strength less than 1 100 MPa*

ISO 9809-2, *Gas cylinders — Design, construction and testing of refillable seamless steel gas cylinders and tubes — Part 2: Quenched and tempered steel cylinders and tubes with tensile strength greater than or equal to 1 100 MPa*

ISO 9809-3, *Gas cylinders — Design, construction and testing of refillable seamless steel gas cylinders and tubes — Part 3: Normalized steel cylinders and tubes*

ISO 10286, *Gas cylinders - Terminology*

ISO 10618, *Carbon fibre — Determination of tensile properties of resin-impregnated yarn*

ISO 11114-1, *Gas cylinders — Compatibility of cylinder and valve materials with gas contents — Part 1: Metallic materials*

ISO 11114-2, *Gas cylinders — Compatibility of cylinder and valve materials with gas contents — Part 2: Non-metallic materials*

ISO 11120, *Gas cylinders — Refillable seamless steel tubes of water capacity between 150 l and 3000 l — Design, construction and testing*

ISO 13341, *Gas cylinders — Fitting of valves to gas cylinders*

ISO 13769, *Gas cylinders — Stamp marking*

ISO 14130, *Fibre-reinforced plastic composites — Determination of apparent interlaminar shear strength by short-beam method*

ASTM D 522-93a, *Standard Test Methods for Mandrel Bend Test of Attached Organic Coatings*

ASTM D1308, *Standard Test Method for Effect of Household Chemicals on Clear and Pigmented Organic Finishes*

ASTM D2794, *Standard Test Method for Resistance of Organic Coatings to the Effects of Rapid Deformation (Impact)*

ASTM D3170, *Standard Test Method for Chipping Resistance of Coatings*

ASTM D7269, *Standard Test Methods for Tensile Testing of Aramid Yarns*

ASTM E1356-08, *Standard Test Method for Assignment of the Glass Transition Temperatures by Differential Scanning Calorimetry*

### 3 Terms and definitions

For the purposes of this document, the terms and definitions in ISO 10286 and the following apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- IEC Electropedia: available at <http://www.electropedia.org/>
- ISO Online browsing platform: available at <https://www.iso.org/obp>

**3.1****aramid fibre**

continuous filaments of aramid laid up in tow form, used for reinforcement

**3.2****autofrettage**

pressure application procedure which strains the metal liner past its yield point sufficient to cause permanent plastic deformation, and results in the liner having compressive stresses and the fibres having tensile stresses when at zero internal gauge pressure

**3.3****batch**

collective term for a set of homogeneous items or material

Note 1 to entry: The number of items in a batch can vary according to the context in which the term is used.

**3.4****batch of load sharing liners**

quantity of liners of the same nominal diameter, length, thickness and design, made successively from the same material cast (heat) and processed in the same heat treatment equipment (i.e. a continuous furnace process or a single furnace charge) using the same heat treatment parameters

**3.5****batch of non-metallic liners**

quantity of non-metallic liners of the same nominal diameter, length, thickness and design, made successively and subjected to the same continuous manufacturing process

**3.6****batch of metal bosses**

quantity of metal bosses of the same nominal diameter, length, thickness and design, made successively from the same material cast (heat) and processed in the same heat treatment equipment using the same heat treatment parameters

**3.7****batch of finished tubes**

production quantity of up to 200 finished tubes successively produced (plus finished tubes required for destructive testing), of the same nominal diameter, length, thickness and design

Note 1 to entry: The batch of finished tubes can contain different batches of liners, fibres and matrix materials.

**3.8****burst pressure**

highest pressure reached in a tube or liner during a burst test

**3.9****carbon fibre**

continuous filaments of carbon laid up in tow form, used for reinforcement

**3.10****composite overwrap**

combination of fibres and matrix used to reinforce the tube, including any barrier or protective layers that are a permanent part of the design

**3.11****dedicated gas service**

service in which a tube is to be used only with specified gas or gases

**3.12****equivalent fibre**

fibre from the same material family and similar properties to a fibre used in a previously prototype tested tube

**3.13**  
**equivalent liner**

liner manufactured from the same nominal raw materials, using the same process of manufacture and having the same physical structure and the same nominal physical properties (within  $\pm 5\%$ ) of the approved liner design

**3.14**  
**equivalent matrix**

resin matrix from the same chemical family and similar properties to the resin matrix used in a previously prototype tested cylinder

**3.15**  
**exterior coating**

layers of material applied to the tube as protection or for cosmetic purposes

Note 1 to entry: The coating can be transparent or opaque.

**3.16**  
**glass fibre**

continuous filaments of glass laid up in tow form, used for reinforcement

**3.17**  
**leak**

escape of gas at a rate greater than  $5 \times 10^{-3}$  mbar.l/s through a defect rather than permeation

**3.18**  
**liner**

inner portion of the composite tube, whose purpose is both to contain the gas and transmit the gas pressure to the fibres

iTeh STANDARD PREVIEW  
(standards.iteh.ai)

**3.19**  
**load sharing liner**

liner that has a burst pressure greater than or equal to 5% of the nominal burst pressure of the finished composite tube

ISO/DIS 11515  
<https://standards.iteh.ai/catalog/standards/sist/10535231-9817-4db4-9cdf-b5601a198854/iso-dis-11515>

**3.20**  
**non-load-sharing liner**

liner that provides no load sharing for the finished composite tube

**3.21**  
**matrix**

material that is used to bind and hold the fibres in place

**3.22**  
**minimum design burst pressure**

minimum burst pressure specified by the manufacturer and that shall be achieved during a burst test

**3.23**  
**representative composite tube**

a shorter tube with the same nominal diameter, and manufactured using the same materials and manufacturing technique, and using a representative wrapping pattern (same number of strands and same number of layers) so as to represent an equivalent stress compared to a full scale prototype

**3.24**  
**tube**

transportable pressure receptacle of a water capacity exceeding 150 litres

**3.25**  
**tubing**

hollow cylindrical body of metal or other material, used for conveying or containing liquids or gases

**3.26****type 2 tube**

hoop wrapped tube with a load sharing metal liner and composite reinforcement on the cylindrical portion only

**3.27****type 3 tube**

fully wrapped tube with a load sharing metal liner and composite reinforcement on both cylindrical portion and dome ends

**3.28****type 4 tube**

fully wrapped tube with a non-metallic, non-load-sharing liner and composite reinforcement on both cylindrical portion and dome ends

**3.29****glass transition temperature  $T_g$** 

the temperature where a polymer substrate changes from a rigid glassy material to a soft (not melted) material, and is usually measured in terms of the stiffness, or modulus

**4 Symbols**

$p_b$	Burst pressure of finished tube	bar
$p_h$	Test pressure	bar
$p_{max}$	Maximum developed pressure at 65 °C	bar
$p_w$	Working pressure	bar

<https://standards.iteh.ai/catalog/standards/sist/10535231-9817-4db4-9cdf-b56b01e7988f/iso-dis-11515>

**5 Inspection and testing**

ISO 11515 is intended to be used under a variety of national regulatory regimes but has been written so that it is suitable for use with the conformity assessment system of the UN Model Regulations for the Transportation of Dangerous Goods. Attention is drawn to requirements in specified relevant national regulations of the country (countries) where the tubes are intended to be used that might override the requirements given in this document. To ensure that the tubes conform to this document, they shall be subject to inspection and testing in accordance with [Clauses 6, 7, 8](#) and [9](#) by an inspection body (hereafter referred to as “the inspector”) authorized to do so.

Tests and examinations performed to demonstrate compliance with this document shall be conducted using instruments calibrated before being put into service and thereafter according to an established programme.

**6 Materials****6.1 Liner materials**

**6.1.1** Load sharing liner materials shall conform in all relevant respects to the appropriate International Standards:

- a) seamless steel liners: ISO 9809-1, ISO 9809-2, ISO 9809-3 or ISO 11120 as appropriate;
- b) seamless aluminium alloy liners: ISO 7866.

Relevant sections are those covering materials, thermal treatments, neck design, construction and workmanship, mechanical tests. Design requirements are excluded since these are specified by the manufacturer for the design of the composite tube (see [7.2.2](#)).

**6.1.1.1** The composite tube manufacturer shall verify that each new batch of materials has the specified properties and qualities, and shall maintain records so that the cast of material and the heat treatment batch (where applicable) used for the manufacture of each tube can be identified. A certificate of conformance from the liner material manufacturer is considered acceptable for the purposes of verification.

**6.1.1.2** The liner shall be manufactured from a metal or alloy suitable for the gas to be contained in accordance with ISO 11114-1.

**6.1.1.3** When a neck ring is provided, it shall be of a material compatible with that of the tube, and shall be securely attached by a method appropriate to the liner material.

**6.1.1.4** Non-load-sharing liner materials shall conform in all relevant respects to the appropriate standards, as follows:

- a) The liner (including metal boss) shall be manufactured from a material suitable for the gas to be contained in accordance with ISO 11114-1 and ISO 11114-2 or demonstrated and documented by suitable testing.
- b) Metal bosses attached to a non-metallic liner shall fulfil the type approval testing requirements of this document.
- c) The tensile yield strength and ultimate elongation of plastic liner material shall be determined at  $-50\text{ °C}$  in accordance with ISO 527-2. The test results shall demonstrate the ductile properties of the plastic liner material at temperatures of  $-50\text{ °C}$  or lower by meeting the values specified by the manufacturer.  
<https://standards.iteh.ai/catalog/standards/sist/10535231-9817-4db4-9cdf/b56b01e7988f/iso-dis-11515>
- d) Polymeric materials from finished liners shall be tested in accordance with a method described in ISO 306. The softening temperature shall be at least  $100\text{ °C}$ .

## 6.2 Composite overwrap

**6.2.1** The overwrap filament materials shall be carbon fibre or aramid fibre or glass fibre (or any mixture thereof).

**NOTE** Glass fibre reinforced composite tubes can be susceptible to chemical attack and degradation after being in contact with aggressive acids (e.g. battery acid).

**6.2.2** The resin matrix shall be a polymer suited to the application, environment and intended life of the product, e.g. epoxy or modified epoxy with amine or anhydride curing agent, vinyl esters and polyesters.

**6.2.3** The supplier of the filament material and the resin matrix system component materials shall provide documentation for the composite tube manufacturer to be able to identify fully the batch of materials used in the manufacture of each tube.

**6.2.4** The composite tube manufacturer shall verify that each new batch of materials has the correct properties and is of satisfactory quality, and maintain records from which the batch of materials used for the manufacture of each tube can be identified. A certificate of conformance from the material manufacturer is considered acceptable for the purposes of verification.

**6.2.5** Batches of materials shall be identified and documented, and supplied to the inspector.

**6.2.6** The manufacturer shall ensure there is no adverse reaction between the liner and the reinforcing fibre, e.g. by the application of a suitable protective coating to the liner prior to the wrapping process (if necessary).

## 7 Design and manufacture

### 7.1 General

**7.1.1** A Type 2 composite tube shall comprise:

- a) an internal metal liner with one or two openings along the central axis only, which carries all the longitudinal load and part of the circumferential load;
- b) the liner designed to withstand a burst pressure greater than 0,85 of the test pressure of the finished tube.
- c) a composite overwrap formed by layers of continuous fibres in a matrix along the parallel portions of the tube sidewall;
- d) an optional exterior coating to provide external protection. When this is an integral part of the design it shall be permanent.

**7.1.2** A Type 3 composite tube shall comprise:

- a) an internal metal liner with one or two openings along the central axis only, which carries part of the longitudinal and circumferential load;
- b) a composite overwrap formed by layers of continuous fibres in a matrix;
- c) an optional exterior coating to provide external protection. When this is an integral part of the design it shall be permanent.

**7.1.3** A Type 4 composite tube shall comprise:

- a) an internal non-metallic non-load-sharing liner with one or two openings along the central axis only;
- b) metallic boss(es) for thread connections, where these are part of the design;
- c) a composite overwrap formed by layers of continuous fibres in a matrix;
- d) an optional exterior coating to provide external protection. When this is an integral part of the design it shall be permanent.

### 7.2 Design submission

**7.2.1** The design submission for each new design of tube shall include a detailed drawing, along with documentation of the design including, manufacturing and inspection particulars as detailed in [7.2.2](#), [7.2.3](#), and [7.2.4](#).

The design submission will cover a design family of composite tubes of the same diameter and pressure with different cylindrical lengths from 2 × diameter and up to 5 × the length of the representative composite tube and with a water capacity between 450 and 3 000 l.

**7.2.2** Documentation for the liner and/or metal boss(es) shall include:

- a) Material details, including limits of chemical analysis;
- b) dimensions, minimum thickness, straightness and out of roundness with tolerances;

- c) process and specification of manufacture;
- d) heat-treatment, temperatures, duration and tolerances (where applicable);
- e) inspection procedures (minimum requirements);
- f) material properties (including hardness for Type 2 and Type 3 tubes);
- g) minimum design burst pressure (for Type 2 and Type 3 tube liners);
- h) dimensional details of valve threads;
- i) method of sealing boss to liner for Type 4 tubes.

**7.2.3** Documentation for the composite overwrap shall include:

- a) fibre material, specification and mechanical properties requirements;
- b) minimum composite thickness;
- c) resin system - main components and resin bath temperature where applicable;
- d) thermoplastic matrix system – main component materials, specifications and process temperatures;
- e) thermosetting matrix – specifications (including resin, curing agent and accelerator), and resin bath temperature where applicable;
- f) overwrap construction including the number of strands used, number of layers, and layer orientation;
- g) curing process, temperatures, duration and tolerances.

STANDARD PREVIEW  
(standards.iteh.ai)

ISO/DIS 11515

**7.2.4** Documentation for the composite tube shall include:

<https://standards.iteh.ai/catalog/standards/sist/10535231-9817-4db4-9cdf-b56b01e7988f/iso-dis-11515>

- a) water capacity in litres;
- b) dimensions, minimum thickness, straightness and out of roundness with tolerances;
- c) list of intended contents if intended for dedicated gas service;
- d) working pressure  $p_w$  which shall not exceed 2/3 test pressure;
- e) composite tube test pressure,  $p_h$ ;
- f) allowable range of elastic expansions and permanent expansions (if appropriate) for the design when volumetric expansion test is used (See 9.5.4), to the satisfaction of the Competent Authority;
- g) maximum developed pressure at 65 °C for specific dedicated gas(es)  $p_{max}$ ;
- h) minimum design burst pressure;
- i) design life in years (15 years or greater);
- j) autofrettage pressure and approximate duration (where applicable);
- k) tensioning of the fibre at winding (where applicable);
- l) weight and manufacturing tolerance;
- m) details of components which are permanently attached and form part of the qualified design (e.g. neck rings, protective boots etc.).

### 7.3 Manufacturing

**7.3.1** The liner and metal bosses, where incorporated, shall be manufactured in accordance with the manufacturer's design (see [7.2.2](#)).

**7.3.2** The composite tube shall be fabricated from a load sharing or non-load-sharing liner over-wrapped with resin impregnated continuous fibres. Winding shall be applied under controlled conditions to develop the design composite thickness and as specified in [7.2.3](#).

Liners can be stripped and re-wound provided that the overwrap has not been cured. The liner shall not be over-wrapped if it has been damaged or scored by the stripping process.

**7.3.3** After winding is completed the composite shall be cured (if appropriate) using a controlled temperature profile as specified in [7.2.3](#). The maximum temperature shall be such that the mechanical properties of the liner material are not adversely affected.

**7.3.4** If tubes are subjected to an autofrettage operation, the autofrettage pressure and duration shall be as specified in [7.2.4](#). The manufacturer shall demonstrate the effectiveness of the autofrettage by appropriate measurement technique(s) acceptable to the inspector.

**7.3.5** If tubes are subjected to a pre-stressing or fibre tensioning during winding to actively change the final stresses in the finished tube, the level of stress shall be as specified in [7.2.4](#) and levels of stress of tensioning shall be recorded or monitored.

iteh STANDARD PREVIEW

## 8 Type approval procedure (standards.iteh.ai)

### 8.1 General

ISO/DIS 11515

<https://standards.iteh.ai/catalog/standards/sist/10535231-9817-4db4-9cdf>

The design submission of each new design of composite tube shall be submitted by the manufacturer to the inspector. The type approval tests detailed in [8.2](#) shall be carried out on each new design or design variant under the supervision of the inspector.

### 8.2 Prototype tests

**8.2.1** A sufficient number of tubes shall be made available from a single batch to complete the prototype testing or testing of the design variant.

Note Additional tubes from the same prototype batch may be made available in case of test equipment failure.

**8.2.2** The inspector shall verify that the batch of liners, prior to being wrapped, conforms to the design requirements and are inspected and tested in accordance with [9.1](#) or [9.2](#), as appropriate.

**8.2.3** The inspector shall verify that the composite material(s), prior to the tubes being wrapped, conform to the design requirements and are tested in accordance with [9.4](#).

**8.2.4** The inspector shall verify that all tubes in the batch produced for new design approval conform to the design submission and are tested in accordance with [9.5](#). Except for the cases identified in [8.2.5](#), the inspector shall supervise the tests shown in [Table 1](#). An "A" in the relevant column of [Table 1](#) shows that the test is required for the appropriate tube category. An "O" in the relevant column of [Table 1](#) shows that