DRAFT INTERNATIONAL STANDARD ISO/DIS 24376

ISO/TC 45/SC 3

Voting begins on: **2021-04-06**

Secretariat: AFNOR

Voting terminates on: 2021-06-29

Rubber, raw natural - Guidelines for technically specified low-protein natural rubber

Caoutchouc naturel brut — Lignes directrices pour le caoutchouc naturel à faible teneur en protéines spécifié techniquement

ICS: 83.040.10

iTeh STANDARD PREVIEW (standards.iteh.ai)

ISO/DIS 24376 https://standards.iteh.ai/catalog/standards/sist/610c2acd-2dfd-4f5a-8fd3-7f17178d7406/iso-dis-24376

THIS DOCUMENT IS A DRAFT CIRCULATED FOR COMMENT AND APPROVAL. IT IS THEREFORE SUBJECT TO CHANGE AND MAY NOT BE REFERRED TO AS AN INTERNATIONAL STANDARD UNTIL PUBLISHED AS SUCH.

IN ADDITION TO THEIR EVALUATION AS BEING ACCEPTABLE FOR INDUSTRIAL, TECHNOLOGICAL, COMMERCIAL AND USER PURPOSES, DRAFT INTERNATIONAL STANDARDS MAY ON OCCASION HAVE TO BE CONSIDERED IN THE LIGHT OF THEIR POTENTIAL TO BECOME STANDARDS TO WHICH REFERENCE MAY BE MADE IN NATIONAL REGULATIONS.

RECIPIENTS OF THIS DRAFT ARE INVITED TO SUBMIT, WITH THEIR COMMENTS, NOTIFICATION OF ANY RELEVANT PATENT RIGHTS OF WHICH THEY ARE AWARE AND TO PROVIDE SUPPORTING DOCUMENTATION. This document is circulated as received from the committee secretariat.



Reference number ISO/DIS 24376:2021(E)

iTeh STANDARD PREVIEW (standards.iteh.ai)

ISO/DIS 24376 https://standards.iteh.ai/catalog/standards/sist/610c2acd-2dfd-4f5a-8fd3-7f17178d7406/iso-dis-24376



COPYRIGHT PROTECTED DOCUMENT

© ISO 2021

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office CP 401 • Ch. de Blandonnet 8 CH-1214 Vernier, Geneva Phone: +41 22 749 01 11 Email: copyright@iso.org Website: www.iso.org

Published in Switzerland

Page

Contents

Forew	ord	iv
Introd	uction	v
1	Scope	1
2	Normative references	1
3	Terms and definitions	1
4	Material composition	2
5	Grade structure	2
6	Specification of requirement	2
7	Sampling	3
8	Packaging	4
Annex	A (informative) Low protein natural rubber (LPNR)	5
Annex	B (informative) Examples of the removal of proteins from raw natural rubber	7
Biblio	graphy	11

iTeh STANDARD PREVIEW (standards.iteh.ai)

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 45, *Rubber and rubber product*, Subcommittee SC 3, *Raw materials (including latex) for use in the rubber industry*. https://standards.iteh.avcatalog/standards/sist/610c2acd-2dfd-4f5a-8fd3-

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at <u>www.iso.org/members.html</u>.

Introduction

Significant developments have taken place in the supply of raw natural rubber, especially in relation to the number of different grades that are technically specified. The constant viscosity (*CV*), latex (*L*) and gel content (*LoV*) grades have been added in addition to the initial grades covered in ISO 2000. The development and availability of physical and/or chemically modified grades are now reported in the technical literature (see Annex A).

This document encompasses raw rubber, natural which has been subjected to a process of removal of naturally occurring proteins that is commonly and commercially referred to as Deproteinised Natural Rubber (DPNR).

However, the processes employed for removal of the proteins from natural rubber do not completely do so. The measurement of these residual proteins and specifying limits for these proteins is necessary to specify these dry rubber grades of low protein rubber. The acronym LPNR would identify and distinguish these grades from the latex grades and from a completely protein free natural rubber should it become available (see <u>Annex B</u>).

This document encompasses some rubbers that are better defined elsewhere. For more precise specifications, reference may need to be made to such specifications in particular cases which may be found in the standards or in the literature of manufacturers of these low protein natural rubber grades.

iTeh STANDARD PREVIEW (standards.iteh.ai)

iTeh STANDARD PREVIEW (standards.iteh.ai)

Rubber, raw natural - Guidelines for technically specified low-protein natural rubber

1 Scope

This document provides guidance on the specification of low protein natural rubber (LPNR). A grading system is proposed, based on the origin of the natural rubber content and differentiated by the two processes, enzymatic and non enzymatic, applied for removal of the proteins.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 247-1, Rubber — Determination of ash — Part 1: Combustion method

ISO 248-1, Rubber, raw — Determination of volatile-matter content — Part 1: Hot-mill method and oven method

ISO 249, Rubber, raw natural — Determination of dirt content

ISO 289-1, Rubber, unvulcanized to beterminations using a shearing-disc viscometer — Part 1: Determination of Mooney viscosity

ISO/DIS 24376 ISO 1656, Rubber, row natural, and rubber latex, natural, 10 Determination of nitrogen content

^{7f17178d7406/iso-dis-24376} ISO 1795, Rubber, raw natural and raw synthetic — Sampling and further preparative procedures

ISO 2007, Rubber, unvulcanized — Determination of plasticity — Rapid-plastimeter method

ISO 2930, Rubber, raw natural — Determination of plasticity retention index (PRI)

ASTM D5712, Standard Test Method for Analysis of Aqueous Extractable Protein in Latex, Natural Rubber, and Elastomeric Products Using the Modified Lowry Method

ASTM D6499, Standard Test Method for Immunological Measurement of Antigenic Protein in Hevea Natural Rubber (HNR) and its Products

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at https://www.iso.org/obp

— IEC Electropedia: available at <u>http://www.electropedia.org/</u>

3.1

technically specified rubber

TSR

natural rubber obtained from the latex of *Hevea brasiliensis* (typically processed into block rubber), and having properties complying with the criteria for the grade concerned

[SOURCE: ISO 2000:2020, 3.1]

3.2

technically specified low protein natural rubber

natural rubber which has been treated for the removal of naturally occurring proteins by an enzymatic or non enzymatic process

3.3

constant viscosity (CV) rubber

natural rubber whose viscosity is controlled, typically by treating it with viscosity-stabilizing agents prior to the drying process

3.4

whole field latex

WF

latex material derived from Hevea Brasiliensis which may be diluted but is not fractionated

4 Material composition

Low protein natural rubber (LPNR) shall be divided into the following two principal groups based on

- a) the treatment process applied the whole field latex to remove the proteins, and
- b) whose viscosity is controlled, typically by treating it with viscosity stabilizing agents prior to the drying process.

5 Grade structure **iTeh STANDARD PREVIEW**

The grade structure of LPNR shall be based on the properties of the DPLNR and the type of material used in its production. See <u>Table 1</u>.

ISO/DIS 24376 https://standartrable.icatal@cradesoffEPNR2acd-2dfd-4f5a-8fd3-7ff7178d7406/iso-dis-24376

Raw material	Characteristics	Grades
Whole field latex treated with an enzymatic protein ex- traction agent	With no specified viscosity -S With controlled viscosity	E-WFS E-CV50 or E-CV60
Whole field latex treated with a non- enzymatic protein extraction agent	With no specified viscosity -S With controlled viscosity	NE-WFS NE- CV50 or NE-CV60

NOTE Several proteolytic enzymes have been reported for the removal of proteins.

Nonenzymatic agents for protein removal include fumed silica, urea and aluminium hydroxide.

Some of these processes are covered by current patents in some countries.

6 Specification of requirement

Any specific values for physical and chemical properties shall be based upon the grade (see Table 2).

Properties	Grade ^a							
	E-WFS	E-CV50	E-CV60	NE-WFS	NE-CV50	NE-CV60	Test method	
Colour coding mark- er ^b	Green	Blue ^b	Blue ^b	Green	Blue ^b	Blue ^b		
Dirt retained on sieve								
maximum	0,03	0,03	0,03	0,03	0,03	0,03	ISO 249	
% (mass fraction)								
Ash								
maximum	0,25	0,25	0,25	0,25	0,25	0,25	ISO 247-1	
% (mass fraction)								
Nitrogen content								
maximum	0,15	0,15	0,15	0,15	0,15	0,15	ISO 1656	
% (mass fraction)								
Volatile matter content								
maximum	0,5	0,5	0,5	0,5	0,5	0,5	ISO 248-1	
% (mass fraction)	iTob (CTAN		DDF				
Initial plasticity (Po)	30	(stand	laras.i	teh ³⁰ ai)	N/A	N/A	ISO 2007	
minimum								
Plasticity retention								
index (PRI) ^c	60	60 <u>1</u> s iteh ai/catalo	SO/L& 2437	<u>6</u> 60 st/610c2acd-2	60 2dfd-4f5a-8fd3	60	ISO 2930	
minimum ***	1902/0unuuuu	7f1717	8d7406/iso-di	s-24376				
Mooney viscosity N/A		55 ± 5°	65 ± 5°	N/A	55 ± 5°	65 ± 10 ^c	ISO 289-1	
ML(1+4) at 100 °C				,				
Extractable protein	100	100	100	100	100	100	ASTM D5712 ^d	
maximum (µg/g)								
Antigenic protein	genic protein		_	_	_	10	ASTM D6499 ^d	
maximum (µg/g) ^e		10						

Table 2 — Typical properties of LPNR

^a The raw material is given in <u>Table 1</u>.

^b Suggested colours.

^c Other viscosity levels may be agreed between interested parties. For specific applications, e.g. low viscosity CV40 for adhesives. In lieu of PRI the application of a maximum P of 12 units may also be agreed between interested parties.

^d ASTM Standard in the absence of an equivalent ISO Standard

^e Grade suitable for food and medical application

7 Sampling

LPNR shall be sampled in accordance with ISO 1795, unless otherwise agreed between interested parties.

Each sample derived from the lot shall comply with the requirements agreed for that grade of LPNR.

8 Packaging

LPNR should normally be packed in bales of nominal mass 33,3 kg \pm 0,5 %.

36 bales are packaged in 1,2 metric tonne wooden crates.

The nominal dimensions of the bale is 330 mm x 670 mm x 170 mm.

On agreement between the interested parties, bales of other weights and nominal dimensions can be used.

Each bale shall be:

- identified;
- marked;
- wrapped either in polyethylene film compatible with natural rubber, having a preferred thickness of 30 μ m to 50 μ m, density of 0,92 g cc⁻¹, melting point 110 °C and a Vicat softening point lower than 95 °C (as set out in ISO 20299-2); or
- in some other form of packaging as agreed between interested parties.

On agreement between the interested parties, a maximum thickness of 65 μ m can be used especially if the removal of the packaging film is desired **NDARD PREVIEW**

(standards.iteh.ai)