



Designation: A751 – 11

# Standard Test Methods, Practices, and Terminology for Chemical Analysis of Steel Products<sup>1</sup>

This standard is issued under the fixed designation A751; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

*This standard has been approved for use by agencies of the Department of Defense.*

## INTRODUCTION

These test methods, practices, and terminology were prepared to answer the need for a single document that would include all aspects of obtaining and reporting the chemical analysis of steel, stainless steel, and related alloys. Such subjects as definitions of terms and product (check) analysis variations (tolerances) required clarification. Requirements for sampling, meeting specified limits, and treatment of data usually were not clearly established in product specifications.

It is intended that these test methods, practices, and terminology will contain all requirements for the determination of chemical composition of steel, stainless steel, or related alloys so that product specifications will need contain only special modifications and exceptions.

## 1. Scope\*

1.1 These test methods, practices, and terminology cover definitions, reference methods, practices, and guides relating to the chemical analysis of steel, stainless steel, and related alloys. It includes both wet chemical and instrumental techniques.

1.2 Directions are provided for handling chemical requirements, product analyses, residual elements, and reference standards, and for the treatment and reporting of chemical analysis data.

1.3 These test methods, practices, and terminology apply only to those product standards which include these test methods, practices, and terminology, or parts thereof, as a requirement.

1.4 In cases of conflict, the product specification requirements shall take precedence over the requirements of these test methods, practices, and terminology.

1.5 Attention is directed to ISO/IEC 17025 when there may be a need for information on criteria for evaluation of testing laboratories.

1.6 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appro-*

*priate safety and health practices and determine the applicability of regulatory limitations prior to use.*

## 2. Referenced Documents

### 2.1 ASTM Standards:<sup>2</sup>

E29 Practice for Using Significant Digits in Test Data to Determine Conformance with Specifications

E30 Test Methods for Chemical Analysis of Steel, Cast Iron, Open-Hearth Iron, and Wrought Iron (Withdrawn 1995)<sup>3</sup>

E50 Practices for Apparatus, Reagents, and Safety Considerations for Chemical Analysis of Metals, Ores, and Related Materials

E60 Practice for Analysis of Metals, Ores, and Related Materials by Spectrophotometry

E212 Test Method for Spectrographic Analysis of Carbon and Low-Alloy Steel by the Rod-to-Rod Technique (Withdrawn 1997)<sup>3</sup>

E293 Test Method for Spectrographic Determination of Acid-Soluble Aluminum in Low-Alloy Steel by the Solution Technique (Withdrawn 1997)<sup>3</sup>

E322 Test Method for X-Ray Emission Spectrometric Analysis of Low-Alloy Steels and Cast Irons

E327 Test Method for Optical Emission Spectrometric Analysis of Stainless Type 18-8 Steels by the Point-to-Plane Technique (Withdrawn 1999)<sup>3</sup>

<sup>1</sup> These test methods, practices, and terminology are under the jurisdiction of ASTM Committee A01 on Steel, Stainless Steel and Related Alloys and are the direct responsibility of Subcommittee A01.13 on Mechanical and Chemical Testing and Processing Methods of Steel Products and Processes.

Current edition approved Nov. 1, 2011. Published November 2011. Originally approved in 1977. Last previous edition approved in 2007 as A751 – 08. DOI: 10.1520/A0751-11.

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, [www.astm.org](http://www.astm.org), or contact ASTM Customer Service at [service@astm.org](mailto:service@astm.org). For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

<sup>3</sup> The last approved version of this historical standard is referenced on [www.astm.org](http://www.astm.org).

\*A Summary of Changes section appears at the end of this standard

**E350** Test Methods for Chemical Analysis of Carbon Steel, Low-Alloy Steel, Silicon Electrical Steel, Ingot Iron, and Wrought Iron

**E352** Test Methods for Chemical Analysis of Tool Steels and Other Similar Medium- and High-Alloy Steels

**E353** Test Methods for Chemical Analysis of Stainless, Heat-Resisting, Maraging, and Other Similar Chromium-Nickel-Iron Alloys

**E354** Test Methods for Chemical Analysis of High-Temperature, Electrical, Magnetic, and Other Similar Iron, Nickel, and Cobalt Alloys

**E404** Test Method for Spectrographic Determination of Boron in Carbon and Low-Alloy Steel by the Point-to-Plane Technique (Withdrawn 2006)<sup>3</sup>

**E415** Test Method for Atomic Emission Vacuum Spectrometric Analysis of Carbon and Low-Alloy Steel

**E421** Test Method for Spectrographic Determination of Silicon and Aluminum in High-Purity Iron (Withdrawn 1997)<sup>3</sup>

**E485** Test Method for Optical Emission Vacuum Spectrometric Analysis of Blast Furnace Iron by the Point-to-Plane Technique (Withdrawn 2011)<sup>3</sup>

**E548** Guide for General Criteria Used for Evaluating Laboratory Competence (Withdrawn 2002)<sup>3</sup>

**E572** Test Method for Analysis of Stainless and Alloy Steels by X-ray Fluorescence Spectrometry

**E663** Practice for Flame Atomic Absorption Analysis (Withdrawn 1997)<sup>3</sup>

**E743** Guide for Spectrochemical Laboratory Quality Assurance (Withdrawn 1998)<sup>3</sup>

**E851** Practice for Evaluation of Spectrochemical Laboratories (Withdrawn 1998)<sup>3</sup>

**E882** Guide for Accountability and Quality Control in the Chemical Analysis Laboratory

**E1019** Test Methods for Determination of Carbon, Sulfur, Nitrogen, and Oxygen in Steel, Iron, Nickel, and Cobalt Alloys by Various Combustion and Fusion Techniques

**E1024** Guide for Chemical Analysis of Metals and Metal Bearing Ores by Flame Atomic Absorption Spectrophotometry (Withdrawn 2004)<sup>3</sup>

**E1063** Test Method for X-Ray Emission Spectrometric Determination of Cerium and Lanthanum in Carbon and Low-Alloy Steels (Withdrawn 1998)<sup>3</sup>

**E1085** Test Method for Analysis of Low-Alloy Steels by X-Ray Fluorescence Spectrometry

**E1086** Test Method for Atomic Emission Vacuum Spectrometric Analysis of Stainless Steel by Point-to-Plane Excitation Technique

**E1097** Guide for Determination of Various Elements by Direct Current Plasma Atomic Emission Spectrometry

**E1184** Practice for Determination of Elements by Graphite Furnace Atomic Absorption Spectrometry

**E1282** Guide for Specifying the Chemical Compositions and Selecting Sampling Practices and Quantitative Analysis Methods for Metals, Ores, and Related Materials

**E1329** Practice for Verification and Use of Control Charts in Spectrochemical Analysis

**E1806** Practice for Sampling Steel and Iron for Determination of Chemical Composition

2.2 *ISO Standards*.<sup>4</sup>

**ISO/IEC 17025** General Requirements for the Competence of Testing and Calibration Laboratories

### 3. Terminology

3.1 *Definitions*:

3.1.1 *Pertaining to Analyses*:

3.1.1.1 *cast or heat (formerly ladle) analysis*—applies to chemical analyses representative of a heat of steel as reported to the purchaser and determined by analyzing a test sample, preferably obtained during the pouring of the steel, for the elements designated in a specification.

3.1.1.2 *product, check or verification analysis*—a chemical analysis of the semifinished or finished product, usually for the purpose of determining conformance to the specification requirements. The range of the specified composition applicable to product analysis is normally greater than that applicable to heat analysis in order to take into account deviations associated with analytical reproducibility (**Note 1**) and the heterogeneity of the steel.

**NOTE 1**—All of the chemical analysis procedures referenced in this document include precision statements with reproducibility data with the exception of Test Methods **E50**.

3.1.1.3 *product analysis tolerances (Note 2)*—a permissible variation over the maximum limit or under the minimum limit of a specified element and applicable only to product analyses, not cast or heat analyses.

**NOTE 2**—The term “analysis tolerance” is often misunderstood. It does not apply to cast or heat analyses determined to show conformance to specified chemical limits. It applies only to product analysis and becomes meaningful only when the heat analysis of an element falls close to one of the specified limits. For example, stainless steel UNS 30400 limits for chromium are 18.00 to 20.00 %. A heat that the producer reported as 18.01 % chromium may be found to show 17.80 % chromium by a user performing a product analysis. If the product analysis tolerance for such a chromium level is 0.20 %, the product analysis of 17.80 % chromium would be acceptable. A product analysis of 17.79 % would not be acceptable.

3.1.1.4 *proprietary analytical method*—a non-standard analytical method, not published by ASTM, utilizing reference standards traceable to the National Institute of Standards and Technology (NIST) (when available) or other sources referenced in Section 10.

3.1.1.5 *referee analysis*—performed using ASTM methods listed in 9.1.1 and NIST reference standards or methods and reference standards agreed upon between parties. The selection of a laboratory to perform the referee analysis shall be a matter of agreement between the supplier and the purchaser.

3.1.1.6 *certified reference material*—a specimen of material specially prepared, analyzed, and certified for chemical content under the jurisdiction of a recognized standardizing agency or group, such as the National Institute of Standards and Technology, for use by analytical laboratories as an accurate basis for comparison. Reference samples should bear sufficient

<sup>4</sup> Available from American National Standards Institute (ANSI), 25 W. 43rd St., 4th Floor, New York, NY 10036, <http://www.ansi.org>.

resemblance to the material to be analyzed so that no significant differences are required in procedures or corrections (for example, for interferences or inter-element effects).

3.1.1.7 *working reference materials*—reference materials used for routine analytical control and traceable to NIST standards and other recognized standards when appropriate standards are available.

3.1.2 *Pertaining to Elements:*

3.1.2.1 *intentionally added unspecified element*—an element added in controlled amounts at the option of the producer to obtain desirable characteristics.

3.1.2.2 *residual element*—a specified or unspecified element, not intentionally added, originating in raw materials, refractories, or air.

3.1.2.3 *specified element*—an element controlled to a specified range, maximum or minimum, in accordance with the requirements of the product specification.

3.1.2.4 *trace element*—a residual element that may occur in very low concentrations, generally less than 0.01 %.

#### 4. Concerning the Specification of Chemical Composition Requirements

4.1 It is recommended that Guide E1282 be consulted as a guide for specifying the chemical compositions for steels.

4.2 The recommended practice for specifying chemical composition limits is to limit the number of significant figures for each element so that the number of figures to the right of the decimal point conforms to the following:

Chemical Concentration		Maximum Number of Figures to the Right of the Decimal Point
Up to 0.010 %, incl.	—	0.XXXX or may be expressed as ppm
Over 0.010 % to 0.10 %, incl.	—	0.XXX
Over 0.10 % to 3.0 %, incl.	—	0.XX
Over 3.0 %	—	0.X

4.3 For those cases in which the composition range spans either 0.10 % or 3.0 %, the number of figures to the right of the decimal is to be determined by that indicated by the upper limit.

4.4 Technical considerations may dictate the employment of less than the number of figures to the right of the decimal as previously recommended.

NOTE 3—The recommendations should be employed to reduce the number of significant figures, such as from 18.00 % to 18.0 %, but a significant figure should never be added unless there is a technical reason for so doing.

#### 5. Cast or Heat Analysis

5.1 The producer shall perform analyses for those elements specified in the material specification. The results of such analyses shall conform to the requirements specified in the material specification.

5.1.1 For multiple heats, either individual heat or cast analysis or an average heat or cast analysis shall be reported. If significant variations in heat or cast size are involved, a weighted average heat or cast analysis, based on the relative quantity of metal in each heat or cast, shall be reported.

5.1.2 For consumable electrode remelted material, a heat is defined as all the ingots remelted by the same process from a

primary heat. The heat analysis shall be obtained from one remelted ingot, or the product of one remelted ingot, from each primary melt. If this heat analysis does not meet the heat analysis requirements of the specification, one sample from the product of each remelted ingot shall be analyzed, and the analyses shall meet the heat analysis requirements.

5.2 If the test samples taken for the heat analysis are lost, inadequate, or not representative of the heat, a product analysis of the semifinished or finished product may be used to establish the heat analysis.

5.2.1 If a product analysis is made to establish the heat analysis, the product analysis shall meet the specified limits for heat analysis and the product analysis tolerances described in Section 6 do not apply.

#### 6. Product Analysis Requirements

6.1 For product analysis, the range of the specified chemical composition is normally greater (designated product analysis tolerances) than that applicable to heat analyses to take into account deviations associated with analytical reproducibility and the heterogeneity of the steel. If several determinations of any element in the heat are made, they may not vary both above and below the specified range.

6.2 Product analysis tolerances may not be used to determine conformance to the specified heat or cast analysis unless permitted by the individual material specification.

6.3 Product analysis tolerances, where available, are given in the individual material specifications or in the general requirement specifications.

#### 7. Unspecified Elements (Note 4)

7.1 Reporting analyses of unspecified elements is permitted.

NOTE 4—All commercial metals contain small amounts of various elements in addition to those which are specified. It is neither practical nor necessary to specify limits for every unspecified element that might be present, despite the fact that the presence of many of these elements is often routinely determined by the producer.

7.2 Analysis limits shall be established for specific elements rather than groups of elements such as “all others,” “rare earths,” and “balance.”

#### 8. Sampling

8.1 *Cast or Heat Analyses:*

8.1.1 Samples shall be taken, insofar as possible, during the casting of a heat, at a time which, in the producer’s judgment, best represents the composition of the cast.

8.1.2 In case the heat analysis samples or analyses are lost or inadequate, or when it is evident that the sample does not truly represent the heat, representative samples may be taken from the semifinished or finished product, in which case such samples may be analyzed to satisfy the specified requirements. The analysis shall meet the specified limits for heat analysis.

8.2 *Check, Product, or Verification Analyses*—Unless otherwise specified, the latest revision of Practice E1806 shall be used as a guide for sampling.