



SLOVENSKI STANDARD
oSIST prEN 4700-002:2024
01-maj-2024

Aeronavtika - Jeklo in zlitine, odporne proti vročini - Gneteni izdelki - Tehnična specifikacija - 002. del: Palice in profili

Aerospace series - Steel and heat-resisting alloys - Wrought products - Technical specification - Part 002: Bars and sections

Luft- und Raumfahrt - Stahl und Hochwarmfesten Legierungen - Umgeformte Erzeugnisse - Technische Lieferbedingungen - Teil 002: Stangen und Profile

Série aérospatiale - Aciers et alliages résistant à chaud - Produits corroyés - Spécification technique - Partie 002 : Barres et profilés

Ta slovenski standard je istoveten z: prEN 4700-002

[oSIST prEN 4700-002:2024](https://standards.slovenski-institut.si/standards/slo-EN/4700-002-2024)

<https://standards.slovenski-institut.si/standards/slo-EN/4700-002-2024>

ICS:

49.025.10	Jekla	Steels
77.140.60	Jeklene palice in drogovi	Steel bars and rods

oSIST prEN 4700-002:2024

en,fr,de

EUROPEAN STANDARD
NORME EUROPÉENNE
EUROPÄISCHE NORM

DRAFT
prEN 4700-002

March 2024

ICS 49.025.10

Will supersede EN 4700-002:2021

English Version

**Aerospace series - Steel and heat-resisting alloys -
Wrought products - Technical specification - Part 002:
Bars and sections**

Série aérospatiale - Aciers et alliages résistant à chaud -
Produits corroyés - Spécification technique - Partie 002
: Barres et profilés

Luft- und Raumfahrt - Stahl und Hochwarmfesten
Legierungen - Umgeformte Erzeugnisse - Technische
Lieferbedingungen - Teil 002: Stangen und Profile

This draft European Standard is submitted to CEN members for enquiry. It has been drawn up by the Technical Committee ASD-STAN.

If this draft becomes a European Standard, CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration.

This draft European Standard was established by CEN in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Türkiye and United Kingdom.

Recipients of this draft are invited to submit, with their comments, notification of any relevant patent rights of which they are aware and to provide supporting documentation.

Warning : This document is not a European Standard. It is distributed for review and comments. It is subject to change without notice and shall not be referred to as a European Standard.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels

Contents	Page
European foreword	3
Introduction	4
1 Scope	5
2 Normative references	5
3 Terms and definitions	7
4 Wording of order	7
5 Health and safety	8
6 Technical requirements	8
6.1 General	8
6.2 Qualification requirements	8
6.3 Release requirements	8
6.3.1 Release tests	8
6.3.2 Retests	9
6.3.3 Rejection	9
6.3.4 Special tests	9
6.3.5 Capability clause	9
6.3.6 Statistical process control	9
6.3.7 Inspection and test report	10
6.4 Traceability	10
7 Requirements	10
Bibliography	34

oSIST prEN 4700-002:2024

<https://standards.iteh.ai/catalog/standards/sist/ca780074-065c-4ea9-946d-52417ad989da/osist-pren-4700-002-2024>

European foreword

This document (prEN 4700-002:2024) has been prepared by ASD-STAN.

After enquiries and votes carried out in accordance with the rules of this Association, this document has received the approval of the National Associations and the Official Services of the member countries of ASD-STAN, prior to its presentation to CEN.

This document is currently submitted to the CEN Enquiry.

This document will supersede EN 4700-002:2021.

The main changes with respect to the previous edition are as follows:

- update of Clause 2 “Normative references”;
- Table 1: addition of a note in line 17 and addition of ASTM E340 and ASTM E 381 for steels in line 51.

iTeh Standards
(<https://standards.iteh.ai>)
Document Preview

[oSIST prEN 4700-002:2024](https://standards.iteh.ai/catalog/standards/sist/ca780074-065c-4ea9-946d-52417ad989da/osist-pren-4700-002-2024)

<https://standards.iteh.ai/catalog/standards/sist/ca780074-065c-4ea9-946d-52417ad989da/osist-pren-4700-002-2024>

prEN 4700-002:2024 (E)

Introduction

This document is part of the series of EN metallic material standards for aerospace applications. The general organization of this series is described in EN 4258.

iTeh Standards
(<https://standards.iteh.ai>)
Document Preview

[oSIST prEN 4700-002:2024](https://standards.iteh.ai/catalog/standards/sist/ca780074-065c-4ea9-946d-52417ad989da/osist-pren-4700-002-2024)

<https://standards.iteh.ai/catalog/standards/sist/ca780074-065c-4ea9-946d-52417ad989da/osist-pren-4700-002-2024>

1 Scope

This document specifies the requirements for the ordering, manufacture, testing, inspection and delivery of steel and heat-resisting alloy bars and sections. It is presupposed to be applied when referred to and in conjunction with the EN material standard unless otherwise specified on the drawing, order or inspection schedule.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 2002-001,¹ *Aerospace series — Metallic materials — Test methods — Part 001: Tensile testing at ambient temperature*

EN 2002-002, *Aerospace series — Metallic materials — Test methods — Part 002: Tensile testing at elevated temperature*

EN 2002-005, *Aerospace series — Test methods for metallic materials — Part 005: Uninterrupted creep and stress-rupture testing*

EN 2002-16, *Aerospace series — Metallic materials — Test methods — Part 16: Non-destructive testing — Penetrant testing*

EN 2032-001, *Aerospace series — Metallic materials — Part 001: Conventional designation*

EN 2032-2, *Aerospace series — Metallic materials — Part 2: Coding of metallurgical condition in delivery condition*

EN 2078, *Aerospace series — Metallic materials — Manufacturing schedule, inspection schedule, inspection and test report — Definition, general principles, preparation and approval*

EN 2950, *Aerospace series — Test method — Wrought heat resisting alloys Semi-finished products and parts — Conditions for macrographic and micrographic examination — Atlas of structures and defects*

EN 2951, *Aerospace series — Metallic materials — Micrographic determination of content of non-metallic inclusions*

EN 3874,¹ *Aerospace series — Test methods for metallic materials — Constant amplitude force-controlled low cycle fatigue testing*

EN 3987, *Aerospace series — Test methods for metallic materials — Constant amplitude force-controlled high cycle fatigue testing*

EN 3988,¹ *Aerospace series — Test methods for metallic materials — Constant amplitude strain-controlled low cycle fatigue testing*

EN 4050-1, *Aerospace series — Test method for metallic materials — Ultrasonic inspection of bars, plates, forging stock and forgings — Part 1: General requirements*

¹ Published as ASD-STAN Standard at the date of publication of this document by ASD-STAN, <https://www.asd-stan.org/>.

prEN 4700-002:2024 (E)

EN 4050-4, *Aerospace series — Test method for metallic materials — Ultrasonic inspection of bars, plates, forging stock and forgings — Part 4: Acceptance criteria*

EN 4259, *Aerospace series — Metallic materials — Definition of general terms*

EN 9100, *Quality Management Systems — Requirements for Aviation, Space and Defence Organizations*

EN 9133, *Aerospace series — Quality Management Systems — Qualification Procedure for Aerospace Standard Products*

EN 10027-1, *Designation systems for steels — Part 1: Steel names*

EN 10079, *Definition of steel products*

EN ISO 148-1, *Metallic materials — Charpy pendulum impact test — Part 1: Test method (ISO 148-1)*

EN ISO 642, *Steel — Hardenability test by end quenching (Jominy test) (ISO 642)*

EN ISO 643, *Steels — Micrographic determination of the apparent grain size (ISO 643)*

EN ISO 3651-1, *Determination of resistance to intergranular corrosion of stainless steels — Part 1: Austenitic and ferritic-austenitic (duplex) stainless steels — Corrosion test in nitric acid medium by measurement of loss in mass (Huey test) (ISO 3651-1)*

EN ISO 3651-2, *Determination of resistance to intergranular corrosion of stainless steels — Part 2: Ferritic, austenitic and ferritic-austenitic (duplex) stainless steels — Corrosion test in media containing sulfuric acid (ISO 3651-2)*

EN ISO 3887, *Steels — Determination of the depth of decarburization (ISO 3887)*

EN ISO 6506-1, *Metallic materials — Brinell hardness test — Part 1: Test method (ISO 6506-1)*

EN ISO 6507-1, *Metallic materials — Vickers hardness test — Part 1: Test method (ISO 6507-1)*

EN ISO 6508-1, *Metallic materials — Rockwell hardness test — Part 1: Test method (ISO 6508-1)*

EN ISO 6892-1, *Metallic materials — Tensile testing — Part 1: Method of test at room temperature (ISO 6892-1)*

EN ISO 6892-2, *Metallic materials — Tensile testing — Part 2: Method of test at elevated temperature (ISO 6892-2)*

EN ISO 15549, *Non-destructive testing — Eddy current testing — General principles (ISO 15549)*

ISO 4967, *Steel — Determination of content of non-metallic inclusions — Micrographic method using standard diagrams*

AMS 2315,² *Determination of Delta Ferrite Content*

AMS 2750,² *Pyrometry*

² Published by: SAE International (US) <https://www.sae.org/>.

ASTM A604,³ *Standard Practice for Macroetch Testing of Consumable Electrode Remelted Steel Bars and Billets*

ASTM E45,³ *Standard Test Methods for Determining the Inclusion Content of Steel*

ASTM E340,³ *Standard Practice for Macroetching Metals and Alloys*

ASTM E381,³ *Standard Method of Macroetch Testing Steel Bars, Billets, Blooms and Forgings*

ASTM E399,³ *Standard Test Method for Linear-Elastic Plane-Strain Fracture Toughness K_{Ic} of Metallic Materials*

ASTM E407,³ *Standard Practice for Microetching Metals and Alloys*

ASTM E1444,³ *Standard Practice for Magnetic Particle Testing*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in EN 4259 and the following apply. For definitions specific to steel, EN 10079 applies.

ISO and IEC maintain terminology databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp/>
- IEC Electropedia: available at <https://www.electropedia.org/>

3.1

batch

quantity of bars and sections consisting of the same nominal dimensions or having the same heat treatment condition

Note 1 to entry: For the general case, see EN 4259.

Note 2 to entry: For heat treatment using a continuous furnace, a continuous run of less than or equal to eight hours [or: ≤ 8 h] may be considered as the same heat treatment charge.

4 Wording of order

The order shall clearly indicate:

- quantities to be supplied;
- dates of delivery;
- material standard number;
- delivery condition and metallurgical code of products;
- dimensions and tolerances or reference to an appropriate dimensional standard;
- product designation, when required;
- forwarding address;

³ Published by: ASTM International (US) <https://www.astm.org/>.

prEN 4700-002:2024 (E)

- nature and type of packing, if required;
- surface protection, if appropriate;
- definition and frequency of any special tests and their retest procedures, if required.

5 Health and safety

The products in the delivery condition shall fulfil the current health and safety laws of the area of the country where it is to be delivered.

A product safety data sheet shall be available.

6 Technical requirements**6.1 General**

The product shall be manufactured in accordance with the requirements of the relevant material standard and the applicable requirements of this specification. A manufacturing schedule shall be established and applied in accordance with EN 2078.

Product shall satisfy the requirements of the material standard and/or order and shall be free from irregularities prejudicial to the subsequent manufacture or use of this product.

Notwithstanding previous acceptance complying with this material standard, any product that is found at a later stage to contain such defects shall be rejected.

Unless otherwise specified, the requirements in Table 1 and Table 2 shall apply in conjunction with those of the relevant material standard. Table 1 relates to lines 1 to 29 (inclusive) of the material standard and Table 2 relates to lines 30 onwards in which the sub-line format is also used. Lines 2 to 98 may also be opened in line 100 if the material standard details specific qualification requirements. If a specific line number is not shown in Table 1 and Table 2, the requirement is stated in the material standard and/or order.

6.2 Qualification requirements

Qualification requirements when invoked by the material standard and/or order are detailed in Table 1 and Table 2. The number of batches and casts shall be agreed between the manufacturer and the purchaser.

6.3 Release requirements**6.3.1 Release tests**

Release testing shall be the responsibility of the manufacturer.

The purchaser reserves the right to perform any of the inspections and/or tests required by the material standard and/or order.

The test samples shall be representative of the product.

When required by the order, the manufacturer shall inform the purchaser of the planned dates for extraction of samples and release testing in order that these operations may be witnessed.

Table 1 and Table 2 detail the requirements for each line of the material standard. Unless otherwise specifically requested by the purchaser, a particular inspection and/or test for release shall be carried out if corresponding acceptance criteria and/or values are stated in the applicable material standard but see also in subclause 6.3.5.

6.3.2 Retests

If any requirement is not met, retests shall be carried out under the following conditions unless otherwise stated in the material standard or order. Products shall be:

- rejected;
- 100 % retested and the conforming products accepted; or
- partially or fully reheat treated if heat treatment can rectify the cause of the failure and retested. For condition of use material, the number of reheat treatments shall not exceed the number specified in Table 1 (line 7). The reheat treatment shall be stated on the release test certificate.

6.3.3 Rejection

Any failure to meet the requirements of the material standard shall be cause for rejection.

6.3.4 Special tests

Special tests may be required by the purchaser. In such cases, the nature of the test, method, frequency and technical requirements shall be specified on the order or inspection schedule and shall be mutually agreed by the manufacturer and the purchaser.

6.3.5 Capability clause

Where the capability clause is invoked and where sufficient statistical evidence exists, the test need not be carried out (unless specifically requested by the purchaser).

However, this in no way reduces the obligations of the manufacturer to fulfil the requirements. If subsequent testing indicates that the product does not comply with the requirements, the batch shall be rejected.

If sufficient statistical evidence does not exist, the test shall be carried out at a frequency agreed between the manufacturer and the purchaser.

6.3.6 Statistical process control

Reduction in the extent of release testing, other than that specified in subclause 6.3.5 above, may be negotiated with the purchaser on the basis of appropriate statistical process control and/or statistical data.