



Designation: F1295 – 11

Standard Specification for Wrought Titanium-6Aluminum-7Niobium Alloy for Surgical Implant Applications (UNS R56700)¹

This standard is issued under the fixed designation F1295; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope*

1.1 This specification covers the chemical, mechanical, and metallurgical requirements for wrought annealed, cold-worked, or hot-worked titanium-6aluminum-7niobium alloy bar, wire, sheet, strip, and plate to be used in the manufacture of surgical implants (1-4).²

1.2 The values stated in either SI units or inch-pound units are to be regarded separately as standard. The values stated in each system may not be exact equivalents; therefore, each system shall be used independently of the other. Combining values from the two systems may result in non-conformance with the standard.

2. Referenced Documents

- 2.1 *ASTM Standards*:³
- E8/E8M Test Methods for Tension Testing of Metallic Materials
 - E29 Practice for Using Significant Digits in Test Data to Determine Conformance with Specifications
 - E290 Test Methods for Bend Testing of Material for Ductility
 - E1409 Test Method for Determination of Oxygen and Nitrogen in Titanium and Titanium Alloys by Inert Gas Fusion
 - E1447 Test Method for Determination of Hydrogen in Titanium and Titanium Alloys by Inert Gas Fusion Thermal Conductivity/Infrared Detection Method
 - E1941 Test Method for Determination of Carbon in Refractory and Reactive Metals and Their Alloys by Combustion Analysis
 - E2371 Test Method for Analysis of Titanium and Titanium Alloys by Direct Current Plasma and Inductively Coupled

- Plasma Atomic Emission Spectrometry (Performance-Based Test Methodology)
- E2626 Guide for Spectrometric Analysis of Reactive and Refractory Metals
- SI 10 American National Standard for Use of the International System of units (SI): The Modern Metric System
- 2.2 *Aerospace Material Specification*:⁴
- AMS 2249 Chemical Check Analysis Limits, Titanium and Titanium Alloys
- AMS 2630 Inspection, Ultrasonic Product Over 0.5 Inch (12.7 mm) Thick
- AMS 2631 Ultrasonic Inspection--Titanium and Titanium Alloy Bar and Billet
- 2.3 *ISO Standards*:⁵
- ISO 5832-11 Implants for Surgery—Metallic Materials—Part 11: Wrought Titanium 6–Aluminum 7–Niobium Alloy
- ISO 6892 Metallic Materials—Tensile Testing—Part 1: Method of Test at Room Temperature
- ISO 9001 Quality Management Systems—Requirements

3. Terminology

- 3.1 *Definitions of Terms Specific to This Standard*:
- 3.1.1 *beta transus, n*—the minimum temperature at which the alpha plus beta phase can transform to 100 % beta phase.
 - 3.1.2 *cold work*—any mechanical deformation process performed below the recrystallization temperature which results in strain hardening of the material.
 - 3.1.3 *lot, n*—the total number of mill products produced from the same melt heat under the same conditions at essentially the same time.
 - 3.1.4 *hot work*—any mechanical deformation process performed above the recrystallization temperature.
 - 3.1.5 *stress relief*—thermal treatment that reduces the residual stresses in the material without affecting the mechanical properties.

¹ This specification is under the jurisdiction of ASTM Committee F04 on Medical and Surgical Materials and Devices and is the direct responsibility of Subcommittee F04.12 on Metallurgical Materials.

Current edition approved Nov. 15, 2011. Published December 2011. Originally approved in 1992. Last previous edition approved in 2005 as F1295 – 05. DOI: 10.1520/F1295-11.

² The boldface numbers in parentheses refer to a list of references at the end of the text.

³ For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

⁴ Available from SAE International (SAE), 400 Commonwealth Dr., Warrendale, PA 15096-0001, http://www.sae.org.

⁵ Available from American National Standards Institute (ANSI), 25 W. 43rd St., 4th Floor, New York, NY 10036, http://www.ansi.org.

*A Summary of Changes section appears at the end of this standard

4. Product Classification

4.1 *Bar*—Rounds, or flats, or other shapes from 0.188 in. (4.76 mm) to 4.0 in. (102 mm) in diameter or thickness. Other sizes and shapes by special order.

4.2 *Forging Bar*—Bar as described in 4.1, used in the production of forgings. This product may be furnished in the hot-worked condition.

4.3 *Wire*—Rounds, flats, or other shapes less than 0.188 in. (4.76 mm) in diameter or thickness.

4.4 *Strip*—Any product 0.188 in. (4.76 mm) and under in thickness and less than 24 in. (610 mm) in width.

4.5 *Sheet*—Any product 0.188 in. (4.76 mm) and under in thickness and 24 in. (610 mm) or more in width.

4.6 *Plate*—Any product 0.188 in (4.76 mm) thick and over 10 in. (254 mm) wide and over, with widths greater than five times thickness. Plate up to 4 in. (101.60 mm), thick inclusive is covered by this specification.

5. Ordering Information

5.1 Include with inquiries and orders for material under this specification the following information:

- 5.1.1 Quantity (weight or number of pieces),
- 5.1.2 Applicable ASTM designation, date of issue.
- 5.1.3 Form (bar, wire, sheet, strip, or plate),
- 5.1.4 Condition (see 6.2),
- 5.1.5 Mechanical Properties (if applicable for special conditions),
- 5.1.6 Finish (see 6.1),
- 5.1.7 Applicable dimensions including size, thickness, width, or drawing number,
- 5.1.8 Special tests, if any,
- 5.1.9 Other requirements.

6. Materials and Manufacture

6.1 *Finish*—The mill product may be supplied as specified by the purchaser with a descaled or pickled, abrasive-blasted, chemically milled, ground, machined, peeled, or polished finish.

6.2 *Condition*—Material shall be furnished in the annealed, cold-worked, or hot-worked condition. The purchaser shall include on drawings or purchase orders whether the material shall be stress-relieved.

7. Chemical Requirements

7.1 The heat analysis shall conform to the chemical composition of **Table 1**. Ingot analysis may be used for reporting all chemical requirements, except hydrogen. Samples for hydrogen shall be taken from the finished mill product. The supplier shall not ship material with chemistry outside the requirements specified in **Table 1**.

7.1.1 Requirements for the major and minor elemental constituents are listed in **Table 1**. Also listed are important residual elements. Analysis for elements not listed in **Table 1** is not required to certify compliance with this specification.

7.2 *Product Analysis*:

TABLE 1 Chemical Requirements

Element	Composition, %
Aluminum	5.50 to 6.50
Niobium	6.50 to 7.50
Tantalum	0.50 max
Iron	0.25 max
Oxygen	0.20 max
Carbon	0.08 max
Nitrogen	0.05 max
Hydrogen	0.009 max
Titanium ^A	Balance

^A The percentage of titanium is determined by difference and need not be determined or certified.

7.2.1 Product analysis tolerances do not broaden the specified heat analysis requirements but cover variations in the measurement of chemical content between laboratories. The product analysis tolerances shall conform to the product tolerances in **Table 2**.

7.2.2 The product analysis is either for the purpose of verifying the composition of a heat or manufacturing lot or to determine variations in the composition within the heat.

7.2.3 Acceptance or rejection of a heat or manufacturing lot of material may be made by the purchaser on the basis of this product analysis. Product analysis outside the tolerance limits allowed in **Table 2** are cause for rejection of the product. A referee analysis may be used if agreed by supplier and purchaser.

7.3 For referee purposes, use Test Methods **E1409**, **E1447**, **E1941**, **E2371**, and **E2626** or other analytical methods agreed upon between the purchaser and the supplier.

7.4 Samples for chemical analysis shall be representative of the material being tested. The utmost care must be used in sampling titanium for chemical analysis because of its affinity for elements such as oxygen, nitrogen, and hydrogen. In cutting samples for analysis, therefore, the operation should be carried out insofar as possible in a dust-free atmosphere. Cutting tools should be clean and sharp. Samples for analysis should be stored in suitable containers.

8. Mechanical Requirements

8.1 The material supplied under this specification shall conform to the mechanical properties given in **Table 3**. Alternative properties may be agreed upon between the purchaser and supplier.

TABLE 2 Product Analysis Tolerances^A

Tolerance Under the Minimum ^B or Over the Maximum Limit	
Aluminum	0.10
Niobium	0.10
Tantalum	0.10
Iron	0.10
Oxygen	0.02
Carbon	0.02
Nitrogen	0.02
Hydrogen	0.002

^A Refer to AMS 2249.

^B Under minimum limit not applicable for elements where only a maximum percentage is indicated.

TABLE 3 Mechanical Properties for Bar and Wire

Condition ^A	Ultimate Tensile Strength, min, psi, (MPa)	Yield Strength (0.2 % Offset), min, psi, (MPa)	Elongation, ^B min, %	Reduction of Area, min, %
Annealed	130 500 (900)	116 000 (800)	10	25
Hot Worked	130 500 (900)	116 000 (800)	10	25
Cold Worked	159 500 (1100)	116 000 (800)	10	25

^A Mechanical properties for conditions other than those listed in this table may be established by agreement between the supplier and purchaser.

^B Elongation of material 0.063 in. (1.6 mm) or greater in diameter (D) or thickness (T) shall be measured using a gauge length of 2 in. or 4D or 4W. The gauge length must be reported with the test results. The method for determining elongation of material under 0.063 in. (1.6 mm) in diameter or thickness may be negotiated. Alternatively, a gauge length of 5.65 times the square root of S_o , where S_o is the original cross-sectional area corresponding to ISO 6892 may be used when agreed upon between supplier and purchaser.

8.2 Specimens for tension tests shall be machined and tested in accordance with Test Methods **E8/E8M**. Tensile properties shall be determined using a strain rate of 0.003 to 0.007 in./in./min (mm/mm/min) through the specified yield and then the crosshead speed shall be increased so as to produce fracture in approximately one additional minute.

8.2.1 *Bar, Forging Bar, and Wire*—Test according to Test Methods **E8/E8M**.

8.2.2 Tensile tests result for which any specimen fractures outside the gauge length shall be considered valid, if both the elongation and reduction of area meet the minimum requirements specified. If either the elongation or reduction of area is less than the minimum requirement, invalidate the specimen and retest. Retest one specimen for each invalidated specimen.

8.2.3 Should any test specimen not meet the specified requirements, test two additional test pieces representative of the same lot, in the same manner, for each failed test specimen. The lot will be considered in compliance only if all additional test pieces meet the specified requirements.

8.3 *Sheet, Strip, and Plate:*

8.3.1 Test according to Test Methods **E8/E8M**. Perform at least one tensile test from each lot in both the longitudinal and transverse directions. Tests in the transverse direction need be made only on product from which a specimen not less than 8.0 in. (200 mm) in length for strip can be taken. Should any of these test specimens not meet the specified requirements, test two additional test pieces representative of the same lot, in the same manner, for each failed test specimen. The lot will be considered in compliance only if all additional test pieces meet the specified requirements.

8.3.2 For sheet and strip, the bend test specimen shall withstand being bent cold through an angle of 105° without fracture in the outside surface of the bent portion. The bend shall be made around a mandrel which has a diameter equal to that shown in **Table 4**. Test conditions shall conform to Test Method **E290**.

9. Dimensions and Permissible Variations

9.1 *Units of Measure:*

9.1.1 *Selection*—This specification requires that the purchaser selects the units (SI or inch-pound) to be used for product certification. In the absence of a stated selection of units on the purchase order, this selection may be expressed by the purchaser in several alternate forms listed in order of precedence.

9.1.1.1 If the purchaser and supplier have a history of using specific units, these units shall continue to be certified until expressly changed by the purchaser.

9.1.1.2 In the absence of historic precedence, if the units used to define the product on the purchaser's PO, specification, and engineering drawing are consistent, these units shall be used by the supplier for product certification.

9.1.1.3 If the purchaser's selection of units is unclear, the units of measure shall be agreed upon between purchaser and supplier.

9.1.2 *Conversion of Units*—If the supplier's test equipment does not report in the selected units, the test equipment units may be converted to the selected units for certification purposes. Accurate arithmetic conversion and proper use of significant digits should be observed when performing this

TABLE 4 Mechanical Properties for Sheet, Strip, and Plate

Condition ^A	Ultimate Tensile Strength min, psi (MPa)	Yield Strength (0.2 % offset), min, psi (MPa)	Elongation ^B in 2 in. (50 mm), min %	Bend Test Mandrel Diameter ^C	
				Under 0.070 in. (1.78 mm) in Thickness	0.070 to 0.188 in. (1.78 to 4.76 mm) in Thickness
Annealed	130 500 (900)	130 500 (900)	10	9T	10T

^A Mechanical properties for conditions other than those listed in this table may be established by agreement between the supplier and purchaser.

^B Elongation of material 0.063 inches (1.6 mm) or greater in thickness shall be measured using a gauge length of 2 inches (50 mm). The gauge length must be reported with the test results. The method for determining elongation of material under 0.063 inches (1.6 mm) in thickness may be negotiated. Alternatively, a gauge length corresponding to ISO 6892 may be used when agreed upon between supplier and purchaser. (5.65 times the square root of S_o , where S_o is the original cross sectional area.) Gauge length will be reported with the elongation value.

^C T equals the thickness of the bend test specimen. Bend tests are not applicable to material over 0.188 in. (4.76 mm) in thickness. The limits listed apply to tests taken both longitudinal and transverse to the direction of rolling.