



Designation: D7735 – 11

Standard Test Method for Type A Durometer Hardness Testing of Road Marking Thermoplastic at Elevated Temperatures¹

This standard is issued under the fixed designation D7735; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This test method covers Type A Durometer hardness of road marking thermoplastic material at elevated temperatures.

1.2 This test method is similar to Test Method D2240 for hardness with special attention given to keeping the temperature of the test sample and instrument constant. Within the highway materials community, it is sometimes known as “indentation resistance.”

1.3 All materials, instruments or equipment used for the determination of temperature, hardness and time shall be traceable to National Institute of Standards and Technology or other internationally recognized organizations parallel in nature.

1.4 The values stated in SI units are to be regarded as standard. The values given in parentheses are for information only.

1.5 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 *ASTM Standards:*²

D16 Terminology for Paint, Related Coatings, Materials, and Applications

D2240 Test Method for Rubber Property—Durometer Hardness

D7307 Practice for Sampling of Thermoplastic Traffic Marking Materials

D7308 Practice for Sample Preparation of Thermoplastic Traffic Marking Materials

¹ This test method is under the jurisdiction of ASTM Committee D01 on Paint and Related Coatings, Materials, and Applications and is the direct responsibility of Subcommittee D01.44 on Traffic Coatings.

Current edition approved Nov. 1, 2011. Published December 2011. DOI: 10.1520/7735-11.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

E177 Practice for Use of the Terms Precision and Bias in ASTM Test Methods

E691 Practice for Conducting an Interlaboratory Study to Determine the Precision of a Test Method

3. Terminology

3.1 *Definitions:*

3.1.1 The terms and definitions in Terminology D16 apply to this method.

3.1.2 *hardness, adv*—the value of resistance of a small penetrating device. In the case of the Type A Durometer in accordance with Test Method D2240, the presser foot/indenter (spherical to 0.79 ± 0.03 mm or 0.03 ± 0.001 in.) is connected to a spring loaded to a total of 0.075 N/Durometer units at full deflection. For reading of Type A hardness the instruments scale reads from 0 to 100. Minimal deflection is 0 (softest) and maximum is 100 (hardest).

3.1.3 *thermoplastic, n*—traffic marking (same as 3.1.4).

3.1.4 *thermoplastic traffic marking*—a highly filled 100 % total solids highway marking system that when heated to a molten state can be extruded or sprayed onto a road surface and when cooled forms a solid durable delineator or road marking thermoplastic usually melted to 220°C (425°F).

4. Summary of Test Method

4.1 This method was developed to enable the testing of hardness or indentation resistance of road marking thermoplastic material at ambient roadway/highway temperatures. Due to the speed at which basic road marking thermoplastic cools, testing its hardness at elevated temperatures is difficult, even at a relatively low 46°C (115°F). Existing non-standard methods are not consistent because they allow the samples to change temperature during testing. By keeping both the test samples and the hardness tester in a regulated environment before and during testing, the results are much more repeatable within a laboratory. The goal for this method is to allow results from this test to be more reproducible from laboratory to laboratory.

4.2 The methodology involves measuring the hardness of roadmarking thermoplastic by keeping the test sample in the elevated temperature environment (a water bath) during the testing process and using a Durometer that can be placed in the

water bath and function. This method could be performed in a glove box/oven if the door was not opened before or during the testing.

5. Significance and Use

5.1 This method is based on the penetration of a specific type of indenter when forced into the material under specified conditions. The indentation hardness is inversely related to the penetration and is dependent on the elastic modulus, viscoelastic behavior of the material, geometry of the indenter, the applied force and temperature at test. This test method is empirical and therefore primarily for control purposes. No simple relationship exists between indentation hardness determined by this test method and any fundamental property of the material tested.

6. Apparatus

6.1 *Safety Glasses.*

6.2 *Aluminum Pans* (20 mL) or adequate size for tester base.

6.3 *A Hardness Tester Type A Needle-type Durometer* in accordance with Test Method [D2240](#).

6.4 *Constant 100 g Load Weight for Type A Durometer.*

6.5 *Optional—Test Block Kit containing Type A Durometer samples with values traceable to an accredited calibration laboratory.*

6.6 *Oven* controllable to $46 \pm 1.0^\circ\text{C}$ ($115 \pm 3.0^\circ\text{F}$) (or within 2.5 % of set point).

6.7 *Water Bath* controllable to $46 \pm 1.0^\circ\text{C}$ ($115 \pm 3.0^\circ\text{F}$) (or within 2.5 % of set point).

6.8 *Digital Timer* in seconds.

7. Hazards

7.1 This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.

8. Calibration and Standardization

8.1 Calibration of the Type A hardness tester shall be done regularly by following the manufacturers recommendations and following the Calibration section of Test Method [D2240](#). The test block kit can be used to verify that the instrument is working properly.

9. Procedure

9.1 Sample the road marking thermoplastic in accordance with Practice [D7307](#) then begin preparation of samples in accordance with Practice [D7308](#).

9.2 Pour thermoplastic that has been heated to 425°F (or per manufacturer's recommendation) into a 20 mL aluminum pan to approximately half full, and then allow cooling to room temperature.

9.3 Turn on heater on water bath and allow the temperature to stabilize to $46 \pm 1.0^\circ\text{C}$ ($115 \pm 3.0^\circ\text{F}$) or as agreed upon by the involved parties

9.4 Turn on oven set to $46 \pm 1.0^\circ\text{C}$ ($115 \pm 3.0^\circ\text{F}$) or as mutually agreed upon by the involved parties and place the Type A Durometer inside

NOTE 1—A bath or oven operated outside the recommended temperature control may result in greater result variability.

9.4.1 Other temperatures can be used when agreed upon between the parties involved.

9.5 Place cooled hardness sample in water bath and turn on oscillator or stirrer.

9.6 Samples should be allowed to equilibrate to the required temperature for at least one hour before being tested. Samples should be tested within three hours of being in the water. When all samples and testing equipment have stabilized to the set temperature, testing can begin.

9.7 Before testing sample, remove lid from water bath and turn off oscillator or stirrer. Quickly place hardness tester from oven in water bath making sure that the needle point and bottom of weight is below the waterline. This will ensure that tester is exactly the same temperature as sample. If the tester is removed from the water during the testing process, its temperature will change and cause variations in results. Sample(s) can be tested multiple times as long as sample and tester bottom are not removed from water during testing.

9.8 To test sample, set timer so that a fifteen second countdown will begin. Place hardness tester over sample keeping both under water at all times.

9.9 Lower the hardness tester over the center of the test sample. As soon as contact is made, start timer and release tester. The tester dial should move constantly lower. When fifteen seconds is reached, note the Type A hardness value on the dial and record. Make at least two readings then average. Caution should be taken when making multiple readings not to test in the same spot or after the tester has been removed from the water.

9.10 Care should be taken to ensure that the force is applied vertically to the indenter tip, as lateral force will cause errors in calibration.

9.11 If sample fails, another reading may be taken immediately, but do not place needle point in the same indentation.

10. Report

10.1 Hardness measurements and average (Type A).

10.1.1 Date of testing.

10.1.2 Oven and water bath temperature.

10.1.3 Manufacturer, type and serial number of the Durometer.

10.1.4 Date of last calibration and calibration due date.

11. Precision and Bias³

11.1 The precision of this test method is based on an Interlaboratory study of ASTM D7735 Standard Test Method for Hardness of Road Marking Thermoplastics, conducted in

³ Supporting data have been filed at ASTM International Headquarters and may be obtained by requesting Research Report RR:D01-1160.