

Designation: E454 – 11

Standard Specification for Industrial Perforated Plate and Screens (Square Opening Series)¹

This standard is issued under the fixed designation E454; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the Department of Defense.

INTRODUCTION

Industrial perforated plate can be produced in many thousands of combinations of size and shape of opening, bar size, thickness of material, and type of metal. Such variety is often confusing and, to the vast majority of perforated plate users, unnecessary, since each usually requires only a very few specifications.

The purpose of this specification is to simplify this problem by a condensed table of recommended specifications covering a wide range of openings in which industrial perforated plate is made, with several recommended bar sizes and thicknesses of plate for each opening, for use in various grades of service.

By making selections from this standard, the user will be guided to specifications that are being regularly produced, thus avoiding inadvertent selection of specifications that, because of little or no demand, are unobtainable, except on special order (usually quite expensive unless the quantity ordered is sufficient to justify the cost of special tooling).

If a user has a specific application for industrial perforated plate that can not be solved by a selection from this standard, it is recommended that he consult his perforated plate supplier on the availability of an acceptable alternative specification.

1. Scope

1.1 This specification covers the sizes of square opening perforated plate and screens for general industrial uses, including the separating or grading of materials according to designated nominal particle size, and lists standards for openings from 5 in. (125 mm) to 0.127 ($\frac{1}{8}$) in. (3.35 mm) punched with bar sizes and thicknesses of plate for various grades of service. Methods of checking industrial perforated plate and screens are included as information in Annex A3.

1.2 This specification does not apply to perforated plate or screens with round, hexagon, slotted, or other shaped openings.

1.3 The values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units that are provided for information only and are not considered standard.

1.4 This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the

responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.

- 2. Referenced Documents
 - 2.1 ASTM Standards:²
 - E323 Specification for Perforated-Plate Sieves for Testing Purposes
 - E1638 Terminology Relating to Sieves, Sieving Methods, and Screening Media
 - 2.2 ISO Standards:³
 - ISO 2194-1972 Wire Screens and Plate Screens for Industrial Purposes—Nominal Sizes of Apertures.
 - **ISO Recommendation R388-1964** Metric Series for Basic Thicknesses of Sheet and Diameters of Wire.


Copyright © ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States.

¹ This specification is under the jurisdiction of ASTM Committee E29 on Particle and Spray Characterization and is the direct responsibility of Subcommittee E29.01 on Sieves, Sieving Methods, and Screening Media.

Current edition approved Nov. 15, 2011. Published December 2011. Originally approved in 1972. Last previous edition approved in 2009 as E454 – 09. DOI: 10.1520/E0454-11.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

³ Available from International Organization for Standardization (ISO), 1, ch. de la Voie-Creuse, Case postale 56, CH-1211, Geneva 20, Switzerland, http://www.iso.ch.



2.3 Other Documents:

Fed. Std. No. 123 Marking for Shipment (Civil Agencies)⁴ Mil-Std-129 Marking for Shipment and Storage⁴

3. Terminology

3.1 *Definitions*—For definitions of related terms, refer to TerminologyE1638.

3.2 Definitions of Terms Specific to This Standard:

3.2.1 *aperture* or *opening*, *n*—dimensions defining an opening in a screen.

3.2.2 *bar*, *n*—metal between perforations measured at the point where perforations are the closest.

3.2.3 *blank*, *n*—unperforated area located other than along the perimeter of a plate.

3.2.4 *break-out*, *n*—term applied to the action that occurs ahead of the punch in its going through the plate.

3.2.4.1 *Discussion*—The fracturing of the material results in a tapered hole with the small dimensions on the punch side.

3.2.5 *centers*, *n*—dimensional sum of one perforation and one bar or the dimensional distance from the center of one perforation to the center of an adjacent perforation.

3.2.6 *die side*, *n*—surface of the plate that was against the die during the punching operation.

3.2.7 *finished end pattern*, *n*—condition that occurs with some specifications of staggered pattern perforations as a result of tool design in which the pattern is completed on both ends of the plate (Fig. 1).

3.2.8 gage (also gauge), n—a number designating a specific thickness of metal sheet tabulated in a standardized series, each of which represents a decimal fraction of an inch.

3.2.9 *margin* or *border*, *n*—unperforated area located along the perimeter of a plate.

3.2.10 *open area*, *n*—ratio of the total area of the apertures to the total area of the screen, usually expressed in percentage.

3.2.11 *perforation*, *n*—aperture or opening produced by punching.

3.2.12 screen, n—(1) surface provided with openings of uniform size; or (2) machine provided with one or more screen surfaces.

3.2.13 *screening*, *v*—process of separating a mixture of different sizes by means of one or more screen surfaces.

3.2.14 *smooth side or punch side*, n—surface of the plate that was uppermost during the punching operation and through which the punch entered the plate.

3.2.15 *unfinished end pattern*, *n*—condition that occurs with some specifications of staggered pattern perforations as a result of tool design.

3.2.15.1 *Discussion*—On one end of the plate, the pattern will appear to be incomplete as a result of unperforated holes in the even numbered rows, while on the other end of the same plate, the pattern will appear to be incomplete because of unperforated holes in the odd numbered rows (Fig. 1).

4. Standard Specifications

4.1 Standard specifications for industrial perforated plate and screens are listed in Table 1.

4.2 *Openings*—The series of standard openings listed in Table 1 include those of the USA Standard Sieve Series, Specification E323, and those of the ISO apertures for industrial plate screens, ISO 2194-1972, with the addition of those openings in common usage.

4.3 *Relationship of Grades*—The purpose of the several grades is to provide combinations of opening and bar size for various types of service, from medium-light to heavy. Since it is possible to vary the bar size independently from the plate thickness, each of the service grades lists up to three combinations of bar and gage for each opening. The entire standard series has been designed for a logical relationship of bar size to opening in each grade and between grades with the capability of also being able to vary the plate thickness.

TABLE 1 USA Standard Specifications for Industrial Perforated Plate and Screens (Square Opening Series)—(U.S. Customary Units)

Perforated O	pening		Medi	um Light			Med	ium		Me	dium Heavy	/		He	eavy	
Standard (metric), mm	USA In- dustrial Standard in.	Open- , ing, in.	Bar, in.	Gage- Steel, in.	Open Area, percent	Open- ing, in.	Bar, in.	Gage- Steel, in.	Open Area, Ope percent ing,			Open Area, percent	Open- ing, in.	Bar, in.	Gage- Steel, in.	
125 125	5 5	5 5	1/2 5/8	1/2 5/8	82.6 79.0	5 5	5/8 3/4	5/8 1/2	79.0 5 75.6 5	3/. 7/1		75.6 72.4	5 5	1 11⁄8	1 7⁄8	69.4 66.6

⁴ Available from Standardization Documents, Order Desk, Bldg. 4 Section D, 700 Robbins Ave., Philadelphia, PA 19111-5098.

€454 – 11

Perforated Opening			Medium Light				Medium				Medium Heavy				Heavy			
Standard (metric), mm	USA In- dustrial Standard, in.			Gage- Steel, in.	Open Area, percent	Open- ing, in.	Bar, in.	Gage- Steel, in.	Open Area, percent	Open- ing, in.	Bar, in.	Gage- Steel, in.	Open Area, percent	Open- ing, in.	Bar, in.	Gage Steel, in.	Open Area, percen	
125	5	5	5⁄8	1/2	79.0	5	3⁄4	5⁄8	75.6	5	7⁄8	3⁄4	72.4	5	1 1⁄8	1	66.6	
		41/2	1/2	1/2	81.0	41/2	5/8	5/8	77.1	41/2	3⁄4	3⁄4	73.4	41/2	1	1	66.9	
		41/2	5⁄8	3⁄8	77.1	41/2	3⁄4	1/2		41/2	7/8	5⁄8	70.1	41/2	11⁄8	7/8	64.0	
		41/2	5⁄8	1/2	77.1	41⁄2	3⁄4	5⁄8	73.4	41⁄2	7/8	3⁄4	70.1	41⁄2	11⁄8	1	64.0	
106	41/4	41/4	1/2	1/2	80.1	41⁄4	5/8	5/8	76.0	41/4	3⁄4	3⁄4	72.3	41/4	1	1	65.5	
106	41/4	41/4	5⁄8	3⁄8	76.0	41/4	3⁄4	1/2		41⁄4	7/8	5⁄8	68.8	41/4	11⁄8	7/8	62.5	
106	41/4	41/4	5/8	1/2	76.0	41/4	3⁄4	5/8	72.3	41/4	7/8	3⁄4	68.8	41⁄4	1 1⁄8	1	62.5	
100	4	4	1/2	1/2	79.0	4	5⁄8	5/8	74.8	4	3⁄4	3⁄4	70.9	4	1	1	64.0	
100	4	4	5/8	3/8	74.8	4	3/4	1/2		4	7/8	5⁄8	67.3	4	11⁄8	7/8	60.9	
100	4	4	5⁄8	1/2	74.8	4	3⁄4	5/8	70.9	4	7/8	3⁄4	67.3	4	11⁄8	1	60.9	
		3¾	1/2	1/2	77.9	3¾	5⁄8	5⁄8		3¾	3⁄4	3⁄4	69.4	3¾	7⁄8	7⁄8	65.7	
		3 ³ ⁄4	5/8	3⁄8	73.5	3 ³ ⁄4	3/4	1/2		3 ³ ⁄4	7/8	5⁄8	65.7	3 ³ ⁄4	1	3⁄4	62.3	
		3¾	5/8	1/2	73.5	3¾	3⁄4	5/8	69.4	33/4	7/8	3⁄4	65.7	3¾	1	7/8	62.3	
90	31/2	31⁄2	1/2	1/2	76.6	31/2	5⁄8	5⁄8	72.0	31/2	3⁄4	3⁄4	67.8	31⁄2	7⁄8	7⁄8	64.0	
90	31/2	31/2	5/8	3/8	72.0	31/2	3/4	1/2		31/2	7/8	5⁄8	64.0	31/2	1	3⁄4	60.5	
90	31/2	31⁄2	5/8	1/2	72.0	31⁄2	3/4	5/8	67.8	31⁄2	7/8	3⁄4	64.0	31⁄2	1	7/8	60.5	
		31⁄4	3⁄8	3/8	80.4	31⁄4	1/2	1/2	75.1	31⁄4	5/8	5/8	70.3	31⁄4	3⁄4	3⁄4	66.0	
		31⁄4	1/2	5⁄16	75.1	31/4	5⁄8	3/8	70.3		3/4	1/2	66.0	31⁄4	7/8	5⁄8	62.1	
		31/4	1/2	3⁄8	75.1	31⁄4	5/8	1/2	70.3	31⁄4	3⁄4	5⁄8	66.0	31⁄4	7/8	3⁄4	62.1	
75	3	3	3⁄8	3/8	79.0	3	1/2	1/2	73.5	3	5⁄8	5⁄8	68.5	3	3⁄4	3⁄4	64.0	
75	3	3	1/2	5/16	73.5	3	5/8	3/8	68.5		3⁄4	1/2	64.0	3	7/8	5/8	59.9	
75	3	3	1/2	3⁄8	73.5	3	5⁄8	1/2	68.5	3	3⁄4	5⁄8	64.0	3	7/8	3⁄4	59.9	
		23⁄4	3/8	3/8	77.4	23/4	1/2	1/2	71.6		5⁄8	5⁄8	66.4	23⁄4	3⁄4	3⁄4	61.7	
		23/4	1/2	5/16	71.6	23/4	5/8	3/8		23/4	3/4	1/2	61.7	2 ³ ⁄ ₄	7/8	5⁄8	57.6	
		23/4	1/2	3/8	71.6	23/4	5/8	1/2	66.4	23/4	3/4	5⁄8	61.7	23⁄4	7/8	3⁄4	57.6	
63	21/2	21/2	3⁄8	3/8	75.6	21/2	1/2	1/2	69.4	21/2	5⁄8	5⁄8	64.0	21/2	3⁄4	3⁄4	59.2	
63	21/2	21/2	1/2	⁵ /16	69.4	21/2	5⁄8	3⁄8		21/2	3/4	1/2	59.2	21/2	7/8 7/	5⁄8	54.9	
63	21/2	21/2	1/2	3/8	69.4	21/2	5/8	1/2	64.0	21/2	3/4	5/8	59.2	21/2	7/8	3⁄4	54.9	
, ,		21⁄4	3⁄8	3⁄8	73.5	21/4	1/2	1/2		21/4	5⁄8	5/8	61.2	21⁄4	3⁄4	3/4	56.3	
nttps://stan	dards.tte	21/41/C	1/2alog	5/16 nd	66.9	21/4 99	5/8) et-	3%9-		21/4 20	- 03/4 ac	000/200	8 56.3	21/4 - (7/8 4-	5/8	51.8	
		21/4	1/2	3/8	66.9	21/4	5/8	1/2	61.2	21/4	3⁄4	5/8	56.3	21/4	7/8	3⁄4	51.8	
53	21/8	21⁄8	5⁄16	5⁄16	76.0	21/8	3⁄8	3⁄8		21/8	1/2	1/2	65.5	21⁄8	5⁄8	5⁄8	59.7	
53	21/8	21/8	3/8 3/	1/4 5/	72.3	21/8	1/2	⁵ /16		21/8	5⁄8	3⁄8	59.7	21/8	3/4 3/	1/2	54.6	
53	21/8	21/8	3/8	5⁄16	72.3	21/8	1/2	3⁄8	59.7	21/8	5/8	1/2	59.7	21/8	3⁄4	5/8	54.6	
50	2	2	5⁄16	5⁄16	74.8	2	3⁄8	3⁄8	70.9		1/2	1/2		2	5⁄8	5⁄8	58.0	
50 50	2 2	2 2	3/8 3/8	1/4 5/16	70.9 70.9	2 2	1/2 1/2	5⁄16 3⁄8	64.0 64.0		5/8 5/8	3/8 1/2	58.0 58.0	2 2	3/4 3/4	1/2 5/8	52.9 52.9	
00	-	-	/0	/10	70.0	-	12	/0	01.0	-	70	12	00.0	-	/ 4	/0	02.0	
		17/8	⁵ /16	5/16	73.5	17/8	3/8	3/8	69.4		1/2	1/2	62.3	17/8	5/8	5/8	56.3	
		17⁄8 17⁄8	3/8 3/8	1/4 5⁄16	69.4 69.4	17⁄8 17⁄8	1/2 1/2	5⁄16 3⁄8	62.3 62.3		5/8 5/8	3⁄8 1⁄2	56.3 56.3	17⁄8 17⁄8	3/4 3/4	1/2 5/8	51.0 51.0	
		170	/8	/10	00.4	178	12	/8	02.0	170	78	12	00.0	170	/4	/0	51.0	
45	13⁄4	1 3⁄4	5/16	⁵ /16	72.0	1 ³ ⁄4	3/8	3/8	67.8		1/2	1/2	60.5	13⁄4	5⁄8	5⁄8	54.3	
45 45	13⁄4 13⁄4	1¾ 1¾	3/8 3/8	1/4 5/16	67.8 67.8	1¾ 1¾	1/2 1/2	5⁄16 3⁄8	60.5 60.5		5/8 5/8	3/8 1/2	49.0 49.0	1¾ 1¾	3/4 3/4	1/2 5/8	49.0 49.0	
40	174	1 /4	/8	/10	07.0	174	12	/8	00.0	1/4	78	12	40.0	1/4	/4	/0	40.0	
		15⁄8	1/4 5/	1/4	75.1	15/8	5⁄16	⁵ /16	70.3		3⁄8	3/8	66.0	15/8	1/2	1/2 3/	58.5	
		15⁄8 15⁄8	^{5/} 16 ^{5/} 16	³ ⁄16 1⁄4	70.3 70.3	15⁄8 15⁄8	3/8 3/8	1/4 5/16	66.0 66.0		1/2 1/2	^{5/} 16 3⁄8	58.5 58.5	15⁄8 15⁄8	5/8 5/8	3/8 1/2	52.1 52.1	
37.5 27 5	1½ 11/2	1½ 11/2	1/4 5/	1/4 3/	73.5	1½ 11/2	⁵ /16	5/16	68.5		3⁄8	3⁄8	64.0	1 ½	1/2 5/-	1/2 3/-	56.3	
37.5 37.5	1½ 1½	1½ 1½	^{5/} 16 ^{5/} 16	³ ⁄16 1⁄4	68.5 68.5	1½ 1½	3⁄8 3⁄8	1/4 5/16	64.0 64.0		1/2 1/2	^{5/} 16 3⁄8	56.3 56.3	1½ 1½	5/8 5/8	3/8 1/2	49.8 49.8	
-																		
		1¾ 1¾	1/4 5/16	1/4 3⁄16	71.6 66.4	1¾ 1¾	^{5/} 16 3⁄8	5⁄16 1⁄4	66.4 61.7		3/8 1/2	3⁄8 5⁄16	61.7 53.8	1¾ 1¾	1/2 5/8	1/2 3/8	53.8 47.3	
		13⁄8	^{5/16}	^{-/16} 1/4	66.4	1% 1%	-78 3/8	5⁄16	61.7		1/2	3⁄8		13⁄8	5/8	78 1/2	47.3	
																	-	

€ 454 – 11

 Perforated Opening			Medi	ium Light			Med	dium			Mediu	m Heavy	/		He	eavy	
Standard (metric), mm	USA In- dustrial Standard, in.	Open- , ing, in.		Gage- Steel, in.	Open Area, percent	Open- ing, in.	Bar, in.	Gage- Steel, in.	Open Area, percent	Open- ing, in.	Bar, in.	Gage- Steel, in.	Open Area, percent	Open- ing, in.	Bar, in.	Gage- Steel, in.	- Open Area, percent
31.5	1 1⁄4	1 1⁄4	1/4	1/4	69.4	1 1⁄4	5⁄16	5⁄16	64.0	1 1⁄4	3⁄8	3⁄8	59.2	1 1⁄4	1/2	1/2	51.0
31.5	1 1⁄4	1 1⁄4	5⁄16	3⁄16	64.0	1 1⁄4	3⁄8	1/4	59.2	1 1⁄4	1/2	5⁄16	51.0	1 1⁄4	5⁄8	3⁄8	44.4
31.5	11⁄4	1 1⁄4	5⁄16	1/4	64.0	11⁄4	3⁄8	5⁄16	59.2	1 1⁄4	1/2	3⁄8	51.0	1 1⁄4	5⁄8	1/2	44.4
		1 ³⁄16	³ ⁄16	3/	74.0	13/	1/	1/	<u> </u>	13/	5/	5/	c0 7	1 ¾16	3/	3/	57.0
		1 %16 1 3⁄16	9/16 1/4	³ ⁄16 8	74.6 68.2	1³⁄16 1³⁄16	1/4 5/16	1/4 3/16	68.2 62.7		5/16 3/8	5/16 1/4	62.7 57.8	1 %16 1 %16	3/8 1/2	3⁄8 5⁄16	57.8 49.5
		1 ³ ⁄16	1/4	3⁄16	68.2	1 ³ ⁄16	⁵ /16	1/4	62.7		3/8	5⁄16	57.8	1 ³ ⁄16	1/2	3/8	49.5
		1 1⁄8	3⁄16	3⁄16	73.5	1 1⁄8	1/4	1/4	66.9	1 1⁄8	5⁄16	5⁄16	61.2	1 1⁄8	3⁄8	3⁄8	56.3
		11⁄8	1/4	8	66.9	11⁄8	5/16	3⁄16		1 1⁄8	3/8	1/4	56.3	11⁄8	1/2	5⁄16	47.9
		11⁄8	1/4	3⁄16	66.9	11/8	5⁄16	1/4	61.2	11/8	3⁄8	5⁄16	56.3	11⁄8	1/2	3/8	47.9
26.5	1 ½16	1 1⁄16	3⁄16	3⁄16	72.2	1 1⁄16	1/4	1/4	65.5	1 1⁄16	5⁄16	5⁄16	59.7	1 1⁄16	3/8	3⁄8	54.6
26.5	1 ¹ /16	1 ¹ /16	1/4	8	65.5	11/16	5⁄16	3⁄16	59.7		3/8	1/4	54.6	1 ¹ /16	1/2	5⁄16	46.2
26.5	11/16	1 ¹ / ₁₆	1/4	3⁄16	65.5	11/16	5⁄16	1/4	59.7		3/8	5⁄16	54.6	1 ¹ / ₁₆	1/2	3⁄8	46.2
25	1	1	3⁄16	3⁄16	70.9	1	1/4	1/4		1	5/16	5⁄16	58.0	1	3⁄8	3⁄8	52.9
25	1	1	1/4	8	64.0	1	⁵ /16	³ /16	58.0		3⁄8	1/4	52.9	1	1/2	⁵ ⁄16	44.4
25	1	1	1/4	3⁄16	64.0	1	5⁄16	1/4	58.0	I	3⁄8	5⁄16	52.9	1	1/2	3⁄8	44.4
		15/16	3⁄16	3⁄16	69.4	15/16	1/4	1/4	62.3	15/16	5⁄16	5⁄16	56.2	15/16	3⁄8	3/8	51.0
		15/16	1/4	8	62.3	15/16	5/16	3⁄16		15/16	3/8	1/4	51.0	15/16	1/2	3⁄16	42.5
		15/16	1/4	3⁄16	62.3	^{15/} 16	5⁄16	1/4	56.2	15/16	3⁄8	5⁄16	51.0	15/16	1/2	3⁄8	42.5
22.4	7/8 7/	7/8 7/	³ /16	³ /16	67.8	7/8 7/	1/4 5/	1/4 3/		7/8 7/	5/16 3/	⁵ /16	54.3	7/8 7/	3⁄8	3/8 5/	49.0
22.4 22.4	7/8 7/8	7/8 7/8	1/4 1/4	8 ¾16	60.5 60.5	7/8 7/8	^{5/} 16 ^{5/} 16	³ ⁄16 1⁄4	54.3 54.3	7/8 7/0	3/8 3/8	1/4 5/16	49.0 49.0	7/8 7/8	1/2 1/2	^{5/} 16 3⁄8	40.5 40.5
22.4	/8	/8	/4	716	00.5	/8	716	/4	34.5	/8	78	716	43.0	/8	12	78	40.5
		13/16	3⁄16	3⁄16	66.0	13/16	1/4	1/4	58.5	13/16	5/16	5⁄16	52.2	13/16	3⁄8	3/8	46.8
		13/16	1/4	8	58.5	13/16	5⁄16	3⁄16	52.2	13/16	3⁄8	1/4	46.8	13/16	1/2	5⁄16	38.3
		¹³ ⁄16	1/4	3/16	58.5	13/16	5⁄16	1/4	52.2	13/16	3/8	5⁄16	46.8	13/16	1/2	3⁄8	38.3
10	2/	2/	2/						50.0	ųеп		E/	40.0	2/	2/	27	
19 19	3/4 3/4	3/4 3/4	³ /16 1/4	³ /16 8	64.0 56.3	3/4 3/4	1/4 5/16	1/4 3/16		3/4 3/4	^{5/} 16 ^{3/8}	5/16 1/4	49.8 44.4	3/4 3/4	3⁄8 1⁄2	3⁄8 5⁄16	44.4 36.0
19	3/4	3/4	1/4	3/16	56.3	3/4	5/16	1/4	49.8	3/4	3/8	⁵ /16	44.4	3/4	1/2	3/8	36.0
	,.	, .	, .								, -	,		, .	, _	, -	
		11/16	3⁄16	3⁄16	61.7	11/16	1/4	1/4		11/16	5⁄16	5⁄16	47.2	11/16	3⁄8	3⁄8	41.9
		¹¹ /16	1/4	8	53.8	11/16	5/16	³ ⁄16	47.2	11/16	3/8	1/4	41.9	¹¹ /16	1/2	5/16	33.5
		11/16	1/4	3⁄16	53.8	11/16	5/16 45	41/411	47.2	11/16	3⁄8	5⁄16	41.9	11/16	1/2	3⁄8	33.5
http://star	nd 5/8 ds. ite	5/8 21/0	5/32	8 tand	64.0	5/8899	3/16	3/16 9-	59.2	5/8 820	- 1/4	cc 1/4 c	8 51.0	5/8 m- 6	5/16	5/16	44.4
16	5/8	5/8	3/16	10	59.2	5/8	1/4	8		5/8	5/16	3/16	44.4	5/8	3/8	1/4	39.1
16	5/8	5/8	3⁄16	8	59.2	5/8	1/4	3⁄16	51.0		5/16	1⁄4	44.4	5⁄8	3⁄8	5/16	39.1
		^{9/16}	5/32	8	61.2	^{9/} 16	³ /16	³ ⁄16	56.2	^{9/} 16	1/4	1/4	47.9	^{9/16}	⁵ /16	⁵ ⁄16	41.3
		9⁄16	³ /16	10 8	56.2	9/16 9/1-	1/4 1/-	8		9⁄16	5⁄16	³ /16	41.3	9⁄16	3⁄8 3⁄8	1/4 5/	36.0 36.0
		9⁄16	3⁄16	0	56.2	9⁄16	1/4	3⁄16	47.9	9⁄16	5⁄16	1/4	41.3	9⁄16	98	5⁄16	30.0
13.2	17/32	17/32	1/8	10	65.5	17/32	5/32	8	59.7	17/32	3⁄16	3⁄16	54.6	17/32	1/4	1/4	46.2
13.2	17/32	17/32	5/32	11	59.7	17/32	3⁄16	10	54.6	17/32	1⁄4	8	46.2	17/32	5⁄16	3⁄16	39.6
13.2	17/32	17/32	5/32	10	59.7	17/32	3⁄16	8	54.6	17/32	1/4	3⁄16	46.2	17/32	5⁄16	1⁄4	39.6
10 5	14	14	14	10	64.0	14	54-	0	58.0	14	3/	3/	50.0	14	1/.	1/.	11 1
12.5 12.5	1/2 1/2	1/2 1/2	1/8 5/32	10 11	64.0 58.0	1/2 1/2	⁵ /32 ³ /16	8 10	58.0 52.9		³ /16 1/4	³ ⁄16 8	52.9 44.4	1/2 1/2	1/4 5/16	1/4 3/16	44.4 37.9
12.5	1/2	1/2	5/32	10	58.0	1/2	³ /16	8	52.9		1/4	3⁄16	44.4	1/2	⁵ /16	1/4	37.9
	, _	/_				/ =	,	÷		, _		,		, _	,	, .	
		15/32	1⁄8	10	62.3	15/32	5/32	8	56.2		3⁄16	3⁄16	51.0	15/32	1/4	1/4	42.5
		15/32	5/32	11	56.2	15/32	3⁄16	10	51.0		1/4	8	42.5	15/32	5⁄16	3⁄16	36.0
		15/32	5/32	10	56.2	15/32	3⁄16	8	51.0	15/32	1/4	3⁄16	42.5	15/32	5⁄16	1/4	36.0
11.2	7/16	7/16	1⁄8	10	60.5	7⁄16	5/32	8	54.3	7/16	3⁄16	3⁄16	49.0	7⁄16	1/4	1/4	40.5
11.2	⁷ /16 7/16	⁷ /16 7/16	5/32	10	54.3	⁷ /16 7/16	9/32 3/16	o 10	49.0		9/16 1/4	916 8	49.0	⁷ /16 7/16	⁷⁴ ^{5/} 16	⁹ ∕4 ³ ∕16	40.5 34.0
11.2	7/16	7/16	5/32	10	54.3	⁷ /16	3/16	8	49.0		1/4	3⁄16		7/16	5/16	1/4	34.0
9.5	3/8	3⁄8	3/32	11	64.0	3⁄8	1⁄8	10	56.3		5/32	8	49.8	3⁄8	3⁄16	3⁄16	44.4
9.5	3/8 3/	3⁄8 3/	1/8 1/	12	56.3	3/8 3/	5/32	11	49.8		³ /16	10	44.4	3⁄8 3/	1/4 1/	8	36.0
9.5	3/8	3⁄8	1⁄8	11	56.3	3/8	5/32	10	49.8	∜8	3⁄16	8	44.4	3⁄8	1/4	3⁄16	36.0
8	5⁄16	5⁄16	3/32	11	59.2	5⁄16	1/8	10	51.0	5/16	5/32	7	44.4	5⁄16	3⁄16	3⁄16	39.0
8	5⁄16	5/16	1/8	12	51.0	5⁄16	5/32	11	44.4		3/16	10	39.0	5⁄16	1/4	8	30.9
8	5/16	5⁄16	1/8	11	51.0	5⁄16	5/32	10	44.4		3/16	8	39.0	5⁄16	1/4	3⁄16	30.9

€454 – 11

Perforated Opening			Medium Light				Med	lium	Mediur					Heavy				
Standard (metric), mm	USA In- dustrial Standard in.	Open- , ing, in.		Gage- Steel, in.	Open Area, percent	Open- ing, in.	Bar, in.	Gage- Steel, in.		ing in	Bar, in.	Gage- Steel, in.	Open Area, percent	Open- ing, in.	Bar, in.	Gage- Steel, in.		
6.7	17/64					17/64	3/32	11	54.6	17/64	1/8	10	46.2	17/64	5/32	8	39.6	
6.7	17/64	17/64	3/32	14	54.6	17/64	1⁄8	12	46.2	17/64	5/32	11	39.6	17/64	3⁄16	10	34.4	
6.7	16/64	17/64	³ / ₃₂	12	54.6	17/64	1⁄8	11	46.2	17/64	5/32	11	39.6	17/64	3⁄16	8	34.4	
6.3	1/4					1/4	3/32	11	52.9	1/4	1/8	10	44.4	1/4	5/32	8	37.9	
6.3	1/4	1/4	3/32	14	52.9	1/4	1/8	12	44.4	1/4	5/32	11	37.9	1/4	3⁄16	10	32.7	
6.3	1/4	1/4	³ / ₃₂	12	52.9	1⁄4	1⁄8	11	44.4	1/4	5/32	10	37.9	1⁄4	3⁄16	8	32.7	
5.6	7/32									7/32	3/32	11	49.0	7/32	1/8	10	40.5	
5.6	7/32					7/32	3/32	14	4.0	7/32	1/8	12	40.5	7/32	5/32	11	34.0	
5.6	7/32					7/32	³ / ₃₂	12	49.0	7/32	1⁄8	11	40.5	7/32	5/32	10	34.0	
4.75	3/16									³ ⁄16	3/32	11	44.4	3⁄16	1/8	10	36.0	
4.75	3/16					3/16	3/32	14	44.4	3⁄16	1/4	12	36.0	3⁄16	5/32	11	29.8	
4.75	3⁄16					3⁄16	³ / ₃₂	12	44.4	3⁄16	1⁄8	11	36.0	3⁄16	5/32	10	29.8	
4	5/32													5/32	3/32	11	39.1	
4	5/32									5/32	3/32	14	39.1	5/32	1/8	12	30.9	
4	5/32									5/32	3/32	12	39.1	5/32	1⁄8	11	30.9	
3.35	1/8																	
3.35	1/8													1/8	3/32	14	32.7	
3.25	1/8													1/8	3/32	12	32.7	

4.4 *Bar*—A choice of six bars is shown for each standard opening from 5- to 0.312-in. (125- to 8-mm) opening, inclusive. For practical reasons, the number of bars or grades available for openings finer than 0.312 in. (8 mm) is progressively reduced.

4.5 *Gage*—A choice of six gages is shown for each standard opening for 5 to 0.312 in. (125 to 8 mm). For practical reasons, the number of gages or grades available for openings finer than 0.312 in. (8 mm) is progressively reduced.

NOTE 1—The gages shown in Table 1 are practical for a low-carbon steel plate. For other materials, consult your perforated plate supplier.

4.6 Equivalent Metric Specification—Table A1.1, in the Annex A1, shows the equivalent metric specifications to the USA Standard, punched in standard ISO Recommendation R388-1964.

5. Types of Perforated Pattern

5.1 This specification covers square openings arranged in a staggered pattern with their midpoints nominally at the vertices of isosceles triangles whose bases shall equal their heights, and also covers square openings arranged in line with their midpoints nominally at the vertices of squares (see Fig. 2).

NOTE 2—The percentage of open area for square apertures is identical for both staggered and straight-line patterns (see Fig. 2).

6. Metal Composition of Plate

6.1 Perforated plate can be punched from a great variety of metals and alloys, but the following are most commonly used:

Steel, low-carbon Steel, high-carbon Steel, heat-treated





FIG. 2 Staggered Pattern



Straight-Line Pattern

Steel, galvanized Stainless steel, Type 304 Stainless steel, Type 316 Stainless steel, Type 410 Brass (Cu 80, Zn 20) Manganese bronze (Cu 61, Zn 37) Monel (high nickel-copper alloy) Aluminum (all grades)

7. Tolerances

3.35

0.127 (1/8)

7.1 Openings-Tolerances on openings in USA Standard Specifications for Industrial Perforated Plate and Screens (Table 1 and Table A1.1) shall be in accordance with those listed in Table 2.

7.2 Bars-Tolerances on bars used in USA Standard Specification for Industrial Perforated Plate and Screens (Table 1 and Table A1.1) shall be in accordance with those listed in Table 3.

TABLE 2	Tolerances on Openings of USA Standard
Specification	s for Industrial Perforated Plate and Screens

Specifications	ate and Sc	reens	45.0	13⁄4		± 1.3	± 0.051			
Perf	orated Opening		Tolerance of	n Openings			15⁄8		±0.047	
					37.5	11/2		±1.1	±0.043	
	LICA Industrial	Additional	Standard	USA Industrial			13⁄8		±0.040	
Standard (metric), mm	USA Industrial Standard, in.	Sizes, in.	(metric), mn		31.5	11/4		±0.9	±0.037	
	Standard, In.	Sizes, in.	(metric), min				1 ³ ⁄16		±0.035	
				in.			11/8		±0.034	
125.0	5		±2.5	±0.100	26.5	1 ¹ /16		±0.8	±0.032	
		41/2		± 0.090	25.0	1		±0.8	±0.030	
106.0	41/4		±2.1	±0.085			15/16		±0.029	
100.0	4		±2.0	±0.080	22.4	7/8		±0.7	±0.028	
		33/4		±0.075		3/	13/16	 + 0.6	±0.026	
90.0	31/2		±1.8	±0.070	19.0	3/4		±0.6	±0.024	
		31/4	<u>//ct</u>	±0.065			11/16	 + 0 E	±0.022	
75.0	3		±1.5	±0.060	16.0			±0.5	±0.021	
		23/4		± 0.055		 17/ ₃₂	9/16		±0.019	
63.0	21/2		±1.3	±0.050	13.2 12.5	1/2		±0.46	±0.018	
		21/4		±0.045			 15/32	±0.44	±0.017	
53.0	21/8		±1.1	± 0.043		 7⁄16		 ±0.41	±0.017 ±0.016	
50.0	2		± 1.0	± 0.040	11.2 9.5	3/8		±0.41 ±0.36	±0.018	
		17⁄8		±0.038	4- 8.0	5/16		±0.30	±0.014 ±0.013	
45.0	1 ³ ⁄ ₄		±0.9	±0.035 D40	6.7	9/16 17/64		±0.32 ±0.29	±0.013 ±0.011	
··· https://standa	rds itch ai/ca	15/8	lande/eist/	±0.033	38 6.3-4b98	-982/2-b4ac	cdec8d2d/as	± 0.29 ± 0.28 $4 - 11$		
37.5 ¹¹ 75775td11dd	11/2		±0.8	±0.030	5.6	7/32	ouc <u>o</u> ouzu/a	±0.27	±0.011 ±0.011	
		13⁄8		± 0.028	4.75	3/16		±0.27	±0.009	
31.5	11⁄4		±0.6	± 0.025	4.00	5/32		±0.23	±0.009	
		13/16		±0.024	3.5	0.127 (1/8)		±0.22	±0.003	
		11/8		±0.023	0.0	0.127 (78)		_0.20	_0.000	
26.5	1 ¹ / ₁₆		±0.5	±0.021						
25.0	1		±0.5	±0.020						
		15/16		±0.019	73 Gaga	s_Tolerance	es on gages u	used in USA	Standard	
22.4	7/8		±0.46	±0.018						
		13/16		±0.016	1		strial Perforat			
19.0	3/4		±0.38	±0.015	(Table 1 an	d Table A1.1) shall be in	accordance v	with those	
		11/16		±0.014	listed in Ta	ble 4				
16.0	5/8		±0.32	±0.013	instea in ita					
		9⁄16		±0.012	Note 3-T	he tolerances ex	pressed in inch-	pound units are	taken from	
13.2	17/32		±0.30	±0.012	the current Al		ipressea in men	pound units are		
12.5	1/2		±0.28	±0.011	the current A	ist values.				
		15/32		±0.011	0 Vormon	da				
11.2	7/16		±0.28	±0.011	8. Keywor	us				
9.5	³ /8		±0.28	±0.010	8.1 indi	istrial perfor:	ated plate; in	dustrial scree	ns: open-	
8.0	⁵ /16		±0.26	±0.010		1	forated openi		· 1	
6.7 6.3	17/ ₆₄		±0.25 ±0.25	±0.009 ±0.009	0 1	le size, per	iorated open	ings, periora	ieu plate;	
5.6	1/4 7/32		±0.25 ±0.24	±0.009 ±0.009	screens					
5.6 4.75	³ /16		±0.24 ±0.21	±0.009 ±0.008						
4.00	9/16 5/32			±0.008 ±0.007						
4.00	732		±0.19	-0.007	5 4 11 1 1		10.11			

⁵ Available from American Iron and Steel Institute (AISI), 1140 Connecticut Ave., NW, Suite 705, Washington, DC 20036, http://www.steel.org.

TABLE 3 Tolerances on Bars of USA Standard Specifications for **Industrial Perforated Plate and Screens**

Perforated Opening

Tolerance on Average

Bar

			Dai	
Standard (metric), mm	USA Industrial Standard, in.	Additional Sizes, in.	Standard (metric), mm	USA Industrial Standard, in.
125.0	5		±3.2	±0.125
		41/2		±0.122
106.0	41/4		±2.9	±0.113
100.0	4		±2.7	± 0.107
		33⁄4		± 0.102
90.0	31/2		±2.5	± 0.097
		31/4		± 0.089
75.0	3		±2.1	± 0.081
		23⁄4		± 0.076
63.0	21/2		±1.8	± 0.069
		21/4		± 0.063
53.0	21/8		±1.5	± 0.059
50.0	2		± 1.4	± 0.056
		11 //8		± 0.054
45.0	13⁄4		±1.3	± 0.051
		15⁄8		± 0.047
37.5	1 ½		±1.1	± 0.043
		13⁄8		± 0.040
31.5	11/4		± 0.9	± 0.037
		1 ³ ⁄16		± 0.035
		11/8		± 0.034
26.5	1 ¹ /16		±0.8	± 0.032
25.0	1		±0.8	± 0.030
		15/16		± 0.029
22.4	7/8		±0.7	± 0.028
		13/16		± 0.026
19.0	3⁄4		±0.6	±0.024
rde ite	n ail	11/16		±0.022
16.0	5/8 .		±0.5	±0.021
		9⁄16		±0.019
13.2	17/32		±0.46	±0.018
12.5	1/2		±0.44	±0.017
		15/32		±0.017
11.2	7/16		±0.41	±0.016
9.5	3/8		± 0.36	±0.014
8.0	5/16		±0.32	±0.013
6.7	17/64		±0.29	±0.011
68 6.3-4098-98	1/2-04acca	zcoaza/astm	±0.28	±0.011
5.6	7/32		±0.27	±0.011
4.75	3/16		±0.23	±0.009
4 00	5/30		+0.22	+0.009

 ± 0.17

 ± 0.006