

# DRAFT INTERNATIONAL STANDARD

## ISO/DIS 10191

ISO/TC 31/SC 3

Secretariat: **AFNOR**

Voting begins on:  
**2020-09-25**

Voting terminates on:  
**2020-12-18**

---

---

## Passenger car tyres — Verifying tyre capabilities — Laboratory test methods

*Pneumatiques pour voitures particulières — Vérification de l'aptitude des pneumatiques — Méthodes d'essai en laboratoire*

ICS: 83.160.10

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

[ISO/DIS 10191](https://standards.iteh.ai/catalog/standards/sist/76a91e15-031b-44ea-9aa4-9f475201e3cc/iso-dis-10191)

<https://standards.iteh.ai/catalog/standards/sist/76a91e15-031b-44ea-9aa4-9f475201e3cc/iso-dis-10191>

THIS DOCUMENT IS A DRAFT CIRCULATED FOR COMMENT AND APPROVAL. IT IS THEREFORE SUBJECT TO CHANGE AND MAY NOT BE REFERRED TO AS AN INTERNATIONAL STANDARD UNTIL PUBLISHED AS SUCH.

IN ADDITION TO THEIR EVALUATION AS BEING ACCEPTABLE FOR INDUSTRIAL, TECHNOLOGICAL, COMMERCIAL AND USER PURPOSES, DRAFT INTERNATIONAL STANDARDS MAY ON OCCASION HAVE TO BE CONSIDERED IN THE LIGHT OF THEIR POTENTIAL TO BECOME STANDARDS TO WHICH REFERENCE MAY BE MADE IN NATIONAL REGULATIONS.

RECIPIENTS OF THIS DRAFT ARE INVITED TO SUBMIT, WITH THEIR COMMENTS, NOTIFICATION OF ANY RELEVANT PATENT RIGHTS OF WHICH THEY ARE AWARE AND TO PROVIDE SUPPORTING DOCUMENTATION.

This document is circulated as received from the committee secretariat.



Reference number  
ISO/DIS 10191:2020(E)

© ISO 2020

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

ISO/DIS 10191

<https://standards.iteh.ai/catalog/standards/sist/76a91e15-031b-44ea-9aa4-9f475201e3cc/iso-dis-10191>



**COPYRIGHT PROTECTED DOCUMENT**

© ISO 2020

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office  
CP 401 • Ch. de Blandonnet 8  
CH-1214 Vernier, Geneva  
Phone: +41 22 749 01 11  
Email: [copyright@iso.org](mailto:copyright@iso.org)  
Website: [www.iso.org](http://www.iso.org)

Published in Switzerland

# Contents

Page

Foreword.....	iv
<b>1 Scope.....</b>	<b>1</b>
<b>2 Normative references.....</b>	<b>1</b>
<b>3 Terms and definitions.....</b>	<b>1</b>
<b>4 Test equipment and conditions.....</b>	<b>3</b>
<b>5 Testing of tyres with diagonal or bias-belted structure and of T-type temporary-use spare tyres.....</b>	<b>3</b>
5.1 Endurance test.....	3
5.1.1 Preparation of tyre.....	3
5.1.2 Test procedure.....	3
5.2 High speed test.....	4
5.2.1 General.....	4
5.2.2 Preparation of tyre.....	4
5.2.3 Test method.....	5
<b>6 Requirements for tyres with diagonal or bias-belted structure and for T-type temporary-use spare tyres.....</b>	<b>6</b>
6.1 Test sample.....	6
6.2 Endurance test.....	6
6.3 High-speed test.....	6
6.4 Strength test.....	6
6.5 Bead unseating resistance (tubeless tyres).....	7
<b>7 Testing of radial tyres.....</b>	<b>8</b>
7.1 Endurance test and low-pressure performance test.....	8
7.1.1 Preparation of tyre.....	8
7.1.2 Test procedure for endurance test.....	8
7.1.3 Preparation of tyre for low-pressure performance test.....	9
7.2 High speed test.....	9
7.2.1 General.....	9
7.2.2 Preparation of tyre.....	10
7.2.3 Test method for tyres with speed symbols F, G, J, K, L, M, N, P, Q, R or S.....	10
7.2.4 Test method for tyres with speed symbols T, U, H, V, W or Y.....	11
7.2.5 Test method for tyres with the code letters ZR in the size designation and both the load index and the speed symbol Y placed within parentheses intended for use at speeds greater than 300 km/h.....	12
<b>8 Requirements for radial tyres.....</b>	<b>12</b>
8.1 Test sample.....	12
8.2 Endurance test and low-pressure performance test.....	12
8.3 High-speed test.....	13
<b>Annex A (informative) High-speed test — Test conditions for tyres without service description marking.....</b>	<b>14</b>
<b>Bibliography.....</b>	<b>16</b>

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 10191 was prepared by Technical Committee ISO/TC 31, *Tyres, rims and valves*, Subcommittee SC 3, *Passenger car tyres and rims*.

This third edition cancels and replaces the second edition (ISO 10191:1995 and also ISO 10191:1995/Amd.1:1998), of which it constitutes a minor revision.

Changes proposed compared to the third edition:

- Separation of test methods and requirements for radial tyres and diagonal tyres, bias-belted tyres and T-type temporary spare tyres [ISO/DIS 10191](https://standards.iteh.ai/catalog/standards/sist/76a91e15-031b-44ea-9aa4-9473201e5cc/iso-dis-10191)
- For diagonal and bias-belted tyres and T-type temporary-use spare tyres the following test methods apply
  - o Endurance test as in third edition
  - o High speed test as in third edition
  - o Plunger test specified in ASTM F414-15 (not radial T-type tyres)
  - o Bead unseating test specified in ASTM F2663-15 (not radial T-type tyres)
- For radial tyres the following test methods apply
  - o Endurance test as in UN GTR No. 16
  - o High speed test as in UN GTR No. 16
- Allow PTFE coating of drums
- Reduce conditioning time for high speed test
- Omit requirement of change in outer diameter after the high speed test for radial tyres
- Allow drum acceleration in steps
- Editorial changes to improve consistency of the text and align with terms defined in ISO 4223-1:2017

# Passenger car tyres — Verifying tyre capabilities — Laboratory test methods

## 1 Scope

This International Standard specifies test methods for verifying the capabilities of tyres for passenger cars. Of the test methods presented, it is possible that only some will be required depending on the construction of the tyre (diagonal, bias-belted, radial or T-type construction) to be tested. The tests are carried out in a laboratory under controlled conditions.

This International Standard includes endurance tests, a low-pressure performance test and high speed tests and requirements for bead unseating and tyre strength.

The test methods presented in this International Standard are not intended for gradation of tyre performance or quality levels. This International Standard applies to all passenger car tyres.

## 2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 4223-1:2017, *Definitions of some terms used in the tyre industry — Part 1: Pneumatic tyres*

ASTM F414-15, *Standard Test Method for Energy Absorbed by a Tire When Deformed by Slow-Moving Plunger*

ASTM F2663-15, *Standard Test Method for Bead Unseating of Tubeless Passenger and Light Truck Tires*

## 3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 4223-1:2017 and the following apply.

### 3.1

#### **bead separation**

breakdown of bond between components in the bead area

[SOURCE: ISO 4223-1:2017, 3.8.1]

### 3.2

#### **belt separation**

parting of rubber compound between belt layers or between belts and plies

[SOURCE: ISO 4223-1:2017, 3.8.2]

### 3.3

#### **chunking**

breaking away of pieces of rubber from the tread exposing reinforcing material (i.e. nylon overlay or steel belts)

[SOURCE: ISO 4223-1:2017, 3.8.3, modified]

**3.3.1**

**parasitic tread block chunking (PTBC)**

an artefact of testing a loaded tire on a roadwheel which results in breaking away of pieces, or tearing, of rubber within a tread block without exposing reinforcing material (e.g., nylon overlay or steel belts); is not indicative of a tire structural problem and does not occur in real-world operation

**3.4**

**cord separation**

parting of the cords from their rubber coating

[SOURCE: ISO 4223-1:2017, 3.8.4]

**3.5**

**cracking**

any parting within the tread, sidewall or inner liner of the tyre that can extend to cord material

[SOURCE: ISO 4223-1:2017, 3.8.5, modified]

**3.6**

**inner liner separation**

parting of inner liner from cord material in the carcass

[SOURCE: ISO 4223-1:2017, 3.8.6]

**3.7**

**open splice**

any parting at any junction of tread, sidewall or inner liner that that can extend to cord material

[SOURCE: ISO 4223-1:2017, 3.8.11, modified]

**3.8**

**ply separation**

parting of adjacent plies

**STANDARD PREVIEW**  
(standards.iteh.ai)  
<https://standards.iteh.ai/catalog/standards/sist/76a91e15-031b-44ea-9aa4-9f475201e3cc/iso-dis-10191>

[SOURCE: ISO 4223-1:2017, 3.8.7]

**3.9**

**sidewall separation**

parting of the rubber compound from the cord material in the sidewall

[SOURCE: ISO 4223-1:2017, 3.8.13]

**3.10**

**tread separation**

pulling away of the tread from the carcass

[SOURCE: ISO 4223-1:2017, 3.8.9]

**3.11**

**test rim**

rim on which the tyre is fitted for specific testing and, unless specified otherwise, approved or recommended or permitted in one of the regional tyre standards for a tyre of that size designation and type

[SOURCE: ISO 4223-1:2017, 3.8.8]

**3.12**

**test drum speed**

peripheral speed of the steel test drum

**3.13****maximum load rating**

reference mass corresponding to the load index used to define the *load capacity* (3.14) of a tyre

**3.14****load capacity**

maximum load that the tyre is able to carry subject to its operating speed and its speed category

**4 Test equipment and conditions**

**4.1 Test drum**, cylindrical driven flywheel (drum) having a diameter of 1,7 m  $\pm$  1 % or 2,0 m  $\pm$  1 %.

The surface of the drum shall be smooth steel; it may be coated with a thin layer of non-stick material, e.g. polytetrafluoroethylene (PTFE), provided that the total drum diameter remains within above limits. The width of the test surface shall be equal to or exceed the overall width of the test tyre.

For the test drum, the loading device shall have a capacity of at least 1 000 kg and the accuracy shall be within  $\pm$  1 % of the full scale. The speed capability of the equipment shall be adequate for the requirements of the test methods. The accuracy of the test drum speed shall be within  $^{+2}_0$  km/h.

**4.2 Inflation pressure gauges**, with a maximum scale value of at least 500 kPa and an accuracy within  $\pm$  5 kPa.

**4.3 Conditioning and test room temperature**. If a tyre manufacture desires to increase test severity, tyre conditioning and the tests may be carried out at a higher temperature than specified in the respective subclauses.

## 5 Testing of tyres with diagonal or bias-belted structure and of T-type temporary-use spare tyres

**5.1 Endurance test****5.1.1 Preparation of tyre**

**5.1.1.1** Mount the tyre on a test rim and inflate it to the pressure specified in [Table 1](#).

**Table 1 — Test inflation pressures for endurance test**

Tyre type	Test inflation pressure
	kPa
Standard	180
Reinforced/extra load	220
T type (temporary use)	360

**5.1.1.2** Maintain the tyre and rim assembly at an ambient temperature of not less than 35 °C for at least 3 h.

**5.1.2 Test procedure**

**5.1.2.1** Readjust the inflation pressure to the value specified in [Table 1](#) immediately before testing.

**5.1.2.2** Mount the tyre and rim assembly on a test axle so that the tyre may be pressed radially against the outer face of test drum.

5.1.2.3 During the test the ambient temperature, at a distance of not less than 150 mm and not more than 1 m from the tyre, shall be at least 35 °C. No provision shall be made for cooling the tyre during the test.

5.1.2.4 Conduct the test, without interruptions, at not less than 80 km/h test speed with loads and test periods not less than those shown in [Table 2](#).

5.1.2.5 Throughout the test, the inflation pressure shall not be corrected, and the test loads shall be kept constant at the value corresponding to each test period.

**Table 2 — Test parameters for endurance test of tyres with diagonal or bias-belted structure**

Test period	Duration min.	Test load as percentage of maximum load rating min.
1	4 h	85 %
2	6 h	90 %
3	24 h	100 %

## 5.2 High speed test

### 5.2.1 General

For those tyres not marked with a service description, note should be taken of the additional test conditions given in [Annex A](#).

iTeh STANDARD PREVIEW  
(standards.iteh.ai)

### 5.2.2 Preparation of tyre

[ISO/DIS 10191](#)

[https://standards.iteh.ai/catalog/standards/sist/76a91e15-031b-44ea-9aa4-](https://standards.iteh.ai/catalog/standards/sist/76a91e15-031b-44ea-9aa4-92175201e3cc/iso-dis-10191)

5.2.2.1 Mount the tyre on a test rim, inflate it to a pressure related to its speed symbol, tyre version and load type, as shown in [Table 3](#).

**Table 3 — Test inflation pressures for high speed test**

Speed symbol	Test inflation pressure				
	kPa				
	Diagonal			Bias-belted	
	LR B / 4PR	LR C / 6PR	LR D / 8PR	Normal (stand-ard)	Reinforced (extra load)
L, M, N	230	270	300	240	280
P, Q, R, S	260	300	330	260	300
T, U, H	280	320	350	280	320
V	300	340	370	300	340
W, Y	n. def.	n. def.	n. def.	320	360

In case of T-type temporary-use spare tyres, the tyre shall be inflated to 420 kPa.

In exceptional cases, a different test inflation pressure may be used. In such a case, the tyre shall be inflated to that pressure.

5.2.2.2 Maintain the tyre and rim assembly at test room temperature for at least 3 h.



### 5.2.3 Test method

5.2.3.1 Before or after mounting the tyre and rim assembly on a test axle, re-adjust the inflation pressure to that specified in 5.2.2.

5.2.3.2 Press the tyre and rim assembly against the outer face of the test drum.

5.2.3.3 Apply a load to the test axle according to Table 4.

**Table 4 — Test loads for high speed test**

Speed symbol	Test load as percentage of the maximum load rating
L, M, N, P, Q, R, S, T, U, H	80 %
V	73 %
W, Y	68 %

5.2.3.4 Throughout the test, the inflation pressure shall not be corrected, and the test load shall be kept constant.

5.2.4.5 During the test the temperature in the test room, measured at a distance of not less than 150 mm and not more than 1,0 m from the tyre, shall be maintained at between 20 °C and 30 °C.

5.2.4.6 The initial test speed is equal to the tyre's speed category:

— less than 40 km/h on a 1,7-m drum or

— less than 30 km/h on a 2,0-m drum.

### 5.2.4.7 Test procedure

Conduct the test, without interruptions, according to Table 5 in relation to the tyre's speed symbol:

**Table 5 — Test speed steps for high speed test of tyres**

Step	Test drum speed	Minimum duration for tyres with speed category 270 km/h (speed symbol W) or below	Minimum duration for tyres with speed cate- gory 300 km/h (speed symbol Y)
1	Acceleration from zero to initial test speed <sup>a</sup>	10 min	10 min
2	initial test speed	10 min	20 min
3	initial test speed plus 10 km/h	10 min	10 min
4	initial test speed plus 20 km/h	10 min	10 min
5	initial test speed plus 30 km/h	10 min	10 min
6	initial test speed plus 30 km/h <sup>(±)</sup> <sup>b</sup>	10 min	not applicable

<sup>a</sup> The acceleration from zero to the initial test speed may be done at a constant rate or in several steps, whereby the area under the speed-time curve shall not be smaller than that with constant acceleration.

<sup>b</sup> On 1,7-m drums, the tyre manufacturer may use a test drum speed equal to the initial test speed plus 40 km/h, if he wishes to increase test severity.

## 6 Requirements for tyres with diagonal or bias-belted structure and for T-type temporary-use spare tyres

### 6.1 Test sample

Two or three tyres with identical characteristics, e.g. size designation and service description or maximum load rating and speed capability, shall comprise a test sample:

- a) one tyre shall be used for the endurance test;
- b) a second tyre shall be used for the high-speed performance test;
- c) for tyres with diagonal or bias-belted structure a third tyre shall be used for the measurement of bead unseating, if applicable, and then of strength.

The inflation pressures, loads, speeds and durations shall be as specified for each test method.

Each test sample shall conform to the requirements specified in [6.2](#) to [6.5](#).

### 6.2 Endurance test

**6.2.1** When a tyre has been subjected to the laboratory endurance test specified in [5.1](#), using a test rim and a valve which undergo no permanent deformation and allow no loss of air, there shall be no visual evidence of tread, sidewall, ply, cord, inner liner, belt or bead separation, chunking, open splices, cracking or broken cords.

**6.2.2** The inflation pressure measured immediately after the test shall not be less than the initial pressure specified in [5.1.1.1](#).

### 6.3 High-speed test

**6.3.1** When a tyre has been subjected to the laboratory high-speed test specified in [5.2](#), using a test rim and a valve which undergo no permanent deformation and allow no loss of air, there shall be no visual evidence of tread, sidewall, ply, cord, inner liner, belt or bead separation, chunking, open splices, cracking or broken cords.

**6.3.2** The inflation pressure measured immediately after the test shall not be less than the initial pressure specified in [5.2.2.2](#).

**6.3.3** The outer diameter of the tyre, measured two hours after completion of the laboratory high-speed test, shall not differ by more than  $\pm 3,5$  per cent from the outer diameter as measured before the test.

### 6.4 Strength test

**6.4.1** When tested in accordance with ASTM F414-15, a tyre with diagonal or bias-belted structure shall meet the requirements for minimum breaking energy specified in [subclause 6.4.2](#) or [6.4.3](#), as applicable.

iTeh STANDARD PREVIEW  
(standards.iteh.ai)

ISO/DIS 10191

<https://standards.iteh.ai/catalog/standards/sist/76a91e15-031b-44ea-9aa4-9f475201e3cc/iso-dis-10191>

**6.4.2** For tyres in standard or reinforced version with nominal section width of 160 mm or above, the minimum breaking energy value is that specified in [Table 6](#).

**Table 6 — Minimum breaking energy**

Tyre version	Minimum breaking energy
	J
Standard	295
Reinforced/extra load	585

In the case of other tyre versions or when test inflation pressures differ from those recommended for tyre measurements in [Table 1](#), the value of the minimum breaking energy,  $E_{\min}$ , in joules, is calculated using the equation:

$$E_{\min} = 7,35 \frac{\text{J}}{\text{kPa}} (p_1 - 140 \text{kPa})$$

where  $p_1$  is the test inflation pressure, in kilopascals, specified for the test.

For tyres in standard or reinforced version with nominal section width less than 160 mm, the minimum breaking energy value shall be reduced by 25 % compared to those specified in [Table 6](#).

**6.4.3** For T-type temporary-use spare tyres, the minimum breaking energy required shall be:

- 295 J for tyres with a maximum load rating of 400 kg (load index 76) and above;
- 220 J for tyres with a maximum load rating below 400 kg (load index 76).

## 6.5 Bead unseating resistance (tubeless tyres)

**6.5.1** When tested in accordance with ASTM F2663-15, a tubeless tyre with diagonal or bias-belted structure shall meet the requirements for the applied force required to unseat the tyre bead at the point of contact specified in [subclause 6.5.2](#) or [6.5.3](#), as applicable.

**6.5.2** For normal or reinforced tyres, the applied force required to unseat the tyre bead at the point of contact shall not be less, in relation to the nominal section width of the tyre, than that shown in [Table 7](#).

**Table 7 — Minimum bead unseating force**

Nominal section width, $SN$ mm	Minimum force N
$SN < 160$	6 670
$160 \leq SN < 205$	8 890
$SN \leq 205$	11 120

**6.5.3** For T-type temporary-use spare tyres, the force required to unseat the tyre bead shall not be less, in relation to the tyre load index, than that shown in [Table 8](#).

**Table 8 — Minimum bead unseating force for T-type temporary-use spare tyres**

Load index, LI	Minimum force N
$LI \leq 75$	6 670
$76 \leq LI \leq 92$	8 890
$93 \leq LI$	11 120