NOTICE: This standard has either been superseded and replaced by a new version or withdrawn. Contact ASTM International (www.astm.org) for the latest information



Designation: E785 – 81 (Reapproved 2011)

Standard Specification for Crucibles, Ignition, Laboratory, Metal¹

This standard is issued under the fixed designation E785; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the U.S. Department of Defense.

1. Scope

1.1 This specification covers two types of metal ignition crucibles, nickel or platinum, complete with covers, for laboratory use.

2. Referenced Documents

2.1 ASTM Standards:²

B162 Specification for Nickel Plate, Sheet, and Strip

2.2 Federal Standards:³

Fed. Std. No. 123 Marking for Shipment (Civil Agencies) 2.3 *Military Standards*.³

MIL-STD-105 Sampling Procedures and Tables for Inspection by Attributes

MIL-STD-129 Marking for Shipment and Storage

MIL-STD-1188 Commercial Packaging of Supplies and Equipment

3. Classification

ocument

3.1 *Types and Capacities*—The crucibles shall be furnished in one or more of the following types or capacities as specified (see S2.1).

3.1.1 *Type I*—Nickel.

Capacity: 100 mL 250 mL

³ Available from Standardization Documents Order Desk, DODSSP, Bldg. 4, Section D, 700 Robbins Ave., Philadelphia, PA 19111-5098, http://www.dodssp.daps.mil.

3.1.2 Type II—Platinum.

Capacity: 20 mL

4. Materials

4.1 *Type I*—Crucibles and covers shall be made from 99.4 % nickel, spun and hardened in conformance with Specification **B162**.

4.2 *Type II*—Crucibles and covers shall be made from 99.9 % platinum plus iridium, with the iridium content of not more than 0.4 %.

5. Physical Requirements

5.1 *Crucibles* shall have a standard shape with a flat base to give a firm and stable resting surface. The side wall shall form a sloping and convex surface extending up to the brim. Crucibles shall be of one-piece construction.

5.2 *Covers* shall be flat, sunken in the center, and shall have an extension to serve as a handle. The sunken area in the center shall fit inside the crucible.

6. Dimensions, Mass, and Permissible Variations

6.1 *Type I* crucibles and covers shall conform to the requirements of Table 1.

6.2 Type II Crucibles and Covers:

6.2.1 Type II crucibles shall conform to the requirements of Table 2.

6.2.2 Type II covers shall conform to the requirements of Table 3.

7. Workmanship

7.1 Crucibles and covers shall be free of defects (scratches, dents, discolorations) or contamination (grease, oil, foreign matter) that detract from their appearance or that impair their serviceability.

8. Keywords

8.1 crucibles; ignition; nickel; platinum

¹This specification is under the jurisdiction of ASTM Committee E41 on Laboratory Apparatus and is the direct responsibility of Subcommittee E41.01 on Apparatus.

Current edition approved Dec. 1, 2011. Published December 2011. Originally approved in 1981. Last previous edition approved in 2006 as E785-81 (2006). DOI: 10.1520/E0785-81R11.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.