



SLOVENSKI STANDARD
oSIST prEN ISO 9556:2024

01-december-2024

Jeklo in železo - Določevanje celotnega ogljika - Infrardeča absorpcijska metoda po zgorevanju v indukcijski peči (ISO/DIS 9556:2024)

Steel and iron - Determination of total carbon content - Infrared absorption method after combustion in an induction furnace (ISO/DIS 9556:2024)

Stahl und Eisen - Bestimmung des Gesamtkohlenstoffgehalts - Verfahren mit Infrarotabsorption nach Verbrennung im Induktionsofen (ISO/DIS 9556:2024)

Aciers et fontes - Détermination du carbone total - Méthode par absorption dans l'infrarouge après combustion dans un four à induction (ISO/DIS 9556:2024)

Ta slovenski standard je istoveten z: prEN ISO 9556

[oSIST prEN ISO 9556:2024](https://standards.metall-catalog.com/standards/sist/20030106-0502-1020180-0000070100/0301-pr-en-iso-9556-2024)

ICS:

77.040.30	Kemijska analiza kovin	Chemical analysis of metals
77.080.01	Železne kovine na splošno	Ferrous metals in general

oSIST prEN ISO 9556:2024

en,fr,de



DRAFT International Standard

ISO/DIS 9556

Steel and iron — Determination of total carbon content — Infrared absorption method after combustion in an induction furnace

*Aciers et fontes — Dosage du carbone total — Méthode par
absorption dans l'infrarouge après combustion dans un four à
induction*

ICS: 77.080.01

ISO/TC 17/SC 1

Secretariat: JISC

Voting begins on:
2024-10-16

Voting terminates on:
2025-01-08

Iron Standards
(<https://standards.iteh.ai>)
Document Preview

[oSIST prEN ISO 9556:2024](https://standards.iteh.ai/catalog/standards/sist/2b03c13b-0532-44c2-b1b0-a0cab089b188/osist-pren-iso-9556-2024)

<https://standards.iteh.ai/catalog/standards/sist/2b03c13b-0532-44c2-b1b0-a0cab089b188/osist-pren-iso-9556-2024>

This document is circulated as received from the committee secretariat.

ISO/CEN PARALLEL PROCESSING

Reference number
ISO/DIS 9556:2024(en)

THIS DOCUMENT IS A DRAFT CIRCULATED FOR COMMENTS AND APPROVAL. IT IS THEREFORE SUBJECT TO CHANGE AND MAY NOT BE REFERRED TO AS AN INTERNATIONAL STANDARD UNTIL PUBLISHED AS SUCH.

IN ADDITION TO THEIR EVALUATION AS BEING ACCEPTABLE FOR INDUSTRIAL, TECHNOLOGICAL, COMMERCIAL AND USER PURPOSES, DRAFT INTERNATIONAL STANDARDS MAY ON OCCASION HAVE TO BE CONSIDERED IN THE LIGHT OF THEIR POTENTIAL TO BECOME STANDARDS TO WHICH REFERENCE MAY BE MADE IN NATIONAL REGULATIONS.

RECIPIENTS OF THIS DRAFT ARE INVITED TO SUBMIT, WITH THEIR COMMENTS, NOTIFICATION OF ANY RELEVANT PATENT RIGHTS OF WHICH THEY ARE AWARE AND TO PROVIDE SUPPORTING DOCUMENTATION.

© ISO 2024

ISO/DIS 9556:2024(en)

iTeh Standards (<https://standards.itih.ai>) Document Preview

[oSIST prEN ISO 9556:2024](https://standards.itih.ai/catalog/standards/sist/2b03c13b-0532-44c2-bfb0-a0cab089b188/osist-pren-iso-9556-2024)

<https://standards.itih.ai/catalog/standards/sist/2b03c13b-0532-44c2-bfb0-a0cab089b188/osist-pren-iso-9556-2024>



COPYRIGHT PROTECTED DOCUMENT

© ISO 2024

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

ISO/DIS 9556:2024(en)

Contents

	Page
Foreword	iv
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Principle	1
5 Reagents	1
6 Apparatus	2
7 Sampling and sample preparation	3
8 Procedure	3
8.1 General operating instructions	3
8.2 Test portion	3
8.3 Blank test.....	4
8.4 Determination.....	4
8.5 Establishment of the calibration graph.....	4
9 Expression of results	7
9.1 Method of calculation.....	7
9.2 Precision.....	7
10 Test report	8
Annex A (Informative) Additional information on the international precision tests	9
Annex B (Informative) Graphical representation of precision data	11
Annex C (Informative) Features of commercial high-frequency induction furnaces and infrared carbon analysers	12
Bibliography	14

oSIST prEN ISO 9556:2024

<https://standards.iteh.ai/catalog/standards/sist/2b03c13b-0532-44c2-bfb0-a0cab089b188/osist-pren-iso-9556-2024>

ISO/DIS 9556:2024(en)

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2. www.iso.org/directives

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received. www.iso.org/patents

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the WTO principles in the Technical Barriers to Trade (TBT) see the following URL: [Foreword - Supplementary information](#)

The committee responsible for this document is ISO/TC17.

This document was prepared by Technical Committee [or Project Committee] ISO/TC 17, Steel, Subcommittee SC 1, Methods of determination of chemical composition.

This second edition cancels and replaces the first edition (ISO 9556:1989), which has been technically revised. The main changes compared to the previous edition are as follows:

— Normative references revised;

— Editorially updated;

— Precision data recalculated

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

Steel and iron — Determination of total carbon content — Infrared absorption method after combustion in an induction furnace

1 Scope

This document specifies an infrared absorption method after combustion in an induction furnace for the determination of the total carbon content in steel and iron.

The method is applicable to carbon contents between 0,003 % (mass fraction) and 4,5 % (mass fraction).

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 648, *Laboratory glassware — Single-volume pipettes*

ISO 1042, *Laboratory glassware — One-mark volumetric flasks*

ISO 14284, *Steel and iron — Sampling and preparation of samples for the determination of chemical composition*

3 Terms and definitions

No terms and definitions are listed in this document.

ISO and IEC maintain terminology databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <https://www.electropedia.org/>

4 Principle

Combustion of a test portion in presence of an accelerator at a high temperature in a high-frequency induction furnace in a current of pure oxygen. Transformation of carbon into carbon dioxide and/or carbon monoxide.

Measurement by infrared absorption of the carbon dioxide and/or carbon monoxide carried by a current of oxygen.

5 Reagents

During the analysis, unless otherwise stated, use only reagents of recognized analytical grade and only distilled water or water of equivalent purity.

5.1 Water, free from carbon dioxide.

Boil water for 30 min, cool to room temperature and bubble with oxygen (5.2) for 15 min. Prepare just before use.

ISO/DIS 9556:2024(en)

5.2 Oxygen, 99,5 % (volume fraction) minimum.

An oxidation catalyst [copper(II) oxide or platinum] tube heated to a temperature above 450 °C shall be used prior to a purifying unit (see [annex C](#)), when the presence of organic contaminants is suspected in the oxygen.

5.3 Pure iron, of known low carbon content less than 0,001 0 % (mass fraction).

5.4 Solvent, appropriate for washing greasy or dirty test samples, for example, acetone.

5.5 Magnesium perchlorate [Mg(ClO₄)₂], particle size : from 0,7 mm to 1,2 mm.

5.6 Barium carbonate

Dry barium carbonate (minimum purity: 99,5 %) at 105 °C to 110 °C for 3 h and cool in a desiccator before use.

5.7 Sodium carbonate

Dry anhydrous sodium carbonate (minimum purity: 99,9 %) at 285 °C for 2 h and cool in a desiccator before use.

5.8 Accelerator: copper, tungsten-tin mixture or tungsten of known low carbon content less than 0,001 0 % (mass fraction).

5.9 Sucrose, standard solution, corresponding to 25 g of C per litre.

Weigh, to the nearest 1 mg, 14,843 g of sucrose (C₁₂H₂₂O₁₁) previously dried at 100 °C to 105 °C for 2,5 h and cooled in a desiccator.

Dissolve in about 100 ml of water ([5.1](#)), transfer quantitatively into a 250 ml one-mark volumetric flask, dilute to the mark with water ([5.1](#)) and mix.

1 ml of this standard solution contains 25 mg of C.

5.10 Sodium carbonate, standard solution, corresponding to 25 g of C per litre.

Weigh, to the nearest 1 mg, 55,152 g of sodium carbonate ([5.7](#)), dissolve in about 200 ml of water ([5.1](#)), transfer quantitatively into a 250 ml one-mark volumetric flask, dilute to the mark with water ([5.1](#)) and mix.

1 ml of this standard solution contains 25 mg of C.

5.11 Inert ceramic (attapulugus clay) impregnated with sodium hydroxide, particle size: from 0,7 mm to 1,2 mm.

6 Apparatus

During the analysis, unless otherwise stated, use only ordinary laboratory apparatus.

All volumetric glassware shall be class A, in accordance with ISO 648 or ISO 1042 as appropriate.

The apparatus required for combustion in a high-frequency induction furnace and the subsequent infrared absorption measurement of the evolved carbon dioxide and/or carbon monoxide may be obtained commercially from a number of manufacturers. Follow the manufacturer's instructions for the operation of the instrument.

Features of commercial instruments are given in [annex C](#).

6.1 Micropipette, 100 µl, limit of error shall be less than 1 µl.

ISO/DIS 9556:2024(en)

6.2 Tin capsule, about 6 mm in diameter, 18 mm in height, 0,3 g in mass and approximately 0,4 ml in volume, of known low carbon content less than 0,001 0 % (mass fraction).

6.3 Ceramic crucible, capable of withstanding combustion in an induction furnace.

Ignite crucibles in an electric furnace in air or in a current of oxygen for not less than 2 h at 1 100 °C and store in a desiccator before use.

NOTE For the determination of low carbon contents it is advisable to ignite crucibles at 1 350 °C in a current of oxygen.

7 Sampling and sample preparation

The sampling and the sample preparation shall be carried out in accordance with ISO 14284 or appropriate national standards for steel and cast iron.

8 Procedure

WARNING — The risks related to combustion analysis are mainly burns in pre-igniting the ceramic crucibles and in the fusions. Use crucible tongs at all times and suitable containers for the used crucibles. Normal precautions for handling oxygen cylinders shall be taken. Oxygen from the combustion process shall be removed effectively from the apparatus since a high concentration of oxygen in a confined space can present a fire hazard.

8.1 General operating instructions

Purify the oxygen supply using tubes packed with the inert ceramic (attapulugus clay) impregnated with sodium hydroxide (5.11) and magnesium perchlorate (5.5), and maintain a quiescent flow rate whilst on standby. Maintain a glass wool filter or a stainless steel net as a dust collector. Clean and change as necessary. The furnace chamber, pedestal post and filter trap shall be cleaned frequently to remove oxide build-up.

Allow each item of equipment to stabilize for the time recommended by the manufacturers of the equipment when the main supply is switched on after being out of action for any length of time.

After cleaning the furnace chamber and/or changing filters or after the equipment has been inoperative for a period, stabilize the apparatus by burning several samples of similar type to the samples to be analysed prior to setting up for analysis.

Flush oxygen through the apparatus and adjust the instrument controls to give a zero reading.

If the instrument used provides a direct reading in percentage of carbon, adjust the instrument reading for each calibration range as follows.

Select a certified reference material with a carbon content close to the maximum carbon content in the calibration range, measure the carbon content of the certified reference material in the manner specified in 8.4.

Adjust the reading of the instrument to the certified value. This adjustment shall be carried out before the calibration specified in 8.5. It cannot replace or correct the calibration.

8.2 Test portion

Degrease the test sample by washing in an appropriate solvent (5.4). Evaporate the last traces of the solvent by heating.

Weigh, to the nearest 1 mg, approximately 1 g of the test sample for carbon contents less than 1,0 % (mass fraction) and approximately 0,5 g for carbon contents higher than 1,0 % (mass fraction).

NOTE The mass of the test portion may depend on the type of instrument used.

ISO/DIS 9556:2024(en)

8.3 Blank test

Prior to the determination, carry out the following blank tests in duplicate.

Transfer a tin capsule (6.2) into a ceramic crucible (6.3). In cases where the calibration graphs of 8.5.1 or 8.5.2 are applied, prepare the tin capsule as follows: using the micropipette (6.1), transfer 100 µl of water (5.1) to a tin capsule (6.2) and dry at 90 °C for 2 h.

Press the tin capsule lightly against the bottom of the crucible. Add the same quantity of pure iron (5.3) as that of the test portion (8.2), and the same quantity of the accelerators (5.8) as will be added to the test portion.

The quantity of accelerators will depend on the individual characteristics of the instrument and the type of material being analysed. The amount used shall be sufficient for complete combustion.

Treat the crucible and contents as specified in the second and third paragraphs of 8.4.

Obtain the reading of the blank tests and convert it to milligrams of carbon by means of the calibration graph (8.5).

The blank value is obtained by subtracting the mass of carbon in the pure iron used (5.3) from the mass of carbon in the blank tests.

The mean blank value (\bar{m}_1) is calculated from the two blank values.

The mean blank value and the difference between the two blank values shall both not exceed 0,01 mg of carbon. If these values are abnormally high, investigate and eliminate the source of contamination.

8.4 Determination

Transfer a tin capsule (6.2) into a ceramic crucible (6.3), press the tin capsule lightly against the bottom of the ceramic crucible, add the test portion (8.2) and cover with the appropriate mass of the accelerators (5.8) (see the fourth paragraph of 8.3).

Place the ceramic crucible and its content on the pedestal post, raise to the combustion position and lock the system. Operate the furnace in accordance with the manufacturer's instructions.

At the end of the combustion and measuring cycle, remove and discard the crucible, and record the analyser reading.

8.5 Establishment of the calibration graph

8.5.1 Samples having carbon contents between 0,003 % (mass fraction) and 0,01 % (mass fraction)

8.5.1.1 Preparation of the calibration series

Transfer the volumes of sucrose standard solution (5.9) or sodium carbonate standard solution (5.10) given in table 1 to five 250 ml one-mark volumetric flasks. Dilute to the mark with water (5.1) and mix.

Using the micropipette (6.1), transfer 100 µl of each of the diluted solutions to five tin capsules (6.2) and dry at 90 °C for 2 h.

Cool to room temperature in a desiccator.