



SLOVENSKI STANDARD
oSIST prEN ISO 2361:2024
01-oktober-2024

Galvansko nanašanje niklja na magnetne in nemagnetne podlage - Merjenje debeline prevleke - Magnetna metoda (ISO/DIS 2361:2024)

Electrodeposited nickel coatings on magnetic and non-magnetic substrates - Measurement of coating thickness - Magnetic method (ISO/DIS 2361:2024)

Elektrolytisch erzeugte Nickelschichten auf magnetischen und nichtmagnetischen Grundmetallen- Messen der Schichtdicke- Magnetverfahren (ISO/DIS 2361:2024)

Revêtements électrolytiques de nickel sur substrat magnétique et non magnétique - Mesurage de l'épaisseur du revêtement - Méthode magnétique (ISO/DIS 2361:2024)

Ta slovenski standard je istoveten z: prEN ISO 2361

[oSIST prEN ISO 2361:2024](https://standards.sist.si/standards/sist/2361/2024)

<https://standards.sist.si/standards/sist/2361/2024>

ICS:

17.040.20	Lastnosti površin	Properties of surfaces
25.220.40	Kovinske prevleke	Metallic coatings

oSIST prEN ISO 2361:2024

en,fr,de



DRAFT International Standard

ISO/DIS 2361

Electrodeposited nickel coatings on magnetic and non-magnetic substrates — Measurement of coating thickness — Magnetic method

*Revêtements électrolytiques de nickel sur métal de base
magnétique et non magnétique — Mesurage de l'épaisseur —
Méthode magnétique*

ICS: ISO ics

[oSIST prEN ISO 2361:2024](https://standards.iteh.ai/catalog/standards/sist/5d02677e-10a8-41cf-ab79-d7421ee9a08e/osist-pren-iso-2361-2024)

<https://standards.iteh.ai/catalog/standards/sist/5d02677e-10a8-41cf-ab79-d7421ee9a08e/osist-pren-iso-2361-2024>

This document is circulated as received from the committee secretariat.

ISO/CEN PARALLEL PROCESSING

Reference number
ISO/DIS 2361:2024(en)

ISO/TC 107

Secretariat: **KATS**

Voting begins on:
2024-08-14

Voting terminates on:
2024-11-06

THIS DOCUMENT IS A DRAFT CIRCULATED FOR COMMENTS AND APPROVAL. IT IS THEREFORE SUBJECT TO CHANGE AND MAY NOT BE REFERRED TO AS AN INTERNATIONAL STANDARD UNTIL PUBLISHED AS SUCH.

IN ADDITION TO THEIR EVALUATION AS BEING ACCEPTABLE FOR INDUSTRIAL, TECHNOLOGICAL, COMMERCIAL AND USER PURPOSES, DRAFT INTERNATIONAL STANDARDS MAY ON OCCASION HAVE TO BE CONSIDERED IN THE LIGHT OF THEIR POTENTIAL TO BECOME STANDARDS TO WHICH REFERENCE MAY BE MADE IN NATIONAL REGULATIONS.

RECIPIENTS OF THIS DRAFT ARE INVITED TO SUBMIT, WITH THEIR COMMENTS, NOTIFICATION OF ANY RELEVANT PATENT RIGHTS OF WHICH THEY ARE AWARE AND TO PROVIDE SUPPORTING DOCUMENTATION.

© ISO 2024

ISO/DIS 2361:2024(en)

iTeh Standards (<https://standards.iteh.ai>) Document Preview

[oSIST prEN ISO 2361:2024](https://standards.iteh.ai/catalog/standards/sist/5d02677e-10a8-41cf-ac79-d7421ee9a08e/osist-pren-iso-2361-2024)

<https://standards.iteh.ai/catalog/standards/sist/5d02677e-10a8-41cf-ac79-d7421ee9a08e/osist-pren-iso-2361-2024>



COPYRIGHT PROTECTED DOCUMENT

© ISO 2024

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

ISO/DIS 2361:2024(en)

Contents

Page

Foreword	iv
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Principle of Measurement	2
5 Factors affecting the measuring accuracy 2 2.....	2
5.1 Type A coatings: Nickel on a magnetic substrate.....	2
5.1.1 Magnetic properties of the basis metal.....	2
5.1.2 Basis metal thickness.....	2
5.1.3 Direction of mechanical working of the basis metal.....	3
5.1.4 Residual magnetism.....	3
5.2 Type B coatings: nickel on a non-magnetic substrate- Coating on the back of the substrate.....	3
5.3 Type A and B coatings.....	3
5.3.1 Coating thickness.....	3
5.3.2 Edge effects.....	3
5.3.3 Curvature.....	3
5.3.4 Surface roughness.....	3
5.3.5 Magnetic fields.....	4
5.3.6 Foreign particles.....	4
5.3.7 Magnetic properties of the coating.....	4
5.3.8 Probe pressure and orientation.....	4
5.3.9 Base Material thickness.....	4
6 Calibration of instruments	4
6.1 General.....	4
6.2 Calibration standards.....	4
7 Procedure	5
7.1 General.....	5
7.2 Basis metal thickness (type A coatings only).....	5
7.3 Direction of mechanical working (type A coatings only).....	5
7.4 Edge effects.....	5
7.5 Curvature.....	5
7.6 Number of readings.....	5
7.7 Residual magnetism (Type A coatings).....	6
7.8 Surface cleanliness.....	6
7.9 Techniques.....	6
7.10 Positioning of the probe.....	6
7.11 Measuring on hot surfaces.....	6
7.12 Measuring underwater.....	6
8 Accuracy requirement	6
9 Test report	7

ISO/DIS 2361:2024(en)

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

ISO draws attention to the possibility that the implementation of this document may involve the use of (a) patent(s). ISO takes no position concerning the evidence, validity or applicability of any claimed patent rights in respect thereof. As of the date of publication of this document, ISO had not received notice of (a) patent(s) which may be required to implement this document. However, implementers are cautioned that this may not represent the latest information, which may be obtained from the patent database available at www.iso.org/patents. ISO shall not be held responsible for identifying any or all such patent rights.

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 107, *Metallic and other inorganic coatings*.

This third edition cancels and replaces the second edition (ISO 2361:1982), which has been technically revised.

The main changes are as follows:

- Split nickel measuring methods in Type A, Type B and Type A and B
- Added common measurement range for every method
- Added headings for the factors influencing the measurement uncertainty
- Restructured and splitted various parts
- Added [Clause 9](#) Test report
- editorial changes

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.