



Designation: D7275 – 07 (Reapproved 2012)

Standard Test Method for Tensile Properties of Bituminous Geomembranes (BGM)¹

This standard is issued under the fixed designation D7275; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This test method is used to measure the tensile properties of bituminous geomembranes (BGM) using a dumbbell shape specimen.

1.2 The values stated in SI units are to be regarded as standard. The values given in parentheses are for information only.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 *ASTM Standards:*²

D638 Test Method for Tensile Properties of Plastics

D4354 Practice for Sampling of Geosynthetics and Rolled Erosion Control Products(RECPs) for Testing

D4439 Terminology for Geosynthetics

D6455 Guide for the Selection of Test Methods for Prefabricated Bituminous Geomembranes (PBGGM)

3. Terminology

3.1 *Definitions of Terms Specific to This Standard:*

3.1.1 *prefabricated bituminous geomembrane (BGM), n*—a material fabricated in a plant and consisting principally of non-woven geotextile, impregnated by a blend of oxidized or polymer-modified bitumen incorporating filler.

3.2 For definitions of other terms used in this test method, refer to Terminology D4439.

¹ This test method is under the jurisdiction of ASTM Committee D35 on Geosynthetics and is the direct responsibility of Subcommittee D35.10 on Geomembranes.

Current edition approved Jan. 1, 2012. Published January 2012. Originally approved in 2006. Last previous edition approved in 2007 as D7275 – 07. DOI: 10.1520/D7275-07R12.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

4. Significance and Use

4.1 This method is used to evaluate the tensile properties of BGM. It can be used for manufacturing quality control or acceptance testing.

4.2 This test method uses a dumbbell specimen. The shape and dimensions of the specimen are defined in this standard. No other shape or dimensions are allowed. Other mechanical properties of BGM may be measured using different test methods. Refer to Guide D6455.

4.3 The reported properties are the maximum strength and elongation at maximum strength.

5. Apparatus

5.1 Tensile instrumentation shall meet the requirements outlined in Test Method D638.

5.2 *Grips*—One of the grips must be self aligning to compensate for uneven distribution of force across the specimen. The clamping force and the clamp surfaces shall hold the specimen firmly without causing damage.

5.3 *Grip Faces*—Grip faces shall be a minimum of 50 mm (2 in.) wide and a minimum of 50 mm (2 in.) in length. Smooth rubber, fine serrated or coarse serrated grip faces have all been found to be suitable for testing BGM. If needed, the use of a silicone-coated paper to help holding the specimen ends into the grips is recommended. The silicone-coated side is to be used in contact with the specimen.

6. Sampling and Test Specimens

6.1 Sampling shall be conducted according to Practice D4354.

6.2 Take a sample that will exclude material from the outer wrap of the roll or the inner wrap around the core. In the case where the sample is taken at the production site, material from the outer wrap may be used if it is undamaged.

6.3 *Test Specimens*—Prepare five specimens with the length of the specimen parallel to the machine direction (MD) and five specimens with the length parallel to the cross-machine direction (XD).

6.4 The specimens shall be cut using an appropriate die to the shape, dimensions, and tolerances presented in Fig. 1.