INTERNATIONAL STANDARD

ISO 15222

Second edition 2021-11

Truck and bus tyres — Method for measuring relative wet grip performance — Loaded new tyres

Pneumatiques pour camions et autobus — Méthode de mesure de l'adhérence relative sur revêtement mouillé — Pneumatiques neufs en charge

iTeh Standards
(https://standards.iteh.ai)
Document Preview

ISO 15222:2021

https://standards.iteh.ai/catalog/standards/iso/6652337f-162b-4f39-92a7-ac4cf44aa0b5/iso-15222-2021



iTeh Standards (https://standards.iteh.ai) Document Preview

ISO 15222:2021

https://standards.iteh.ai/catalog/standards/iso/6652337f-162b-4f39-92a7-ac4cf44aa0b5/iso-15222-2021



COPYRIGHT PROTECTED DOCUMENT

© ISO 2021

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office CP 401 • Ch. de Blandonnet 8 CH-1214 Vernier, Geneva Phone: +41 22 749 01 11 Email: copyright@iso.org Website: www.iso.org

Published in Switzerland

Co	Contents				
For	eword		.		
1	Scop	ne	1		
2	Norr	native references	1		
3	Terms and definitions				
	Methods for measuring wet grip				
4					
5	Gene 5.1	eral test conditions			
	5.1	Track characteristics 5.1.1 General			
		5.1.2 Standard reference test tyre method			
	5.2	Wetting conditions	4		
	5.3	Atmospheric conditions			
	5.4	Reference tyre			
6	Measurement of tyre wet grip on a standard vehicle				
	6.1	Principles			
	6.2	Equipment			
		6.2.2 Measuring equipment			
	6.3	Conditioning of the test track			
	6.4	Measurement requirements for test speed	<i>6</i>		
	6.5	Tyres and rims 14611 Staffdal 418			
		6.5.1 Vehicle equipment 6.5.2 Tyre preparation and break-in 6.5.2 Tyre preparation and 6.5.2 Tyre preparation a	6		
		6.5.3 Tyre load			
		6.5.4 Tyre inflation pressure			
	6.6	Procedures			
	6.7	Processing of measurement results			
		6.7.1 Calculation of the braking force coefficient	8		
		6.7.2 Validation of results 6.7.3 Calculation of the adjusted braking force coefficients of the reference tyre			
		6.7.4 Calculation of the relative wet grip index of the tyre	C		
	6.8	Wet grip performance comparison between a candidate tyre and a reference tyre			
		using a control tyre			
		6.8.1 General			
		6.8.2 Principle of the approach			
		6.8.4 Storage and preservation of control tyres			
		6.8.5 Replacement of control tyres			
7	Test method using a trailer or a tyre test vehicle				
,	7.1	Principle	11		
	7.2	Apparatus			
	7.3	Instrumentation			
		7.3.1 General			
	7.4	7.3.2 General requirements for measurement system Selection and preparation of test tyres			
	7. 4 7.5	Preparation of the apparatus and the test track			
	7.0	7.5.1 Towed trailer			
		7.5.2 Tyre test vehicle			
		7.5.3 Instrumentation and equipment			
	76	7.5.4 Conditioning of the track General test conditions			
	7.6 7.7	Procedure			
	7.7	Processing of measurement results	15		

ISO 15222:2021(E)

7.8.1	General	15		
7.8.2	Validation of results	16		
7.8.3	Calculation of the relative wet grip index of the tyre	16		
Annex A (informative) Example test reports of wet grip index				
Bibliography				

iTeh Standards (https://standards.iteh.ai) Document Preview

ISO 15222:2021

https://standards.iteh.ai/catalog/standards/iso/6652337f-162b-4f39-92a7-ac4cf44aa0b5/iso-15222-2021

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 31, Tyres, rims and valves.

This second edition cancels and replaces the first edition ISO 15222:2011 been technically revised.

The main changes compared to the previous edition are as follows:

- the SRTT for tracks validation has been changed (from SRTT 14" to SRTT 16" due to SRTT 14" discontinuation);
 - the SRTT selection rules (wide SRTT or narrow SRTT) have been revised;
 - test results' calculations and validation have been clarified and simplified;
 - the wording and designations have been aligned with ISO 23671 for better consistency.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

iTeh Standards (https://standards.iteh.ai) Document Preview

ISO 15222:2021

https://standards.iteh.ai/catalog/standards/iso/6652337f-162b-4f39-92a7-ac4cf44aa0b5/iso-15222-2021

Truck and bus tyres — Method for measuring relative wet grip performance — Loaded new tyres

1 Scope

This document specifies the method for measuring relative wet grip braking performance index to a reference under loaded conditions for new tyres for use on commercial vehicles on a wet-paved surface.

The methods developed in this document are meant to reduce the variability. The use of a reference tyre is necessary to limit the variability of the testing method procedures.

This document applies to all commercial vehicle, truck and bus tyres.

This document does not apply to:

- tyres fitted with additional devices to improve traction properties (e.g. studded tyres);
- professional off-road tyres.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 4209-1, Truck and bus tyres and rims (metric series) — Part 1: Tyres

ISO 4223-1, Definitions of some terms used in the tyre industry — Part 1: Pneumatic tyres

ISO 23671, Passenger car tyres — Method for measuring relative wet grip performance — Loaded new tyres

ASTM E965-15, Standard Test Method for Measuring Pavement Macrotexture Depth Using a Volumetric Technique

3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 4223-1 and the following apply.

ISO and IEC maintain terminology databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at https://www.iso.org/obp
- IEC Electropedia: available at https://www.electropedia.org/

3.1

test run

single pass of a loaded tyre over a given test surface

3.2

candidate tyre

Т

test tyre that is part of an evaluation programme

3.3

reference tyre

standard reference test tyre (3.17) that is used as a benchmark in an evaluation programme

Note 1 to entry: These tyres usually have carefully controlled design features to minimize variation.

3.4

control tyre

intermediate tyre that is used when the candidate tyre (3.2) and the reference tyre (3.3) cannot be directly compared on the same vehicle

3.5

braking force

longitudinal force between a tyre and the road resulting from braking torque application

Note 1 to entry: It is expressed in newtons.

3.6

braking force coefficient

BFC

<vehicle method> ratio between the average deceleration in a test run (3.1) and the acceleration gravity $(9.81 \text{ m}\cdot\text{s}^{-2})$

dynamic tyre braking force coefficient Teh Standards

<trailer (or tyre test vehicle) method> ratio between the braking force (3.5) and the vertical load (3.10) acquired in real time

3.8

peak braking force coefficient

<trailer or tyre test vehicle method> maximum value of the dynamic tyre braking force coefficient (3.7) that occurs prior to the *lockup of a wheel* (3.9) as the braking torque is progressively increased

3.9

lockup of a wheel

condition of a wheel in which its rotational velocity about the wheel spin axis is zero and it is prevented from rotating in the presence of applied wheel torque

3.10

vertical load

normal force (Z-direction) of a tyre exerted on the road resulting from the mass supported by the tyre

Note 1 to entry: It is expressed in newtons.

3.11

tyre test vehicle

trailer vehicle

special purpose tyre evaluation vehicle which has instruments to measure the vertical and longitudinal forces on one tyre during braking

3.12

hitch height

coupling height

height when measured perpendicularly from the centre of the articulation point of the trailer towing coupling or hitch to the ground, when the towing vehicle and trailer are coupled together

Note 1 to entry: The vehicle and trailer shall be standing on level pavement surface in their test mode complete with the appropriate tyre(s) to be used in the particular test.

3.13

braking test

series of a specified number of test runs (3.1) of the same tyre repeated within a short time frame

3.14

braking test cycle

series of *braking tests* (3.13) that consist of an initial braking test of the *reference tyre* (3.3) set, of up to three braking tests of either *candidate tyre* (3.2) sets or *control tyre* (3.4) sets, or both, and a final braking test of the same reference *tyre set* (3.16)

3.15

tyre set

<vehicle method> four or six tyres depending on the test vehicle

3.16

tyre set

<trailer or a tyre test vehicle method> one or two tyres

3.17

standard reference test tyre \$1/\$tandard\$.iteh.ai)

SRTT

tyre that is produced, controlled and stored under specific conditions, in order to be used as reference tyre for testing

Note 1 to entry: These tyres usually have carefully controlled design features to minimize variation. The requirements for SRTTs are given in ASTM international standards.

4 Methods for measuring wet grip

Relative wet grip braking performance for loaded commercial vehicle new tyres travelling straight ahead on a wet, paved surface can be measured by one of the following methods:

- a vehicle method consisting of testing a tyre set mounted on a standard vehicle;
- a test method using a trailer or a tyre test vehicle equipped with a test tyre set.

5 General test conditions

5.1 Track characteristics

5.1.1 General

The surface shall be a dense asphalt surface with a uniform gradient of not more than 2 % and shall not deviate more than 6 mm when tested with a 3 m straight edge.

The test surface shall have a pavement of uniform age, composition and wear. The test surface shall be free of loose material or foreign deposits.

The maximum chipping size shall be from 8 mm to 13 mm.

ISO 15222:2021(E)

The macro texture depth MTD of the area of the track to be used for the wet grip test shall be measured as specified in ASTM E965-15, and shall be (0.7 ± 0.3) mm.

In order to verify the wetted frictional properties of the surface, the following method in 5.1.2 shall be used.

5.1.2 Standard reference test tyre method

This method uses P225/60R16 97S, defined in ASTM F2493-20, SRTT (SRTT16).

Perform at least six valid measurements of the peak braking force coefficients (μ_{peak}) with SRTT16 using a trailer or special purpose tyre evaluation vehicle test procedure as specified in Clause 7 or in ISO 23671 at 65 km/h and 180 kPa.

The average of the measured peak braking force coefficients ($\mu_{\text{peak,ave}}$) shall be corrected for the effects of temperature as follows:

$$\mu_{\text{peak,corr}} = \mu_{\text{peak,ave}} + a \cdot (\vartheta - \vartheta_0)$$

where

 $\mu_{\mathrm{peak,corr}}$ is the temperature corrected average peak braking force coefficient;

a is equal to $0,002 \, ^{\circ}\text{C}^{-1}$;

artheta is the wetted surface temperature in degree Celsius;

 ϑ_0 is equal to 20 °C. (1) S: //StandardS.iteh.ai)

 $\mu_{\rm peak,corr}$ shall be not less than 0,65 and not greater than 0,90.

The test shall be conducted using the lanes and length of the track to be used for the wet grip test.

For the trailer method, testing is run in such a way that braking occurs within 10 m distance in length of where the surface was characterized.

5.2 Wetting conditions

The surface may be wetted from the track-side or by a wetting system incorporated into the test vehicle or the trailer.

If "external watering" is used, water the test surface at least half an hour prior to testing in order to equalize the surface temperature and water temperature. External watering should be supplied continuously throughout testing.

For both external watering and self-watering systems, the water depth shall be not less than 0,5 mm and not greater than 2,0 mm measured from the peaks of the pavement for the braking lanes used.

5.3 Atmospheric conditions

The wind conditions shall not interfere with wetting of the surface (windshields are allowed).

The ambient and the wetted surface temperatures shall be between 5 $^{\circ}$ C and 35 $^{\circ}$ C and shall not vary during the test by more than 10 $^{\circ}$ C.

5.4 Reference tyre

In order to cover the range of tyre sizes fitting the commercial vehicles the three standard reference test tyres SRTT16C, SRTT19.5 and SRTT22.5 shall be used to measure the relative wet grip index according to Table 1.