



Designation: ~~C933-09~~ Designation: C933 - 11

Standard Specification for Welded Wire Lath¹

This standard is issued under the fixed designation C933; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope*

1.1 This specification covers welded wire lath, flat or self-furring, with or without backing, designed for use as a base to receive portland cement-based interior plaster and exterior stucco.

1.2 The values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units that are provided for information only and are not considered standard.

2. Referenced Documents

2.1 *ASTM Standards*:²

A641/A641M [Specification for Zinc Coated \(Galvanized\) Carbon Steel Wire](#)

C11 [Terminology Relating to Gypsum and Related Building Materials and Systems](#)

2.2 *Federal Specifications*:

UU-B-790 Building Paper, Vegetable Fiber: (Kraft, Waterproofed, Water Repellent and Fire Resistant)³

3. Terminology

3.1 Definitions of terms used in this standard shall be in accordance with Terminology C11.

4. Materials and Manufacture

4.1 Welded wire lath shall be fabricated from not less than 0.0625 in. (1.588 mm), cold-drawn, galvanized steel wire, conforming to Specification A641/A641M.

~~4.1.1 The wire shall be zinc-coated (galvanized) in accordance with Specification~~

4.1.1 Diameter tolerance for galvanized wire shall be in accordance with Specification A641/A641M.

~~4.1.2 The backing shall conform to Federal Specification UU-B-790~~

4.1.2 The wire shall be zinc-coated (galvanized) in accordance with Specification A641/A641M.

4.1.3 The backing shall conform to Federal Specification UU-B-790. The backing shall be either absorptive or water resistant. The backing shall have a bursting strength of not less than that required to maintain integrity under normal hand- or machine-application pressures.

~~4.1.3 The~~ 4.1.4 The backing shall be attached to the lath to prevent accidental removal during shipping, handling or installation. Attachment of the backing shall allow lapping of wire-to-wire and backing-to-backing of not less than one mesh at ends and edges and shall permit full embedment, in not less than 1/4 in. (6 mm) of plaster, of not less than one-half of the total length and width of the wire.

~~4.1.4 The~~ 4.1.5 The thickness of the embedment of the lath and plaster shall be measured from the back plane of the back wire, exclusive of furring, to the backing or surface of the substrate.

5. Dimensions and Permissible Variations

5.1 *Openings and Stiffening*:

5.1.1 Lath shall be welded at all intersections of wire to form openings not more than 2 in. (51 mm) by 2 in. (51 mm).

5.1.2 Heavy-duty lath shall be stiffened continuously and parallel to the long dimension of the lath at intervals of not more than 6 in. (152 mm). Wire stiffeners used for this purpose shall range from 15-gauge (0.072 in.) to 11-gauge (0.1205 in.). The weight

¹ This specification is under the jurisdiction of ASTM Committee C11 on Gypsum and Related Building Materials and Systems and is the direct responsibility of Subcommittee C11.02 on Specifications and Test Methods for Accessories and Related Products.

~~Current edition approved July 15, 2009. Published August 2009. Originally approved in 1980. Last previous edition approved in 2007 as C933-07b. DOI: 10.1520/C0933-09.~~

Current edition approved Dec. 1, 2011. Published January 2011. Originally approved in 1980. Last previous edition approved in 2009 as C933-09. DOI: 10.1520/C0933-11.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

³ Available from Standardization Documents Order Desk, Bldg. 4 Section D, 700 Robbins Ave., Philadelphia, PA 19111-5094, Attn: NPODS.

*A Summary of Changes section appears at the end of this standard.